PPPL NONCONF	UNMAINCE REFURI	NO: <sup>3621</sup> Open I			
-	Closed NCR	Trend			
Department NC	SX	Division	NCSX	Project	
	NDOR				
Item Dwg/Part# SE	141-116, Rev. 6 Pr	rocurement # S00524	42-F	Cost	t Center 9450 1*** 1404
RAP# 3209 J	<b>b Doc</b> # S005242-F	Vendor Energy In	dustries	of Ohio	
RAP Title NCSX - Mc	dular Coil Winding Forms				
HoldTag Applie	ed				
	n interference where back spotf Rev. 6, Sheet 1, in area D-4 ar	nd the actual condition is sho	insufficie own in th	ne attached photo	0.
	1 Sample Size In		] Lot	Reje	# Rejected 1 Date 10/06/05
neuvileu DV Hallo	DOUIOS S Validate			vanualeu	
Disposition: Rework This condition is due to t overcast on the high side	Poulos S Validate * Repair* Use As I he overcast ("padding") being of the tolerance band to assur- grees to grind the overcast in the	s* Return To Vend on the high side of the tolera re that the part can be mach	nce. We	Scrap* e concur with EIC m the casting an	Use As Is D's decision to keep the ad to assist in casting
Disposition: Rework This condition is due to t overcast on the high side	* Repair* Use As I he overcast ("padding") being c	s* Return To Vend on the high side of the tolera re that the part can be mach	nce. We	Scrap* e concur with EIC m the casting an	Use As Is D's decision to keep the ad to assist in casting
Disposition: Rework This condition is due to t overcast on the high side flow/solidification. EIO a \$85=\$85.	he overcast ("padding") being of the tolerance band to assure	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe	nce. We hined fro erence w	Scrap* e concur with El0 m the casting an ith bolts. Cost o	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @
Disposition: Rework This condition is due to t overcast on the high side flow/solidification. EIO a \$85=\$85.	* <b>Repair</b> * <b>Use As I</b> he overcast ("padding") being o e of the tolerance band to assur grees to grind the overcast in th	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe	nce. We hined fro erence w	Scrap* e concur with El0 m the casting an ith bolts. Cost o	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u>
Disposition: Rework This condition is due to t overcast on the high side flow/solidification. EIO a \$85=\$85.	* Repair* Use As I he overcast ("padding") being o e of the tolerance band to assur grees to grind the overcast in th of vendor supplied equip	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in informatio \$G&A	nce. We hined fro erence w	Scrap* e concur with El0 m the casting an ith bolts. Cost o	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u> Insp <u>Various</u> Proj. Doc Control (when
Disposition: Rework This condition is due to t overcast on the high side flow/solidification. EIO a \$85=\$85. For rework or repair #Hours	* Repair* Use As I he overcast ("padding") being o e of the tolerance band to assur grees to grind the overcast in th of vendor supplied equip \$Est Labor	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A \$Total	nce. We hined fro erence w	Scrap* e concur with El0 m the casting an ith bolts. Cost o	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u> Insp <u>Various</u> Proj. Doc Control (when closed) QC Files
Disposition: Rework This condition is due to t overcast on the high side flow/solidification. EIO a \$85=\$85. For rework or repair #Hours \$Material	* Repair* Use As Is   he overcast ("padding") being of   e of the tolerance band to assurgrees to grind the overcast in the   of vendor supplied equip   \$Est Labor   \$Burden   Heitzenroeder P	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$Total	on belo	Scrap* e concur with El0 m the casting an ith bolts. Cost of <b>w:</b>	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u> Insp <u>Various</u> Proj. Doc Control (when closed) QC Files Malsbury J
Disposition: Rework This condition is due to t overcast on the high side flow/solidification. EIO a \$85=\$85. For rework or repair #Hours \$Material Disposition By	* Repair* Use As Is   he overcast ("padding") being of e of the tolerance band to assurgrees to grind the overcast in the equip \$Est Labor   of vendor supplied equip \$Est Labor   *Est Labor   *Burden   Heitzenroeder P   r Nelson B, NCSX C	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$Total core Systems Mgr	on belo \$85 Date	Scrap* e concur with El0 m the casting an ith bolts. Cost of w:  	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u> Insp <u>Various</u> Proj. Doc Control (when closed) QC Files
Disposition: Rework This condition is due to to overcast on the high side flow/solidification. EIO as \$85=\$85. For rework or repair #Hours \$Material Disposition By Supervisor's Concu	* Repair* Use As Is   he overcast ("padding") being of e of the tolerance band to assurgrees to grind the overcast in the grees to grind the overcast in the second secon	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$G&A Gore Systems Mgr	on belo \$85 Date Date	Scrap* e concur with El0 m the casting an ith bolts. Cost of w: 	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog Heitzenroeder P Insp Various Proj. Doc Control (when closed) QC Files Malsbury J Boscoe J Chrzanowski J Heitzenroder P
Disposition: Rework This condition is due to to overcast on the high side flow/solidification. EIO at \$85=\$85. For rework or repair #Hours \$Material Disposition By Supervisor's Concu Eng. Dept. Head Co	* Repair* Use As Is   he overcast ("padding") being of e of the tolerance band to assurgrees to grind the overcast in the equip \$Est Labor   of vendor supplied equip \$Est Labor   *Est Labor   *Burden   Heitzenroeder P   r Nelson B, NCSX C	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$G&A Gore Systems Mgr	on belo \$85 Date Date Date	Scrap* e concur with El0 m the casting an ith bolts. Cost of w: 	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u> Insp <u>Various</u> Proj. Doc Control (when closed) QC Files Malsbury J Boscoe J Chrzanowski J
Disposition: Rework This condition is due to to overcast on the high side flow/solidification. EIO at \$85=\$85. For rework or repair #Hours \$Material Disposition By Supervisor's Concu Eng. Dept. Head Co	* Repair* Use As Is   he overcast ("padding") being of e of the tolerance band to assurgrees to grind the overcast in the grees to grind the overcast in the second secon	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$G&A Gore Systems Mgr	on belo \$85 Date Date Date	Scrap* e concur with El0 m the casting an ith bolts. Cost of w: 	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog Heitzenroeder P Insp Various Proj. Doc Control (when closed) QC Files Malsbury J Boscoe J Chrzanowski J Heitzenroder P Sutton L Malinowski F Nelson B
Disposition: Rework This condition is due to to overcast on the high side flow/solidification. EIO at \$85=\$85. For rework or repair #Hours \$Material Disposition By Supervisor's Concu Eng. Dept. Head Co	* Repair* Use As Is   he overcast ("padding") being of e of the tolerance band to assurgrees to grind the overcast in the overcas	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$G&A Gore Systems Mgr	on belo \$85 Date Date Date	Scrap* e concur with El0 m the casting an ith bolts. Cost of w: 	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog <u>Heitzenroeder P</u> Insp <u>Various</u> Proj. Doc Control (when closed) QC Files Malsbury J Boscoe J Chrzanowski J Heitzenroder P Sutton L Malinowski F
Disposition: Rework This condition is due to to overcast on the high side flow/solidification. EIO as \$85=\$85. For rework or repair #Hours \$Material Disposition By Supervisor's Concu Eng. Dept. Head Co WCO/Other	* Repair* Use As Is   he overcast ("padding") being of e of the tolerance band to assurgrees to grind the overcast in the experiment of the overcast in	s* Return To Vend on the high side of the tolera re that the part can be mach nese regions to avoid interfe ments, fill in information \$G&A\$G&A Gore Systems Mgr	on belo \$85 Date Date Date Date	Scrap* e concur with El0 m the casting an ith bolts. Cost of <b>w:</b> 	Use As Is D's decision to keep the ad to assist in casting f re-work: Grinding, 1 hr. @ Distribution Cog Heitzenroeder P Insp Various Proj. Doc Control (when closed) QC Files Malsbury J Boscoe J Chrzanowski J Heitzenroder P Sutton L Malinowski F Nelson B Williams M