

**Energy Industries of Ohio**

**Contract # S005242-F**

**Modular Coil Winding Form**

**A-1 Documentation Package**

**10/4/06**

# **This A-1 Documentation consists of:**

## **Part 1**

**Final documentation package Metal Tek Intl. – Pages 3 – 160**  
**Latest revision 10/4/2006**  
**Foundry documentation**

## **Part 2**

**Final documentation package Major Tool - Pages 161 - 235**  
**Latest revision 8/28/2006**  
**Machine shop documentation**

**NOTE - MTM – new EIO TOC is on page 235. Use this as a reference for finding files in MTM portion of Doc package.**

## **Part 3**

**Metal Tek radiographic films from part 1 (shipped to PPPL)**

**Major Tool radiographic films from part 2 (shipped to PPPL)**

# **Energy Industries of Ohio**

**Contract # S005242-F**

**Modular Coil Winding Forms**

## **A-1 Documentation Package**

**Part 1 – Metal Tek International  
Casting Data Package**

**Revised 3/31/2006**

\*\*Note – Document #'s listed in the TOC (page 4) are not necessarily the same as the number hand written on the top of the document. Please use page # to find relevant document.

**Revised 10/04/2006**

Added MTK – CA 1320 & CA 1379 Replaced CA 1371 with CA 1625 which superseded CA 1371 – CA 1371 & CA 1403 are a part of CA 1625

NOTE – A-1 coil only used Lincoln weld lot # 3018926/78309 Any test results for Metrode or other Lincoln lots included in the test documents were for samples used on other MCWF or other projects unrelated to NCSX. These tests were run in tandem with tests for the above mentioned lot and so were reported on the same document from the test lab.

# A-1 Documentation Package

## List of Documents 10-04-06

Doc #	Description	Page #
1	MTR for weighted average of chemistry – 3 ladles replaced by product analysis	5
2	MTR from Wisconsin Centrifugal	6
3	MTR for C-4 Shim revised 9/24/05	7
4	Lincoln weld metal product conformance spec Lot 3018926/78309	8
5	St Louis Test Lab dated 8/9/05 mech test results at RT & CVN @ 293°k for Lincoln lot 3018926/78309 (Note – page 3 of 3 unrelated & omitted)	9
6	Westmoreland mech test & CVN @ -320°F dated 9/13/05 Lot 3018926/78309	11
7	Westmoreland Tensile test report @ -320°F dated 9-9-05	13
8	St Louis Test Lab dated 10-10-05 – incl. tensile test results @ room temp & Charpy V Notch (CVN) at 77°K & 293°K	14
9	Weld map	17
10	MQS Radiographic Technique for A coils	26
11	MQS Radiographic Inspection Report dated 8/13/05	41
12	MTK Radiographic Interpretation Report dated 10/24	46
13	MTK Radiographic Shooting Sketch for A coils	47
14	C-4 Coil heat treat chart dated 7/26/05	48
15	C-4 Coil stress relief dated 10/29/05	49
16	A-1 Shim heat treat chart dated 06/02/05	50
17	MTK signed MTS A-1 Coil	51
18	MTK signed MTS A-1 Coil shim	63
19	CA 1308 – shim chemistry out of spec	69
20	CA 1320 - Lack of test material	71
21	CA 1323 – CA for sulfur & phosphorus readings - final ver. 2/26/06	73
22	CA 1324 – Major weld defects	78
23	CA 1347 – Thin wall condition on areas of shell – revised 1/31/06	80
24	CA 1379 – Failed test result on Lincoln weld material – NOTE inserted for historic purposes only. Material was retested for cryogenic Charpy & correct test result document is included in this Doc package – Doc #6	83
25	CA 1625 for welding failures – incl earlier CA 1371 & CA 1403	85
26	Final inspection report A-1 coil – dated 8/30/2005	89
27	C of C for A-1 Coil	90
28	Final Inspection report A-1 Shim	91
29	C of C for A-1 shim	92
30	EIO shipping release for A-1 Coil	93
<b>Thin Wall Addendum</b>		
i	EIO summary of root cause analysis for thin walled condition	95
ii	3D ScanCo explanation of tolerance shift	97
iii	3D ScanCo rescan of A-1	101
iv	3D Scanco – review of initial scan on A pattern	109
v	EIO evaluation of stocked model for A casting	124
vi	EIO discussion slides on thin wall	125
vii	Preliminary FEA analysis on A-1	141
viii	FEA analysis report from PPPL	145
10/04/06		



### Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

## Material Test Report

ENERGY INDUSTRIES OF OHIO

Purchase Order Number PPPL-FP-LTS-2  
Pattern Number MCWF-A1  
CAF Metal Designation CF8MNMnMod  
Material Spec CF8MNMnMOD

Cert Number 169470-1  
Pour Date 5/24/2005

Weighted average of 3 heats - 29516(39%),29517(23%),29519(38%) Total Weight 32422 lbs.

Revised 12/5/05

Element	Min	Actual	Max
C	0.04	0.04	0.07
MN	2.3	2.4	2.8
SI	0.0	0.4	0.5
CR	18.0	18.2	18.5
NI	13.0	13.3	13.5
MO	2.1	2.4	2.5
P*	0.0	0.022	0.035
S*	0.0	0.009	0.025
N	0.24	0.26	0.28

\*P & S taken from cast on bar, zones 1,2,&3 and analyzed by wet chemistries, ASTM E1019-03 for sulfur and Colormetric for phosphorous.

#### PRODUCT ANALYSIS

Results of spectrometer analysis of cast on test bar after spectrometer preventive maintenance performed and at Wisconsin Centrifugal.

\*\*\*Not analyzed on spectrograph.

Element	CAF after PM	WC Analysis
C	***	0.06
MN	1.6	1.6
SI	0.6	.06
CR	18.2	18.1
NI	13.5	13.7
MO	2.4	2.4
P	0.028	0.027
S	0.009	0.009
N	***	0.25

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager

Superior Quality Engineered Metal Products

[www.MetalTekInt.Com](http://www.MetalTekInt.Com)



## Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

## Material Test Report

ENERGY INDUSTRIES OF OHIO

Purchase Order Number PPPL-FP-LTS-2

Pattern Number MCWF-A1

CAF Metal Designation CF8MNMnMod

Material Spec CF8MNMnMOD

Analysis performed by Wisconsin Centrifugal

Cert Number 169470-1

Pour Date 5/24/2005

Revised 11/3/05

Element	Min	Actual	Max
C	0.04	0.06	0.07
MN*	2.3	1.6	2.8
SI	0.0	0.6	0.7
CR	18.0	18.1	18.5
NI*	13.0	13.7	13.5
MO	2.1	2.4	2.5
P	0.0	0.027	0.035
S	0.0	0.009	0.025
N	0.24	0.25	0.28

\* See Corrective Action Number 1323.

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager

Superior Quality Engineered Metal Products

[www.MetalTekInt.Com](http://www.MetalTekInt.Com)

# Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

## Material Test Report

### ENERGY INDUSTRIES OF OHIO

Purchase Order Number PPPL-FP-LTS-2 Heat Number 29198 Pour Date 4/28/2005  
Pattern Number SE-141-073 COIL C SHIM (-3 thru -6 Parts) Cert Number S73220-2 and  
SE-141-033 COIL A SHIM (-1 thru -6 Parts) Cert Number S76220-1  
CAF Metal Designation CF8MNMnMod  
Material Spec CF8MNMN MOD

Revised 9/24/05

Element	Min	Actual	Max
C	0.040	0.070	0.070
CR	18.000	18.100	18.500
MN	2.300	2.970	2.800
MO	2.100	2.450	2.500
N	0.240	0.255	0.280
NI	13.000	13.120	13.500
P*	0.000	0.013	0.035
S*	0.000	0.010	0.025
SI	0.000	0.700	0.700

MN & SI previously reported on CA 1308 and were accepted.

\*P & S taken from test from heat parts were poured from and analyzed by wet chemistry, ASTM E1019-03 for sulfur and Gravimetric for phosphorous.

This report covers the eleven castings poured from heat 29198. Only parts listed above however will be shipped for this order. Each casting has a unique number stamped in the part adjacent to the pattern number to differentiate the part and subsequent reporting that will be traced to the casting.

Specification limits have been updated to latest specification.

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager

**Superior Quality Engineered Metal Products**

[www.MetalTekInt.Com](http://www.MetalTekInt.Com)

045

ER316 MNN F

9



# PRODUCT CONFORMANCE REPORT

Product	LNM 4455	Size(s) mm	1,2
Class.	EN 12072-99: G 20 16 3 Mn L	Lot/Batch	3018926/78309
		Item No.	692129

Customer	CK SUPPLY Contact Ernie Simpson Eureka (MISSOURI) 63025 UNITED STATES	Quantity	450,0 KG
		Customer ref.	P.O.: SL 057549
		LSW Order No.	SD424496

Chemical analysis (%)										EN10204 3.1B
C	Si	Mn	P	S	Cr	Ni	Mo	Cu	N	
0,02	0,4	7,3	0,019	0,001	20,1	16,3	2,9	0,1	0,200	

Mechanical tests, all weld metal	EN10204
----------------------------------	---------

Additional information Other tests	EN10204
---------------------------------------	---------

## Remarks

The product identified above has been manufactured, tested and supplied in compliance with a Quality Assurance Programme that fulfils the requirements of EN 29000/ ISO 9000/BS 5750 or similar standard.  
We herewith certify that the product complies with the above-mentioned standards.  
Certified ISO 9001:2000.

Company	Issued by	Function	Date	Cert.No.
Lincoln Smitweld B.V.	P. van Etteger	QS Manager	10/02/2005	3018926/7830

Registered Office  
Nieuwe Dukenburgseweg 20  
6534 AD NIJMEGEN



Telephone:  
31 24 3522911

Fax:  
31 24 3522200





2810 Clark Avenue • St. Louis, MO 63103-2574 • (314) 531-8080 • FAX (314) 531-8085  
 Chemical, Metallurgical, Mechanical, Nondestructive, Environmental Testing, Analyses and Field Service.

**METALTEK INTERNATIONAL**  
 8600 Commercial Blvd.  
 Pevely, MO 63070

August 8, 2005  
 Lab No. 05P-2334  
 P.O. No. 21024  
 Page 1 of 3

Attention: **CHUCK RUUD**

**REPORT OF MECHANICAL TESTS**

- SAMPLE ID:**
- 1) STOCK# LNM 4455, LINCOLN LOT 3018926/78309
  - 2) STOCK# LNM 4455, LINCOLN LOT 3017006/72262
  - 3) STOCK# LNM 4455, LINCOLN LOT 3012668/82743
  - 4) STOCK# B316NF METRODE, W021735

Sample ID	Original Area Sq. Inches	Reduced Area Sq. Inches	Reduction in Area %	Modules of Elasticity	Yield Strength PSI	Tensile Strength PSI	Elongation (2.0" Gage Length)	
							in.	%
1	0.1385	0.0897	54.3	24.5 Msi	56900	93900	0.84	42.0
2	0.1886	0.0935	50.4	24.9 Msi	54900	92100	0.85	42.5
3	0.1909	0.0951	50.2	22.6 Msi	57400	93700	0.83	41.5
4	0.1901	0.0962	49.4	23.0 Msi	54800	88200	0.75	37.5


Round, reduced section all weld tensiles

Yield taken at .2% offset

Tested in accordance with ASTM A 370-03a

*Identification of tested specimens provided by the client.*


KS/tlv

  
 Karl Schmitz, Director  
 Materials Testing



Certificate No. 0397-01  
 Certificate No. 0397-02

AN OFFICIAL COPY OF TEST REPORT WILL BE PROVIDED BY THIS LABORATORY ON REQUEST.  
 NOT OFFICIAL WITHOUT THE RAISED SEAL OF ST. LOUIS TESTING LABORATORIES, INC.  
 SEE REVERSE FOR CONDITIONS.





2810 Clark Avenue • St. Louis, MO 63103-2574 • (314) 531-8080 • FAX (314) 531-8085  
 Chemical, Metallurgical, Mechanical, Nondestructive, Environmental Testing, Analyses and Field Service.

**METALTEK INTERNATIONAL**  
 8600 Commercial Blvd.  
 Pevely, MO 63070

August 8, 2005  
 Lab No. 05P-2334  
 P.O. No. 21324  
 Page 2 of 3

Attention: Chuck Ruud

**REPORT OF CHARPY IMPACT TEST**

**MATERIAL (SAMPLE ID):** STOCK# LNM 4455, LINCOLN LOT 3018926/78309  
 STOCK# LNM 4455, LINCOLN LOT 3017006/72262

**SPECIFICATION:** ASTM A 370-03a  
**SPECIMEN TYPE:** "A" Vee Notch  
**SPECIMEN SIZE:** 10 mm x 10 mm (All Weld)  
**TEMPERATURE OF TEST:** 293°K

**REQUIREMENTS:**

ALL WELD	FOOT LBS.	LATERAL EXPANSION	% SHEAR
78309-7	97	0.074	50
78309-8	96	0.076	50
78309-9	108	0.075	50
<b>Average</b>	100	0.075	50
ALL WELD	FOOT LBS.	LATERAL EXPANSION	% SHEAR
72262-7	126	0.098	50
72262-8	102	0.080	50
72262-9	123	0.087	50
<b>Average</b>	117	0.088	50

Identification of tested specimen provided by client.

KS/tlv

*[Signature]*  
 Karl Schmitz, Director  
 Materials Testing



Certificate No. 0397-01  
 Certificate No. 0397-02

AN OFFICIAL COPY OF TEST REPORT WILL BE PROVIDED BY THIS LABORATORY ON REQUEST.  
 NOT OFFICIAL WITHOUT THE RAISED SEAL OF ST. LOUIS TESTING LABORATORIES, INC.  
 SEE REVERSE FOR CONDITIONS.



# Westmoreland Mechanical Testing & Research, Inc.

P.O. Box 388

Westmoreland Drive

Youngstown, Pa. 15696-0388 U.S.A.


Telephone: 724-537-3131 Fax: 724-537-3151

Website: [www.wmtr.com](http://www.wmtr.com)

WMT&R is a technical leader in the material testing industry.



621-01 & 621-02



September 13, 2005

## CERTIFICATION

MetalTek International  
The Carondelet Division  
8600 Commercial Blvd.  
I-55 Industrial Park  
Pevely, MO 63070-1528

Attention: Jim Galaske

Subject: All processes, performed upon the material as received, were conducted at WMT&R, Inc. in accordance with the WMT&R Quality Assurance Manual, Rev. 9, dated 4/1/2000.  
The following tests were performed on this order: IMPACT and TENSILE

WMT&R Report No. 5-34328  
P.O. No. 19386 Rel No.18  
Requisition No. 4934

TENSILE RESULTS: ASTM E21-03a

Requirements: UTS ksi (Min 95\Max ---) 0.2% YS ksi (Min 72\Max ---) 4D Elong. % (Min 32\Max ---) Modulus Msi (Min 21\Max ---)

SOAK TIME: 5 Minutes

SPEED OF TESTING: 0.0030 in./in./min., 0.0500 in./min./in.

MATERIAL: 316 S/S

DISPOSITION: Acceptable

Reference	Lot No.   Batch No.   Specimen ID	TestLog Number	Temp. °F	UTS ksi	0.2% YS ksi	Elong %	RA %	Modulus Msi	Ult. Load lbf	0.2% YLD. lbf
Lincoln LNM4455	3018926   78309   Tensile	C43938	-320	182.1	128.2	34	24	27.0	17560	12360

AU/R: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

DISPOSITION: Acceptable

Reference	Lot No.   Batch No.   Specimen ID	TestLog Number	Orig. Dia. (in.)	Final Dia. (in.)	4D Orig GL (in.)	4D Final GL (in.)	Orig. Area (sq. in.)	Machine Number	AU/R
Lincoln LNM4455	3018926   78309   Tensile	C43938	0.3504	0.3048	1.40	1.87	0.09643131	M9	A

AU/R: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

Requirements supplied by MetalTek International.

  
Roy E. Starr (Matt Wojton)  
Technical Services Manager / Tensile Supervisor

9-13-05  
September 13, 2005

KNOWINGLY OR WILLFULLY FALSIFYING OR CONCEALING A MATERIAL FACT ON THIS FORM OR MAKING FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR REPRESENTATIONS HEREIN COULD CONSTITUTE A FELONY PUNISHABLE UNDER FEDERAL STATUTES. THIS CERTIFICATE OR REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT THE WRITTEN APPROVAL OF WMTR, INC.

Testing Specialists for Aerospace, Automotive, and Material Testing Fields  
Locations in Youngstown, PA U.S.A. ~ Tel. (724) 537-3131 and  
Banbury U.K. ~ Tel. +44 (0) 1295 261211

# Westmoreland Mechanical Testing & Research, Inc.

P.O. Box 388

Westmoreland Drive

Youngstown, Pa. 15696-0388 U.S.A.

Telephone: 724-537-3131 Fax: 724-537-3151

Website: [www.wmtr.com](http://www.wmtr.com)

WMT&R is a technical leader in the material testing industry.



621-01 & 621-02

WMT&R Report No. 5-34328

P.O. No. 19386 Rel No.18

Requisition No. 4934

## CERTIFICATION

September 13, 2005

MetalTek International  
The Carondelet Division  
8600 Commercial Blvd.  
I-55 Industrial Park  
Pevely, MO 63070-1528

Attention: Jim Galaske

Subject: All processes, performed upon the material as received, were conducted at WMT&R, Inc. in accordance with the WMT&R Quality Assurance Manual, Rev. 9, dated 4/1/2000.

The following tests were performed on this order: IMPACT and TENSILE

IMPACT RESULTS: ASTM E23-02

REQUIREMENTS: Energy (Min 35\Max ---)


MATERIAL: Lincoln LNM4455

SAMPLE TYPE: Charpy V-Notch

DISPOSITION: Acceptable

Reference	Lot No.   Batch No.   Specimen ID	TestLog Number	Sample Size	Temp. °F	Energy ft-lbs	Mils Lat Exp	% Shear Fracture	AIUR
Lincoln LNM4455	3018926   78309   Cvn-1	C43939	Standard	-320	56	18	40	Acceptable
Lincoln LNM4455	3018926   78309   Cvn-2	C43940	Standard	-320	52	18	40	Acceptable
Lincoln LNM4455	3018926   78309   Cvn-3	C43941	Standard	-320	53	12	40	Acceptable


Requirements supplied by MetalTek International.

  
Roy E. Star, Matt Wojton  
Technical Services Manager / Tensile Supervisor

9-13-05  
September 13, 2005

KNOWINGLY OR WILLFULLY FALSIFYING OR CONCEALING A MATERIAL FACT ON THIS FORM OR MAKING FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR REPRESENTATIONS HEREIN COULD CONSTITUTE A FELONY PUNISHABLE UNDER FEDERAL STATUTES. THIS CERTIFICATE OR REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT THE WRITTEN APPROVAL OF WMT&R, INC.

Testing Specialists for Aerospace, Automotive and Material Testing Fields  
Locations in Youngstown, PA U.S.A. ~ Tel. (724) 537-3131 and  
Banbury U.K. ~ Tel. +44 (0) 1295 261211



# Westmoreland Mechanical Testing & Research, Inc.

P.O. Box 388

Westmoreland Drive

Youngstown, Pa. 15696-0388 U.S.A.

Telephone: 724-537-3131 Fax: 724-537-3151

Website: [www.wmtr.com](http://www.wmtr.com)

WMT&R is a technical leader in the material testing industry.



621-01 & 621-02



June 17, 2005

## CERTIFICATION

MetalTek International  
The Carondelet Division  
8600 Commercial Blvd.  
I-55 Industrial Park  
Pavely, MO 63070-1528

Section 1 of 1

WMT&R Report No. 5-29323

Req. No. 5394

Attention: Rick Suria

Subject: All processes, performed upon the material as received, were conducted at WMT&R, Inc. in accordance with the WMT&R Quality Assurance Manual, Rev. 9, dated 4/1/2000.  
The following tests were performed on this order: TENSILE

TENSILE RESULTS: ASTM E21-03a

SOAK TIME: 5 Minutes

SPEED OF TESTING: 0.0030 in./in./min., 0.0500 in./min./in.

MATERIAL: Metaltek CF8MNMnMOD

DISPOSITION: Report

Sample	Test Log Number	Temp. °F	UTS ksi	0.2% YS ksi	Elong %	RA %	Modulus Msi	Codes	Ult Load lbf	0.2% YLD. lbf	Orig. Dia. (in.)	Final Dia. (in.)	4D Orig GL (in.)	4D Final GL (in.)	Orig. Area (sq. in.)	Machine Number	AIUR
A1 (Z1)	C03040	-320	165.1	95.5	51	37	25.9	---	33210	19210	0.5060	0.4002	2.00	3.02	0.20109020	M9	R
A1 (Z2)	C03041	-320	165.1	94.6	59	51	25.4	---	33120	18980	0.5054	0.3543	2.00	3.18	0.20061359	M9	R
A1 (Z3)	C03042	-320	168.7	101.8	58	57	25.2	---	33840	20420	0.5054	0.3305	2.00	3.16	0.20061359	M9	R
C2 (Z1)	C03043	-320	163.6	94.0	51	41	25.9	D	32840	18880	0.5056	0.3891	2.00	3.03	0.20077240	M9	R
C2 (Z2)	C03044	-320	162.4	91.7	61	61	25.0	---	32580	18390	0.5054	0.3163	2.00	3.21	0.20061359	M9	R
C2 (Z3)	C03045	-320	165.5	93.9	61	61	25.7	---	33230	18850	0.5056	0.3163	2.00	3.21	0.20077240	M9	R

AIUR: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

D - Failed outside middle half of gage length.

KNOWINGLY OR WILLFULLY FALSIFYING OR CONCEALING A MATERIAL FACT ON THIS FORM OR MAKING FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR REPRESENTATIONS HEREIN COULD CONSTITUTE A FELONY PUNISHABLE UNDER FEDERAL STATUTES. THIS CERTIFICATE OR REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL WITHOUT THE WRITTEN APPROVAL OF WMT&R, INC.

*Matthew J. Winton*  
Roy E. Star (Matt Winton)  
Technical Services Manager / Tensile Supervisor

6-17-05  
June 17, 2005

Testing Specialists for Aerospace, Automotive, and Material Testing Fields  
Locations in Youngstown, PA U.S.A. ~ Tel: (724) 537-3131 and  
Banbury U.K. ~ Tel: +44 (0) 1295 261211

**METALTEK INTERNATIONAL**  
 8600 Commercial Blvd.  
 Pevely, MO 63070

June 14, 2005  
 Lab No. 05P-1741  
 P.O. No. 12516  
 Page 1 of 3

Attention: Chuck Ruud

**REPORT OF CHARPY IMPACT TEST**

**MATERIAL (SAMPLE ID):** Alloy CF8 MNMn-Mod, A-1 COIL  
**SPECIFICATION:** ASTM A 370-03a  
**SPECIMEN TYPE:** "A" Vee Notch  
**SPECIMEN SIZE:** 10 mm x 10 mm  
**TEMPERATURE OF TEST:** 293°K / 68° F

**RESULTS:**

BASE METAL	FOOT LBS.	LATERAL EXPANSION	% SHEAR
Z1-7	152	0.125	100
Z1-8	152	0.086	100
Z1-9	182	0.089	100
<b>Average</b>	162	0.100	100
BASE METAL	FOOT LBS.	LATERAL EXPANSION	% SHEAR
Z2-7	152	0.131	100
Z2-8	164	0.084	100
Z2-9	170	0.105	100
<b>Average</b>	162	0.107	100
BASE METAL	FOOT LBS.	LATERAL EXPANSION	% SHEAR
Z3-7	196	0.117	100
Z3-8	164	0.104	100
Z3-9	142	0.088	100
<b>Average</b>	167	0.103	100

Identification of tested specimen provided by client.

Karl Schmitz, Director  
 Materials Testing



**METALTEK INTERNATIONAL**  
 8600 Commercial Blvd.  
 Pevely, MO 63070

June 14, 2005  
 Lab No. 05P-1741  
 P.O. No. 12516  
 Page 2 of 3

Attention: Chuck Ruud

**REPORT OF CHARPY IMPACT TEST**

**MATERIAL (SAMPLE ID):** Alloy CF8 MNMn-Mod, A-1 COIL  
**SPECIFICATION:** ASTM A 370-03a  
**SPECIMEN TYPE:** "A" Vee Notch  
**SPECIMEN SIZE:** 10 mm x 10 mm  
**TEMPERATURE OF TEST:** 77°K / -320°F

**RESULTS:**

BASE METAL	FOOT LBS.	LATERAL EXPANSION	% SHEAR
Z1-7	82	0.040	60
Z1-8	73	0.053	60
Z1-9	78	0.045	60
<b>Average</b>	78	0.046	60
BASE METAL	FOOT LBS.	LATERAL EXPANSION	% SHEAR
Z2-7	94	0.061	70
Z2-8	90	0.053	70
Z2-9	76	0.057	70
<b>Average</b>	87	0.057	70
BASE METAL	FOOT LBS.	LATERAL EXPANSION	% SHEAR
Z3-7	59	0.028	30
Z3-8	83	0.059	40
Z3-9	72	0.043	40
<b>Average</b>	71	0.043	37

Identification of tested specimen provided by client.

*Karl Schmitz*  
 Karl Schmitz, Director  
 Materials Testing





2810 Clark Avenue • St. Louis, MO 63103-2574 • (314) 531-8080 • FAX (314) 531-8085

**METALTEK INTERNATIONAL**  
 8600 Commercial Blvd.  
 Pevely, MO 63070

June 14, 2005  
 Lab No. 05P-1741  
 P.O. No. 12516  
 Page 3 of 3

**Attention: CHUCK RUUD**

**REPORT OF MECHANICAL TESTS**

**SAMPLE ID:** 3 EA., A-1 COIL, Z1, Z2, Z3

Sample ID	Original Area Sq. Inches	Reduced Area Sq. Inches	Reduction in Area %	Modules of Elasticity	Yield Strength PSI	Tensile Strength PSI	Elongation (2.0" Gage Length)	
							in.	%
Z1	0.1886	.0716	62.0	21.8 Msi	37600	85700	1.06	53.0
Z2	0.1886	0.0707	62.5	21.5 Msi	35500	79300	1.11	55.5
Z3	0.1940	0.0855	55.9	21.7 Msi	36800	82100	1.02	51.0


Round, reduced section room temperature tensiles

Yield taken at .2% offset

Tested in accordance with ASTM A 370

*Identification of tested specimens provided by the client.*

KS/tlv

  
 Karl Schmitz, Director  
 Materials Testing






# A-1 COIL WELD MAP

Defect Number	Drawing View	Length Inches	Width Inches	Depth Inches	Over 20% wall Over 1 inch Over 10 <sup>2</sup> inches Yes/No
1	Front	48	1 1/2	1/2	Yes
5	Front	7	5 1/4	1	Yes
9	Front	3 3/4	2	1 1/8	Yes
10	Front	5 1/2	4 1/2	1 3/4	Yes
11	Front	2 1/2	2	1	Yes
23	Front	7	2 1/2	1/2	Yes
24	Front	11	2 1/2	1 1/2	Yes
32	Front	4	2 1/4	1	Yes
42	Front	5	2 1/2	2 1/4	Yes
46	Front	28 1/2	6	Through	Yes
51	Front	9	3	1/4	Yes
55	Front	10	1 1/2	1	Yes
56	Front	6	2 1/4	2	Yes
63	Front	10	8 1/2	3/4	Yes
64	Front	7	3	1/4	Yes
69	Front	5 1/4	5	1/2	Yes
72	Front	9	6 1/2	1	Yes
88	Front	13	1 1/2	2 1/2	Yes
93	Front	11	1 1/2	1 1/2	Yes
95	Front	8	4	1	Yes
102	Front	3 1/2	3 1/4	1 1/8	Yes
103	Front	13	3	1	Yes
105	Front	8	3	2	Yes
111	Front	9	4	1	Yes
116	<del>Front</del> TOP	2 1/2	2	7/8	Yes
117	Top	1 1/4	1	3/4	Yes
118	Top	2	1 1/2	3/4	Yes
119	Top	2 1/2	2 1/2	1	Yes
123	Top	9 3/4	4 1/2	2	Yes
128	Top	4 1/4	4	1/4	Yes
131	Top	5	3	1	Yes
135	Top	9 1/2	2	1/4	Yes
140	Right	5 1/2	5	1	Yes
144	Right	6	3	1/4	Yes
145	Right	33	3 1/2	1 3/4	Yes
146	Right	16 3/4	1 1/4	1/4	Yes
147	Right	9	6	1/4	Yes
152	Right	5	3 3/4	Through	Yes
154	Right	8	4	Through	Yes


# A-1 COIL WELD MAP

Defect Number	Drawing View	Length Inches	Width Inches	Depth Inches	Over 20% wall Over 1 inch Over 10 <sup>2</sup> inches Yes/No
155	Right	8 1/2	7	1/4	Yes
157	Right	6 3/4	4	1/4	Yes
158	Right	7 1/2	3 1/4	1/4	Yes
162	Right	7	2	1/2	Yes
166	Right	4 3/4	2	1	Yes
168	Right	9	4 1/2	1/4	Yes
170	Right	5 3/4	2	3/4	Yes
171	Right	10	3	Through	Yes
172	Right	7 1/2	3	1/2	Yes
173	Right	9	3 1/2	1/2	Yes
176	Right	5 1/2	3	Through	Yes
177	Right	9 1/2	1 3/4	5/16	Yes
181	Right	4	3 1/2	1/4	Yes
183	Right	10	2	1/2	Yes
191	Right	3 3/4	3 1/2	2	Yes
197	Right	4	3 1/2	3/4	Yes
198	Right	5	2 3/4	Through	Yes
204	Right	16	2 1/2	5/16	Yes
205	Bottom	7 1/2	6 1/2	Through	Yes
206	Bottom	3 1/2	1 3/4	1	Yes
207	Bottom	8	2 1/2	3/16	Yes
212	Bottom	9	4	1/4	Yes
214	Bottom	8 3/4	5	3/4	Yes
216	Bottom	7	2	1	Yes
220	Left	6 3/4	4	Through	Yes
222	Left	4 1/2	2	1	Yes
228	Back	13	8	Through	Yes
234	Back	13/4	13/4	1 1/4	Yes
237	Back	5	2 1/4	3/4	Yes
239	Back	5 1/2	5	3/4	Yes
240	Back	6 1/2	2 3/4	1	Yes
242	Back	9	3 1/2	Through	Yes
246	Back	5 3/4	4 1/2	3/4	Yes
256	Back	3	2 3/4	7/8	Yes
259	Back	6	2 1/2	1	Yes
260	Back	6	2	3/4	Yes
271	Back	4	2 1/2	1	Yes
273	Back	6 1/2	4 1/2	Through	Yes
281	Back	3 1/2	2	1	Yes







Front




Back



Top



Bottom



Left





Right

# TEAM COOPERHEAT-MQS, INC.

## RADIOGRAPHIC TECHNIQUE SHEET

FORM 20.3-61 Rev. 4

5512 W. State St-Milwaukee, WI 53208 (414) 771-3060 Fax (414)771-9481 (800) 818-6403 www.cooperheat-mqs.com

CUSTOMER RSS NO.: \_\_\_\_\_ SHEET: \_\_\_\_\_ REV: \_\_\_\_\_ MQS TECH. NO.: 13043  
 MQS RSS NO.: \_\_\_\_\_

CUSTOMER METALTEK INTERNATIONAL / CARONDOLET DIV. DATE: 6/16/2005

PART NO. MCWF-A DESCRIPTION A-COIL MATERIAL SS

TOTAL NUMBER OF VIEWS 117 NUMBER X-RAY VIEWS 117 NUMBER GAMMA RAY VIEWS 0

MACH(s) MAKE(s) VARIAN MODEL(s) L2000 S/N(s) 20 MAX KV(s) 7500

SOURCE(s) N/A

PROCEDURE SPECIFICATION ASTM E94-93 ACCEPTANCE CRITERIA MSS-SP-54-1999

MQS PROCEDURE NO. 20.H.010 REV. 0 PENETRAMETER SPEC. ASTM E142-86

PROCESSING: AUTOMATIC  PROCESSOR B2000 MANUAL  TEMPERATURE 27.5°

TECHNICIAN JP,SS,ST NDT LEVEL II APPROVED BY C RUDOLPH NDT LEVEL III

VIEW IDENTIFICATION	SEE ATTACHED				
SOURCE/X-RAY MACH USED	VARIAN				
CURIES OR KV	7500 KV				
MA OR PULSES	N/A				
SOURCE TO FILM DISTANCE	*				
EXPOSURE TIME OR RADS	*				
MATERIAL THICKNESS	*				
MATERIAL GROUP	1				
PENETRAMETER SIZE/(AMT)	GP. 1	*			
SHIM BLOCK SIZE	GP. <input type="checkbox"/>	N/A			
FILM SIZE	*				
FILM TYPE/BRAND	*				
PB SCREEN, FRONT	.010				
PB SCREEN, BACK	.010				
SENSITIVITY	2-2T				
FILTER TYPE/LOCATION	N/A				
MASKING TYPE/LOCATION	N/A				
ANGLE	N/A				
NO. OF FILMS IN CASSETTE	*				
VIEWING: SING./DOUB./BOTH	B				
FOCAL SPOT SIZE	2 MM				
SKETCH AND/OR REMARKS	*				
GEOMETRIC UNSHARPNESS	N/A				

\*\*ATTACHED PHOTOS PG. 1-15



CUSTOMER METALTEK INT./CARONDOLET RSS # 13043 PART NO. MCWF-A

VIEW	SFD	EXP. TIME	FILM TYPE	FILM SIZE	THK. RANGE	IQI
30-31	75"	35 KR	T	14 X 17	2.75"	50 (2)
31-32	75"	35 KR	T	14 X 17	2.75"	50 (2)
32-33	75"	35 KR	T	14 X 17	2.75"	50 (2)
33-34	75"	35 KR	T	14 X 17	2.75"	50 (2)
34-35	75"	35 KR	T	14 X 17	2.75"	50 (2)
35-36	75"	35 KR	T	14 X 17	2.75"	50 (2)
37-38	75"	35 KR	T	14 X 17	2.75"	50 (2)
38-39	75"	35 KR	T	14 X 17	2.75"	50 (2)
39-40	75"	35 KR	T	14 X 17	2.75"	50 (2)
41-42	75"	90 KR	AA-M100-T	14 X 17	2.75 X 5.5"	50 (2), 100 (2)
43-44	75"	90 KR	AA-M100-T	14 X 17	2.75 X 5.5"	50 (2), 100 (2)
44-45	75"	75 KR	AA-M100	14 X 17	2.75 X 5.5"	50 (2), 100 (2)
45-46	75"	75 KR	AA-M100	14 X 17	2.75 X 5.5"	50, 100 (2)
46-47	75"	75 KR	AA-AA	14 X 17	5.5"	100 (2)
47-48	75"	75 KR	AA-AA	14 X 17	5.5"	100 (2)
48-49	75"	75 KR	AA-AA	14 X 17	5.5"	100 (2)
50-51	75"	35 KR	T	14 X 17	2.75"	50 (2)
51-52	75"	35 KR	T	14 X 17	2.75"	50 (2)
52-53	75"	35 KR	T	14 X 17	2.75"	50 (2)
54-55	75"	35 KR	T	14 X 17	2.75"	50 (2)
55-56	75"	35 KR	T	14 X 17	2.75"	50 (2)
57-58	97"	45 KR	M125-T	14 X 17	1.5 - 1.75"	30, 35
58-58A-59	80"	110 KR	D8-R50-T-D8	14 X 17	1.5 - 8"	30, 100, 140, 160
59-60	80"	30 KR	M125-T	14 X 17	1.5"	30 (2)
60-61	80"	30 KR	M125-T	14 X 17	1.5"	30 (2)
61-62	80"	30 KR	M125-T	14 X 17	1.5"	30 (2)
62-63	85"	90 KR	D8-M125-D8	14 X 17	3 - 8"	60, 120, 160
62A-63A	85"	90 KR	D8-M125-Dumb	14 X 17	3 - 6"	60, 120
63-64	80"	45 KR	AA-M125-M100-T	14 X 17	1.5 - 4"	30 (2), 50, 80
64-65	80"	45 KR	M125-M100	14 X 17	1.5"	30 (2)
65-65A-66	80"	95 KR	AA-M125-T	14 X 17	1.5 - 5.5"	30, 100 (2)
66-67	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
67-68	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
68-69	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
69-70	80"	40 KR	AA-M100-T	14 X 17	1.5 - 3"	30 (2), 50, 60
70-71	80"	40 KR	AA-M100-T	14 X 17	1.5 - 4"	30 (2), 60, 80
71-72	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
72-73	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
73-74	80"	60 KR	AA-AA	14 X 17	3 - 6"	60, 100, 120
74-75	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
75-76	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
76-77	80"	40 KR	M125-M100	14 X 17	1.5"	30 (2)
77-78	80"	150 KR	D8-AA-T-D8	14 X 17	3 - 8"	60, 80, 100, 120, 160
78-79	80"	40 KR	AA-M125-T	14 X 17	1.5 - 3"	30 (2), 40, 60
79-80	85"	50 KR	T/M100	14 X 17	1.5 - 3"	30 (2), 40, 50, 60
80-81	80"	40 KR	T/M100	14 X 17	1.5 - 2.5"	30 (2), 40, 50

Form 20.4 - 61 Attachment A

CUSTOMER METALTEK INT./CARONDOLET RSS # 13043 PART NO. MCWF-A

VIEW	SFD	EXP. TIME	FILM TYPE	FILM SIZE	THK. RANGE	IQI
81-82	80"	40 KR	T-M100	14 X 17	1.5 - 2.5"	30(2),40,50
82-83	80"	40 KR	T-M100	14 X 17	1.5 - 2.50"	30(2),40,50
84-85	75"	90 KR	D8-R50-M125-T	14 X 17	1.5 - 6"	30,50,60,80,100,120
85-86	75"	60 KR	T-R50-M125	14 X 17	1.5 - 4"	30,40,50,60,80
86-87	75"	60 KR	AA-M125-T	14 X 17	1.5 - 5"	30, 50, 60, 80, 100
87-88A	70"	60 KR	AA-M125-T	14 X 17	3" - 5"	60,80,100
88-89	80"	40 KR	M125-M100	14 X 17	1.5"	30(2)
89-90	80"	40 KR	M125-M100	14 X 17	1.5"	30(2)
90-91	80"	40 KR	M125-M100	14 X 17	1.5"	30(2)
92-93	65"	30 KR	T-M125	14 X 17	1.5 - 3"	30(2),40,60
94-95	84"	40 KR	T	14 X 17	2.75"	50(2)
95-96	84"	40 KR	T	14 X 17	2.75"	50(2)
96-97	84"	40 KR	T	14 X 17	2.75"	50(2)
97-98	84"	40 KR	T	14 X 17	2.75"	50(2)
98-99	84"	40 KR	T	14 X 17	2.75"	50(2)
99-100	84"	40 KR	T	14 X 17	2.75"	50(2)
100-101	84"	40 KR	T	14 X 17	2.75"	50(2)
102-103	84"	40 KR	T	14 X 17	2.75"	50(2)
103-104	84"	40 KR	T	14 X 17	2.75"	50(2)
104-105	84"	40 KR	T	14 X 17	2.75"	50(2)
106-107	84"	40 KR	T	14 X 17	2.75"	50(2)
107-108	84"	40 KR	T	14 X 17	2.75"	50(2)
108-109	84"	40 KR	T/M125	14 X 17	1.5 - 2.75"	30,50(2)
109-110	84"	40 KR	T/M125	14 X 17	1.5 - 2.75"	30,50(2)
111-112	84"	40 KR	T	14 X 17	2.75"	50(2)
112-113	84"	40 KR	T	14 X 17	2.75"	50(2)
113-114	84"	40 KR	T	14 X 17	2.75"	50(2)
115-116	84"	40 KR	T	14 X 17	2.75"	50(2)
116-117	84"	40 KR	T	14 X 17	2.75"	50(2)
118-119	80"	55 KR	M125/M100	14 X 17	1.5"	30(2)
119-120	80"	55 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
121-122	80"	40 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
122-123	80"	40 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
123-124	80"	40 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
124-125	80"	40 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
125-126	80"	40 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
126-127	80"	40 KR	M125/M100	14 X 17	1.5 - 2"	30(2), 40
127-128	80"	50 KR	D8/M100/M125	14 X 17	1.5 - 6"	30(2),120
128-129	80"	40 KR	M125/M100	14 X 17	1.5"	30(2)
130-131	80"	40 KR	M125/M100	14 X 17	1.5"	30(2)
131-132	80"	40 KR	M125/M100	14 X 17	1.5"	30(2)
V133	80"	50 KR	D8/M125/AA	7 X 17	1.5 - 6"	30(2),120,140
V134	80"	50 KR	D8/M125/AA	7 X 17	1.5 - 6"	30(2),120,140

Form 20.4 - 61 Attachment A

Page 4 of 4




1-1



1-2



1-3



1-4



1-5



1-6



2-1



2-2



2-3



2-4



3-1



3-2



3-2



3-4



3-5



3-6



3-7



3-8





3-9



3-10



3-11



3-12



3-13



3-14



3-15



3-16



3-17



3-18



3-19



3-20



3-21



3-22



3-23



3-24



3-25



3-26



3-27



3-28



3-29



3-30



4-1



4-2



4-3



4-4



4-5



4-6



4-7



5-1



5-2



5-3



5-4



5-5



5-6



5-7



5-8



6-1



6-2



6-3



6-4



6-5



6-6



6-7



6-8



6-9



6-10



# TEAM COOPERHEAT-MQS, INC.

## CERTIFIED RADIOGRAPHIC INSPECTION REPORT

FORM 6061-RT- 002 Rev.2

5512 W. State St. Milwaukee, WI 53208 Tel:(414)771-3060 Fax:(414)771-9481 (800)818-6403 www.cooperheat-mqs.com

CUSTOMER		DATE	WORK ORDER NO.
NAME METAL TEK INTERNATIONAL		06/16/2005	361-02341
ADDRESS 8600 COMMERCIAL BLVD		P.O. NUMBER Rick Suria	XRAY X
CITY PEVELY STATE MO ZIP 63070			GAMMA
PROCEDURE SPECIFICATION ASTM E94-93	ACCEPTANCE CRITERIA MSS-SP-54-1999	SHEET 1 OF 5	

PART NUMBER	Serial No	View	No Apparent Indications		Incomplete Penetration		Shrinkage		Film Artifacts			REMARKS
			Acceptable	Rejection	Dross or Slag	Porosity	Lack of Fusion	Hot Tears	Undercut	Surface		
MCWFA-1	1	1-2	✓									
		2-3		R			4					✓
Z103990		3-4	✓		1		1					
HT# M169470		4-5		R			4					
CO40851		5-6	✓				2					
		6-7		R			4					
		7-8	✓				4					
		8-9	✓		2							✓
		9-10	✓		2							✓
		10-11	✓									✓
		11-12	✓		2							✓
		12-13	✓									✓
		13-14	✓									✓
		V15		R	2			4				✓
		16-17	✓									
		17-18	✓				1					
		18-19	✓				2					
		19-20	✓									
		20-21	✓		1							✓
		21-22	✓		1		1					✓
		22-23	✓									✓
		23-24	✓					2				✓
		24-25		R			2					
		25-26	✓									
		26-27		R								

ACCEPTED	NO. REJECTED 1	MQS TECH. NO. 12970	SHT.	REV.
COMMENTS		CUST. RSS NO.	SHT.	REV.
* Extra Film Shot For Pen Coverage.		REVIEWER <i>John Petroske</i>		
		CERTIFIED NOT LEVEL (RT)		
		John Petroske RT II Exp. 01/08		

# TEAM COOPERHEAT-MQS, INC.

## CERTIFIED RADIOGRAPHIC INSPECTION REPORT

FORM 6061-RT- 002 Rev.2

5512 W. State St. Milwaukee, WI 53208 Tel:(414)771-3060 Fax:(414)771-9481 (800)818-6403 www.cooperheat-mqs.com

CUSTOMER		DATE	WORK ORDER NO.
NAME METAL TEK INTERNATIONAL		06/16/2005	361-02341
ADDRESS 8600 COMMERCIAL BLVD		P.O. NUMBER	XRAY X
CITY PEVELY STATE MO ZIP 63070		Rick Suria	GAMMA
PROCEDURE SPECIFICATION ASTM E94-93	ACCEPTANCE CRITERIA MSS-SP-54-1999	SHEET <u>2</u> OF <u>5</u>	

PART NUMBER	Serial No	View	No Apparent Indications		Incomplete Penetration		Shrinkage		Film Artifacts		REMARKS
			Acceptable	Rejected	Dross or Slag	Porosity	Lack of Fusion Gas Cracks	Hot Tears	Under cut	Surface	
MCWFA-1	1	27-28		R				4			
		28-29		R				2	4	R	
Z103990		29-1		R				4			
T# M169470		30-31		R						R	
CO40851		31-32		R					4		
		32-33		R				5		R	
		33-34	✓								
		34-35	✓								
		35-36		R						R	✓
		37-38		R						R	✓
		38-39	✓								✓
		39-40	✓								✓
		41-42		R						R	✓
		43-44	✓					1			
		44-45	✓								
		45-46	✓								
		46-47	✓								
		47-48	✓								
		48-49	✓								
		50-51		R	4						
		51-52		R	4						
		52-53		R	4					R	
		54-55	✓								
		55-56	✓								

ACCEPTED COMMENTS	NO. REJECTED	MQS TECH. NO.	SHT.	REV.
0	1	12970		
		CUST. RSS NO.	SHT.	REV.
		REVIEWER <i>John Petroske</i>		
		CERTIFIED NDT LEVEL (RT)		
		John Petroske RT II Exp. 01/08		

# TEAM COOPERHEAT-MQS, INC.

## CERTIFIED RADIOGRAPHIC INSPECTION REPORT

FORM 6061-RT- 002 Rev.2

5512 W. State St. Milwaukee, WI 53208 Tel:(414)771-3060 Fax:(414)771-9481 (800)818-6403 www.cooperheat-mqs.com

CUSTOMER		DATE	WORK ORDER NO.
NAME METAL TEK INTERNATIONAL		06/16/2005	361-02341
ADDRESS 8600 COMMERCIAL BLVD		P.O. NUMBER Rick Suria	XRAY X
CITY PEVELY STATE MO ZIP 63070			GAMMA
PROCEDURE SPECIFICATION ASTM E94-93	ACCEPTANCE CRITERIA MSS-SP-54-1999	SHEET 3 OF 5	

PART NUMBER	Serial No	View	No Apparent Indications		Incomplete Penetration		Shrinkage		Film Artifacts			REMARKS
			Acceptable	Rejection	Inclusion or Slag	Porosity	Lack of Fusion	Gas Cracks	Hot Tears	Undercut	Surface	
MCWFA-1	1	57-58	✓									
		58-58A-59	✓					1				
Z103990		59-60	✓									
HT# M169470		60-61	✓									
CO40851		61-62	✓		2						✓	
		62-63		R						R		
	62A-	63A		R						R		
		63-64		R			4	2				
		64-65	✓				2					
	65-	65A-66		R				2	R			
		66-67		R			4					
		67-68	✓								✓	✓
		68-69		R			4	3-4				
		69-70		R				4				
		70-71	✓					2				
		71-72		R				4				
		72-73	✓									
		73-74	✓									
		74-75	✓									
		75-76	✓					1			✓	
		76-77		R							✓	✓
		77-78	✓					4				✓
		78-79	✓									
		79-80	✓									
		80-81	✓									
ACCEPTED COMMENTS			φ	NO. REJECTED			1	MQS TECH. NO.		12970	SHT.	REV.
								CUST. RSS NO.			SHT.	REV.
								REVIEWER		<i>John Petroske</i>		
								CERTIFIED NDT LEVEL (RT)		John Petroske RT II Exp. 01/08		

# TEAM COOPERHEAT-MQS, INC.

## CERTIFIED RADIOGRAPHIC INSPECTION REPORT

FORM 6061-RT- 002 Rev.2

5512 W. State St. Milwaukee, WI 53208 Tel:(414)771-3060 Fax:(414)771-9481 (800)818-6403 www.cooperheat-mqs.com

CUSTOMER		DATE	WORK ORDER NO.
NAME METAL TEK INTERNATIONAL		06/16/2005	361-02341
ADDRESS 8600 COMMERCIAL BLVD		P.O. NUMBER	XRAY X
CITY PEVELY STATE MO ZIP 63070		Rick Suria	GAMMA
PROCEDURE SPECIFICATION ASTM E94-93	ACCEPTANCE CRITERIA MSS-SP-54-1999	SHEET <u>4</u> OF <u>5</u>	

PART NUMBER	Serial No	View	No Apparent indications		Dross		Incomplete Penetration		Shrinkage		Firm Artifacts			REMARKS
			Acceptable	Rejected	Included	or Porosity	Lack of Fusion	Gas Cracks	Hot Tears	Under cut	Surface			
MCWFA-1	1	81-82	✓						2					
		82-83	✓											
Z103990		84-85	✓										✓	
HT# M169470		85-86	✓										✓	
CO40851		86-87	✓						2					
		87-88A	✓						1					
		88-89	✓					1					✓	
		89-90	✓					1					✓	
		90-91	✓										✓	
		92-93			R									
		94-95			R				5					
		95-96			R				5					
		96-97			R				5					
		97-98			R									
		98-99			R									
		99-100	✓						4					
		100-101	✓						2					
		102-103	✓						2					
		103-104	✓						2				✓	
		104-105			R				4					
		106-107	✓											
		107-108	✓											
		108-109			R				5				✓	
		109-110	✓						2					
		111-112	✓											

ACCEPTED COMMENTS	NO. REJECTED	1	MQS TECH. NO.	12970	SHT.	REV.
			CUST. RSS NO.		SHT.	REV.
			REVIEWER	<i>John Petroske</i>		

CERTIFIED NDT LEVEL (RT)  
John Petroske RT II Exp. 01/08

# TEAM COOPERHEAT-MQS, INC.

## CERTIFIED RADIOGRAPHIC INSPECTION REPORT

FORM 6061-RT- 002 Rev.2

5512 W. State St. Milwaukee, WI 53208 Tel:(414)771-3060 Fax:(414)771-9481 (800)818-6403 www.cooperheat-mqs.com

<b>CUSTOMER</b> NAME <u>METAL TEK INTERNATIONAL</u> ADDRESS <u>8600 COMMERCIAL BLVD</u> CITY <u>PEVELY</u> STATE <u>MO</u> ZIP <u>63070</u>	DATE <u>06/16/2005</u> P.O. NUMBER <u>Rick Suria</u>	WORK ORDER NO. <u>361-02341</u> XRAY <input checked="" type="checkbox"/> X GAMMA <input type="checkbox"/>
PROCEDURE SPECIFICATION <u>ASTM E94-93</u>	ACCEPTANCE CRITERIA <u>MSS-SP-54-1999</u>	SHEET <u>5</u> OF <u>5</u>

PART NUMBER	Serial No	View	No Apparent Indications		Incomplete Penetration		Shrinkage		Film Artifacts		REMARKS
			Acceptable	Rejected	Inclusion or Slag	Porosity	Lack of Fusion	Gas Cracks	Hot Tears	Under cut	
MCWFA-1	112-113		✓								
	113-114			R	5			2			
Z103990	115-116		✓					4			
HT# M169470	116-117			R				2			
CO40851	118-119		✓					4			
	119-120		✓								✓
	121-122		✓								
	122-123		✓								✓
	123-124			R				4			
	124-125			R				4			
	125-126			R							
	126-127		✓					1			
	127-128		✓					1			
	128-129		✓					1			
	130-131		✓								✓
	131-132		✓					1			
	V 133			R				4			
	N 134		✓					1			

NO. ACCEPTED <u>0</u> COMMENTS	NO. REJECTED <u>1</u>	MQS TECH. NO. <u>12970</u>	SHT. <u>  </u>	REV. <u>  </u>
		CUST. RSS NO. <u>  </u>	SHT. <u>  </u>	REV. <u>  </u>
REVIEWER <u>John Petroske</u> CERTIFIED NDT LEVEL (RT) John Petroske RT II Exp. 01/08				



# MetalTek INTERNATIONAL

## RADIOGRAPHIC STANDARD SHOOTING SKETCH

Customer <i>Energy Industries of Ohio</i>	Pattern Number <i>MCWFA-1</i>
Material <i>CF8M MMN MOD 1</i>	Traceability Number
Film Manufacturer	Source Number <i>47.5 ci TR192</i>
IQI LEVEL <u>2-2T</u> From CQP 401 <input checked="" type="checkbox"/> Other (Specify, E.G. 2-4T, 2-1T) <u>N/A</u>	

Exposures (views)	<i>35-36</i>	<i>68-69</i>	<i>69-70</i>	<i>104-105</i>	<i>113-114</i>	<i>124</i>	<i>125</i>	<i>128</i>				
Thickness (IN.)	<i>2 3/4</i>	<i>1 1/2</i>	<i>1 1/2-3</i>	<i>2 3/4</i>	<i>2 3/4</i>	<i>1 1/2-2</i>	<i>1 1/2-2</i>	<i>1 1/2</i>				
S/F Distance (IN.)	<i>16</i>	<i>20"</i>	<i>20"</i>	<i>16"</i>	<i>16"</i>	<i>20"</i>	<i>20"</i>	<i>20"</i>				
Penetrator	<i>50x2</i>	<i>30x2</i>	<i>30x2</i>	<i>50x2</i>	<i>50x2</i>	<i>30x2</i>	<i>30x2</i>	<i>30x2</i>				
Time (MIN.)	<i>30m</i>	<i>17m</i>	<i>12m</i>	<i>30m</i>	<i>28m</i>	<i>12m</i>	<i>12m</i>	<i>12m</i>				
Focal Spot (IN.)	<i>1</i>											
Film Size (IN.)	<i>14x17</i>											
Screen Size (Pb)	<i>.01</i>											
Front/Back												
S.W.E./D.W.E.	<i>SWE</i>											
S.W.V/D.W.V.	<i>SWV</i>											
Film Type	<i>59/80</i>	<i>59/80</i>	<i>59 29</i>	<i>59/80</i>	<i>59/80</i>	<i>59/80</i>	<i>59/80</i>	<i>59/80</i>				
Acceptance Standard	<i>E186</i>	<i>E446</i>	<i>E446</i>	<i>E186</i>	<i>E186</i>	<i>E446</i>	<i>E446</i>	<i>E446</i>				
Severity Level	<i>see Acceptance Standards</i>											


Shooting Sketch (Use Additional Pages as Needed)

*see original drawing*

Technique Prepared By: *Doug Kelly* Level: *IP* Date: *8-30-05*  
 Technique Approved By: \_\_\_\_\_ Level: \_\_\_\_\_ Date: \_\_\_\_\_








TS-1  
 R10 8-30-05  
 A1 COLC  
 169470-1

A+C Shims etc



File

25

**A-1 Coil**

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

1 OF 11 CO# 40851 Dated 3-9-05 Revision: Rev 5 Dated Issued: 5-10-05

OPER. #	STATION	DESCRIPTION OF PROCESS	Name	Date
10	QUALITY RELEASE	REVIEW AND APPROVE MTS. RECEIVED APPROVAL FROM EIO ON <u>5/10/05</u> FROM <u>Kate D.</u> SIGNED QUALITY MANAGER	<u>CAF</u>	<u>5/12/05</u>
15	PATTERN NPA1 SOP 0100REV2	APPLY APPROPRIATE PART NUMBER, SERIAL NUMBER, AND FOUNDRY MARK, TO THE PATTERN. CAST ON BARS REQUIRED. Place numbers on the bars as to their location.	<u>DWC</u>	<u>5-24-05</u>
20	COREMAKE CORE SOP 0100 REV 6 CALIBRATION PER CORE SOP 0200R4/0300R6	MAKE CORES IN SAND MIXTURES AS DESCRIBED BY METALTEK ENGINEERING AND VERIFIED IN MODELING TRIALS. METALTEK CORE SOP 0100 REV 6) CORE WASH WITH ZIRCONIUM CORE WASH. (CALIBRATION OF EQUIPMENT REQUIRED PER CORE SOP 0200,R4 / 0300,R6)  VERIFY COUNT AND INSPECT.	<u>DWC</u>	<u>5-24-05</u>
30	MOLD MOLD SOP 0400 REV 8 CALIBRATION PER MOLD SOP 0900 REV 5 PREPARATION PER MOLD SOP 1100R2/1200R2/13 00R1 SAND TESTING PER MOLD SOP 1400R2/1500R3/16 00R2	MOLD PER WORK INSTRUCTIONS IN MAPICS ROUTING AND SOPS REFERENCED. ENGINEER OF RECORD - ROGER BROMAN, CONSULT ON MOLD-RELATED CONCERNS. MOLD MATERIALS REQUIRED PER MAPICS BOM. NOTIFY ENGINEER OF ANY SUBSTITUTIONS.	<u>DWC</u>	<u>5-24-05</u>
40	POUR MELT SOP 0100R5 MELT SOP 0700R2 MELT SOP 0600R2	METAL MUST BE AOD REFINED OR AOD INGOT. VIRGIN METAL ADDITIONS ALLOWED. RECORD POURING TEMPERATURE: <u>2950</u> CASTING POURED AT: _____ DATE: <u>5/25/05</u> HEAT #'s: <u>29516</u> , <u>29517</u> , <u>29518</u> , <u>29519</u> , <u>29520</u> ELAPSED POUR TIME: <u>1:25</u> KEEL BLOCKS POURED: <u>NA Cast on bars</u> Sample from ladle to be analyzed for final chemical analysis and reported on material certifications. Sample Taken by: <u>SR</u> Analyzed: <u>G. Hurt</u> Date: <u>5-25-05</u>	<u>3 Ladles</u> <u>J. Galante</u>	<u>5-25-05</u>

to Rev  
6.  
Ch

A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

2 OF 11

CO# 40851 Dated 3-9-05 Revision: Rev 6

Dated Issued: 5-29-05

Rep 5  
Stan  
low

50	MELT SOP 0800R2	SHAKEOUT	CA	5-28
60	ARC RISE SOP 0100R1	REMOVE RISERS AS DIRECTED BY SUPERVISOR.	RCC	5-31
70	HEAT TREAT HEAT SOP 0103R5	SOLUTION ANNEAL. MAKE SURE TO BLOCK ALL FLANGES OF FORM AND RACETRACK TO MINIMIZE CREEP DISTORTION. Soak Temp: 2050F, Soak Time: 4HR + 1/2 HR/IN, Quench Type: Air Cool	RLS	6-6-05
75	PHYSICAL TESTING	OBTAIN TEST SPECIMENS AND SUBMIT FOR PHYSICAL TESTING. REPORT RESULTS AS PART OF STEP 510.	DLS	6/2/05
NOTE		<b>THE ORDER OF CLEANING PROCESSES MAY BE ALTERED DUE TO CAPACITY CONSTRAINTS. HOLD POINTS AND COMPLIANCE WILL NOT BE COMPROMISED. EIO WILL BE ADVISED OF ALL CHANGES THAT MAY RESULT IN A REQUEST FOR DEVIATION FROM REQUIREMENTS.</b>	WLH	6/6/05
80	GRIND GSA SOP 0100R3	SWING GRIND TO REMOVE RISER REMAINS AND FLASH IF REQUIRED.	AB	6-6-05
85	GRIND GCHI SOP 0100R2	CHIP AND HAD GRIND SURFACE OF PART AS REQUIRED FOR CONTOUR.	CS	6-10-05
90	SAND BLAST BLAS SOP 0100R6	SANDBLAST (REMOVE ALL BLAST MATERIAL FROM CASTING) SANDBLASTING WILL BE DONE USING RECYCLED SHARP ANGULAR AGGREGATE.	MTW	6/6
NOTICE	WITNESS NOTIFICATION <b>HOLD FOR EIO APPROVAL</b>	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF LAYOUT. EIO NOTIFIED ON <u>6/3/05 pm</u> DCMA NOTIFIED ON <u>6/3/05 pm</u> APPROVAL RECEIVED ON <u>6/7/05 pm</u>	Q ENG OR QA MGR	RS
100	LAYOUT SOP LAYOUT 0100	INSPECT CASTING TO VERIFY DIMENSIONS. THIS STEP MAY BE DELAYED. DIMENSIONED <u>6/7</u> DATE _____ RELEASED <u>RB</u> (ENGINEER ONLY) NOTE: THE FIRST PART PRODUCED OF EACH TYPE A, B AND C WILL BE DIMENSIONED BY <u>LAWTON PATTERN</u> . IF DIMENSIONED BY LAWTON IT WILL BE DOCUMENTED HERE. Subsequent casting done internally per Romer Arm.	Lawton Pattern	6/7



6/7/05

A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

3 OF 11 CO# 40851 Dated 3-9-05 Revision: Rev 6 Dated Issued: 5-29-05

110	VISUAL INSPECTION CQP-500 REV 4	VISUALLY INSPECT 100% of COMPONENT ACCORDING TO ASTM A802 LEVEL 3 ALL CONDITIONS. IF OK CHECK HERE _____ IF REJECTED CHECK HERE ____ . MARK AND REPAIR AT STEP 120.	VT - LEVEL II	<p><i>Expected to RT will perform before return</i></p> <p><i>Coln</i></p> <p>↓</p> <p><i>RS</i></p>
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF LP STEP. EIO NOTIFIED ON <u>5/7/05</u> DCMA NOTIFIED ON <u>5/7/05</u>	Q ENG OR QA MGR	
115	100% L.P. CQP 0300 REV 10	L.P. 100% OF COMPONENT. ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE _____ IF REJECTED CHECK HERE _____ MARK AND REPAIR AT STEP 120.	LP - LEVEL II	
120	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING 100% VISUAL AND LP INSPECTION.		
125	GRIND GCHI SOP 0100R2	CHIP AND HAND GRIND EXCAVATION AS REQUIRED.		
130	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE _____ IF REJECTED SEND BACK TO STEP 125.	LP - LEVEL II	
165	SAND BLAST BLAS SOP 0100R6	SANDBLAST (REMOVE ALL BLAST MATERIAL FROM CASTING) SANDBLASTING WILL BE DONE USING RECYCLED SHARP ANGULAR AGGREGATE.		
170	<b>HOLD POINT WELD MAP</b>	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS INDICATING LOCATION. SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE, FILE WITH QA. USE YELLOW MARKER. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS>10% YES _____, REPORT SENT BY _____ DATE _____ DEFECTS < 10 % _____ SIGN BY QA ENG. <b>MAJOR WELD REPAIRS MAY NOT PROCEED UNTIL INFORMATION IS SUBMITTED.</b>		
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF X-RAY AND DIMENSIONAL STEPS. EIO NOTIFIED ON <u>6/7</u> DCMA NOTIFIED ON <u>5/3 6/7</u>	Q ENG OR QA MGR	

**A-1 Coil**

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

4 OF 11 CO# 40851 Dated 3-9-05 Revision: Rev 6 Dated Issued: 5-29-05

190	X-RAY AT MQS MQS PROCEDURE 20.H.010 REV 0	X-RAY PER TECHNIQUE # 12726 USE CALIBRATED DENSITOMETER FOR DENSITY VERIFICATION. WHEN MARKING USE BLACK MARKERS. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET.	RT - LEVEL II	
210	X-RAY CQP 401 REV 5	X-RAY INTERPRETATION. ACCEPTANCE MSS SP 54. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET. IF OK CHECK HERE _____ AND SEND TO STEP 340. REJECTED CHECK HERE _____ MARK UP DEFECTS AND SEND THE CASTING TO STEP 220.	RT - LEVEL II	
220	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING RADIOGRAPHY.		
225	GRIND GCHI SOP 0100R2	CHIP AND HAND GRIND EXCAVATION AS REQUIRED.		
230	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE _____ IF REJECTED SEND BACK TO STEP 225.	LP - LEVEL II	
240	<b>HOLD POINT</b> WELD MAP	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS INDICATING LOCATION . SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE, FILE WITH QA. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS>10% YES _____, REPORT SENT BY _____ DATE _____ DEFECTS < 10 % _____ SIGN BY QA ENG. <b>MAJOR WELD REPAIRS MAY NOT PROCEED UNTIL INFORMATION IS SUBMITTED.</b> MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER PRIOR TO REPAIR. ONCE THE REPORT IS SENT, WELDING MAY START.		
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF WELD STEP. EIO NOTIFIED ON _____ DCMA NOTIFIED ON _____	Q ENG OR QA MGR	
260	QA APPROVAL HOLD POINT	QA TO APPROVE ELECTRODE PRIOR TO USE. PROCEDURE USED: _____ MATERIAL/LOT USED: _____ QUALITY ENG. Name: _____ Date: _____		
270	WELD SOP 0100 REV 7	WELD REPAIR DEFECTS AS MARKED. FOR WELDS <2" - WPS 10-SMAW-CF8MNMN MOD REV 1 FOR WELDS <8" - WPS 15-GMAW-CF8MNMN MOD REV 2		

*RS 4/24/05 to Rev 7*

A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

4 OF 11 CO# 40851 Dated 3-9-05 Revision: Rev 7 Dated Issued: 6-14-05

190	X-RAY AT MQS MQS PROCEDURE 20.H.010 REV 0	X-RAY PER TECHNIQUE # 12726 USE CALIBRATED DENSITOMETER FOR DENSITY VERIFICATION. WHEN MARKING USE BLACK MARKERS. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET.	RT - LEVEL II <i>RS/6/17/05</i>	
210	X-RAY CQP 401 REV 5	X-RAY INTERPRETATION. ACCEPTANCE MSS SP 54. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET. IF OK CHECK HERE _____ AND SEND TO STEP 340. REJECTED CHECK HERE <input checked="" type="checkbox"/> MARK UP DEFECTS AND SEND THE CASTING TO STEP 220.	RT - LEVEL II <i>RK 6/12</i>	<i>to Rev 7</i> ↓
220	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING RADIOGRAPHY.	<i>BM 6/23</i> <i>BM 8-23</i>	+ -
225	GRIND GCHI SOP 0100R2	CHIP AND HAND GRIND EXCAVATION AS REQUIRED.	<i>QB 6-25</i> <i>8-23</i>	+ -
230	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE _____ IF REJECTED SEND BACK TO STEP 225.	LP-CC LEVEL II <i>CC 6-26</i> <i>6-27</i>	+ -
240	<b>HOLD POINT</b> WELD MAP	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS INDICATING LOCATION. SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE, FILE WITH QA. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS > 10% YES <input checked="" type="checkbox"/> , REPORT SENT BY <u><i>7/18/05</i></u> DATE <u><i>Chn</i></u> DEFECTS < 10 % _____ SIGN BY QA ENG. <b>MAJOR WELD REPAIRS MAY NOT PROCEED UNTIL INFORMATION IS SUBMITTED.</b> MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER PRIOR TO REPAIR. ONCE THE REPORT IS SENT, WELDING MAY START.	<i>Chn 7/18</i>	
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF WELD STEP. EIO NOTIFIED ON <u><i>7/10</i></u> DCMA NOTIFIED ON <u><i>7/10</i></u>	Q ENG OR QA MGR <i>Chn</i>	
260	QA APPROVAL HOLD POINT	QA TO APPROVE ELECTRODE PRIOR TO USE. PROCEDURE USED: <u><i>15-GMAW-CF8MNM</i></u> MATERIAL/LOT USED: <u><i>316M/NF/78309</i></u> QUALITY ENG. Name: <u><i>Rick</i></u> Date: <u><i>7/12/05</i></u>	<i>3018926/</i>	
270	WELD SOP 0100 REV 7	WELD REPAIR DEFECTS AS MARKED. FOR WELDS <2" - WPS 10-SMAW-CF8MNMN MOD REV 1 FOR WELDS <8" - WPS 15-GMAW-CF8MNMN MOD REV 2	<i>TLS 8/12</i>	-

A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

5 OF 11

CO# 40851 Dated 3-9-05 Revision: Rev 7

Dated Issued: 6-14-05

		ADD WPS FOR VERTICAL WELDS.		
280	GRIND GCHI SOP 0100R2	HAND GRIND WELDS.	M.G	8/12 -
290	L.P. WELD CQP 0300 REV 10	L.P. WELD REPAIRS ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE <input checked="" type="checkbox"/> WASH AND SEND TO STEP 300. IF REJECTED CHECK HERE _____	LP - LEVEL II CC	8/12 -
	REPEAT	REPEAT STEPS 220 TO 290 AS REQUIRED TILL CLEAR THROUGH VISUAL INSPECTION & PENETRANT INSPECTION. DOCUMENT REWORK ON STEPS S220 TO S290 ON LAST PAGE OF MTS. IF OK CHECK HERE _____ AND PROCEED TO STEP 295.	N/A	
295	TEST MAG PERM SOP MAG PERM 100, REV 1	TEST MAG PERMEABILITY REPAIR AREAS RECORD ON WELD MAP LIST. TEST AT LEAST 5 POINTS PER WELD. ACCEPTANCE 1.02. IF OK CHECK HERE <input checked="" type="checkbox"/> AND GO TO STEP 300. IF REJECTED CHECK HERE _____.	CGA	8/12 -
296	GRIND GCHI SOP 0100R2	GRIND AREAS OF NON COMPLIANCE AND RETURN TO STEP 295. REPEAT UNTIL COMPLIANCE IS ACHIEVED.	N/A	
300	X-RAY (NOTE)	IF RADIO GRAPHED AREAS ARE GREATER THAN FOUR TO FIVE INCHES THE CASTING WILL BE SENT TO MQS. SEND TO MQS CHECK HERE _____ RADIOGRAPH AT CAF CHECK HERE <input checked="" type="checkbox"/>	QA ENGINE ER RBK	8-21-05
310 A	MQS X-RAY DEFECTS REPAIRED BY WELDING	X-RAY PER TECHNIQUE # 12726 USE CALIBRATED DENSITOMETER FOR DENSITY VERIFICATION. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET.	LEVEL II N/A	
310 B	CAF X-RAY DEFECTS REPAIRED BY WELDING CQP 401 REV 5	X-RAY PER TECHNIQUE # 12726 USE CALIBRATED DENSITOMETER FOR DENSITY VERIFICATION. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET.	RT - LEVEL II RBK	8-21-05 -



A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

6 OF 11 CO# 40851 Dated 3-9-05 Revision: Rev 7 Dated Issued: 6-14-05

320	X-RAY CQP 401 REV 5	X-RAY INTERPRETATION. ACCEPTANCE MSS SP 54. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET. IF OK CHECK HERE _____ AND SEND TO STEP 340. REJECTED CHECK HERE <input checked="" type="checkbox"/> MARK UP DEFECTS AND SEND THE CASTING TO STEP 220.	RT - LEVEL II ABK 8-21-05	
	REPEAT	REPEAT STEPS 220 TO 320 AS REQUIRED TILL WELDS CLEAR X-RAY. DOCUMENT REWORK ON A SUPPLEMENTAL MTS	QA ENG. PS	10522
340	SAND BLAST BLAS SOP 0100R6	SANDBLAST (REMOVE ALL BLAST MATERIAL FROM CASTING) SANDBLASTING WILL BE DONE USING RECYCLED SHARP ANGULAR AGGREGATE.	MW 8/31/05	
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF VISUAL AND LP STEPS. EIO NOTIFIED ON 8/21 DCMA NOTIFIED ON 8/21	Q ENG OR QA MGR	CS
350	FINAL VISUAL INSPECTION CQP-500 REV 4	VISUALLY INSPECT 100% of COMPONENT ACCORDING TO ASTM A802 LEVEL 2 ALL CONDITIONS. IF OK CHECK HERE <input checked="" type="checkbox"/> IF REJECTED CHECK HERE _____. MARK AND REPAIR AT STEP 385. MUST BE PERFORMED BY LEVEL II in VT.	VT - LEVEL II KRA 8-31-05	
360	FINAL L.P. CQP 0300 REV 10	FINAL L.P. 100% OF COMPONENT. ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE _____ WASH AND SEND TO STEP 455. IF REJECTED CHECK HERE CC. REJECT	LP - LEVEL II I.C. 8-31-05	
380	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING FINAL PENETRANT INSPECTION.	M/A ATG 8-31-05	
385	GRIND GCHI SOP 0100R2	CHIP AND HAD GRIND EXCAVATION AS REQUIRED.	DWP 8-31-05	
390	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. GRIND ONLY IF OK CHECK HERE _____ IF REJECTED SEND BACK TO STEP 385.	LP - LEVEL II KRA 8-31-05	

**A-1 Coil**

**Energy Industries of Ohio**

**Manufacturing and Test Sequence (MTS) Serial Number A-1**

7 OF 11 **CO# 40851 Dated 3-9-05 Revision: Rev 7 Dated Issued: 6-14-05**

400	<b>HOLD POINT WELD MAP</b>	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS INDICATING LOCATION. SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE. FILE WITH QA. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS.>10% YES _____, REPORT SENT BY _____ DATE _____ DEFECTS < 10% _____ SIGN BY QA ENG. <b>MAJOR WELD REPAIRS MAY NOT PROCEED UNTIL INFORMATION IS SUBMITTED.</b> MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER PRIOR TO REPAIR. ONCE THE REPORT IS SENT, WELDING MAY START.	N/A	
420	<b>QA APPROVAL HOLD POINT</b>	QA TO APPROVE ELECTRODE PRIOR TO USE. PROCEDURE USED: _____ MATERIAL/LOT USED: _____ QUALITY ENG. Name: _____ Date: _____		
430	WELD SOP 0100 REV 7	WELD REPAIR DEFECTS AS MARKED. FOR WELDS <2" - WPS 10-SMAW-CF8MNMN MOD REV 1 FOR WELDS <8" - WPS 15-GMAW-CF8MNMN MOD REV 2 <b>ADD WPS FOR VERTICAL WELDS.</b>		
440	GRIND GCHI SOP 0100 REV 2	HAND GRIND WELDS.		
450	L.P. WELDS CQP 0300 REV 10	L.P. WELD REPAIRS ACCEPTANCE PER ASTM A903. IF OK CHECK HERE _____ WASH AND SEND TO STEP 460. IF REJECTED CHECK HERE _____ AND RETURN TO STEP 440.	LP - LEVEL II N/A	
	REPEAT	REPEAT STEPS 350 TO 450 AS REQUIRED TILL WELDS CLEAR FINAL LIQUID PENETRANT INSPECTION. DOCUMENT REWORK ON A SUPPLEMENTAL MTS	QA ENG. N/A	
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF VISUAL AND LP STEPS. EIO NOTIFIED ON <u>8/21</u> DCMA NOTIFIED ON <u>8/21</u>	Q ENG OR QA MGR	CA
460	FINAL VISUAL INSPECTION CQP-500 REV 4	VISUALLY INSPECT 100% of COMPONENT ACCORDING TO ASTM A802 LEVEL 2 ALL CONDITIONS. IF OK CHECK HERE <input checked="" type="checkbox"/> . IF REJECTED CHECK HERE _____. MARK AND REPAIR AT STEP 390. MUST BE PERFORMED BY LEVEL II in VT. <b>GRIND ONLY</b>	VT - LEVEL II KRA 8-31-05	

### A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

8 OF 11 CO# 40851 Dated 3-9-05 Revision: Rev 7 Dated Issued: 6-14-05

470	FINAL L.P. CQP 0300 REV 10	FINAL L.P. 100% OF COMPONENT. ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE <input checked="" type="checkbox"/> WASH AND SEND TO STEP 455. IF REJECTED CHECK HERE _____	LP - LEVEL II KLA	8/31
480	TEST MAG PERM SOP MAG PERM 100, REV 1	TEST MAG PERMEABILITY REPAIR AREAS. RECORD ON WELD MAP LIST. TEST AT LEAST 5 POINTS PER WELD. ACCEPTANCE 1.02. IF OK CHECK HERE _____ AND GO TO STEP 430. IF REJECTED CHECK HERE _____.	N/A	
490	GRIND GCHI SOP 0100R2	GRIND AREAS OF NON COMPLIANCE AND RETURN TO STEP 451. REPEAT UNTIL COMPLIANCE IS ACHIEVED.	↓	
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF MAG PERM STEPS. EIO NOTIFIED ON <u>8/21</u> DCMA NOTIFIED ON <u>8/21</u>	Q ENG OR QA MGR	
500	FINAL MAG PERM INSPECTION SOP MAG PERM 100, REV 1	PERFORM MAG PERM TESTING WITH SEVRIN GAUGE. ACCEPTANCE 1.02. CHECK THE ENTIRE SURFACE ON A 6"BY6" GRID. REPORT RESULTS. USE A 6" SQUARE BLOCK TO INDICATE TEST LOCATIONS AND RECORD RESULTS. COMPLIANT AREAS WILL NOT BE MARKED. MARK NONCOMPLIANT AREAS WITH AN "X" FOR REPAIR. OK CHECK HERE <input checked="" type="checkbox"/> AND GO TO STEP 530. IF REJECTED CHECK HERE _____	Car	8/31
510	GRIND GCHI SOP 0100 REV 2	HAND GRIND WITH SUITABLE CONE OR OTHER SIMILAR GRINDER AS REQUIRED TO ENSURE REMOVAL OF MATERIAL TO ACHIEVE MAG PERM REQUIREMENT. CIRCLE AREA REMEDIATE FOR RETEST.	N/A	
520	RETEST MAG PERM SOP MAG PERM 100, REV 1	RETEST MAG PERMEABILITY AT FAILED TEST POINTS. MARK NONCOMPLIANT AREAS WITH AN "X" FOR REPAIR. ACCEPTANCE 1.02. IF OK CHECK HERE _____ . IF REJECTED CHECK HERE _____ RETURN TO STEP 510.	↓	
530	DOC. REVIEW	REVIEW DOCUMENTS AS REQUIRED IN CAF CHECKLIST, ALL DOCUMENTS NOTED TO BE ACCESSIBLE FOR AUDITING. (SHIPPER, C OF C, M.T.R., M.T.S., INSPECTION REPORT, X-RAY READER SHEETS AND HEAT TREAT CHARTS)	Car	9/30
NOTICE	RELEASE FROM EIO	PROVIDE DOCUMENTS TO EIO. SENT ON <u>9/30</u> BY <u>Car</u> . RECEIVED RELEASE FROM EIO ON _____.	Q ENG OR QA MGR	Car
540	PACK AND SHIP	PACKAGE AND SHIP TO MAJOR TOOL.		
1000	REVISION HISTORY	ORIGINAL 12-14-04. Approved 12-14-04. Revision level 1- Revised 1-26-05 new page 8, correct High stress areas, Revision level 2 3-16-05, delete LO s 59455. Revision 3 3-28-05 Added note regarding	CARUUD	

# A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

9 OF 11

CO# 40851 Dated 3-9-05

Revision: Rev 7

Dated Issued: 6-14-05

		hold point at weld step 400. Revision level 4 written for C-2 casting 4-18-05. Rev 5 added Layout SOP# and note regarding first casting layout responsibility, 5-10-05. Rev 6 5-29-05 added "LOT" to weld material steps. Rev 7 6-14-05 added "LOT" to supplement page weld step.		
--	--	---	--	--

**RED AREA INDICATES HIGH STRESSED AREA**



A-1 Coil

Energy Industries of Ohio

Manufacturing and Test Sequence (MTS) Serial Number A-1

10 OF 11

CO# 40851 Dated 3-9-05

Revision: Rev 7

Dated Issued: 6-14-05

	REPEAT STEPS	SUPPLEMENTAL REPAIR STEPS	1 <sup>ST</sup>	2 <sup>N</sup>	3 <sup>RD</sup>	4 <sup>TH</sup>	5 <sup>T</sup>
			D	D			H
S220	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING RADIOGRAPHY.	nc 8/21	8/26			
S230	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING.	IP LEVE L II cc 8/28	8/26			
S240	WELD MAP	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS INDICATING LOCATION . SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE, FILE WITH QA. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS>10% YES <input checked="" type="checkbox"/> , REPORT SENT BY <u>CB</u> DATE <u>8/21</u> <u>8/26</u> DEFECTS < 10% <input type="checkbox"/> SIGN BY QA ENG. <b>REPAIRS MAY NOT PROCEED UNTIL INFORMATION IS SUBMITTED.</b>	8/21	8/26			
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF WELD STEP. EIO NOTIFIED ON <u>8/21</u> DCMA NOTIFIED ON <u>8/21</u>	Q ENG OR QA MGR				
S260	QA APPROVAL HOLD POINT	QA TO APPROVE ELECTRODE PRIOR TO USE. PROCEDURE USED: MATERIAL/LOT USED: <u>78309</u> QUALITY ENG. Name: <u>RS</u> Date: <u>8/23</u>					
S270	WELD SOP 0100 REV 7	WELD REPAIR DEFECTS AS MARKED. FOR WELDS <2" - WPS 10-SMAW-CF8MNMN MOD REV 1 FOR WELDS <8" - WPS 15-GMAW-CF8MNMN MOD REV 2 <b>ADD WPS FOR VERTICAL WELDS.</b>	TAP 8/23	TS 8/27			
S280	GRIND GCHI SOP 0100R2	HAND GRIND WELDS.	AB 8/24	OFB 8/28			
S290	L.P. WELD CQP 0300 REV 10	L.P. WELD REPAIRS ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA-LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING. IF OK CHECK HERE _____ WASH AND <del>61</del> ND TO STEP 300.	LP - LEVE L II cc 8/28 cc 8/24	OK REJ	OK REJ	OK REJ	OK RE

RT  
2 FS  
RT  
DK

**A-1 Coil**

**Energy Industries of Ohio**

**Manufacturing and Test Sequence (MTS) Serial Number A-1**

11 OF 11

CO# 40851

Dated 3-9-05

Revision: Rev 7

Dated Issued: 6-14-05

		IF REJECTED CHECK HERE _____ AND RETURN TO STEP 220.	RA				J
	REPEAT	REPEAT STEPS S220 TO S290 AS REQUIRED TILL CLEAR THROUGH VISUAL INSPECTION & PENETRANT INSPECTION. DOCUMENT REWORK ON A SUPPLEMENTAL MTS	QA ENG	8/28			

Energy Industries of Ohio  
 Manufacturing and Test Sequence (MTS) Coill A Shim -1



CO# 40851, Pattern SE 141-033 MS76220-1 Dated December 14, 2004 Revision: Original

Page 1 of 6

Dated Issued: 4-27-05

OPER. #	STATION	DESCRIPTION OF PROCESS	Name	Date
		Keep all parts together. Sign and date each step when all 6 parts have been completed.		
10	QUALITY RELEASE	REVIEW AND APPROVE MTS. RECEIVED APPROVAL FROM EIO ON __12-15-04__ FROM __Pete D. __ SIGNED QUALITY MANAGER	CAR	12/15/04
20	PATTERN NPAT SOP 0100REV2	APPLY APPROPRIATE PART NUMBER, SERIAL NUMBER, FOUNDRY MARK, TO THE PATTERN.	TB	4/27/05
30	MOLD MOLD SOP 0400 REV 8 CALIBRATION PER MOLD SOP 0900 REV 5 PREPARATION PER MOLD SOP 1100R2/1200R2/1300R1 SAND TESTING PER MOLD SOP 1400R2/1500R3/1600R2	MOLD PER WORK INSTRUCTIONS IN MAPICS ROUTING AND SOPS REFERENCED. ENGINEER OF RECORD - ROGER BROMAN, CONSULT ON MOLD-RELATED CONCERNS. MOLD MATERIALS REQUIRED PER MAPICS BOM. NOTIFY ENGINEER OF ANY SUBSTITUTIONS.	CR	4/27/05
40	POUR MELT SOP 0100R5 MELT SOP 0700R2 MELT SOP 0600R2	METAL MUST BE AOD REFINED OR AOD INGOT. VIRGIN METAL ADDITIONS ALLOWED. RECORD POURING TEMPERATURE: <u>2825</u> CASTING POURED AT: <u>1245 A</u> DATE: <u>4/28</u> HEAT #'s: <u>29198</u> ELAPSED POUR TIME <u>N/A</u> KEEL BLOCKS POURED: <u>yes</u> Sample from ladle to be analyzed for final chemical analysis and reported on material certifications. Sample Taken by: <u>SR</u> Analyzed: <u>Gfuri</u> Date: <u>4/28</u>  <b>Note: Make 15 additional test bars for mechanical testing.</b>	JG	4/28/05
50	MELT SOP 0800R2	SHAKEOUT	CA	4/29
60	ARC RISE SOP 0100R1	REMOVE RISERS AS DIRECTED BY SUPERVISOR.	BHV#	6/16/05
70	HEAT TREAT HEAT SOP 0103R5	SOLUTION ANNEAL. With C-1 Coil.	DLS	4/2/05

Energy Industries of Ohio  
 Manufacturing and Test Sequence (MTS) Coill A Shim -1

CO# 40851, Pattern SE 141-033 MS76220-1 Dated December 14, 2004 Revision:Original

Page 2 of 6

Dated Issued:4-27-05

80	PHYSICAL TESTING	OBTAIN TEST SPECIMENS AND SUBMIT FOR PHYSICAL TESTING. REPORT RESULTS AS PART OF STEP 480.	wH	4/29/03
90	GRIND GSA SOP 0100R3 GCHI SOP 0100R2	SWING GRIND TO REMOVE RISER REMAINS AND FLASH IF REQUIRED. CHIP AND HAD GRIND SURFACE OF PART AS REQUIRED.	Att	8/23/05
100	SAND BLAST BLAS SOP 0100R6	SANDBLAST (REMOVE ALL BLAST MATERIAL FROM CASTING) SANDBLASTING WILL BE DONE USING RECYCLED SHARP ANGULAR AGGREGATE.		AGM 8/23
110	VISUAL INSPECTION CQP-500 REV 4	VISUALLY INSPECT 100% of COMPONENT ACCORDING TO ASTM A802 LEVEL 3 ALL CONDITIONS. IF OK CHECK HERE <input checked="" type="checkbox"/> . IF REJECTED CHECK HERE ____ . MARK AND REPAIR AT STEP 130.	VT - LEVEL II CC	8/24
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF LP STEP. EIO NOTIFIED ON <u>7/28</u> DCMA NOTIFIED ON <u>7/28</u>	Q ENG OR QA MGR	RS
120	100% L.P. CQP 0300 REV 10	L.P. 100% OF COMPONENT ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA- LEVEL 2. IF OK CHECK HERE <input checked="" type="checkbox"/> . IF REJECTED CHECK HERE ____ MARK AND REPAIR AT STEP 120.	LP - LEVEL II CC	8/24
130	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING 100% VISUAL AND LP INSPECTION.	N/A	
140	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. ACCEPTANCE CRITERIA- LEVEL 2.	LP - LEVEL II	
150	SAND BLAST BLAS SOP 0100R6	SANDBLAST (REMOVE ALL BLAST MATERIAL FROM CASTING) SANDBLASTING WILL BE DONE USING RECYCLED SHARP ANGULAR AGGREGATE.		
160	WELD MAP	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS. SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE, FILE WITH QA.. USE YELLOW MARKER. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS > 10% YES ____, REPORT SENT BY _____ DATE _____ DEFECTS < 10% _____ SIGN BY QA ENG.		
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF XRAY AND LAYOUT STEPS. EIO NOTIFIED ON _____ DCMA NOTIFIED ON _____	Q ENG OR QA MGR	



Energy Industries of Ohio  
Manufacturing and Test Sequence (MTS) Coill A Shim -1

CO# 40851, Pattern SE 141-033 MS76220-1 Dated December 14, 2004 Revision:Original

Page 3 of 6

Dated Issued:4-27-05

170	CAF X-RAY CQP 401 REV 5	X-RAY PER TECHNIQUE: To be determined. USE CALIBRATED DENSITOMETER FOR DENSITY VERIFICATION. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET.	RT - LEVEL II  RBK	8-29-05
180	X-RAY CQP 401 REV 5	X-RAY INTERPRETATION. ACCEPTANCE MSS SP 54. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET. IF OK CHECK HERE _____ AND SEND TO STEP 310. REJECTED CHECK HERE <input checked="" type="checkbox"/> MARK UP DEFECTS AND SEND THE CASTING TO STEP 200.	RT - LEVEL II  RBK	8-29-05
190	LAYOUT	INSPECT CASTING TO VERIFY DIMENSIONS. THIS MAY BE PERFORMED BEFORE OR AFTER STEP 180. DIMENSIONED <u>2 only</u> DATE <u>8-31-05</u> RELEASED <u>DR</u> (ENGINEER ONLY)	JAS	8-31-05
200	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING RADIOGRAPHY.	TLS	8-29-05
210	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903. ACCEPTANCE CRITERIA- LEVEL 2.	LP - LEVEL II CC	8-29-05
220	WELD MAP	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS. SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE, FILE WITH QA. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS > 10% YES <input checked="" type="checkbox"/> REPORT SENT BY _____ DATE _____ DEFECTS < 10% <input checked="" type="checkbox"/> SIGN BY QA ENG. <u>Ch</u>	Ch	8/29
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF WELD STEP. EIO NOTIFIED ON <u>8/24</u> DCMA NOTIFIED ON <u>8/24</u>	Q ENG OR QA MGR Ch	
230	QA APPROVAL HOLD POINT	QA TO APPROVE ELECTRODE PRIOR TO USE. PROCEDURE USED: _____ MATERIAL USED: <u>316M NAF / 78309</u> QUALITY ENG. Name: <u>Ch</u> Date: <u>8/29</u> <u>(30/8926/78309)</u>	Full#	
240	WELD SOP 0100 REV 7	WELD REPAIR DEFECTS AS MARKED. FOR WELDS < 2" - WPS 10-SMAW-CF8MNMN MOD REV 1 FOR WELDS < 8" - WPS 15-GMAW-CF8MNMN MOD REV 2	TLS	8-29-05
250	GRIND GCHI SOP 0100R2	HAND GRIND WELDS.	TLS	8-29-05

  
 8/31/05

Energy Industries of Ohio  
Manufacturing and Test Sequence (MTS) Coill A Shim -1

CO# 40851, Pattern SE 141-033 MS76220-1 Dated December 14, 2004 Revision:Original

Page 4 of 6

Dated Issued:4-27-05

260	L.P. WELD CQP 0300 REV 10	L.P. WELD REPAIRS ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA-LEVEL 2. IF OK CHECK HERE <input checked="" type="checkbox"/> WASH AND SEND TO STEP 300. IF REJECTED CHECK HERE <input type="checkbox"/> AND RETURN TO STEP 220.	LP - LEVEL II N/A C/C	8-29-05
	REPEAT	REPEAT STEPS 220 TO 260 AS REQUIRED TILL CLEAR THROUGH VISUAL INSPECTION & PENETRANT INSPECTION. DOCUMENT REWORK ON A SUPPLEMENTAL MTS	QA ENG.	
270	TEST MAG PERM SOP MAG PERM 100, REV 1	TEST MAG PERMEABILITY REPAIR AREAS RECORD ON WELD MAP LIST. TEST AT LEAST 5 POINTS PER WELD. ACCEPTANCE 1.02. <input checked="" type="checkbox"/> IF OK CHECK HERE <input type="checkbox"/> AND GO TO STEP 290. IF REJECTED CHECK HERE <input type="checkbox"/> .	C/A	8/29/05
280	GRIND GCHI SOP 0100R2	GRIND AREAS OF NON COMPLIANCE AND RETURN TO STEP 270. REPEAT UNTILL COMPLIANCE IS ACHIEVED.		
290	CAF X-RAY DEFECTS REPAIRED BY WELDING CQP 401 REV 5	X-RAY PER TECHNIQUE: To be determined. USE CALIBRATED DENSITOMETER FOR DENSITY VERIFICATION. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET.	RT - LEVEL II KAR	8-29-05
300	X-RAY CQP 401 REV 5	X-RAY INTERPRETATION. ACCEPTANCE MSS SP 54. ATTACH TECHNIQUE, READER SHEET FOR ALL RADIOGRAPHS. MUST INDICATE RADIOGRAPHER AND ASNT CERTIFICATION LEVEL ON READER SHEET. IF OK CHECK HERE <input checked="" type="checkbox"/> AND SEND TO STEP 310. REJECTED CHECK HERE <input type="checkbox"/> MARK UP DEFECTS AND SEND THE CASTING TO STEP 200.	RT - LEVEL II KAR	8-29-05
	REPEAT	REPEAT STEPS 200 TO 300 AS REQUIRED TILL WELDS CLEAR X-RAY. DOCUMENT REWORK ON A SUPPLEMENTAL MTS	QA ENG. N/A	
310	SAND BLAST BLAS SOP 0100R6	SANDBLAST (REMOVE ALL BLAST MATERIAL FROM CASTING) SANDBLASTING WILL BE DONE USING RECYCLED SHARP ANGULAR AGGREGATE.	M	8/31
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIO AND DCMA AT LEAST FIVE DAYS IN ADVANCE OF VISUAL AND LP STEPS. EIO NOTIFIED ON 8/21 DCMA NOTIFIED ON 8/21	Q ENG OR QA MGR	at
320	FINAL VISUAL INSPECTION CQP-500 REV 4	VISUALLY INSPECT 100% of COMPONENT ACCORDING TO ASTM A802 LEVEL 2 ALL CONDITIONS. IF OK CHECK HERE <input checked="" type="checkbox"/> IF REJECTED CHECK HERE <input type="checkbox"/> MARK AND REPAIR AT STEP 340.	VT - LEVEL II KAR	8/31



Energy Industries of Ohio  
 Manufacturing and Test Sequence (MTS) Coill A Shim -1

CO# 40851, Pattern SE 141-033 MS76220-1 Dated December 14, 2004 Revision:Original

Page 5 of 6

Dated Issued:4-27-05

		MUST BE PERFORMED BY LEVEL II in VT.		
330	FINAL L.P. CQP 0300 REV 10	FINAL L.P. 100% OF COMPONENT. ACCEPTANCE PER ASTM A903. ACCEPTANCE CRITERIA- LEVEL 1 FOR HIGH STRESSED AREAS, LEVEL 2 FOR ALL OTHER AREAS. SEE LP DRAWING.  IF OK CHECK HERE <input checked="" type="checkbox"/> WASH AND SEND TO STEP 410. IF REJECTED CHECK HERE <input type="checkbox"/>	LP - LEVEL II <i>JOK</i> 8/31	
340	WELD SOP 0100 REV 7	EXCAVATE ANY DEFECTS FOUND DURING FINAL PENETRANT INSPECTION.	<i>MP</i>	
350	L.P. EXCAVATION CQP-300 REV 10	L.P. ALL EXCAVATIONS PRIOR TO WELDING TO ENSURE REMOVAL OF DEFECT. ACCEPTANCE PER A903.	LP - LEVEL II	
370	WELD MAP	MAP ALL WELDS WITH DIGITAL PHOTO/MAPS. SERIALIZE DEFECTS ON CASTING, USE SCALE IN PHOTOS AND DOCUMENT SIZE. THIS IS TO BE PERFORMED BY SUPERVISOR, INSPECTION LEAD MAN OR THEIR DESIGNEE. FILE WITH QA. MUST SEND REPORT ON ALL WELDS OVER 10% OF NOMINAL WALL THICKNESS TO CUSTOMER. NOMINAL WALL THICKNESS TO CUSTOMER. DEFECTS >10% YES _____, REPORT SENT BY _____ DATE _____ DEFECTS < 10 % _____ SIGN BY QA ENG.		
380	WELD SOP 0100 REV 7	WELD REPAIR DEFECTS AS MARKED. FOR WELDS <2" - WPS 10-SMAW-CF8MNMN MOD REV 1 FOR WELDS <8" - WPS 15-GMAW-CF8MNMN MOD REV 2		
390	GRIND GCHI SOP 0100 REV 2	HAND GRIND WELDS.		
400	L.P. WELDS CQP 0300 REV 10	L.P. WELD REPAIRS ACCEPTANCE PER ASTM A903. IF OK CHECK HERE <input type="checkbox"/> WASH AND SEND TO STEP 460. IF REJECTED CHECK HERE <input type="checkbox"/> AND RETURN TO STEP 390.	LP - LEVEL II	
	REPEAT	REPEAT STEPS 390 TO 410 AS REQUIRED TILL WELDS CLEAR FINAL LIQUID PENETRANT INSPECTION. DOCUMENT REWORK ON A SUPPLEMENTAL MTS	QA ENG.	
410	TEST MAG PERM SOP MAG PERM 100, REV 1	TEST MAG PERMEABILITY REPAIR AREAS. RECORD ON WELD MAP LIST. TEST AT LEAST 5 POINTS PER WELD. ACCEPTANCE 1.02. IF OK CHECK HERE <input type="checkbox"/> AND GO TO STEP 430.		

Energy Industries of Ohio  
 Manufacturing and Test Sequence (MTS) Coill A Shim <sup>(-1)</sup>

CO# 40851, Pattern SE 141-033 MS76220-1 Dated December 14, 2004 Revision:Original

Page 6 of 6

Dated Issued:4-27-05

420	GRIND GCHI SOP 0100R2	GRIND AREAS OF NON COMPLIANCE AND RETURN TO STEP 420. REPEAT UNTILL COMPLIANCE IS ACHIEVED.		
NOTICE	WITNESS NOTIFICATION	PROVIDE NOTICE TO EIOAND DCMA AT LEAST FIVE DAYS IN ADVANCE OF MAG PERM STEP. EIO NOTIFIED ON <u>8/21</u> DCMA NOTIFIED ON <u>8/21</u>	Q ENG OR QA MGR	<i>Cfr</i>
430	FINAL MAG PERM INSPECTION SOP MAG PERM 100, REV 1	PERFORM MAG PERM TESTING WITH SEVRIN GAUGE. ACCEPTANCE 1.02. CHECK THE ENTIRE SURFACE ON A 6"BY6" GRID. REPORT RESULTS. USE A 6" SQUARE BLOCK TO INDICATE TEST LOCATIONS AND RECORD RESULTS. COMPLIANT AREAS WILL NOT BE MARKED. MARK NONCOMPLIANT AREAS WITH AN "X" FOR REPAIR. OK CHECK HERE <input checked="" type="checkbox"/> AND GO TO STEP 470. IF REJECTED CHECK HERE _____		<i>Cfr 8/31</i>
440	GRIND GCHI SOP 0100 REV 2	HAND GRIND WITH SUITABLE CONE OR OTHER SIMILAR GRINDER AS REQUIRED TO ENSURE REMOVAL OF MATERIAL TO ACHIEVE MAG PERM REQUIREMENT. CIRCLE AREA REMEDIATE FOR RETEST.		<i>N/A</i>
450	RETEST MAG PERM SOP MAG PERM 100, REV 1	RETEST MAG PERMEABILITY AT FAILED TEST POINTS. MARK NONCOMPLIANT AREAS WITH AN "X" FOR REPAIR. ACCEPTANCE 1.02. IF OK CHECK HERE _____ . IF REJECTED CHECK HERE _____ RETURN TO STEP 450		
460	PHOTOGRAPH	TAKE DIGITAL PICTURES.		
470	AUDIT REVIEW	PROCESS DOCUMENT TO PROGRAM MANAGER FOR COMPLIANCE AUDIT.		
480	DOC. REVIEW	REVIEW DOCUMENTS AS REQUIRED IN CAF CHECKLIST, ALL DOCUMENTS NOTED TO BE ACCESSIBLE FOR AUDITING. (SHIPPER, C OF C, M.T.R., M.T.S., INSPECTION REPORT, X-RAY READER SHEETS AND HEAT TREAT CHARTS)		<i>Cfr 8/31</i>
NOTICE	RELEASE FROM EIO	PROVIDE DOCUMENTS TO EIO. SENT ON <u>8/31</u> BY <u><i>Cfr</i></u> . RECEIVED RELEASE FROM EIO ON _____.	Q ENG OR QA MGR	
490	PACK AND SHIP	PACKAGE AND SHIP TO MAJOR TOOL.		
1000	REVISION HISTORY	ORIGINAL 12-14-04.	CARUUD	



Corrective Action 1308  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 6/13/2005  
CA Originator C. Ruud  
Pattern Number: C and A Coil Shims 11 Pieces

**Description of Defect / Non-Conformance**

Chemistry for 11 shim castings is out of specification.

**Root Cause**

Chemistry specification was not changed in system and not communicated to Lab personnel.

**Corrective Action**

Specification was corrected in system and Lab personnel trained. Mag permeability was checked on the parts and are less than 1.02u.

**Verification of Corrective Action**

Chemistries were checked on subsequent parts and are within specification.

**Preventive Action**

Create Inspection and Test Plan summarizing all requirements.

**Estimated Completion Date**

6/15/05

**Actual Completion Date**

Complete.

A handwritten signature in black ink, appearing to read "C. Ruud".

Signed: C. Ruud

CC: Roger Broman, Barry Craig, Joe Edwards, E.J. Kubick

**Nonconformance Report:** MetalTek CA 1308

**Project Disposition:** Use as is.

**Approvals**

Procurement Technical Representative \_\_\_\_\_  
Wayne Reiersen for Phil Heitzenroeder

Responsible Line Manager \_\_\_\_\_  
Mike Cole for Brad Nelson



Corrective Action 1320  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 7/5/2005  
CA Originator C. Ruud  
Pattern Number: C 1, C2 and A1 Coil castings

**Description of Defect / Non-Conformance**

Lack of test material in violation of paragraph 4.2.2.4 Additional Test Material.

**Root Cause**

Specification was not communicated to Pattern shop personnel.

**Corrective Action**

Test coupons were added to pattern and will be cast on all future coils.

**Verification of Corrective Action**

Pattern was inspected prior to molding C-4 casting.

**Preventive Action**

Create Inspection and Test Plan summarizing all requirements.

**Actual Completion Date**

Complete.

A handwritten signature in black ink, appearing to be "C. Ruud", written over a light grey rectangular background.

Signed: C. Ruud

CC: Roger Broman, Barry Craig, Joe Edwards, E.J. Kubick

PPPL and EIO agree that additional test material is not available for the C1, C2, and A1 castings, but will be provided for the remaining castings.

This NCR is approved based on EIO's corrective action and the above agreement.

**Brad Nelson**

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US, o=ORNL,  
ou=FED, email=nelsonbe@ornl.gov  
Date: 2005.07.12 17:01:58 -04'00'

---

Brad Nelson, NCSX Core Systems Engineering Manager

Phil Heitzenroeder

2005.07.12 15:42:35 -04'00'

---

Phil Heitzenroeder, NCSX MCWF Subcontract Tech. Rep.



**Nonconformance Report: CA 1323 (phosphorus levels exceeds specification limits for castings C1- C4 and A1 and C1 shim and four Type C and six A coil shims)**

**Project Disposition:**

The erroneous levels were due to calibration errors with the spectrometer. As reported in MTK's attached report, preventive maintenance has since been performed on the spectrometer. The reported chemistry will be accepted for the castings and shims noted above. The specification chemistry will not be changed at this time.

**Approvals:**

**Phil  
Heitzenroeder**

Digitally signed by Phil Heitzenroeder  
DN: CN = Phil Heitzenroeder, C = US,  
O = PPPL, OU = Mech. Eng. Division  
Reason: I agree to 'specified' portions  
of this document  
Date: 2006.02.21 11:49:56 -05'00'

---

Procurement Technical Representative

**Brad  
Nelson**

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2006.02.21 14:16:12  
-05'00'

---

Responsible Line Manager:



Corrective Action 1323  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 7/27/2005  
CA Originator C. Ruud  
Applies to: Coil castings C-1, C-2, C-3, C-4 and A-1 and C 1 shim and four C coil and six A coil shims

**Description of Defect / Non-Conformance**

Phosphorus levels in material produced to date exceed specification limits. Both phosphorus and sulfur readings reported erroneously in certifications.

Certification reports have shown phosphorus and sulfur levels in the <.01% range. Independent laboratory data confirmed phosphorus in the .018 to .033% range and sulfur in the .005 to .022% range. Actual levels of some tests are above those in PPPL Specification NCSX-CSPEC-141-03-07 Rev 7.

Nonconformance was first suspected as a result of analysis of zoned attached test specimens volunteered by MetalTek International as response to PPPL questions on weighted average chemical analysis and quality of blending in the gating system. Nonconformance was verified on the bars used in the study and has been extended to evaluation of previously poured products.

**Root Cause**

Specification limits were set below the levels achievable through use of available raw materials. Spectrometer did not properly calibrate for phosphorus and sulfur at levels of specification due to equipment malfunction.

The chemical specification of EIO heats uses alloy CF8MNMn-Mod which incorporates a type standard calibration with a certified reference material (CRM) BS180. This enables the operator of the spectrometer to match the elemental concentrations of this alloy with corrective factors. These factors are determined by analyzing the CRM and having them compared with the calibration curves for each element. The phosphorus and sulfur content have very low measured intensities due to low concentrations. Intermittent failure of the spectrometer intensity measuring card caused higher intensity readings for phosphorus and sulfur. Subsequent checks with the CRM resulted in low corrective factors that were not detected. This in turn resulted in low reported concentrations for the EIO samples. All the major elements, which are measured on other intensity cards, have been closely monitored and matched very well with the CRM and thus were reported correctly.

**Corrective Action**

Modification to specification for phosphorus and sulfur will be requested. Limits will be set based on process capability and consistent with other stainless steel grades. Replacement of deficient card in spectrometer will be made upon delivery.

Subsequent immediate analysis of chemistry results, obtained by wet analysis, is attached and demonstrate top of specification for sulfur and over specification for phosphorus. The spectrometer manufacturer has performed an analysis to determine the cause of the malfunction and verified that the intensity card has an intermittent fault and must be replaced. The card has been ordered and scheduled for replacement on August 15, 2005.

Until the card is replaced we will be performing additional type standardizations to ensure accurate sulfur and phosphorus analysis. Additionally, for coils made until the card is replaced, an independent laboratory will perform a verification of the chemical analysis.

**Verification of Corrective Action**

Will be determined at a later date.

**Preventive Action**

In addition to spectrometer faults, we have identified that the specification ranges for sulfur and phosphorus is unattainable. Analysis and specifications for virgin charge materials predict sulfur at 0.040% maximum and phosphorus at 0.040% maximum. We have no way to remove phosphorus from the melt and do not intentionally add phosphorus. So, the confirmed coil analyses, along with analyses of virgin material heats, demonstrate sulfur in the range of 0.010% to 0.022% and phosphorus in the range of 0.018% to 0.033%. These results are consistent with our charge material analysis. We will request a deviation for phosphorus in the subject parts and also request a permanent specification change to 0.040% maximum for both phosphorus and sulfur, to allow us to provide non-discrepant material. This change will not affect, in any way, the physical properties or material performance because all coils and test material exhibited sulfur and phosphorus within the new ranges despite inaccurate reporting. Other actions: Specifications have been added to the BS 180 standard and the type standard will be measured against the criteria.

**Estimated Completion Date**

August 15, 2005

**Actual Completion Date TBD**

Signed: C. Ruud



CC: Jim Galaske, Barry Craig, Joe Edwards, E.J. Kubick

**Guide to St Louis Testing Report Dated 7-26-05**

Sample name	Sample origin
A1Z1	Cast on bar A-1 coil, zone 1
A1Z2	Cast on bar A-1 coil, zone 2
A1Z3	Cast on bar A-1 coil, zone 3
C1	Cast on bar C-1 coil
C2Z1	Cast on bar C-2 coil, zone 1
C2Z2	Cast on bar C-2 coil, zone 2
C2Z3	Cast on bar C-2 coil, zone 3
C3Z1	Cast on bar C-3 coil, zone 1
C3Z2	Cast on bar C-3 coil, zone 2
C3Z3	Cast on bar C-3 coil, zone 3
F1	Final analysis button from ladle for C-4 coil
F2	Final analysis button from ladle for C-4 coil
F3	Final analysis button from ladle for C-4 coil
P1	Preliminary analysis button from ladle for C-4 coil

Testing is underway of the heat used to pour the four C coil and six A coil shims.

*Attachment to  
CA 1323*



Chemical, Metallurgical, Mechanical, Nondestructive, Environmental Testing, Analyses and Field Service.

July 26, 2005  
Lab No. 05C-0608  
Invoice No. 59891  
P.O. No. 21324  
Page 1 of 1

**METALTEK INTERNATIONAL**  
8600 Commercial Blvd.  
Pevely, MO 63070

**Attention: Chuck Ruud**

**REPORT OF CHEMICAL ANALYSIS**

**SAMPLE ID:** A1 Z1, A1 Z2, A1 Z3, C1, C2 Z1, C2 Z2, C2 Z3,  
C3 Z1, C3 Z2, C3 Z3, F1, F2, F3, P1

**RESULTS: %**

ANALYTE	A1Z1	A1Z2	A1Z3
Sulfur	.013	.005	.010
Phosphorus	.025	.023	.018

ANALYTE	C1	C2Z1	C2Z2	C2Z3
Sulfur	.014	.022	.018	.015
Phosphorus	.018	.024	.021	.025

ANALYTE	C3Z1	C3Z2	C3Z3
Sulfur	.013	.014	.012
Phosphorus	.024	.025	.021

ANALYTE	F1	F2	F3	P1
Sulfur	.014	.015	.012	.010
Phosphorus	.029	.033	.028	.030

Sulfur Test Method: ASTM E1019-03

Phosphorous Test Method: Colormetric

Identification of tested specimen provided by the client.

Robin E. Sinn  
Laboratory Director



**MetalTek International***Carondelet Division - CA / PA / RGA Database*

Corrective Action

1324

Corrective Action Type FOR CASTING DISCONTINUITIES

Date 7/18/2005

CA Originator C. Ruud

Pattern Number: A-1 Coil

**Description of Defect / Non-Conformance**

98 major weld defects found in the A-1 coil casting.

**Root Cause :** Casting defects primarily due gas and shrink.**Corrective Action:** Weld upgrade A1 casting. Welding will be performed following the approved procedure FOR WELDS <2" - WPS 10-SMAW-CF8MNMN MOD REV 1. FOR WELDS <8" - WPS 15-GMAW-CF8MNMN MOD REV 2.**Verification of Corrective Action:** All repairs will be verified by the inspection method used to discover the original defect.**Preventive Action:** We will use the xray information from the A1 casting to determine if changes are required to the tooling.**Verification Of Preventative Action:** Radiograph A-2 coil and compare results.**Estimated Implementation Date:** Prior to shipment.

Signed: CA Ruud

CC: EIO, Barry Craig, Joe Edwards, E.J. Kubick, Geoff Mergel, File

Disposition for CA 1324: Perform weld upgrades per MTM procedures.

Approved:

Phil Heitzenroeder

Tech. Representative

2005.08.25 16:20:38 -04'00'

RLM Brad  
Nelson

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonba@ornl.gov  
Date: 2005.08.25 17:23:22 -04'00'



## Carondelet Division

8600 Commercial Blvd. • Pevely, MO 63070 USA

Phone: 636-475-2199 • Fax: 636-479-3399

E-Mail: Charles.Ruud@MetalTek.com

Corrective Action 1347  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 8/1/2005 Revised 1-31-06  
CA Originator C. Ruud  
Applies to: A-1Coil

### Description of Defect / Non-Conformance

Wall thickness below model minimum. Localized areas were measured below the 1.375" minimum wall thickness during metrology. MetalTek independently verified wall thickness and confirmed condition.

### Root Cause

The tooling produces a casting with a wall thickness less than required by the model. Measurements taken on A-3, A-4 and A-5 are consistent and lower than predicted by the model. Material losses during normal processing and heat treat with A-1 and A-2 are also a factor.

### Corrective Action

Request "Use As Is" disposition on wall thickness related dimensions on A-1 coil.

### Verification of Corrective Action

Not required. PPPL independently verified in conjunction with ORNL the design performance at a wall thickness of 1.05". Results were deemed adequate. Minimum measured dimension is 1.18" (to be verified). **Scans of A-2 and 3 coils shows that the walls are above the 1.18" minimum dimension in all but a few isolated locations. The areas were identified and repaired by approved welding procedures.**

### Preventive Action

Several steps need to be taken to resolve and propose:

1. Validation of 3D Scanco data. MetalTek proposes to use Romer Arm with Laser scanner as validation technique. This instrument will be used to validate subsequent parts and minimizes measurement technique error.  
- Completed - The data provided by 3D Scanco has been validated on A1.
2. Report to PPPL/ORNL. Understanding the concern that the wall not be thinner than measured and the limitations of the process, e.g. setting a large core into a mold with overhead crane, MetalTek will submit layout results to EIO wand set teleconference to review remediations to tool.  
- It was determined to produce A2 with no tooling changes.



3. Upon verification of 3D Scanco data, MetalTek will confirm results to EIO team to begin root cause determination. Additional layout may be required to assure compliance of tooling, depending on results of layout.
  - Transfer caliper dimensions were taken on A-2 and A-3 at pre-clean step and shown to exceed required minimum wall thickness. **However scans performed using Romer Arm on A-2 and A-3 indicated dimensions consistent with A-1.**
4. Modification to tooling. Limited tooling modifications may be performed without severely impacting schedule or negating previous engineering (solidification modeling, etc.). These will be evaluated and proposed, where appropriate.
  - No tooling changes have been made.
5. Permanent deviation. Based on results of above, a permanent deviation may be required to dimensional tolerances in limited areas of the component. These will be known in greater detail later.

**Actual Completion Date**

All items complete, except a deviation.

Signed: C. Ruud



CC: Roger Broman, Barry Craig, Joe Edwards, E.J. Kubick, J. Markham

## NCSX Disposition to CA 1347

Analyses were performed to determine the effect of the thin section on deflections and stresses and are summarized below.

- Thin shell areas like that of A1 **has an extremely minor affect on the stresses and displacements in ANY of the coils or shells** with the thickness being either 1.18" as for A1 or even with the thickness being 1.05" which MTK projects is the minimum if the shell is not changed. Reasons:
  - a) The shape of the tee is not changed by this, and the tee provides most of the bending stiffness
  - b) Some EM forces are transferred to the shell B from the wing.
  - c) The thin wall region is not the location for the peak stress and much of the area will be machined away.

Run #	Configuration	Shell Type A		Coil Type A		All Coils	
		Max.	Max.	Max.	Max.	Max.	Max.
		Displacement - mm	Stress - Mpa	Displacement - mm	Stress - Mpa	Displacement - mm	Stress - Mpa
1	Baseline	0.98	168	1.246	239	2.711	239
5	Updated E	1.17	160	1.513	248	2.934	248
6	Updated E; thin sect. =1.18"	1.169	161	1.516	249	2.984	249
4	Updated E; thin sect. =1.05"	1.168	161	1.517	248	2.971	248

Since the effect has been shown to be extremely minor, the disposition for the A1 winding form is **Accept As Is**.

**However, since the root cause determination is still underway, this NCR should be kept open. It is requested that EIO re-issue an amended CA with the root cause determination and preventive action; PPPL will disposition that portion of the NCR at that time.**

**Approved:**

Phil Heitzenroeder  
2005.08.19 14:10:46 -04'00'

**P. Heitzenroeder, Tech. Rep.**

**Brad Nelson**

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2005.08.19 16:56:28 -04'00'

**B. Nelson, RLM**



Corrective Action 1379  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 8/31/2005  
CA Originator C. Ruud  
Applies to: Weld Material Lincoln 3018926-78309

**Description of Defect / Non-Conformance**

Material failed elongation and one of three Charpy impact tests at -320 F. The average of the specimens exceeds the minimum. See S8 of ASTM A 703/A 703M.

**Root Cause**

The sample of the weld contained defects not detected.

**Corrective Action**

Retest material already at Lab.  
If needed, make a new weld plate after reviewing process with welder and weld another sample.

**Verification of Corrective Action**

Retest results. If new plates are needed, the new plate will be x-rayed prior to testing.

**Estimated Completion Date**

9-2-05

**Actual Completion Date TBD**

Signed: C. Ruud

A handwritten signature in black ink, appearing to be "C. Ruud".

CC: R. Suria, Barry Craig, Joe Edwards, E.J. Kubick

**Nonconformance Report: CA1379**

**Project Disposition:**

Since the re-test meets requirements, this NCR can now be considered closed.


**Approvals:**

Phil  
Heitzenroeder

Digitally signed by Phil Heitzenroeder  
DN: CN = Phil Heitzenroeder, C = US,  
O = PPPL, OU = Mech. Eng. Division  
Reason: I am approving this document  
Date: 2005.11.07 10:09:53 -0500

---

Procurement Technical Representative

 11/7/05

---

Responsible Line Manager:



## Carondelet Division

8600 Commercial Blvd. • Pevely, MO 63070 USA

Phone: 636-475-2199 • Fax: 636-479-3399

E-Mail: Charles.Ruud@MetalTek.com

Corrective Action 1625  
Carondelet Division  
Corrective Action Type NCR  
Date 3-1-06  
CA Originator C. Ruud  
Applies to: A-1 Coil

### Description of Defect / Non-Conformance

Crack like defect found during machining of A-1 coil.

### Root Cause

The defects may be lack of fusion and sand inclusion. The area was repaired by welding prior to shipment. RT and LP were acceptable. This area is covered by views 62-63 and 113-114. During the processing of C-3 and A-1 coils problems surfaced with repeated lack of fusion defects. Corrective action reports 1371 and 1403 were issued. The action items were completed are the problem decreased significantly. Both CA are part of this CA report.

### Corrective Action

Completed.

### Verification of Corrective Action

Subsequent coils have not had the issue.

### Preventive Action

Monitoring of gas lines and flow rates continues.

### Verification Of Preventative Action

Subsequent coils have not had the issue. .

### Actual Completion Date

October 4, 2005 for the last item on CA 1403.

Signed: C. Ruud

A handwritten signature in black ink, appearing to read "C. Ruud", written over a horizontal line.

CC: B. Craig, J. Edwards, E.J. Kubick, J. Markham, J. Galaske





## Carondelet Division

8600 Commercial Blvd. • Pevely, MO 63070 USA

Phone: 636-475-2199 • Fax: 636-479-3399

E-Mail: Charles.Ruud@MetalTek.com

Corrective Action 1371  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 8/23/2005  
CA Originator R. Suria  
Applies to: A-1Coil

### **Description of Defect / Non-Conformance**

Lack of fusion and porosity in weld repairs were observed during radiography of the R-2 through R-6 x-ray confirmation shots.

### **Root Cause**

Porosity was caused by the use of fans in the welding booth. Lack of fusion was the result of poor operator technique and or fatigue. Some repair loops resulted from the original defects not fully being removed during excavation.

### **Corrective Action**

Unplug fans during GMAW welding. Reviewed proper GMAW gun angles and excavation techniques with the welders.

### **Verification of Corrective Action**

Re x-ray the defective welds.

### **Estimated Completion Date**

8/31/05

### **Actual Completion Date**

8/31/05

Signed: R. Suria

CC: Barry Craig, Joe Edwards, E.J. Kubick



## Carondelet Division

8600 Commercial Blvd. • Pevely, MO 63070 USA

Phone: 636-475-2199 • Fax: 636-479-3399

E-Mail: Charles.Ruud@MetalTek.com

Corrective Action 1403  
Carondelet Division - CA / PA / RGA Database  
Corrective Action Type NCR  
Date 9-30-05  
CA Originator C. Ruud  
Applies to: C-3 Coil

### Description of Defect / Non-Conformance

Lack of fusion and porosity in weld repairs were observed during radiography of the R-2 through R-7 x-ray confirmation shots.

### Root Cause

Porosity and lack of fusion was caused by leaks in the lines feeding gas to the welding booths and leaks from the leads on one welding machine. Some repair loops resulted from the original defects not fully being removed during excavation.

### Corrective Action

Took all welders off the main lines and supplied with bottled gas. Inspect all lines from the bulk tanks to the weld booth. Replaced defective lead. Reviewed proper excavation techniques with the welders. The start up procedure for welders has been revised to include a flow check. If flow is not adequate, welding will not be performed until repairs are complete and re test indicate proper flow.

### Verification of Corrective Action

Re x-ray the defective welds.

.

### Estimated Completion Date

9/16/05 for repairs, other actions 10/21/05.

### Actual Completion Date

9/16/05 for bottle gas, repairs and RT. 10/4/05 for leads.

Signed: C. Ruud

CC: R Suria, B. Craig, J. Edwards, E.J. Kubick





### Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

### Final Inspection Report

Customer Name: ENERGY INDUSTRIES OF OHIO      Pattern: MCWF-A1 COIL

Order Number: PPPL-FP-LTS-2

ASTM Metal CF8MNMN MOD

Date 8/30/2005

Type Description	Cert Number	Procedure	Acceptance Criteria	Actual
Liquid Penetrant	169470-1	CQP - 300 Rev 9	SEE NOTE	Acceptable
Notes Acceptance per ASTM A903. Acceptance criteria - level 1 for high stressed areas, level 2 for all other areas.				
Mag Perm	169470-1	SOP Mag Perm 100 Rev 1	<1.02	Acceptable
Radiographic	169470-1	Technique # 12726	MSS SP 54	Acceptable
Visual	169470-1	CQP - 500 REV 4	ASTM A802 LEVEL 2	Acceptable

Liquid Penetrant  
Visual

Technician: Kevin Anderson  
ASNT Level II

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager



## Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

### Certificate of Conformance

ENERGY INDUSTRIES OF OHIO

Order Number PPPL-FP-LTS-2

Pattern MCWF-A1 COIL

ASTM Metal CF8MNMN MOD

Date 8/30/2005

Cert Number

169470-1

A handwritten signature in black ink, appearing to read "CAR", is located in the lower right quadrant of the page.

We certify that we have complied in accordance with the drawings(s) and specifications(s) listed on the above purchase order. The articles furnished were made and/or processed from parts and/or materials in accordance with all applicable drawings(s) and specifications(s) pursuant to the afore mention purchase order.

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager

**Superior Quality Engineered Metal Products**

[www.MetalTekInt.Com](http://www.MetalTekInt.Com)



### Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

### Final Inspection Report

Customer Name: ENERGY INDUSTRIES OF OHIO

Pattern: SE-141-033 COIL A SHIM

Order Number: PPPL-FP-LTS-2

ASTM Metal CF8MNMN MOD

Date 8/30/2005

Type Description	Cert Number	Procedure	Acceptance Criteria	Actual
Liquid Penetrant	S76220-1	CQP - 300 Rev 9	ASTM A903 Level II	Acceptable
Mag Perm	S76220-1	SOP Mag Perm 100 Rev 1	<1.02	Acceptable
Radiographic	S76220-1	Technique # 12726	MSS SP 54	Acceptable
Visual	S76220-1	CQP - 500 REV 4	ASTM A802 LEVEL 2	Acceptable

#### Liquid Penetrant

Technician: Jason Reese  
ASNT Level III

#### Visual

Technician: Kevin Anderson  
ASNT Level II

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager



3

## Carondelet Division

8600 Commercial Blvd. - Pevely, MO 63070 USA  
Phone: 636-479-4499 - Fax: 636-479-3399

### Certificate of Conformance

ENERGY INDUSTRIES OF OHIO

Order Number PPPL-FP-LTS-2

Pattern SE-141-033 COIL A SHIM S/N 2

Alloy CF8MNMnMOD

Date 8/30/2005

Cert Number

S76220-1

A shim for A-1 coil was poured from heat number 29198. No weld repairs were necessary.

A handwritten signature in black ink, appearing to read "CAR", is located in the lower right quadrant of the page.


We certify that we have complied in accordance with the drawings(s) and specifications(s) listed on the above purchase order. The articles furnished were made and/or processed from parts and/or materials in accordance with all applicable drawings(s) and specifications(s) pursuant to the afore mention purchase order except as noted by corrective actions.

Respectfully Submitted,  
Charles A. Ruud  
Quality Assurance Manager

**Superior Quality Engineered Metal Products**

www.MetaltekInt.Com

**EIO**  
**Energy Industries of Ohio**  
**SUPPLIER QUALITY RELEASE**

\_\_\_\_\_  \_\_\_\_\_ Date: 9-01-05


I. General Information:		
Project Name:	Modular Coil Winding Form A1	
PO No:	NCSX-SOW-141-02-01	Rev.:
Supplier:	MetalTek	
Procurement Agent:	EIO	
Shipment:	<input checked="" type="checkbox"/> Partial <input type="checkbox"/> Final	


II. Material Description	
Casting A1 Coil 1	

III. Release Checklist	
Plan Requirements Complete?	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No <input type="checkbox"/> N/A (If identified "No" provide explanation in comments section below)
Variations?	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No <input type="checkbox"/> N/A (If identified "No" provide explanation in comments section below)
Princeton Notified of Shipment?	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No <input type="checkbox"/> N/A (If identified "No" provide explanation in comments section below)
DCMA Notified of Shipment?	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No <input type="checkbox"/> N/A (If identified "No" provide explanation in comments section below)
<input checked="" type="checkbox"/> Conditional <input type="checkbox"/> Unconditional	Explain conditional releases in comments section.

IV. Comments	
Metallurgical Re- testing pending, unable to complete prior to shipment see CA#1379 Elongation failure no results -320 weld material	

By signing below you acknowledge that the casting has met all applicable standards and contractual requirements

V. Supplier Quality Representative Sign Off		
Charles Ruud	X 	9-01-05
Supplier Quality Representative (SQR) Print/Type Name	Supplier Quality Representative (SQR) Signature	Date

VI. Supplier Approval For Shipment		
Procurement Agent Notified of Shipment	Date: 9-01-05	
Required Vendor Data Ready for Shipment	Date: 9-01-05	
Peter A Djordjevich		9-01-05
	X	

**EIO**  
**Energy Industries of Ohio**  
**SUPPLIER QUALITY RELEASE**

		Date: 9-01-05
--	--	---------------

I. General Information:		
Project Name:	Modular Coil Winding Form A1	
PO No:	NCSX-SOW-141-02-01	Rev.:
Supplier:	MetalTek	
Procurement Agent:	EIO	
Shipment:	<input checked="" type="checkbox"/> Partial <input type="checkbox"/> Final	
Supplier's Representative Print/Type Name	Supplier's Signature	Date

1. Enter:  
Project Name  
PO Number  
Supplier  
Procurement Agent
  
2. Enter a brief description of items being released, including applicable drawing number(s), dash or item number(s), drawing revision letter, specification(s), and serial number(s).
  
3. Self-Explanatory
  
4. Record any unusual circumstance, such as a conditional release.
  
5. The Supplier's representative shall sign and date.
  
7. Signature and date of the Supplier's authorized representative indicating shipping date.
  
8. In case of partial release, the supplier shall maintain copies of each sequential "Supplier Quality Release" and establish complete accountability of material release on final shipment.
  
9. Supplier shall include a copy of the completed form with each shipment.

**Energy Industries of Ohio**

**Corrective Action Report/Request ID#0002**

**Date 12-28-05**

**Due: N/A**

**Initiated By: Peter Djordjevich**

**Issue/Non Conformance: A series coil, thin wall condition  
Per previous MTK issue NCR#1347**

**Root Cause: Casting shrinkage in excess of factored pattern shrink. Due to solidification variances casting shrinkage varied from the norm. Although this is not 100% conclusive it is the most likely culprit.**

**Corrective Action: Although the pattern can be stocked, after review it has been determined to use as is. A minimum wall thickness has been established and adhered to.**

**Verification of Corrective Action: Per team discussions the above has been implemented.**

**Completion / Verification Date 01-03-06**

**Signature EIO Quality**

**Peter Djordjevich**




December 28, 2005

**Project # 0412**  
**Fusion Chamber Castings**  
**A Casting**

Tim Wenninger  
Project Manager  
Lawton Pattern Division  
1950 De Pere, WI 54115  
[timw@calawton.com](mailto:timw@calawton.com)  
920-983-4053

This letter is intended to document a tolerance loss observed during dimensional inspection of an A casting and the corrective actions that were used to recover satisfactory tolerances. The tolerance loss occurred due to an unforeseen set of circumstances and Standard Operating Procedures will be updated to prevent future problems even in such a rare occurrence.



The castings were scanned in three separate “sessions” as shown in yellow, green, and gray. Each session was scanned using a Konica-Minolta 9i/PSC-1 measurement system ISO certified to +/-0.05mm (0.002in).

This system uses a widely accepted technique called Photogrammetry to establish the accuracy of the measurement session. Theoretically only 3 points are required to establish a reference system. When more than three points are used the redundancy allows the system to track error. For this part, over 300 reference markers were used.

Figure 1: The part was measured in 3 separate measurement sessions.

Each of the three major sessions shown above when considered independently is known to be within the accuracy capabilities of the system. The task of combining the separate measurement sessions typically relies on simply locking in overlapping data to lock in the separate sessions together. The unique geometries provide a 3d “lock and key” that ensures an accurate alignment.

The problem encountered on this casting occurred when trying to locate the bottom session (in grey above) relative to the main session (in green above). The main session was taken with the part resting on the floor such that the entire grey surface was not accessible as shown in Figure 2.




Figure 2: The main scan was performed with the part in an upright orientation. This left the underside of the part un-scanned since it was facing the floor.

Typically the goal is to get enough overlap between any two sessions so as to enable a tight lock between them, as shown between the yellow and green sessions in Figures 2 and 3. When the part was layed down to scan the bottom (grey side) the problem was that the edge of the scan almost exactly matched the edge of the green session. There was some overlap on the left side but the lack of overlap on the right side caused a misalignment to occur that resulted in the grey session not being placed properly and thus producing error in thickness calculations in that area. The fact that the outlines (shown in red) matched so closely is a rare occurrence that caused an unforeseen problem.




Figure 3: The edges of the green and grey sessions are shown in red.

### **The Solution:**

To rectify the problem, reference marks were recovered from the original data. The points circled in Figure 4 were captured in the background on the opposite side of the part. These reference marks were then able to be used to register the grey session to the green session. Not only did it provide a solution for aligning the two but it also provides an achieved accuracy result. The cluster of reference marks matched from grey to green sessions to within  $\pm 0.00175$  inches! Unfortunately because there were no reference marks in common in the foreground of the grey scan and the fact that these reference marks are on the opposite side of the part, a lever arm effect must be accounted for to compensate for how a small error on the opposite side is magnified before it resolves on the foreground side.





Figure 4: A cluster of reference markers was fortunately recovered in the background of this scan.

**Achieved Accuracy:**

All three sessions independently remained within working tolerances during the scanning operation and thus the quoted system accuracy of 0.05mm (0.002in) applies. When considering the entire inspection as a whole, the largest error source is from this lever arm effect due to having to use reference marks from across the part. A conservative distance of 120in was used for the lever arm as the part can easily fit inside that distance. Similarly a conservative “platform width” of 24in was used to approximate the width of the “base” of the lever arm since the cluster of reference marks used is at least 24in in the narrowest area. Therefore the achieved accuracy when considering the fact that there is a lever arm effect comes to  $120 \tan(\sin^{-1}(0.0035/24)) = 0.018\text{in}$  or  $\pm 0.009\text{in}$ . Therefore the thickness measurements and all other measurements on the inspection should have tolerance of  $\pm 0.009\text{in}$  taken into consideration at all times. If that achieved accuracy is not sufficient, then it may be necessary to rescan in order to attempt to achieve a higher tolerance.



3dScanCo	
Project	0412
Measured by	Karol Hatzilias
Dates	6-7-05 & 7-5-05
Scanner Make	Konica Minolta
Scanner Model Number	9i
Scanner Serial Number	1001020
Scanner Last Calibrated	6-6-05
Scanner Cal Artifact	1001020
Photogrammetry Make	Konica Minolta
Photogrammetry Model	PSC-1
Photogrammetry Serial	7281026
Photogrammetry Last Cal	6-6-05 & 6-16-05
Photog Cal Artifact	7141013

**Disclaimer:**

The results of this analysis are believed to be reliable but are not to be construed as providing a warranty, including any warranty of merchantability or fitness for purpose, or representation for which 3dScanCo assumes legal responsibility. Client should undertake sufficient verification and testing to determine the suitability of any information presented. It is the sole responsibility of the Client to review the results and make any determinations. Nothing herein is to be taken as permission, inducement or recommendation by 3dScanCo to practice any patented invention without a license or to in any way infringe upon the intellectual property rights of any other party.

### Whole Deviation Session

Type: **Surface Type**

Name: **Whole Deviation 2**

1st Reference Entity: scan\_2\_merge3\_PGNOPG and scan\_merge\_02

2nd Reference Entity: 521 Surfaces

Calculate Tolerance: 2.81862


Acceptable Tolerance: 0.00000





Maximum Range: 1.00000



Minimum Range: -1.00000



Average: -0.01692

Standard Deviation: 0.26034


















### Annotation Session

Reference Whole Deviation Name: **Whole Deviation 2**









Name	Scan Data Position			Design Data Position			Displacement			Distance
	X	Y	Z	X	Y	Z	X	Y	Z	
Annotation 6				52.63935	-0.64813	-4.82390				-0.62804

December 28, 2005

**Project # 0412  
Fusion Chamber Castings  
A Patterns**

Tim Wenninger  
Project Manager  
Lawton Pattern Division  
1950 De Pere, WI 54115  
[timw@calawton.com](mailto:timw@calawton.com)  
920-983-4053


After reviewing the scan data from the A patterns it is evident the original results provided with inspection results are sound. A double check of the data was done for all core boxes including the cope and drag. The alignment of the scan data to CAD was also verified.

The patterns are machined using precision CNC mills. The accuracy achieved on these patterns is at least an order of magnitude better than that observed on the casting. The patterns all came in with an RMS residual error under 0.0050" except core box 6, which was the largest RMS value at 0.0052". Each pattern was scanned using a photogrammetry session, each session has an overall RMS residual error. This means we are confident in the data of each session to this value. Here are the results of each photogrammetry session.


Core Box	Overall RMS residual error(mm)
1	0.0299
2	0.0425
3	0.117
4	0.0593
5	0.0744
6	0.132
7	0.0642
8	0.0647
9	0.0743
10	0.0793
cope	0.113
drag	0.106
polodial	0.0303

The color maps below show the deviations of scan data when compared to CAD. These are the same color maps as were in the original inspection reports. Shown here is also the histogram report, which shows how much of the data resides within each deviation band. For example 100% of the 428,125 points scanned for box 1 are within 0.025" and the majority are within 0.005".


**Box 1:** 458125 data points



**Box 2:** 102077 data points




**Box 3:** 1396426 data points







**Box 4:** 382140 data points




**Box 5: 685973 data points**




**Box 6:** 1583613 data points




**Box 7:** 573572 data points




**Box 8:** 668847 data points




**Box 9:** 438097 data points



**Box 10:** 425102 data points




Cope: 612115 data points









**Drag:** 258097 data points



**Polodial:** 998922 data points






**Disclaimer:**

The results of this analysis are believed to be reliable but are not to be construed as providing a warranty, including any warranty of merchantability or fitness for purpose, or representation for which 3dScanCo assumes legal responsibility. Client should undertake sufficient verification and testing to determine the suitability of any information presented. It is the sole responsibility of the Client to review the results and make any determinations. Nothing herein is to be taken as permission, inducement or recommendation by 3dScanCo to practice any patented invention without a license or to in any way infringe upon the intellectual property rights of any other party.

## Evaluation of stocked A model for adequate stock



### Notes:

1. Measurements shown are through-wall thickness measurements of the stocked A model (no shrink) created by Lawton Patterns.
2. Measurements taken along wall where the A-1 casting is exhibiting thin wall conditions ranging down to 1.18"
3. Software used to verify wall thickness of model – Solid View/Pro 2003.1
4. Measurements taken on 8/2/05 by Roy Sheppard of EIO

# Energy Industries of Ohio


A-Coil Winding Form

Metrology Discussion – Pattern  
Verification


# Issues

- Dimensional data supports a under tolerance condition exists on an area of the shell
  - Limited options on increasing thickness on A1
- 3D Scanco data correlates to physical measurements taken by MetalTek on the A1
  - MetalTek dimension taken from shell at cut-thru
- Dimensional data supports that the A-B alignment will be achieved at the flanges, but may not align shells (no interference issues)
  - Root cause not confirmed
- Dimensional changes to A1 part are all long time period changes and involve extensive work to part and matching work on pattern equipment
  - Quickest path forward may be FEA and Waiver

# Location of 3 cross sections




# Left View







# Right View



# Cross Section 1




# Cross section 2




# Cross Section 3




# Machined Coil A




# Back wall after machining



# Additional points snagged for orientation





# Comparison of Machined Part to 3DScanco Layout



Views are slightly  
rotated. Use racetrack 129  
reference



# MetalTek Verification



Excised hole for  
dimensional verification  
(1.24-1.27")

# Summary of Layout

- A substantial amount of the wall appears to be under the design thickness
- 3DScanco data is at 95% Confidence Level (Approx. 0.018" error per 3DS)
- MetalTek verified one area with direct measurements
- Remediation options are limited and have risk





# Remediation Options

- Option 1 – Permanent Waiver
  - PPPL would need to assess part dimensions and FEA and assure that thin wall will not impact performance
  - Affects all A-coils
- Option 2 – Use-As-Is NCR
  - Would move A1 forward, but at risk of continued dimensional learning and schedule
  - Affects A1
- Option 3 – Weld Build Up
  - Would have to optimize part and identify areas for build up. Substantial shape risk on component. Large schedule impact.
- Option 4 – Remake
  - Would have schedule slip on both pattern and component in schedule. Would likely complete C coils and have production gap in program while B pattern completes and A is adapted.



# Request

- Energy Industries of Ohio Team requests that PPPL analyze this and respond with preferred direction to move forward
  - MetalTek can offer additional laser scanning for verification of shape/dimension
  - Lawton has offered transfer measurement as a means for direct measurement of thickness, MetalTek has experience using similar technique
  - Component is on process hold pending resolution. Time is of the essence.


# Stresses in Shell A1 for E=193 GPa




# Stresses in Shell A1 for $E(A)=152$ GPa and $E(B\&C)=193$ GPa



# Stresses in Shell A1 for E=193 GPa




Top View





Side View

# Stresses in Shell A1 for $E(A)=152$ GPa and $E(B\&C)=193$ GPa



Top View



Side View





# FEA Analyses Results of the A1 Casting with Thin Wall Regions

August 8, 2005


# Thin Wall Areas in the A1 Casting

thin areas in light blue



Machined Casting

Note That Much Of the Thin Area is Machined Away, Lessening its Effect




FEA model – thin areas are tan.

# SCANCO data well quantifies the actual wall thicknesses

Specified thickness is 1.375"  
+0.25 / -0.00

Thinnest actual section is 1.18".

"Guesstimate" is the thin area is 15% of the wall area.



# FEA Studies for the Shell A Thin Wall Region:

- Run #1: **Baseline Engineering Analysis used E for 316 SS.** The E=193 GPa was based on data for 316 stainless steel as an interim value until E for cast “Stellalloy” was determined.

- Run #5: **Analysis Corrected for the E of “Stellalloy”.** All shells having E=145 GPa, the value given by the specification for “Stellalloy”.

- Run #6: **This model reflects the updated E and also thin shell regions in A1 with wall thicknesses  $t=1.18$ ”.** The E of shell A is modified by a thickness ratio of 1.18/1.375. The E of shell A become 124 GPa. (Note: In the FEA model, the affect of the thin wall is achieved by modifying the effective modulus, E, rather than actually changing the wall thickness in the model )

- Run #4: **This model uses a corrected E and models All Type A Castings as Having A Thin Region Like A1 but 1.05” thick.** E of shell is 145 GPa except in the shell A thin wall regions, where E=111 GPa

The slides which follow show that this is by far the most significant affect!

The Analyses Show That The Thin Region With Either Thickness Has a Very Minimal affect!

# The Stress Allowable Based on the Spec. Minimum



Property at 77 K			
Property	Required	C-1 Casting Heat 27728 (averages)	LNM 4455 Electrode
Elastic Modulus E	21 Msi (144.8 Gpa)	23.3	27.1
0.2% Yield Strength	72 ksi (496.4 Mpa)	98.4 124	126.3
Tensile Strength	95 ksi (655 Mpa)	170.2 170.2	187.7
Elongation	32%	55% 58.7%	33%
Charpy V – notch Energy	35 ft. lbs. (47.4 J)	78	51

- The allowable is the lesser of  $\frac{1}{2}$  tensile strength or  $\frac{2}{3}$  yield.
- Using the spec minimum, this would be **322.5 MPa**. (the lesser of 322.5 or 327.6)

# The Baseline Analysis: Stresses in Shell Type A

(Run 1)


- E=193 GPa




Stress Plot up to 120MPa

# Baseline: Axial Stresses in Modular Coils for Run No. 1


- E=193 GPa



Coil Type A




Top View



# Analysis Results with the E Updated for “Stellalloy”

Stresses in Shell Type A for Run No. 5


- E=145 GPa








# E Updated for "Stellalloy" Axial Stresses in Modular Coils for Run No. 5

- E=145 GPa




Coil Type A



***This model reflects the updated E and also thin shell regions in A1 with wall thicknesses  $t=1.18''$ .*** Stresses in Shell


Type A for Run No. 6

- E=145 GPa except E(thin wall region)=124 GPa






***This model reflects the updated E and also thin shell regions in A1 with wall thicknesses  $t=1.18''$ .*** Axial Stresses in Modular Coils for Run No. 6

- E=145 GPa except E(thin wall region)=124 GPa




Coil Type A



***This model uses a corrected E and models All Type A Castings as Having A Thin Region Like A1 but  $t=1.05$ "***

Modulus of Elasticity in Shell Type A for Run No. 4,



Left View

Right View



In the pink regions,  
 $E = 145 \text{ GPa}$

In the brown regions,  
 $E=111 \text{ GPa}$  to  
simulate a wall  
 $t=1.05$ ".


# ***This model uses a corrected E and models All Type A Castings as Having A Thin Region Like A1 but $t=1.05''$***

Stresses in Shell Type A for Run No. 4

- E=145 GPa except E(thin wall region)=111 GPa




Stress Plot up to 120MPa





# ***This model uses a corrected E and models All Type A Castings as Having A Thin Region Like A1 but $t=1.05$ "***

Axial Stresses in Modular Coils for Run No. 4  
 - E=145 GPa except E(thin wall region)=111




Coil Type A



151

Top View



# Summary:

---

- As the table below shows **the most significant effect is the updating of the modulus E to that of the “Stellalloy”**.
- Thin shell areas like that of A1 **has an extremely minor affect on the stresses and displacements in ANY of the coils or shells** with the thickness being either 1.18” as for A1 or even with the thickness being 1.05” which MTK projects is the minimum if the shell is not changed. Reasons:
  - a) The shape of the tee is not changed by this, and the tee provides most of of the bending stiffness
  - b) Some EM forces are transferred to the shell B from the wing.
  - c) The thin wall region is not the location for the peak stress and much of the area will be machined away.

<u>Run #</u>	<u>Configuration</u>	<u>Shell Type A</u>		<u>Coil Type A</u>		<u>All Coils</u>	
		Max. Displacement - mm	Max. Stress - Mpa	Max. Displacement - mm	Max. Stress - Mpa	Max. Displacement - mm	Max. Stress - Mpa
1	Baseline	0.98	168	1.246	239	2.711	239
5	Updated E	1.17	160	1.513	248	2.934	248
6	Updated E; thin sect. =1.18"	1.169	161	1.516	249	2.984	249
4	Updated E; thin sect. =1.05"	1.168	161	1.517	248	2.971	248

# Consequently...

- Since the thin section of A1 has virtually no affect on stresses or deflections of either the coil or shell, the NCR for A1 with the thin region having a minimum thickness of 1.18” will be dispositioned to “Accept As Is”.
- Pending the root cause analysis and EIO’s recommendation, if necessary, based on these analyses, we have the flexibility to allow the wall thickness IN AN AREA SIMILAR TO A1 for all future Type A Castings to be a minimum of 1.050” and a maximum of  $1.375 + 0.250 = 1.625$ ” (which is the same as the upper limit currently specified).



**Energy Industries of Ohio**

**Contract # S005242-F**

**Modular Coil Winding Form**

**A-1 Documentation Package**

**Part 2**

**Major Tool & Machine**


**Revised 8/28/2006**

**\*\*Note – The table of contents that follows a supplemental EIO TOC as an aide to locating documents. Documents may be duplicated in this package; 1<sup>st</sup> as an attachment to a NC (not listed) & the 2<sup>nd</sup> time in the order noted in the MTM TOC.**

# A-1 Documentation Package

## List of Documents 8-28-06

Doc #	Description	Page #
-	MTM – Original TOC & document list	157
1	Certificate of Conformance	159
2	Completed shop travelers – 65709-1	160
3	NC 19709 Tool gouge - welded	166
4	NC 19783 Counterbore depths	171
5	NC 19891 PT Rejections	173
6	NC 19916 RT Rejections	186
7	NC 19933 Misc Items - final visual	188
8	NC 19942 Final Dimensional	199
9	Material certification Loctite 411	201
10 & 15	Material certification G-11 round bar	202
11	IDC – Electrical Resistance Check	204
12	Material certification – weld wire – Metrode lot # W020132 Test certificate # 193695 & 194227	205
13	Westmoreland test results Metrode weld lot # W020132	207
14	Material certification – GE G11-CR flat sheet insulating material	211
15	Material certification G-11 round bar ( <b>Same as document 10</b> )	202
16	LP inspection certificate – Final inspection	212
17	MQS – RT map & reader sheet	213
18	IDC – Mag perm – Final inspection	215
19	IDC – Poloidal break	216
20	IDC – Final dimensional	217
21	Material certificate – South Texas Bolt - stud	223
22	Material certificate – South Texas Bolt - nut	224
23	Interim penetrant inspection certification for NC 19709 (doc # 3)	225
24	IDC – Mag perm – In process – weld repaired areas - NC 1709 (Doc # 3)	226
25	IDC – Mag Permeability of bearing plates - short	227
26	IDC – Mag Permeability of bearing plates - long	228



# ENERGY INDUSTRIES OF OH

Purchase Order Number:

S005242-F

Part Number:

SE141-114

Part Name:

MCWF A-1

MTM Work Order Number:

65709/1.0



*Major*

Tool & Machine, Inc.

Customer: 8909 - ENERGY INDUSTRIES OF OHIO  
 Customer P.O.: S005242-F  
 Customer Part ID: SE141-114 - MCWF A-1

Item#	Document Description / Material Description / File Name / Heat Lot
1	CERTIFICATE OF CONFORMANCE
2	COMPLETED SHOP TRAVELERS: - 65709-1 completed shop travelers.pdf
3	NC19709 - TOOL GOUGE: - NC19709_Welded_A1Gouge_w-Atts.pdf
4	NC19783 - COUNTERBORE DEPTHS: - NC19783 S5242_A1Bushings_050806.pdf
5	NC19891 - PT REJECTIONS: - NC19891 rev 1S5242_A1DP.pdf
6	NC19916 - RT REJECTIONS: - NC19916 S5242_A1RTRej.pdf
7	NC19933 - MISC. ITEMS: - NC19933 S5242_A1MiscDefects.pdf
8	NC19942 - FINAL DIMENSIONAL: - NC19942 S5242_idc_A1.pdf

**SE141-048 - POLOIDAL BREAK SHIM ASSEMBLY**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
9	2	30	20	Certificate of Conformance: FROM SUPPLIER / LOCTITE 411 - LOCKING COMPOUND - mc106320.tif / CERTIFIED

**SE141-048-03 - INSULATING SLEEVE**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
10	3	10	10	Certificate of Conformance: / G11CR_1 - ROUND, BAR, 1.75 DIA - mc108545.tif / CERTIFIED

**SE141-101**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
11	1	140		Inspection Data Checklist: 2 steps

**SE141-101-1 - MOD COIL WINDING FORM ASSEMBLY TYPE-A**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
12	0	10	10	Material Certification: Trace ID: 113686 / ER316MNNF_093_GTAW - WELD WIRE,GTAW .093 DIA - mc106164.pdf / W020132 / W020132
13	0	10	10	Material Certification: Trace ID: 116252 / ER316MNNF_093_GTAW - WELD WIRE,GTAW .093 DIA - mc106579.tif / W020132 / W020132

**SE141-101-4 - INSULATING SHEET**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
14	7	10	10	Certificate of Conformance: G11CR / G11CR_3 - SHEET, FLAT - mc107081.tif / CERTIFIED

**SE141-101-5 - INSULATING SLEEVE**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
15	5	10	10	Certificate of Conformance: / G11CR_1 - ROUND, BAR, 1.75 DIA - Same as Item #10 / CERTIFIED

**SE141-114 - MODULAR COIL WINDING FORM TYPE-A**

Item#	Sub	Op	Pc	Document Description / Material Description / File Name / Heat Lot
16	1	100		Nondestructive Liquid Penetrant Test Certification #16747
17	1	110		Map(s): RT MAP AND READER SHEET - MC119140.PDF

**Customer: 8909 - ENERGY INDUSTRIES OF OHIO**  
**Customer P.O.: S005242-F**  
**Customer Part ID: SE141-114 - MCWF A-1**

18	1	120		Inspection Data Checklist: 2 steps
19	1	130		Inspection Data Checklist: 4 steps
20	1	132		Inspection Data Checklist: 80 steps
21	15	10	10	Material Certification: / DS141-036 - STUD - mc118607.tif / XFR/E3930
22	15	10	20	Material Certification: / DS141-060 - NUT - mc118608.tif / XFR/5407813
23	17	40		NC19709 - Penetrant Test Certification #16858
24	17	50		NC19709 - IDC 1 step

**SE141-141 - BEARING PLATE DETAIL TYPE "A" SHORT**

<u>Item#</u>	<u>Sub</u>	<u>Op</u>	<u>Pc</u>	<u>Document Description / Material Description / File Name / Heat Lot</u>
25	18	30		Inspection Data Checklist: 1 steps

**SE141-142 - BEARING PLATE DETAIL TYPE "A" LONG**

<u>Item#</u>	<u>Sub</u>	<u>Op</u>	<u>Pc</u>	<u>Document Description / Material Description / File Name / Heat Lot</u>
26	19	30		Inspection Data Checklist: 1 steps

CERTIFICATE OF CONFORMANCE

Page: 1  
Date: 08/02/06  
User ID: GRIFFIT#

TO: ENERGY INDUSTRIES OF OHIO

DATE: 06/12/2006

ATTENTION: Receiving Department

Seller certifies that:

Part Number: SE141-114

Purchase Order: S005242-F

Part Name: MCWF A-1

Workorder: 65709/1.0

Part Serial Number: A1

Quantity: 1

1. These materials and/or parts were produced in conformance with all contractually applicable Government and/or Customer specifications referred in, or furnished with, the above Purchase Order.
2. The materials and/or parts furnished under the above Purchase Order were produced:
  - From materials furnished by Customer for the production of such parts.
  - From materials for which the seller has available for examination chemical and/or physical test reports or other evidence of conformance to applicable specifications.
3. All processes required in the production of these part and/or materials are listed below and were performed by a facility or personnel approved or certified by the Seller and the customer when such approval or certification is required by contract.

Certifications are on file at this plant.

Other Requirements:

MANUFACTURED PER B.P. SE141-101 REV. 3 AND P.O. REQUIREMENTS.

Signature: 

Title: Quality Mgr

Date: 8/2/06



Activity	Visual Mfg Ref.	Op Status	Close Date	Emp ID
Manufacturing Planning- QA planning- Production Support	65709/1.0 -Sub:0 Op#:10	Closed	3/3/2006	965-T.Hayden
Final Inspection----Prepare part for source inspection.----Review and complete QA data package per QAP and the requirements of the product specification NCSX-CSPEC-141-03-05 September 23- 2004.--Contact CFT to review data package prior to notifying source	65709/1.0 -Sub:0 Op#:20	Closed	6/1/2006	840-G.Masood
Source Inspection	65709/1.0 -Sub:0 Op#:30	Closed	6/1/2006	840-G.Masood
ORIENT PART WITH DATUM E FLANGE DOWN.---ENUSURE PART SURFACES ARE CLEAN AND FREE OF GRIT AND DEBRIS. THE PART IS NOT TO BE OILED.--THE ENTIRE PART IS TO BE WRAPPED IN PLASTIC.--PLACE FOAM ON THE 4X6 BEAMS THAT THE FLANGE WILL BE SITTING ON. LOWER THE PAR	65709/1.0 -Sub:0 Op#:40	Closed	6/3/2006	567-R.Hupp
Receive customer supplied material. ---Customer material data package will not be received with the part. This record will be obtained and linked later.---Part Number: SE141-114 Rev: 6--Part Description: PRODUCTION WINDING FORM TYPE-C	65709/1.0 -Sub:1 Op#:10	Closed	5/9/2006	219-T.Laird
SETUP AND MACHINE THE FLANGE FACES AND FLANGE PERIPHERY TO WITHIN .100- STOCK. USE SCRIBING PROGRAM TO LAY OUT AREAS OF CASTING TO BE BURN OUT.	65709/1.0 -Sub:1 Op#:18	Closed	2/21/2006	631-J.Pond
WELD BRACES OVER THE PRE-CUT POLOIDAL BREAK IN THE -T-. SEE RON BACK FOR LOCATION OF BRACES.---MARK INSIDE EACH AREA TO BE REMOVED USING A METAL STAMP WITH THE SERIAL NUMBER FOR EACH PART AS APPLICABLE- A1- A2- A3- ETC...LOCATION OF STAMPING IS OPTIONAL.	65709/1.0 -Sub:1 Op#:19	Closed	2/22/2006	374-J.Connell
SET CASTING ON RISERS WITH DATUM -E- FLANGE DOWN. ROUGH MACHINE OUTSIDE POLOIDAL BREAK FLANGES TO WITHIN .030- OF FINISH. MACHINE POLOIDAL BREAK THROUGH THE FLANGES AND CASTING WALL TO 2.050- LEAVING THE T SECTION TO BE CUT AT A LATER TIME.	65709/1.0 -Sub:1 Op#:20	Closed	3/3/2006	493-J.Walker
USING TABS CUT FROM CUSTOMER SUPPLIED MATERIAL- WELD TEMPORARY SHIM IN PLACE. WELD TABS TO SHIM AND TABS TO CASTING. (DO NOT WELD SHIM DIRECTLY TO CASTING)--USE MACHINED QUALIFIERS TO HELP POSITION THE SHIM.	65709/1.0 -Sub:1 Op#:25	Closed	3/8/2006	713-M.Smith



Activity	Visual Mfg Ref.	Op Status	Close Date	Emp ID
SET UP FIXTURE PLATE MTMFX-3101 AND MACHINE LOCATING PADS AS NECESSARY.--SET UP CASTING WITH DATUM -E- AGAINST THE FIXTURE.-- FINISH MACHINE ALL AREAS BELOW THE T SECTION.-- MACHINE T SECTION TO WITHIN .030.-- FINISH MACHINE DATUM -D- FLANGE.--	65709/1.0 -Sub:1 Op#:30	Closed	4/7/2006	493-J.Walker
SET UP FIXTURE PLATE MTMFX-3102 AND MACHINE LOCATING PADS AS NECESSARY.--SET UP CASTING WITH DATUM -D- AGAINST THE FIXTURE.-- FINISH MACHINE ALL AREAS BELOW THE T SECTION.-- MACHINE T SECTION TO WITHIN .030.-- FINISH MACHINE DATUM -E- FLANGE.--	65709/1.0 -Sub:1 Op#:35	Closed	4/22/2006	744-P.Schumacher
U5 FINAL MACHINING OPERATION	65709/1.0 -Sub:1 Op#:50	Closed	5/12/2006	313-R.Bachek
PROTECT PART FROM METAL CONTAMINATION DUE TO CONTACT WITH IRON- SPECIFICALLY WHEN RIGGING PART FOR MOVEMENT.-- ALL GRINDING WHEELS AND DISKS MUST BE VIRGIN MATERIAL NOT PREVIOUSLY USED ON ANY OTHER MATERIAL TO AVOID MATERIAL CONTAMINATION.----- CAREFULLY R	65709/1.0 -Sub:1 Op#:85	Closed	5/16/2006	219-T.Laird
PROTECT PART FROM METAL CONTAMINATION DUE TO CONTACT WITH IRON- SPECIFICALLY WHEN RIGGING PART FOR MOVEMENT.-- ALL GRINDING WHEELS AND DISKS MUST BE VIRGIN MATERIAL NOT PREVIOUSLY USED ON ANY OTHER MATERIAL TO AVOID MATERIAL CONTAMINATION.-- WEIGH PART AN	65709/1.0 -Sub:1 Op#:88	Closed	6/2/2006	524-G.Davis
PROTECT PART FROM METAL CONTAMINATION DUE TO CONTACT WITH IRON- SPECIFICALLY WHEN RIGGING PART FOR MOVEMENT.-- MOVE PART INTO WASH BOOTH. --THOROUGHLY CLEAN AND DRY ALL SURFACES AND HOLES PER SECTION 9 OF PS583. --PARTS TO BE WASHED USING HEATED- DE-MINERA	65709/1.0 -Sub:1 Op#:90	Closed	5/18/2006	219-T.Laird
PT 100% OF FINISHED MACHINED SURFACES ONLY. SEE PS582 FOR PROCESSING INSTRUCTIONS. ---TAKE PHOTOS OF ALL REJECTIONS AND NUMBER THEM. IF THERE ARE SEVERAL INDICATIONS CLOSE TOGETHER- NUMBER THE GROUP AND RECORD THE LARGEST INDICATION.--MAKE A LIST OF THE	65709/1.0 -Sub:1 Op#:100	Closed	5/20/2006	581-D.Edwards
GOVERNMENT SOURCE INSPECTOR TO WITNESS PT RESULTS.	65709/1.0 -Sub:1 Op#:101	Closed	6/1/2006	840-G.Masood





Activity	Visual Mfg Ref.	Op Status	Close Date	Emp ID
THE -T- AREAS DEFINED AS -HIGH STRESS- ARE TO BE RT 100%. SEE PS581 FOR PROCESS INSTRUCTIONS.—HAND SKETCH A LAYOUT OF ALL FILM LOCATIONS ON ATTACHED RT MAP. —ALL FILM IS TO BE DOUBLED UP IN ORDER TO SUPPLY THE CUSTOMER WITH A COMPLETE SET OF FILM.—	65709/1.0 -Sub:1 Op#:110	Closed	5/25/2006	010-R.Contractor
GOVERNMENT SOURCE INSPECTOR TO WITNESS RT RESULTS.	65709/1.0 -Sub:1 Op#:111	Closed	6/1/2006	840-G.Masood
PERFORM A MAG PERMEABILITY CHECK OF THE MACHINED SURFACES USING A SEVERN PERMEABILITY INDICATOR GAGE. PERMEABILITY SHOULD BE NO GREATER THAN 1.02μ.—CHECK THE PERMEABILITY IN 3 PLACES ON EACH SIDE OF THE T SECTION AT LOCATIONS ADJACENT TO EVERY 5TH HOLE	65709/1.0 -Sub:1 Op#:120	Closed	5/31/2006	854-R.Upchurch
SOURCE FOR MAG PERMEABILITY	65709/1.0 -Sub:1 Op#:121	Closed	6/1/2006	840-G.Masood
SET PART ON RISERS WITH DATUM -D- FLANGE DOWN. PLACE A RISER ON EITHER SIDE OF THE POLOIDAL BREAK TO ENABLE CLAMPING TO ENSURE THAT THE DATUMS ARE COPLANER. LAY A STRAIGHT EDGE ACROSS THE DATUM -D- FLANGE TO VERIFY ALIGNMENT. ENSURE RADIAL ALIGNMENT BY LA	65709/1.0 -Sub:1 Op#:130	Closed	5/22/2006	825-B.Jarrett
CMM INSPECT AND COMPLETE IDC. OUTPUT INSPECTION RESULTS FOR VERIFICATION USING VERISURF SOFTWARE.—Part Number: SE141-114—Part Description: PRODUCTION WINDING FORM TYPE-A	65709/1.0 -Sub:1 Op#:132	Closed	6/1/2006	339-E.Root
SOURCE FOR DIMENSIONAL	65709/1.0 -Sub:1 Op#:133	Closed	6/1/2006	840-G.Masood
THE RESISTANCE OF THE MID-PLANE ELECTRICAL INSULATION SHALL BE GREATER THAN 500 KOHMS WHEN TESTED AT 100 VDC.— -TEST 1:—THE INSULATION RESISTANCE BETWEEN THE MID-PLANE POLOIDAL BREAK SHIM AND WINDING FORM SHALL BE MEASURED. DURING THIS TEST- THE BOLTS S	65709/1.0 -Sub:1 Op#:140	Closed	5/25/2006	840-G.Masood
SOURCE FOR ELECTRICAL TEST	65709/1.0 -Sub:1 Op#:150	Closed	5/25/2006	840-G.Masood
Receive customer supplied material. Part had been returned to vendor for rework.—Part Number: SE141-114 Rev: 5—Part Description: PRODUCTION WINDING FORM TYPE-C	65709/1.0 -Sub:9 Op#:10	Closed	1/21/2006	085-D.Gregory
SAW MATERIAL TO LENGTH PER MATERIAL CARD.	65709/1.0 -Sub:12 Op#:10	Closed	2/28/2006	266-R.Keith



Activity	Visual Mfg Ref.	Op Status	Close Date	Emp ID
MACHINE SLAVE HARDWARE BUSHINGS TO THE FOLLOWING:--- 1.620 O.D.+0/-.002--1.376 I.D. +.004/-.000--LENGTH 1.350 +/- .010--- THESE BUSHINGS ARE FOR SLAVE HARDWARE SHIM MOUNTING. DELIVERY THESE PARTS TO RON BACK WHEN COMPLETE. THEY ARE TEMPORARY BUSHINGS THAT	65709/1.0 -Sub:12 Op#:20	Closed	3/2/2006	821-J.Leggins
DOCUMENT THE LOCATION OF THE TOOLING BALLS PRIOR TO REMOVING THE PART.--REMOVE PART FROM THE U5 AND SETUP FOR WELDING.	65709/1.0 -Sub:17 Op#:10	Closed	4/25/2006	231-B.Blankenberger
WELD REPAIR TOOLING GOUGE.--PLACE INDICATORS ON AND AROUND THE T SECTION TO MONITOR MOVEMENT DURING WELDING. ALTER WELD PROCESS AS REQUIRED TO PREVENT ANY PART MOVEMENT GREATER THAN .01-. IF REQUIRED- WELD ON THE OPPOSITE SIDE OF THE T TO COMPENSATE FOR A	65709/1.0 -Sub:17 Op#:20	Closed	5/1/2006	509-S.Roberts
REPEAT SETUP #1 ON U5. RE-ESTABLISH TOOLING BALL LOCATIONS FROM PREVIOUS SETUP.--RE MACHINE THE AREA THAT WAS WELD REPAIRED.	65709/1.0 -Sub:17 Op#:30	Closed	5/1/2006	315-C.Land
PENETRANT INSPECT WELD REPAIR.--REFERENCE NC19709 ON PT CERTIFICATION.--Specification: ASTM A903/A903M LEVEL 1--MTM NDT Cert: REPAIR OF DEFECTS	65709/1.0 -Sub:17 Op#:40	Closed	5/26/2006	581-D.Edwards
PERFORM A RELATIVE MAGNETIC PERMEABILITY CHECK OF THE REPAIRED AREA. VERIFY PERMEABILITY IS LESS THAN 1.02. PERMEABILITY TO BE CHECKED AT A MINIMUM OF 1 POINT EVERY 2 SQR. INCHES IN THE REPAIRED REGION.--	65709/1.0 -Sub:17 Op#:50	Closed	6/1/2006	840-G.Masood
MACHINE INSERTS COMPLETE PER DRAWING.--STELLALLOY MATERIAL FROM BURN OUT DROPS MUST BE USED TO MANUFACTURE THE INSERTS.	65709/1.0 -Sub:20 Op#:10	Closed	5/12/2006	236-M.Jennings
THREAD MILL THE TWO HOLES TO ACCEPT A 2.5-10 UNC-2B PLUG. (SEE TEAM LEADER FOR CLARIFICATION)--INSTALL THE PLUGS .010- TO .020- ABOVE THE DATUM -E- FACE TO ALLOW STOCK TO MACHINE FLUSH.--TACK WELD PLUGS IN PLACE TO PREVENT ROTATION. TACK IN TWO PLACES PER	65709/1.0 -Sub:20 Op#:20	Closed	5/26/2006	891-T.Gilliland
RECEIVE CUSTOMER SUPPLIED CASTING	65709/1.0 -Sub:2 Op#:10	Closed	2/24/2006	854-R.Upchurch
MACHINE THE SHIM COMPLETE PER THE DRAWING AND CNC PROGRAMS.	65709/1.0 -Sub:2 Op#:20	Closed	2/24/2006	234-E.Booher



Activity	Visual Mfg Ref.	Op Status	Close Date	Emp ID
ASSEMBLE ALL OF THE INSULATING SLEEVES INTO THE SHIM AND BOND USING LOCTITE 411.	65709/1.0 -Sub:2 Op#:30	Closed	5/19/2006	825-B.Jarrett
SAW OFF 16- AND MOVE TO NEXT WORK CENTER.	65709/1.0 -Sub:3 Op#:10	Closed	6/1/2005	227-D.Bockover
MACHINE PER THE DRAWING FOR A SLIP FIT WITH MATING DETAILS. --MACHINE ID TO 1.376- / 1.377-.--MEASURE THRU HOLES IN PART AND MATCH BUSHING OD FOR A .001- - .002- SLIP FIT.--	65709/1.0 -Sub:3 Op#:20	Closed	5/16/2006	236-M.Jennings
RECEIVE MATERIAL--NOTIFY CFT AND FORWARD MATERIAL STORES.	65709/1.0 -Sub:4 Op#:10	Closed	6/1/2005	131-W.Allen
SAW OFF 30- LENGTH AND MOVE TO NEXT WORK CENTER.	65709/1.0 -Sub:5 Op#:10	Closed	6/1/2005	227-D.Bockover
MACHINE PER THE DRAWING FOR A SLIP FIT WITH MATING DETAILS. --MACHINE ID TO 1.376- / 1.377-.--MEASURE THRU HOLES IN PART AND MATCH BUSHING OD FOR A .001- - .002- SLIP FIT.--	65709/1.0 -Sub:5 Op#:20	Closed	5/17/2006	821-J.Leggins
SAW 13- LENGTH AND MOVE TO NEXT WORK CENTER.	65709/1.0 -Sub:6 Op#:10	Closed	6/1/2005	227-D.Bockover
RECEIVE MATERIAL	65709/1.0 -Sub:7 Op#:10	Closed	4/5/2005	131-W.Allen
MACHINE THE G-11 SHIM PIECES:--THERE ARE TWO PROGRAMS- ONE FOR EACH SIDE OF THE BREAK SHIM.--EACH PROGRAM WILL GENERATE 3 SHIM PIECES FOR A TOTAL OF 6 PIECES FOR THIS OPERATION.	65709/1.0 -Sub:7 Op#:20	Closed	5/12/2006	129-E.Taina
CHECK AND RECORD PERMEABILITY OF PLATES PRIOR TO GRIND.	65709/1.0 -Sub:14 Op#:10	Closed	3/6/2006	176-J.Denney
VERIFY THICKNESS OF PLATES AND DETERMINE HOW MUCH STOCK REMAINS.--GRIND EACH SIDE OF PLATES TO A CLEAN UP WHILE KEEPING THE THICKNESS OF THE PLATES IN TOLERANCE.	65709/1.0 -Sub:14 Op#:20	Closed	3/6/2006	552-D.Lee
CHECK PERMEABILITY OF PLATES AGAINST PREVIOUSLY RECORDED VALUES TO SEE IF GRINDING REDUCED THE READINGS.	65709/1.0 -Sub:14 Op#:30	Closed	3/6/2006	503-B.Houk
RECEIVE HARDWARE- SCAN CERTIFICATIONS AND COMPLETE IDC.-- MOVE TO STORES--	65709/1.0 -Sub:15 Op#:10	Closed	5/15/2006	261-T.Dunn
PLACE THE FOLLOWING IN STORES:--7 PCS - DS141-036 STUD--14 PCS - DS141-060 NUT	65709/1.0 -Sub:15 Op#:20	Closed	5/17/2006	490-J.Smith



Activity	Visual Mfg Ref.	Op Status	Close Date	Emp ID
MACHINE THICKNESS OF SHIM TO 2.125 +/- .001-.--REMOVE AN EVEN AMOUNT OF STOCK FROM EACH FACE OF THE SHIM. THERE IS APPROXIMATELY 1/16- PER SIDE OF STOCK ON THE PART.--DRILL / TAP FOR A 3/8-16 LIFTING HOLE 1- DEEP IN EACH END OF THE SHIM. CENTER THE HOLES	65709/1.0 -Sub:16 Op#:10	Closed	5/26/2006	891-T.Gilliland
NO CERTIFICATIONS REQUIRED.--VERIFY QUANTITY AND FORWARD PARTS TO NEXT WORK CENTER.	65709/1.0 -Sub:18 Op#:10	Closed	5/12/2006	437-J.Hiatt
MACHINE COMPLETE PER PRINT	65709/1.0 -Sub:18 Op#:20	Closed	5/15/2006	129-E.Taina
PERFORM A MAGNETIC PERMEABILITY CHECK USING A SEVERN PERMEABILITY INDICATOR GAGE. PERMEABILITY SHOULD BE NO GREATER THAN 1.02μ.--Part Number: SE141-141--Part Description: BEARING PLATE TYPE -A- SHORT	65709/1.0 -Sub:18 Op#:30	Closed	5/16/2006	261-T.Dunn
NO CERTIFICATIONS REQUIRED.--VERIFY QUANTITY AND FORWARD PARTS TO NEXT WORK CENTER.	65709/1.0 -Sub:19 Op#:10	Closed	5/12/2006	437-J.Hiatt
MACHINE COMPLETE PER PRINT	65709/1.0 -Sub:19 Op#:20	Closed	5/16/2006	129-E.Taina
PERFORM A MAGNETIC PERMEABILITY CHECK USING A SEVERN PERMEABILITY INDICATOR GAGE. PERMEABILITY SHOULD BE NO GREATER THAN 1.02μ.--Part Number: SE141-142--Part Description: BEARING PLATE TYPE -A- LONG	65709/1.0 -Sub:19 Op#:30	Closed	5/18/2006	503-B.Houk

**Customer: ENERGY INDUSTRIES OF OHIO**

Contact: NANCY HORTON  
 E-Mail: NKHFlowen@aol.com

Telephone: 216-496-2314  
 Fax: 216-328-2001

**Part: SE141-114 / MODULAR COIL WINDING FORM TYPE**

Drawing ID: SE141-114      Revision: 6  
 Links: 1-Type:W: 65709/1.0 Sub: 1 Op: 30

Customer P.O.: S005242-F/Ln:1  
 Serial No./Qty: A1

Reported By: MIKE GRIFFITH  
 E-Mail: mGriffith@MajorTool.com

Telephone: 317-636-6433  
 Fax: 317-634-9420

Problem: Reference sheet 4, zone G7.

There is a tool gouge along the short leg of the T section on the Datum -D- side. The gouge is approximately 13.5" long, .900" wide and .200 deep. See attachments for clarification.

**Proposed Disposition:**

Propose to weld repair the tool gouge. Indicators would be applied on and around the T section to monitor any part movement caused by welding. The welding process would altered as needed to minimize movement. A local mag permeability and PT inspection would be performed. This gouge is located on the short leg in the area designated as "High Stress". During the RT of the High Stress area an additional shot would be taken of the repaired area. It is likely that this RT shot would prove inconclusive due to it's location.

Number of additional pages: \_\_\_\_\_

Customer Disposition:     Use As Is     Rework     Repair     Scrap     Replace

NCSX agrees with MTM's recommended disposition to weld repair, followed by local mag. perm. inspection, PT inspection, and RT during the RT of the high stress area. MTM is requested to provide documentation after the repair is completed.

**Tech. Rep.:** Phil Heitzenroeder  
Digitally signed by Phil Heitzenroeder  
 DN: CN = Phil Heitzenroeder, C = US, O = PPPL, OU = Mech. Eng. Division  
 Reason: I signed to certify portions of this document  
 Date: 2006.04.25 16:08:41 -0400

**Title:** \_\_\_\_\_ **Date:** \_\_\_\_\_

**RLM:** Hutch Neilson  
Digitally signed by Hutch Neilson  
 DN: CN = Hutch Neilson, C = US, O = PPPL  
 Date: 2006.04.25 17:08:22 -0500

**Title:** \_\_\_\_\_ **Date:** \_\_\_\_\_

**Major Tool Implemented By:** Mike Griffith  
Digitally signed by Mike Griffith  
 DN: CN = Mike Griffith, OU = Machine Tool and Methods, O = MTM  
 Reason: I signed to certify portions of this document  
 Date: 2006.04.25 14:37:36 -0400

**Title:** \_\_\_\_\_ **Date:** \_\_\_\_\_


**Root Cause 1: 816-PROGRAMMING ERROR**

Resource: CAD/CAM - MEDIUM MILLING      Equipment:

Description: There are 2 root causes here.

- 1) The tool gouged the wall because the toolpath was generated incorrectly. The check surface (back wall) was not selected and therefore the toolpath gouged the back wall.
- 2) The toolpath (n/c program 31501) was released as a good program because the verification did not show / flag an error of the toolpath violating the design model.

**Corr Actn: 1:** \_\_\_\_\_ **Action:** \_\_\_\_\_ **By:** \_\_\_\_\_  
 Description: \_\_\_\_\_









**Frank A. Malinowski**

---

**From:** Nelson, Brad E. [nelsonbe@ornl.gov]  
**Sent:** Friday, June 02, 2006 1:36 PM  
**To:** Frank A. Malinowski  
**Cc:** Phil Heitzenroeder  
**Subject:** FW: NC19709 completed Corrective Action  
**Attachments:** NC19709\_Signed\_Off\_A1Gouge.pdf; NC19709 PT and MAG Perm.pdf

Frank

I understand there was a positioning problem with the RT of the weld repair for this tool gouge. However, the location of this weld should not pose any structural issues and I agree with Phil's disposition.

Bra

Brad Nelson  
Oak Ridge National Laboratory  
P.O. Box 2008  
Oak Ridge, TN 37831-6169  
nelsonbe@ornl.gov  
voice: 865-574-1507  
fax: 865-576-7926

---

**From:** Phil Heitzenroeder [mailto:pheitzen@pppl.gov]  
**Sent:** Thursday, June 01, 2006 4:55 PM  
**To:** Nelson, Brad E.  
**Subject:** FW: NC19709 completed Corrective Action

Brad,  
This NC was already signed, but it did not include Mike's note below that the RT could not be performed was not included. Frank would like to include this to the NCR with our noted acceptance. If you're in agreement, please add your statement of agreement and return to Frank. Thanks  
Phil

Waiver of RT noted below for NC19709 Accepted by:

P. Heitzenroeder, Tech. Rep.

**From:** Griffith, Mike [mailto:mgriffith@majortool.com]  
**Sent:** Thursday, June 01, 2006 2:41 PM  
**To:** NKHFlowen@aol.com; royjratc-aol-com-offsite; pdjlord@sbcglobal.net  
**Cc:** Phil Heitzenroeder; Frank A. Malinowski  
**Subject:** NC19709 completed Corrective Action

Attached is the signed off corrective action for NC19709 and the PT/MAG Perm checks. During the RT process the technician was not able to position the film and source in order to get a clean shot of the repair area.

**Mike Griffith**  
Major Tool and Machine, Inc

**Customer: ENERGY INDUSTRIES OF OHIO**

Contact: NANCY HORTON  
E-Mail: NKHFlowen@aol.com

Telephone: 216-496-2314  
Fax: 216-328-2001

**Part: SE141-114 / MODULAR COIL WINDING FORM TYPE**  
Drawing ID: SE141-114                      Revision: 6

Customer P.O.: S005242-F/Ln:1  
Serial No./Qty: A1

Reported By: MIKE GRIFFITH  
E-Mail: mGriffith@MajorTool.com

Telephone: 317-636-6433  
Fax: 317-634-9420

Problem: Sheet 2, Zone B5; 96X .625 diameter counterbore, .188" +/- .005 deep.  
31 counterbores plus the 1 hole in poloidal break (total of 32) check from .210" to .310".  
34 counterbores are under the low limit of the tolerance.  
(see attachment for details)

**Proposed Disposition:**

Propose to machine all of the discrepant deep holes (32 places) to a depth of .310". The holes that are currently shallow will be machined to meet the drawing requirements.  
Major Tool will provide PPPL with 14 bushings to compensate for the machining error in the holes that require clamps.

Number of additional pages: 1 attachment

Customer Disposition:     Use As Is     Rework     Repair     Scrap     Replace

NCSX agrees with MTM's proposed disposition. The bushings shall be made per dwg. SE 142C-294. It is recommended that MTM consider increasing the quantity of bushings being made as contingency if needed in the future..

Approved by:

Phil  
Heitzenroeder

Digitally signed by Phil Heitzenroeder  
DN: cn=Phil Heitzenroeder, c=US,  
o=PPPL, ou=Mech. Eng. Division  
Reason: I agree to specified portions  
of this document  
Date: 2006.05.08 17:50:47 -04'00'

Brad  
Nelson

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2006.05.08 18:30:29 -04'00'

Tech. Rep.

RLM

Mike Griffith

Digitally signed by Mike Griffith  
DN: cn=Mike Griffith, ou=US, o=Major Tool and  
Machine, ou=CFT - White,  
email=mgriffith@majortool.com  
Reason: I agree to the terms defined by the  
placement of my signature on this document  
Date: 2006.06.01 11:29:57 -04'00'

Major Tool Implemented By: \_\_\_\_\_ Title: \_\_\_\_\_ Date: \_\_\_\_\_

# SE141-114 TYPE A1

## NC19783 Attachment

Holes are numbered from center of Lead Block Slot toward the Poloidal Break.

Hole #	Depth
1	0.242
2	0.242
3	0.242
4	0.244 C
5	0.247
6	0.26 C
7	0.27
8	0.275 C
9	0.29
10	0.295 C
11	0.3
12	0.31 C
13	0.31
14	0.31 C
15	0.31
16	0.298 C
17	0.295
18	0.295 C
19	0.286
20	ACCEPT
21	ACCEPT
22	ACCEPT
23	ACCEPT
24	ACCEPT
25	ACCEPT
26	ACCEPT
27	ACCEPT
28	ACCEPT
29	ACCEPT
30	ACCEPT
31	ACCEPT
32	ACCEPT
33	ACCEPT

Hole #	Depth
34	ACCEPT
35	S
36	S
37	N/M
38	N/M
39	N/M
40	N/M
41	N/M
42	N/M
43	N/M
44	S
45	S
46	S
47	S
48	S
49	S
50	S
51	S
52	S
53	S
54	S
55	S
56	S
57	S
58	ACCEPT
59	0.215 C
60	ACCEPT
61	ACCEPT
62	ACCEPT
63	0.21 C
64	0.225
65	S
66	S

Hole #	Depth
67	S
68	S
69	N/M
70	N/M
71	N/M
72	N/M
73	N/M
74	S
75	S
76	S
77	S
78	S
79	S
80	S
81	S
82	S
83	S
84	S
85	S
86	S
87	S
88	0.26 C
89	0.262 C
90	0.258 C
91	0.253
92	0.25 C
93	0.25
94	0.246 C
95	0.245
96	0.245
Break	0.282

S = Shallow

N/M = Not Machined

ACCEPT = Within Tolerance

C = designates clamp hole which will require special bushing per DWG SE142C-294 Rev. 0

**Customer: ENERGY INDUSTRIES OF OHIO**

Contact: NANCY HORTON  
E-Mail: NKHFlowen@aol.com

Telephone: 216-496-2314  
Fax: 216-328-2001

**Part: SE141-114 / MODULAR COIL WINDING FORM TYPE**  
Drawing ID: SE141-114                      Revision: 6  
Links: I-Type:W: 65709/1.0 Sub: 1 Op: 100

Customer P.O.: S005242-F/Ln:1  
Serial No./Qty: A1

Reported By: MIKE GRIFFITH  
E-Mail: mGriffith@MajorTool.com

Telephone: 317-636-6433  
Fax: 317-634-9420

Problem: PART IS REJECTED PER ASTM A903/A903M LEVEL 1.  
SEE ATTACHMENT FOR SIZES AND LOCATIONS.

Rev. 1  
5-31-06 Attachment revised to include additional photo of item 15.

**Proposed Disposition:**

Propose to Use As Is.

Number of additional pages: 12 page attachment

Customer Disposition:     Use As Is     Rework     Repair     Scrap     Replace

The attached group of indications were reviewed during a conference call between F. Malinowski, R. Sheppard, M. Griffith, (who were all at MTM) and D. Williamson and P. Heitzenroeder on 5/24/06. After consideration of each, it was determined that all are accepted as is based on an assessment of the stress in these regions (which were acceptably low ).

Accepted by:

**Phil  
Heitzenroeder**

Digitally signed by Phil Heitzenroeder  
DN: cn=Phil Heitzenroeder, c=US,  
o=PPPL, ou=Mech. Eng. Division  
Reason: I am approving this  
document  
Date: 2006.06.01 17:12:50 -04'00'

**Brad  
Nelson**

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2006.06.02 13:28:27  
-04'00'

Tech. Rep.

RLM

**Mike  
Griffith**

Digitally signed by Mike Griffith  
DN: cn=Mike Griffith, c=US, o=Major Tool  
and Machine, ou=CFE - Whisp,  
email=mgriffith@majortool.com  
Reason: I agree to the terms defined by the  
placement of my signature on the  
document.  
Date: 2006.06.06 07:06:06 -04'00'

Major Tool Implemented By: \_\_\_\_\_


Title: \_\_\_\_\_

Date: \_\_\_\_\_

# PT Inspection Results of A1 – NC19891

Rev. 1 – revised to include addition photo of item 15.


1. Cluster of linear indications – longest is 2". Reference dwg. Sheet 4, zone G6. The indications are on the edge of the large cutout. These indications were previously reported (see the picture to the left). The photo on the right is of the final PT inspection.



- 1a. Cluster of linear indications. Longest is .600". These indications are adjacent to the area shown in #1 but are on the face of the foot. See dwg. Sheet 3, zone F4.



- 1b. Rounded and linear indications. Longest is .400". These indications are also adjacent to #1 but are on the Datum D flange face. The picture on the right is of the indication when previously noted prior to final machining.



Mike Griffith

Page 1 of 12


5/31/2006




*Major*  
Tool & Machine, Inc.

## PT Inspection Results of A1 – NC19891

2. Linear indication, 3.6" in length. Indication is beneath the VPI groove in the radius of the inner casting wall. (D flange side close to hole 30).




3. Linear and rounded cluster, longest is 2". Located on D flange side close to hole 30. Along both the long and short legs.





# PT Inspection Results of A1 – NC19891

4. Linear cluster, longest is .400". Located on D side close to hole 34. Beneath VPI.



Pictures of Indications 1 – 4.




Mike Griffith

Page 3 of 12


5/31/2006

# PT Inspection Results of A1 – NC19891

5. Rounded and linear cluster, longest is .400". Located on D side close to hole 77.



6. Rounded and linear cluster, longest is .750". Located on E side close to hole 28.





## PT Inspection Results of A1 – NC19891

7. Rounded and linear cluster, longest is .500". Located on E flange side close to hole 43.




8. Rounded and linear cluster, longest is .300". Located on E flange side close to hole 76.




# PT Inspection Results of A1 – NC19891

9. Single linear, .350" in length. Located on E side close to hole 80.




10. Linear cluster, longest is 1". Located on E side close to hole 80.




# PT Inspection Results of A1 – NC19891

## Pictures of Indications 8-10.




11. Linear cluster, longest is 1.9". See sheet 3, zone C4. On face of foot, located closest to datum D flange.



# PT Inspection Results of A1 – NC19891


12. Linear and rounded cluster, longest is .300". See sheet 5, zone D5.



13. Linear cluster in wall of counterbore relief. Longest is .500". Located on sheet 5, zone C6, 44.87" from Datum A.





14. .700" long linear in counterbore relief. Located on sheet 5, zone G6, 40.28" from Datum A.




## PT Inspection Results of A1 – NC19891

15. Indication with a total length of approx. 1.700". Indication starts at edge of relief, travels down the side approx. .700", along the face approx. .5" and down the wall of the hole approx. .500". Located on sheet 5, zone G6, 43.40" from Datum A.




## PT Inspection Results of A1 – NC19891

16. Linear cluster on 4.0" diameter boss, longest is .600". Located on Sheet 3, zone F4.



17. Rounded cluster, largest is .130". Located on sheet 4, zone D5, 32.35 from datum A.




## PT Inspection Results of A1 – NC19891

18. .200" rounded indication. Located on sheet 4, zone C5, 35.37 from datum A.




**Pictures of Indications 17-18.**



# PT Inspection Results of A1 – NC19891

19. .750" long linear located on sheet 3, zone C6.





**Customer: ENERGY INDUSTRIES OF OHIO**

Contact: NANCY HORTON  
E-Mail: NKHFlowen@aol.com

Telephone: 216-496-2314  
Fax: 216-328-2001

**Part: SE141-114 / MODULAR COIL WINDING FORM TYPE**

Drawing ID: MCWF TYPE-A XRAY MA Revision:

Customer P.O.: S005242-F/Ln:1  
Serial No./Qty: A1

Reported By: MIKE GRIFFITH  
E-Mail: mGriffith@MajorTool.com

Telephone: 317-636-6433  
Fax: 317-634-9420

Problem: Radiograph View Number 2-3 reveals three separate indications:

- 1 linear @ .375",
- 1 linear @ .250",
- 4 rounded from .090" to 120"

**Proposed Disposition:**

RT REJECTS ARE THE SAME REJECTS AS REPORTED ON THE PT REPORT, REJECTION #7.  
PROPOSE TO USE AS IS.

Number of additional pages: RT attachment

Customer Disposition:  Use As Is     Rework     Repair     Scrap     Replace

Please refer to NC19891, since as noted in the Proposed Disposition above, these rejections are the same as reported in that NCR based on the die penetrant inspections. As noted in the disposition of that NCR, the defects were reviewed and accepted as is.

Accepted By:

Phil  
Heitzenroeder

Digitally signed by Phil Heitzenroeder  
DN: cn=Phil Heitzenroeder, c=US,  
o=PPPL, ou=Mech. Eng. Division  
Reason: I am approving this  
document  
Date: 2006.05.31 16:52:14 -04'00'

Brad  
Nelson

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2006.06.01 15:29:20  
-04'00'

Tech. Rep.

RLM

Mike Griffith

Digitally signed by Mike Griffith  
DN: cn=Mike Griffith, c=US, o=Major Tool and  
Machine, ou=CFI, email=  
mike-griffith@majortool.com  
Reason: I agree to the terms defined by the  
placement of my signature on this document  
Date: 2006.06.02 13:04:46 -04'00'

Major Tool Implemented By: \_\_\_\_\_

Title: \_\_\_\_\_

Date: \_\_\_\_\_

SE141-114 TYPE A1  
NC19916 RT ATTACHMENT

Photo of RT film 2-3





Photo of PT rejection #7 (reference NC19891 attachment)



**Customer: ENERGY INDUSTRIES OF OHIO**

Contact: NANCY HORTON  
E-Mail: NKHFlowen@aol.com

Telephone: 216-496-2314  
Fax: 216-328-2001

**Part: SE141-114 / MODULAR COIL WINDING FORM TYPE**

Drawing ID: SE141-114

Revision: 6

Customer P.O.: S005242-F/Ln:1  
Serial No./Qty: A1

Reported By: MIKE GRIFFITH  
E-Mail: mGriffith@MajorTool.com

Telephone: 317-636-6433  
Fax: 317-634-9420

Problem: SEVERAL MISCELLANEOUS ITEMS WERE FOUND DURING THE FINAL VISUAL INSPECTION OF THE PART. SEE ATTACHMENT FOR DETAILS.

**Proposed Disposition:**

PROPOSE TO USE AS IS.

Number of additional pages: 10 page attachment

Customer Disposition:     Use As Is     Rework     Repair     Scrap     Replace

The list was reviewed during a conference call attended by J. Chrzanowski, F. Malinowski, D. Williamson, L. Sutton, and P. Heitzenroeder. M. Griffith was added to the call to discuss the "short" G-10 insulators which are mostly due to the stocking on the casting. He agreed that all remaining insulators will be extended as required. The list of miscellaneous defects was dispositioned as indicated below:

#1-Accept as is; PPPL will install GI/Ep in the gaps after VPI is completed. MTM agreed to make remaining insulators extend to the edge of the parts.

#2-Accept as is.

#3-Accept as is; PPPL will install GI/Ep in the gaps after VPI is completed. MTM agreed to make remaining insulators extend to the edge of the parts.

#4-

#5-Accept as is. PPPL will verify that dye will not degrade G-10.

#6-Accept as is.

#7-Accept as is.

#8-Accept as is.

#9-Accept as is.

#10-Accept as is.

#11-Accept as is.

#12-Accept as is.

#13-Accept as is.

#14-Accept as is.

Approved by:

Phil  
Heitzenroeder

Digitally signed by Phil Heitzenroeder  
DN: cn=Phil Heitzenroeder, c=US,  
o=PPPL, ou=Mech. Eng. Division  
Reason: i am approving this document  
Date: 2006.05.31 16:20:10 -04'00'

Brad  
Nelson

Digitally signed by Brad Nelson  
DN: cn=Brad Nelson, c=US,  
o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2006.06.01 07:50:21  
-04'00'

Tech. Rep.

RLM

Mike Griffith

Digitally signed by Mike Griffith  
DN: cn=Mike Griffith, o=Major Tool and  
Machine, ou=CT - White, email=mgriff@major-tool.com  
Reason: I agree to the terms defined by the  
placement of my signature on this document  
Date: 2006.06.02 13:37:06 -04'00'


Major Tool Implemented By: \_\_\_\_\_

Title: \_\_\_\_\_


Date: \_\_\_\_\_

SE141-114 A1  
NC19933 attachment

1. G11 shim between break flanges and bearing plates.




G11 shim has a full radius on both ends. The drawing shown below shows only the radius toward the inside cast wall.





SE141-114 A1  
NC19933 attachment

2. Photo below shows areas where counterbore clearances were cut heavy into the casting wall. These areas will not accept the 3" diameter clearance gage. These areas and others were identified and reported on RFD 14-020.



3. Poloidal Break, Datum D side. Casting radius between T section and inner wall extends beyond the G11 shim approximately .300" on each side.



Mike Griffith

Page 2 of 10

5/31/2006




*Major*  
Tool & Machine, Inc.

SE141-114 A1  
NC19933 attachment

4. Poloidal Break, Datum E side. Casting radius between T section and inner wall extends beyond the G11 shim .050" on each side.




5. One of the G11 shims from the Datum D view is contaminated with the Liquid Penetrant used during the PT process.




SE141-114 A1  
NC19933 attachment

6. Tool gouge on datum E flange. Gouge measures .038" deep by 3.25" long by .50" at its widest point. Radial gouge from 6" face. The gouge is located on the datum E flange in section C5 on sheet 5 of the drawing.





7. Various tool cutter marks on the D side short leg between holes 34 and 42. Cutter marks are no deeper than .010".



Cont. on next page.



SE141-114 A1  
NC19933 attachment



Mike Griffith

Page 5 of 10

5/31/2006



*Major*  
Tool & Machine, Inc.




SE141-114 A1  
NC19933 attachment

8. Various cutter marks on the E side of the T section. Cutter marks are no more than .010" deep.

Short leg of T near hole 79.



In radius between long and short legs near hole 89.



In radius between long and short legs near hole 87.



Mike Griffith

Page 6 of 10




5/31/2006



*Major*  
Tool & Machine, Inc.

SE141-114 A1  
NC19933 attachment

The following photos are of the short leg of T between holes 15 and 19.



Mike Griffith

Page 7 of 10


5/31/2006



*Major*  
Tool & Machine, Inc.

SE141-114 A1  
NC19933 attachment

9. Approx. 20% of counterbore did not clean up to 100%. Hole is located on the datum E flange next to the poloidal break. (area shaded in photo below).




10. There is also an oversized area in this same 1.885 hole. The hole checks  $\text{Ø}1.884''$  from the datum E face to a depth of .950". The oversized area extends approximately 1/3 around the diameter (the oversized area is offset to the centerline of the bore). At its largest point, the bore checks  $\text{Ø}1.948''$ .





SE141-114 A1  
NC19933 attachment

11. The pad shown below has excess casting stock which was machined flush with the pad face. See detail J in section F2 on sheet 7.



12. Various dings on the datum flange edges. Dings are being caused by swivel hoist rings when lifting the parts. Any raised metal around the areas have been polished flush to the surrounding surfaces.




Mike Griffith

Page 9 of 10


5/31/2006

SE141-114 A1  
NC19933 attachment

13. There are two impressions on the datum E flange face that were caused by handling damage. Any raised metal around the areas have been polished flush to the surrounding surfaces.



14. The area shown below on the datum E flange exceeds the  $v^{125}$  surface finish requirement. Area checks approximately  $v^{250}$ . This area is located on sheet 5, zone D5.



**Customer: ENERGY INDUSTRIES OF OHIO**

Contact: NANCY HORTON  
E-Mail: NKHFlowen@aol.com

Telephone: 216-496-2314  
Fax: 216-328-2001

**Part: SE141-114 / MODULAR COIL WINDING FORM TYPE**

Drawing ID: SE141-114

Revision: 6

Customer P.O.: S005242-F/Ln:1  
Serial No./Qty: A1

Reported By: MIKE GRIFFITH

E-Mail: mGriffith@MajorTool.com

Telephone: 317-636-6433  
Fax: 317-634-9420

Problem: Workorder: 65709/1.0 Sub:1 Op:132

Inspection Test #: 70 rejected: {h|,02|A}: .046  
Inspection Test #: 80 rejected: 48.50 ± .03: : 48.454  
Inspection Test #: 130 rejected: OUTER AS CAST SURFACES: {g|,5|A|B|C}: -0.165 TO 0.288  
Inspection Test #: 140 rejected: 2 X .40: : .350 TO .420  
Inspection Test #: 150 rejected: 4 X .03 X 45: : .010 TO .040  
Inspection Test #: 170 rejected: P TO M: {g|,2|R|T|S}: POINTS NOT COLLECTED  
Inspection Test #: 180 rejected: DATUM D SIDE  
VERIFY SHELL INTERSECT CLEARANCE USING GAGE MTMFX-3473: : AREAS BY T HOLES 5-10,  
15 - 42, 84 - 94 WILL NOT ACCEPT GAGE  
Inspection Test #: 190 rejected: M TO M1: {g|,02|R|T|S}: -.0287 TO .268  
Inspection Test #: 210 rejected: Q TO N: {g|,2|R|T|S}: POINTS NOT COLLECTED  
Inspection Test #: 230 rejected: N TO N1: {g|,02|R|T|S}: -.0297 TO .0321  
Inspection Test #: 240 rejected: 2 X .06/.09 X 45: : .030 TO .060  
Inspection Test #: 270 rejected: .375-16 HOLES: {#|,06|R|T|S}: .002 TO .066  
Inspection Test #: 280 rejected: DATUM E FLANGE: {f|,01}: .029  
Inspection Test #: 285 rejected: surface 250  
Inspection Test #: 290 rejected: DATUM D FLANGE: {f|,01}: .028  
Inspection Test #: 410 rejected: Ø1.375-6: {#|d,06|M|A|D}: .062  
Inspection Test #: 480 rejected: Ø1.885: {#|d,06|N|A|E}: .007 TO .076  
Inspection Test #: 640 rejected: 2X .88 - 1.13: : 1.13 TO 1.14  
Inspection Test #: 780 rejected: INNER AS CAST SURFACES: {g|,5|A|B|C}: -.321 TO .149  
Inspection Test #: 790 rejected: WING SURFACES: {g|-,12;;;|,25|A|B|C}: .009 TO -.150

Workorder: 65709/1.0 Sub:1 Op:130

Inspection Test #: 10 rejected: CHECK CLEARANCE OF ITEM 5 TO  
ITEM 6.  
: d.001 - d.002: .004 TO .005

**Proposed Disposition:**

PROPOSE TO USE AS IS.

Number of additional pages: 9 Page IDC Attachment

**Customer Disposition:**     Use As Is     Rework     Repair     Scrap     Replace

The list was reviewed during a conference call held on 6/1/06 at 4 pm. Tom Brown and Dave Williamson spent the morning reviewing the dimensional documentation and discrepancies. D. Williamson used the attached slide set while discussing some of the points, and went item by item through the remainder of the list. It was agreed that all will be accepted "as is". Attendees included M. Griffith, T. Brown, D. Williamson, L. Sutton, F. Malinowski, N. Horton, P. Heitzenroeder, and (part time) S. Raftopoulos and A. Brooks.

Phil  
Heitzenroeder

Digitally signed by Phil Heitzenroeder  
DN: cn=Phil Heitzenroeder, c=US,  
o=PPPL, ou=Mech. Eng. Division  
Reason: I am approving this document  
Date: 2006.06.01 17:38:52 -04'00'

Brad  
Nelson

Digitally signed by Brad  
Nelson  
DN: cn=Brad Nelson,  
c=US, o=ORNL, ou=FED,  
email=nelsonbe@ornl.gov  
Date: 2006.06.02 11:27:19  
-04'00'

Mike  
Griffith

Digitally signed by Mike Griffith  
DN: cn=Mike Griffith, c=US, o=Major Tool  
and Machine, ou=CFT - White,  
email=mgriffith@majortool.com  
Reason: I agree to the terms defined by the  
placement of my signature on this document  
Date: 2006.06.05 07:04:44 -04'00'

Major Tool Implemented By: \_\_\_\_\_

Title: \_\_\_\_\_

Date: \_\_\_\_\_

MAJOR TOOL & MACHINE INC  
1458 E 19TH ST  
INDIANAPOLIS IN 46218

**YOUR PURCHASE ORDER NUMBER**  
P05-01332

MCMASTER-CARR  
600 COUNTY LINE ROAD  
ELMHURST IL 60126-2001  
IF THERE ARE ANY QUESTIONS ABOUT THIS SHIPMENT CONTACT OUR SALES DEPARTMENT (630)633-0300

PAGE 1 (MORE)  
MCM NUMBER 6241663-02

Warehouse Location	McMaster Carr Part Number	FRI Quantity	Item Description	Your Line	Your Order	This Shipment
<b>P A C K I N G L I S T  E X T R A</b>	74765 A86	1 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1	5	1 EA	1
	74765 A86	1 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1	6	1 EA	1
	74765 A86	1 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1	7	1 EA	1
	74765 A86	1 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1	8	1 EA	1
	74765 A86	0 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1 Balance of 1 EA expected to ship by 3/9/2005	9	1 EA	0
	74765 A86	0 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1 Balance of 1 EA expected to ship by 3/9/2005	10	1 EA	0
	74765 A86	0 EA	LOCTITE PRISM SUPER GLUE TOUGHENED,NUMBER 411,1-POUND BOTTLE,CLEAR HZ-N 1 Balance of 1 EA expected to ship by 3/9/2005	11	1 EA	0

REFER TO: 6241663-02  
MAJOR TOOL & MACHINE INC

TAG  
CCP



3/10/05

3/10/05

94115

Lines 5-8


PACKER	Number of CARTONS	FILLER

LNS: 7

CYCLE

**CERTIFICATION OF COMPLIANCE**

This is to certify that, according to our records, the above item(s) furnished on your purchase order was supplied in accordance with the description and as illustrated in our catalog.

Sincerely,  
  
Brian Hedstrom  
Quality Manager

MCM NO. 6241663-02 04

**PURCHASE ORDER**  
P05-01332

FROM:  
MCMASTER-CARR  
600 COUNTY LINE ROAD  
ELMHURST IL 60126-2001 USA

SHIP TO:

MAJOR TOOL & MACHINE INC  
1458 E 19TH ST  
INDIANAPOLIS IN

46218

CCP

X







**Spaulding**  
COMPOSITES

55 Nadeau Drive  
Rochester, NH 03867  
Ph: (603) 332-4555 Fax: (603) 332-5357  
www.spauldingcom.com

Shipping List 072435  
Customer No 101193  
Sales Order Shipper

Sold to : STANDARD GRINDING & MFG CO  
3721 W. CHASE AVENUE  
SKOKIE, IL 60076  
United States

Ship to : STANDARD GRINDING & MFG CO  
3721 W. CHASE AVENUE  
SKOKIE, IL 60076  
United States

Ship Date	Customer PO	Sales Order	# of Boxes	Weight	Ship VIA	B/L of Lading	FOB
05/17/2005	60624	065171-06	1	0	YELLOW	072435	DE
Item	Part / Description / Details				Order Quantity	Ship Qty	
000001	39G1CNT73125NMWLF U/M SHY SO Item 4				1.00000		
	G-11-CR 48" untrimmed X 36" untrimmed Thickness: 3.125" +/- .110"  PLEASE NOTE THAT THERE IS NO NEMA STANDARD FOR G-11 CR SHEET  SPAULDING C OF C TO G-11 CR SHEET NO TESTING REQUIRED AT TIME OF ORDER  <i>Sheet lead 3.5000</i>					1.00000	
					 L11CS 1, 2 B-1 (MTM 09) 5/31/05		

**CERTIFICATE of CONFORMANCE**

WE HEREBY CERTIFY THAT THE MATERIAL SUPPLIED ON THIS ORDER WAS MADE IN ACCORDANCE WITH THE STANDARDS AND PROCESSES ESTABLISHED BY SPAULDING COMPOSITES COMPANY FOR THE REQUIREMENTS OF MATERIAL DESCRIBED ABOVE.

LOT # \_\_\_\_\_ DOM \_\_\_\_\_  
 Authorized By: Mark A. Candillo Date: 05/17/2005

Customer Copy

Page # 1

Form: SCSHIP Rev: 8/99

000/200

ATLAS FIBRE CO.

8647 674 1720

05/28/05 13:00



**Spaulding**  
COMPOSITES

55 Nadeau Drive  
Rochester, NH 03867  
Ph: (603) 332-0552 Fax: (603) 332-5357  
www.spauldingcom.com


Shipping List 072434

Customer No 101193  
Sales Order Shipper

Sold to : STANDARD GRINDING & MFG CO  
3721 W. CHASE AVENUE  
SKOKIE, IL 60076  
United States

Ship to : STANDARD GRINDING & MFG CO  
3721 W. CHASE AVENUE  
SKOKIE, IL 60076  
United States

Ship Date	Customer PO	Sales Order	# of Boxes	Weight	Ship VIA	Bill of Lading	FOB
05/17/2005	60624	063169-00	1	716	YELLOW	072434	DE
Item	Part / Description / Details				Order Quantity	Ship Qty	
000001	39G1CNT71850NMWLF U/M SHT SO Item 5				1.00000		
	G-11-CR 48" *UNTRIMMED X 36" *UNTRIMMED THK: 1.850" +/- .070"  PLEASE NOTE THAT THERE IS NO NEMA STANDARD FOR G-11 CR SHEET  SPAULDING C OF C TO G-11 CR SHEET NO TESTING REQUIRED AT TIME OF ORDER					1.00000	



5/31/05  
MTM 09

**CERTIFICATE of CONFORMANCE**

WE HEREBY CERTIFY THAT THE MATERIAL SUPPLIED ON THIS ORDER WAS MADE IN ACCORDANCE WITH THE STANDARDS AND PROCESSES ESTABLISHED BY SPAULDING COMPOSITES COMPANY FOR THE REQUIREMENTS OF MATERIAL DESCRIBED ABOVE.

LOT #

DOM.

Authorized By:

*Mark L. Cardillo*

Date: 05/17/2005

Customer Copy

Page # 1

Form: SCSHIP Rev: 8/99

000/000

ATLAS FIBRE CO.

0047 674 1723

05/26/05 13:00

**INSPECTION DATA CHECKLIST**

Quality Assurance Documentation for Part ID: SE141-101 - Item: 11

Workorder: 65709/1-0 Sub:1 Op:140

Part: SE141-101 - MODULAR COIL WINDING FORM TYPE-A - PRODUCTION MODULAR COIL WINDING FORM TYPE-A

Drawing ID: SE141-101 Rev: 3			INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY			
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT	
*		<u>T E S T 1</u> RESISTANCE TO BE >500 kohms CHECK RESISTANCE BETWEEN THE MID-PLANE POLOIDAL BREAK SHIM AND THE WINDING FORM.	MULTIMETER	QA		J-1358	218 TO 225 MEGA OHMS	840-G.M			A
(10)								06-01-06			
*		<u>T E S T 2</u> RESISTANCE TO BE >500 kohms CHECK RESISTANCE BETWEEN THE JUMPERED BOLTS AND JUMPERED MID-PLANE CASTING AND WINDING FORM.	MULTIMETER	QA		J-1358	280 TO 330 MEGA OHMS	840-G.M			A
(20)								06-01-06			

METRODE PRODUCTS LIMITED  
HANWORTH LANE, CHERTSEY

SURREY, UK, KT16 9LL

Tel: +44 (0) 1832 586721

Fax: +44 (0) 1832 585188

Email: info@metrode.com

Website: www.metrode.com

**CERTIFIED MATERIAL  
TEST REPORT**



THIS PRODUCT HAS BEEN MANUFACTURED  
AND SUPPLIED THROUGH A SYSTEM  
APPROVED TO ISO 9001 & 2 OR EQUIVALENT



**TEST CERTIFICATE NUMBER**

183695

INVOICE TO
EUROWELD LTD
255 ROLLING HILLS ROAD
MOORESVILLE
NC 28117
USA

DESPATCHED TO
EUROWELD LTD
255 ROLLING HILLS ROAD
MOORESVILLE
NC 28117
USA

CUSTOMER ORDER NUMBER	N.05-34
DELIVERY NOTE DOCUMENT NUMBER	DN0105859
QUANTITY (KG)	15.0000
OUR ORDER REFERENCE	SO1787730 / 1
DATE	02/03/05

METRODE WELDING CONSUMABLE	ER316MNNF TIG 2.4mm
FORM	TIG WIRE
BATCH NUMBER	W020132
SPECIFICATION	BS EN 12072:2000 W 20 18 3 Mn L

Chemical Analysis (Weight %)										Type: BS EN 10204: 3.1.B / ASME SFA-5.01: Sch. H	
C	Mn	Si	S	P	Cr	Ni	Mo	N	Cu		
0.016	7.43	0.42	0.008	0.014	19.9	15.4	2.62	0.14	0.20		

--	--	--	--	--	--	--	--	--	--	--	--

Mechanical Tests						Type: BS EN 10204: 2.2 / ASME SFA-5.01: Sch. G		
Tensile Tests						Impact Energies		
Condition	Test Temperature	R <sub>p0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A4 (%)	Z (%)	Temperature (°C)	Impact Energy (J)	Lateral Expansion (mm)
AS-WELDED	ROOM	>400	>600	40	-	-196	70	-

Metrode Products Limited certifies that the above material conforms to the included specifications.

This document is produced electronically and is valid without signature.

IMPORTANT: Any liability arising from other reliance on this certificate, or use of our products, is strictly limited and governed by our conditions of business.

Barrie Kyiel - Q.A. Manager

ASME SFA-5.01; Lot classification S4

3/3/05  
93911  
Line 1 B.1

Notes:  
% Mn includes incidental Co unless otherwise specified.  
% Ni (Co) includes incidental Fe unless otherwise specified.  
Porosities given as FN (surface number) and measured on 80-mesh pad using instrument calibrated against NBS-related secondary standards (see AWS A5.1-97) unless otherwise specified.

META  
C9  
3/7/05

METRODE PRODUCTS LTD  
 HANWORTH LANE  
 CHERTSEY SURREY  
 ENGLAND KT16 9LL  
 Tel: +44 (0)1932 566721  
 Fax: +44 (0)1932 565168  
 Email: mfo@metrode.com  
 Internet: http://www.metrode.com



**TEST CERTIFICATE**

THIS PRODUCT HAS BEEN MANUFACTURED  
 AND SUPPLIED THROUGH A SYSTEM APPROVED  
 TO ISO 9001 & 2 OR EQUIVALENT



TEST CERTIFICATE NUMBER 194277

INVOICE TO

EUROWELD LTD  
 255 ROLLING HILLS ROAD  
 MOORESVILLE  
 NC 28117  
 USA

DESPATCHED TO

EUROWELD LTD  
 255 ROLLING HILLS ROAD  
 MOORESVILLE  
 NC 28117  
 USA

BATCH No.	W020132
OUR ORDER REF.	S01788013 / 1
DATE	09/03/05
PRODUCT	ER316MNNF TIG 2.4MM
FORM	TIG WIRE
SPECIFICATION	BS EN 12072:2000 W 20 16 3 Mn L

IMPORTANT: Any liability arising from either reliance on this certificate, or use of our products, is strictly limited and governed by our conditions of business.

CUSTOMER ORDER No.

N. 05-39

DELIVERY NOTE DOCUMENT No.

DN0106163

QUANTITY (Kg)

17.5000

CHEMICAL ANALYSIS (WEIGHT %)				TYPE CERTIFIED MATERIAL TEST REPORT: BS EN 10204: 3.1.B							
C	Mn	Si	S	P	Cr	Ni	Mo	N	Cu		
0.015	7.43	0.42	0.006	0.014	19.9	15.4	2.62	0.14	0.20		

TYPICAL ALL-WELD METAL MECH. PROPERTIES, AS WELDED:-  
 TS: >600 N/mm<sup>2</sup>; 0.2%PS: >400 N/mm<sup>2</sup>; EL. ON 4D: 40 %;  
 CVN @ -196 DEG.C: 70 J.

3/23/05  
 44534  
 Live!  
 B-2

3/23/05  
 MTM  
 09

Metrode Products Ltd. certifies that the above material conforms to the indicated specifications


B. KYIET  
 QA MANAGER

*B. Kyiet*

NOTES \*He includes incidental Co unless otherwise specified  
 \*Ni (Co) includes incidental Ti unless otherwise specified  
 Ferrite is given as FN (Ferrite Number) and measured on all-weld pad using instrument calibrated against NBS related secondary standards (See AWS A4 2-87) unless otherwise specified

All Test certificates issued by METRODE will contain this embossed seal  
 Any recipient of a copy of METRODE Test Certificate without the seal should ensure from the supplier that it is a true and accurate reproduction of the original

mc106579.tif (1652x2103x2.tif)



# Westmoreland Mechanical Testing & Research, Inc.

P.O. Box 388

Westmoreland Drive

Youngstown, Pa. 15696-0388 U.S.A.

Telephone: 724-537-3131 Fax: 724-537-3151

Website: [www.wmtr.com](http://www.wmtr.com)

WMT&R is a technical leader in the material testing industry.



621-01 & 621-02

April 22, 2005

## CERTIFICATION

Major Tool & Machine Inc.  
1458 East 19th Street  
Indianapolis, IN 46218

Corrected Date  
May 4, 2005

Page IM1 of 1

WMT&R Report No. 5-25008  
P.O. No. P05-01764  
PQR No. 434  
Welder Jason Bever #465

Attention: Josh Mayne

Subject: All processes, performed upon the material as received, were conducted at WMT&R, Inc. in accordance with the WMT&R Quality Assurance Manual, Rev. 9, dated 4/1/2000.  
The following tests were performed on this order: IMPACT and TENSILE

IMPACT RESULTS: ASME Section IX and AWS B2.1, ASTM E23-02

No Requirements

MATERIAL: Metaltek CF8MNMN MOD

SAMPLE TYPE: Charpy V-Notch

DISPOSITION: Report

Specimen ID	TestLog Number	Sample Size	Temp. °F/°C	Energy ft-lbs	Energy joules	Mis Lat Exp	AIUR
Weld-1	B65835	Standard	68/20	173	234.6	84	Report
Weld-2	B65836	Standard	68/20	160	216.9	68	Report
Weld-3	B65837	Standard	68/20	157	212.9	81	Report


AIUR: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

KNOWINGLY OR WILLFULLY FALSIFYING OR CONCEALING A MATERIAL FACT ON THIS FORM OR MAKING FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR REPRESENTATIONS HEREIN COULD CONSTITUTE A FELONY PUNISHABLE UNDER FEDERAL STATUTES. THIS CERTIFICATE OR REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT THE WRITTEN APPROVAL OF WMT&R, INC.

Richard G. Parks  
Project Manager/Industrial Technology Engineer

5/4/05  
May 4, 2005

Testing Specialists for Aerospace, Automotive, and Material Testing Fields  
Locations in Youngstown, PA U.S. 207 Tel. (724) 537-3131 and  
Banbury U.K. ~ Tel. +44 (0) 1295 261211



*Westmoreland Mechanical Testing & Research, Inc.*  
 P.O. Box 388  
 Westmoreland Drive  
 Youngstown, Pa. 15696-0388 U.S.A.  
 Telephone: 724-537-3131 Fax: 724-537-3151  
 Website: [www.wmtr.com](http://www.wmtr.com)  
*WMT&R is a technical leader in the material testing industry.*



621-01 & 621-02

April 20, 2005

**CERTIFICATION**

Major Tool & Machine Inc.  
 1458 East 19th Street  
 Indianapolis, IN 46218

Attention: Josh Mayne

Subject: All processes, performed upon the material as received, were conducted at WMT&R, Inc. in accordance with the WMT&R Quality Assurance Manual, Rev. 9, dated 4/1/2000.  
 The following tests were performed on this order: IMPACT and TENSILE

Section 1 of 2

WMT&R Report No. 5-25008  
 P.O. No. P05-01764  
 PQR No. 434  
 Welder Jason Bever #465

**TENSILE RESULTS: ASME Section IX and AWS B2.1, ASTM E21-03a**

**SOAK TIME: 5 Minutes**

**SPEED OF TESTING: 0.0050 in./in./min., 0.0500 in./min./in.**

**MATERIAL: Metrode ER316Mnnf**

**DISPOSITION: Report**

Specimen ID	TestLog Number	Temp. °F/°C	UTS KSI/MPA	0.2% YS KSI/MPA	Elong %	RA %	Modulus MSI/GPA	Ult. Load LBS/NEWTONS	0.2% YLD. LBS/NEWTONS
T1	B65833	-320/-196	191.8/1320	148.7/1030	27	39	28.7/198	2630/11699	2039/9071

A/U/R: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

**DISPOSITION: Report**

Specimen ID	TestLog Number	Orig. Width (in./mm)	Final Width (in./mm)	Orig. Thick (in./mm)	Final Thick (in./mm)	Orig. Dia. (in./mm)	4D Orig GL (in./mm)	4D Final GL (in./mm)	Orig. Area (Sq. In./Sq. mm)	Failure Location/Type	Machine Number	A/U/R
T1	B65833	0.1802/4.57708	0.1437/3.650	0.0761/1.933	0.0582/1.478	0.2511/6.378	0.70/17.78	0.89/22.61	0.04183816/26.992307	WELD/DUCTILE	M9	R


A/U/R: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

KNOWINGLY OR WILLFULLY FALSIFYING OR CONCEALING A MATERIAL FACT ON THIS FORM OR MAKING FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR REPRESENTATIONS HEREIN COULD CONSTITUTE A FELONY PUNISHABLE UNDER FEDERAL STATUTES. THIS CERTIFICATE OR REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT THE WRITTEN APPROVAL OF WMT&R, INC.

Roy E. Starr/Matt Wojton  
 \_\_\_\_\_ Technical Services Manager/ \_\_\_\_\_ Tensile Supervisor

April 20, 2005

*Testing Specialists for Aerospace, Automotive, and Material Testing Fields*  
 Locations in Youngstown, PA U. 208 Tel. (724) 537-3131 and  
 Banbury U.K. ~ Tel. +44 (0) 1295 261211



Westmoreland Mechanical Testing & Research, Inc.  
 P.O. Box 388  
 Westmoreland Drive  
 Youngstown, Pa. 15696-0388 U.S.A.  
 Telephone: 724-537-3131 Fax: 724-537-3151  
 Website: www.wmtr.com  
 WMT&R is a technical leader in the material testing industry.



621-01 & 621-02

Section 2 of 2

WMT&R Report No. 5-25008  
 P.O. No. P05-01764

April 20, 2005

**CERTIFICATION**

Major Tool & Machine Inc.

TENSILE RESULTS: ASME Section IX and AWS B2.1, ASTM E21-03a

SOAK TIME: 5 Minutes

SPEED OF TESTING: 0.0050 in./in./min., 0.0500 in./min./in.

MATERIAL: Metrode ER316Mnnf

DISPOSITION: Report

Specimen ID	TestLog Number	Temp. °F/°C	UTS KSI/MPA	0.2% YS KSI/MPA	Elong %	RA %	Modulus MSI/GPA	Ult. Load LBS/NEWTONS	0.2% YLD. LBS/NEWTONS
T2	B65834	-320/-196	204.7/1410	156.5/1080	29	34	29.9/206	5095/22664	3894/17323

A/U/R: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

DISPOSITION: Report

Specimen ID	TestLog Number	Orig. Dia. (in./mm)	Final Dia. (in./mm)	4D Orig GL (in./mm)	4D Final GL (in./mm)	Orig. Area (Sq. In./Sq. mm)	Failure Location/Type	Machine Number	A/U/R
T2	B65834	0.1780/4.521	0.1444/3.668	0.70/17.78	0.90/22.86	0.02488456/16.054520	WELD/DUCTILE	M9	R

A/U/R: A=ACCEPTABLE, U=UNACCEPTABLE, R=REPORT

KNOWINGLY OR WILLFULLY FALSIFYING OR CONCEALING A MATERIAL FACT ON THIS FORM OR MAKING FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR REPRESENTATIONS HEREIN COULD CONSTITUTE A FELONY PUNISHABLE UNDER FEDERAL STATUTES. THIS CERTIFICATE OR REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT THE WRITTEN APPROVAL OF WMT&R, INC.

  
 Roy E. Starr/Matt Wojton  
 Technical Services Manager / Tensile Supervisor

4-20-05  
April 20, 2005

Testing Specialists for Aerospace, Automotive, and Material Testing Fields  
 Locations in Youngstown, PA U. 209 Tel. (724) 537-3131 and  
 Banbury U.K. ~ Tel. +44 (0) 1295 261211







# WESTMORELAND MECHANICAL TESTING & RESEARCH, Inc

Stress vs. Strain

Phone: (724)537-3131

Customer: Major Tool & Machine Inc.  
WMT&R Report: 5-25008

P.O. No.: P05-01764  
PQR No.: 434  
Welder: Jason Bever #465





# Nondestructive Test

## Certification for Liquid Penetrant Examination

Quality Assurance Documentation for Part ID: SE141-114 - Item: 16

1458 E. 19th Street, Indianapolis, In 46218  
 TEL:(317)636-6433 FAX:(317)634-9420

**Date of Inspection:** 05/20/2006

**Type of Material:** CAST STAINLESS

**NDT#:** 16747

<b>Stage of Inspection:</b> <input type="checkbox"/> Incoming Inspection <input type="checkbox"/> In-Process Inspection <input type="checkbox"/> After Repair <input checked="" type="checkbox"/> Final Inspection	<b>Manufacturing Process:</b> <input type="checkbox"/> Weldment <input type="checkbox"/> Bar Stock <input type="checkbox"/> Forging	<input checked="" type="checkbox"/> Casting <input type="checkbox"/> Plate <input type="checkbox"/> Other	<b>Surface Condition:</b> <input checked="" type="checkbox"/> Machined <input type="checkbox"/> Rough <input type="checkbox"/> Other FINAL MACHINED	<b>Test Being Run to:</b> <input checked="" type="checkbox"/> Router Instructions <input checked="" type="checkbox"/> Drawing <input type="checkbox"/> Test Plan <input type="checkbox"/> Technique Card SEE NOTES	<b>Heat Treated:</b> <input type="checkbox"/> Yes <input checked="" type="checkbox"/> No
--	--	---	---	---	--

<b>Part Information:</b> MTM Job Number: 65709/1.0 -Sub:1 -Op:100 Resource ID: 810-LIQUID PENETRANT INSPE Part ID: SE141-114 Part Name: MODULAR COIL WINDING FOR Serial Number: Customer P.O.: S005242-F Customer Unit/Plant:	<b>Test Results:</b> Quantity Inspected: 1 Quantity Accepted: 0 Quantity Rejected: 1  Run Hours: 0.0	<b>Inspection Results:</b> Customer N/C #: <input type="checkbox"/> Accepted <input checked="" type="checkbox"/> Rejected <input type="checkbox"/> N/C-Report <input type="checkbox"/> Rework MTM N/C #: 19891
--	---	--

<b>Customer Inspection Plan:</b> SEE NOTES Test Step: Revision: Material Test Number:	<b>Inspection Criteria:</b> Customer Specification: ASTM A903/A903M MTM Spec Number: PS582 (REF NDT-W1-09) Acceptance Standard: ASTM A903 (SEE NOTES)
--	--

<b>Inspection Materials Used:</b> Manufacturer: SHERWIN Type of Penetrant: DP-51 Batch Number: 41-E47 Developer: D-100 Batch Number: 65-C6	<b>Penetrant Examination Processes:</b> Type: II (Visible) / Dwell Time: 20 Minutes Method: A (Water Wash) Method of Drying: Forced Air Fan Form: e (nonaqueous for Type II visible dye) / Dwell Time: 20 Min
---	---

**Inspection Requirements:**

100 % of all accessible surfaces     Joint Preps     Root Pass     Back Gouge     Cover Pass     Other

**Notes:**  
 INSPECT 100% OF SURFACES ON PRODUCTION MODULAR COIL WINDING FORM TYPE-A.  
 SPECIFICATION: ASTM A903/A903M  
 METHOD: ASTM E165

ACCEPTANCE CRITERIA: ASTM A903/A903M LEVEL I FOR MACHINED SURFACES INCLUDING THE ENTIRE "T" SECTION (HIGH STRESS AREAS)

PART HAS REJECTABLE INDICATIONS PER CUSTOMER REQUIREMENTS ON MACHINED SURFACES. SEE NCR-19891 AND PHOTOS FOR MORE DETAILED INFO.

This is to certify that the pieces specified have been inspected in accordance with the specifications shown.

**Inspector:** 581-D.EDWARDS

**Date:** 05/20/2006

*Douglas D. Edwards Level II*









Figure 7-4- High Stress Region Identification for Type-A MCWF



65709/10/1/110/818  
SE141-114  
5/25/06  
Page 2 of 2

Quality Assurance Documentation for Part ID: SE141-114 - Item: 18

Workorder: 65709/1-0 Sub:1 Op:120

Part: SE141-114 - MODULAR COIL WINDING FORM TYPE-A - PRODUCTION MODULAR COIL WINDING FORM TYPE-A

Drawing ID: SE141-114 Rev: 6			INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY			
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT	
*		D A T U M - E - S I D E MAG PERMEABILITY TO BE NO GREATER THAN 1.02μ. CHECK 3 PLACES ADJACENT TO EVERY 5TH HOLE IN T SECTION.	MASTER GAGE	QA		J-1165	LESS THAN 1.02	854-R.U			A
(10)								05-31-06			
*		D A T U M - D - S I D E MAG PERMEABILITY TO BE NO GREATER THAN 1.02μ. CHECK 3 PLACES ADJACENT TO EVERY 5TH HOLE IN T SECTION.	MASTER GAGE	QA		J-1165	LESS THAN 1.02	854-R.U			A
(20)								05-31-06			

**INSPECTION DATA CHECKLIST**

Quality Assurance Documentation for Part ID: SE141-114 - Item: 19

Workorder: 65709/1-0 Sub:1 Op:130

Part: SE141-114 - MODULAR COIL WINDING FORM TYPE-A - PRODUCTION MODULAR COIL WINDING FORM TYPE-A

Drawing ID: SE141-101 Rev: 3			INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY			
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT	
2* (10)	D3	Ø.001 - Ø.002 CHECK CLEARANCE OF ITEM 5 TO ITEM 6.		QA			.004 TO.005 (NC1994 2)	242-M.G 05-25-06		242-M.G 08-02-06	R
* (15)		THE GAP BETWEEN THE POLOIDAL BREAK BUSHINGS AND FLANGE SHAL BE LESS THAN .002"		QA			.001	242-M.G 05-25-06			A
2* (20)	F2	ENSURE THAT THE CUMULATIVE GAP AT ANY SINGLE CROSS SECTION OF THE POLOIDAL FLANGE ELEMENTS IS LESS THAN .005".		QA			LESS THAN .002	242-M.G 05-25-06			A
* (30)		THE MAX. GAP AT THE POLOIDAL BREAK PERIMETER IS .015" AND CANNOT EXCEED 1/8" FROM THE EDGE		QA			LESS THAN .002	242-M.G 06-01-06			A

Quality Assurance Documentation for Part ID: SE141-114 - Item: 20






Workorder: 65709/1-0 Sub:1 Op:132

Part: SE141-114 - MODULAR COIL WINDING FORM TYPE-A - PRODUCTION MODULAR COIL WINDING FORM TYPE-A

Drawing ID: SE141-114 Rev: 6			INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY		
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT
1* (10)	F3	NOTE 14 - BACK SPOTFACE ALL THRU HOLES TO MINIMUM CLEAN UP.		QA			1 HOLE DID NOT CLEAN UP 100% (NC19933)	242-M.G 05-31-06		R
1* (20)	E8	FLANGE PROFILE +/- .25 IN THIS AREA	CMM	QA		00064	.0104	339-E.R 06-01-06		A
1* (30)	D8	///.02 A	CMM	QA		00064	.006	339-E.R 05-31-06		A
1* (40)	D8	54.20 ± .03	CMM	QA		00064	54.194	339-E.R 05-31-06		A
1* (50)	C8	54.20 ± .03	CMM	QA		00064	54.194	339-E.R 05-31-06		A
1* (60)	B8	///.02 A	CMM	QA		00064	.006	339-E.R 05-31-06		A
1* (70)	D5	///.02 A	CMM	QA		00064	.046 [N/C:19942-Doc:NC19942]	339-E.R 05-31-06		R
1* (80)	D5	48.50 ± .03	CMM	QA		00064	48.454 [N/C:19942-Doc:NC19942]	339-E.R 05-31-06		R
1* (90)	C5	48.50 ± .03	CMM	QA		00064	48.503	339-E.R 05-31-06		A
1* (100)	B5	///.02 A	CMM	QA		00064	.003	339-E.R 05-31-06		A
1* (110)	D4	VERIFY PART MARKING: MAJOR TOOL SE141-114 A(casting number) (weight) LBS.		QA		VISUAL	ACCEPT	242-M.G 05-31-06		A
1* (120)	D4	RECORD WEIGHT		QA		VISUAL	5280 LBS	242-M.G 05-31-06		A
1* (130)	D3	⤴.5 A B C OUTER AS CAST SURFACES	CMM	QA		00064	-0.165 TO 0.288 [N/C:19942-Doc:NC19942]	339-E.R 05-31-06		R



### INSPECTION DATA CHECKLIST

2* (140)	F8	2 X .40	CALIPER	QA		P-5075	.350 TO .420 [N/C:1 9942-Doc:NC19942]	533-B.C 05-30-06			R
2* (150)	F8	4 X .03 X 45	CALIPER	QA		P-5075	.010 TO .040 [N/C:1 9942-Doc:NC19942]	533-B.C 05-30-06			R
2* (160)	G6	2 X R.187 +.025 / -.005	PIN GAGE	QA		J-651-2	.184 TO .205	533-B.C 05-30-06			A
2* (170)	G5	 P TO M	CMM	QA		00064	POINTS NOT COLLECT D [N/C:19942-Doc:NC 19942]	339-E.R 05-31-06			R
2* (180)	G5	DATUM D SIDE VERIFY SHELL INTERSECT CLEARANC USING GAGE MTMFX-3473		QA		MTMFX-3473	5-10, 15 - 42, 84 - 94 OUT OF SPEC. [N /C:19942-Doc:NC1994 2]	339-E.R 06-01-06			R
2* (190)	F5	 M TO M1	CMM	QA		00064	-.0287 TO .268 [N/C :19942-Doc:NC19942]	339-E.R 05-31-06			R
2* (200)	E5	 M1 TO N1	CMM	QA		00064	-.0223 TO .0294	339-E.R 05-31-06			A
2* (210)	G3	 Q TO N	CMM	QA		00064	POINTS NOT COLLECT D [N/C:19942-Doc:NC 19942]	339-E.R 05-31-06			R
2* (220)	F3	DATUM E SIDE VERIFY SHELL INTERSECT CLEARANC USING GAGE MTMFX-3473		QA		MTMFX-3473	ACCEPT	339-E.R 06-01-06			A
2* (230)	F3	 N TO N1	CMM	QA		00064	-.0297 TO .0321 [N/ C:19942-Doc:NC19942 ]	339-E.R 05-31-06			R
2* (240)	B4	2 X .06/.09 X 45	CALIPER	QA		P-5075	.030 TO .060 [N/C:1 9942-Doc:NC19942]	533-B.C 05-30-06			R
2* (250)	B5	Ø .375-16 UNC ▽ .750 +.1 -0 96 X	THREAD PLUG GA	QA	100%	A-444	ACCEPT	242-M.G 05-31-06			A
2* (260)	B5	└┐Ø.625 ▽ .188	CALIPER	QA		P-5075	.622 DEPT H .188 TO .310 (NC1 9783) [N/C:19942-Do c:NC19942]	242-M.G 06-01-06			R

### INSPECTION DATA CHECKLIST

2* (270)	B5	$\varnothing$ .06   R   T   S 375-16 HOLES	CMM	QA		00064	.002 TO .066 [N/C:1 9942-Doc:NC19942]	339-E.R 05-31-06			R
3* (280)	H3	$\square$   .01 DATUM E FLANGE	CMM	QA		00064	.029 [N/C:19942-Doc :NC19942]	339-E.R 05-31-06			R
3* (285)	H4	$\surd$ <sup>125</sup> DATUM E FLANGE		QA		VISUAL	250 [N/C:19942-Doc: NC19942]	339-E.R 06-01-06			R
3* (290)	F2	$\square$   .01 DATUM D FLANGE	CMM	QA		00064	.028 [N/C:19942-Doc :NC19942]	339-E.R 05-31-06			R
3* (295)	F3	$\surd$ <sup>125</sup> DATUM D FLANGE		QA		VISUAL	ACCEPT	339-E.R 06-01-06			A
3* (300)	E4	$\varnothing$ 2.50 THRU	CALIPER	QA		P-5075	2.500	533-B.C 05-31-06			A
3* (310)	F4	$\varnothing$ .060   A   B   C $\varnothing$ 2.50	CMM	QA		00064	SEE IGES DATA	339-E.R 05-31-06			A
3* (320)	C7	8X $\varnothing$ 1-8UNC $\nabla$ 2	THREAD PLUG GA	QA		A-665	ACCEPT	533-B.C 05-31-06			A
3* (330)	C7	$\varnothing$ .010   A   B   C 8X $\varnothing$ 1-8 UNC	CMM	QA		00064	SEE IGES DATA	339-E.R 05-31-06			A
3* (340)	D5	8X $\varnothing$ 1-8UNC THRU	THREAD PLUG GA	QA		A-665	ACCEPT	533-B.C 05-31-06			A
3* (350)	D5	$\varnothing$ .010   A   B   C 8X $\varnothing$ 1-8 UNC	CMM	QA		00064	SEE IGES DATA	339-E.R 05-31-06			A
3* (360)	D3	$\varnothing$ 2.50 THRU	CALIPER	QA		P-5075	2.500	533-B.C 05-31-06			A
3* (370)	D3	$\varnothing$ .060   A   B   C $\varnothing$ 2.5	CMM	QA		00064	SEE IGES DATA	339-E.R 05-31-06			A
3* (380)	D1	40.90	CMM	QA		00064	SEE IGES DATA	339-E.R 05-31-06			A
4* (390)	H6	$\square$ $\varnothing$ 2.000-2.001 $\nabla$ 0.990-1.000	DIAL BORE GAGE  CALIPER			J-1401  P-5075	2.0000 TO 2.0002 DEPTH .991 T O .997	533-B.C 05-30-06			A
4* (400)	F4	$\varnothing$ 1.375-6UNC THRU	THREAD PLUG GA	QA		A-375	ACCEPT	533-B.C 05-31-06			A
4* (410)	F4	$\varnothing$ .06   M   A   D $\varnothing$ 1.375-6	CMM	QA		00064	.062 [N/C:19942-Doc :NC19942]	339-E.R 05-31-06			R
4* (420)	D4 &	$\varnothing$ 1.885 $\pm$ .003 THRU	DIAL BORE GAGE	QA		J-1400	1.884 TO 1.886	533-B.C 05-31-06			A

INSPECTION DATA CHECKLIST

4* (430)	D4 &	$\Phi$ .06 M A D Ø1.885	CMM	QA	00064	.012 TO .060	339-E.R 05-31-06		A
4* (440)	B6	3X Ø1.5	CALIPER	QA	J-1103	1.500	533-B.C 05-31-06		A
4* (450)	B6	$\Phi$ .06 M A D 3X Ø1.5	CMM	QA	00064	.030 TO .040	339-E.R 05-31-06		A
4* (460)	A4	6X .25-20 UNC $\nabla$ .5 .5 X 82° CHAMFER	THREAD PLUG GA	QA	A-235	ACCEPT	533-B.C 05-30-06		A
5* (470)	D8/D6	Ø1.885 ±.003	DIAL BORE GAGE	QA	J-1400	1.884 TO 1.886	533-B.C 05-31-06		A
5* (480)	D8/D6	$\Phi$ .06 N A E Ø1.885	CMM	QA	00064	.007 TO .076 [N/C:1 9942-Doc:NC19942]	339-E.R 05-31-06		R
5* (490)	F8	Ø1.375-6UNC THRU	THREAD PLUG GA	QA	A-375	ACCEPT	533-B.C 05-31-06		A
5* (500)	F8	$\Phi$ .06 N A E Ø1.375-6 UNC	CMM	QA	00064	.044	339-E.R 05-31-06		A
5* (510)	F6	8X 1/4 -20 UNC-2B	THREAD PLUG GA	QA	A-716	ACCEPT	533-B.C 05-31-06		A
5* (520)	D6	3X Ø1.5 $\nabla$ 2.33	CALIPER	QA	J-1103	1.500 DEPTH 2.335 TO 2.340	533-B.C 05-31-06		A
5* (530)	D6	$\Phi$ .06 N A E 3X Ø1.5	CMM	QA	00064	.004 TO .034	339-E.R 05-31-06		A
5* (540)	B3	6X .25 - 20 UNC $\nabla$ .6 Ø.5 X 82° CHAMFER	THREAD PLUG GA	QA	A-716	ACCEPT	533-B.C 05-31-06		A
6* (550)	H7	6.00	CMM	QA	00064	SEE IGES DATA	339-E.R 05-31-06		A
6* (560)	H7	1.00	CMM	QA	00064	SEE IGES DATA	339-E.R 05-31-06		A
6* (570)	G8	6.70	CMM	QA	00064	SEE IGES DATA	339-E.R 05-31-06		A
6* (600)	F8	6.70	CMM	QA	00064	SEE IGES DATA	339-E.R 05-31-06		A
6* (610)	E7	5.75	CMM	QA	00064	SEE IGES DATA	339-E.R 05-31-06		A
6*	E7		CMM	QA	00064	SEE IGES DATA	339-E.R		A

(620)		1.00						05-31-06		
6*	E6	4X Ø1.00	PIN GAGE	QA	J-921	.999		533-B.C		A
(630)								05-30-06		
6*	G5		CALIPER	QA	J-1389	1.13 TO 1.14 [N/C:1		533-B.C		R
(640)		2X .88 - 1.13				9942-Doc:NC19942]		05-30-06		
6*	F5	.06-.09 X 45° TYP	CALIPER	QA	P-5075	ACCEPT		533-B.C		A
(650)								05-31-06		
7*	G2		CMM	QA	00064	SEE IGES DATA		339-E.R		A
(660)		19.00						05-31-06		
7*	F2		CALIPER	QA	P-5075	2.001		533-B.C		A
(670)		2.00						05-31-06		
7*	F2		CMM	QA	00064	SEE IGES DATA		339-E.R		A
(680)		6.75						05-31-06		
7*	F2		CALIPER	QA	P-5075	3.752		533-B.C		A
(690)		3.75						05-31-06		
7*	F1	4X Ø.75-10 UNC ▽ 1.50	THREAD PLUG GA	QA	A-232	ACCEPT		533-B.C		A
(700)								05-30-06		
7*	D1		CALIPER	QA	P-5075	1.558 TO 1.560		533-B.C		A
(710)		2X 1.56 OPEN THRU						05-30-06		
7*	C1	.375-16 UNC-2B TAP ▽ .75 .03 X 45° CHAMFER 6X	THREAD PLUG GA	QA	A-52	ACCEPT		533-B.C		A
(720)								05-30-06		
7*	C4	VERIFY THAT HOLE LOCATIONS ARE SCRIBED ON THE PART.		QA	VISUAL	ACCEPT		533-B.C		A
(730)								05-31-06		
7*	B3		CALIPER	QA	P-5075	8.500		533-B.C		A
(740)		8.50 DISTANCE BETWEEN SCRIBE MARKINGS.						05-31-06		
9*	H1	2X Ø.50	CALIPER	QA	P-5075	.502		533-B.C		A
(750)								05-31-06		
9*	B7	TC2 HOLE TO BE .625" IN DIAMETER APPRO 2.52" DEEP AND .25" IN DIAMETER AT LEAST 1" DEEP.	CALIPER	QA	P-5075	.625 DEPTH 2.5 30		533-B.C		A
(760)								05-31-06		
*			CALIPER	QA	P-5075	.625		533-B.C		A



**SOUTH TEXAS BOLT & FITTING, INC**  
 4845 HOMESTEAD RD #500  
 HOUSTON TEXAS 77028  
 PH # 713 673 5376  
 FAX# 713 673 5379


**\* MATERIAL TEST REPORT \***  
 Date 05 17 2006

**SOLD TO** Major Tool & Machine Inc  
 1458 East 19th Street  
 Indianapolis IN 46218

Customer P/O # P06 01393  
 STBF Order # 81140

ITEM	QTY	DESCRIPTION	LOT / HEAT				
1	50	138 6 x 9 1 2 660B Broached Tapend Stud Silver Plated per AMS 2410	XFR / E3930				
<b>Chemical Properties</b>							
C 046	Mn 26	P 015	S 001	Si 28	Ni 25.60	Cr 14.10	Mo 1.21
Cu 13	Co 08	V 22	Al 24	Ti 2.18	B 0.054		
<b>Mechanical Properties</b>							
Tensile 163310	Yield 11090	Elong 23.10	RA 49.90	Hardness 290hb	Temperature 1325 f	Macro Pass	
Remarks ASTM A453 03							

**Certificate of Conformance**  
 This is to certify that the material purchased on this order was made in accordance with and to conform to the specifications and descriptions required by the American Society for Testing Materials (ASTM) and the American Society of Mechanical Engineers (ASME)

**SOUTH TEXAS BOLT & FITTING**  
  
 Lance Byrns  
 Quality Coordinator

**RECEIVED**  
 MAY 15 2006  
 107579 JH

*lines 1-5*

  
 MAY 17 2006

**SOUTH TEXAS BOLT & FITTING, INC.**  
 4845 HOMESTEAD RD, #500  
 HOUSTON, TEXAS 77028  
 PH # 713-673-5376  
 FAX# 713-673-5379

**\* MATERIAL TEST REPORT \***  
 Date: 05-17-2006

**SOLD TO:** Major Tool & Machine, Inc.  
 1458 East 19th Street  
 Indianapolis, IN 46218

**Customer P/O #** P06-01394  
**STBF Order #** 81140-1

ITEM	QTY	DESCRIPTION	LOT / HEAT
------	-----	-------------	------------

1	16	1 3/8"-6 660B 12 Point Hex Nut Silver Plated Per AMS 2410	XFQ / 5407813
---	----	---	---------------

**Chemical Properties**

C	Mn	P	S	Si	Ni	Cr	Mo
.034	1.50	.007	.0016	.54	25.00	14.70	1.22
Cu	Co	V	Al	Ti	B	Pb	
.06	.05	.26	.27	2.25	.0074	.0001	

**Mechanical Properties**

Tensile	Yield	Elong	RA	Hardness	Temperature	Macro
160000	109000	27.60	43.10	319hr	720°C	Pass

Remarks: ASTM A453


**Certificate of Conformance**

This is to certify that the material purchased on this order was made in accordance with, and to conform to, the specifications and descriptions required by the American Society for Testing Materials (ASTM) and the American Society of Mechanical Engineers (ASME).

**SOUTH TEXAS BOLT & FITTING**



Lance Byrns  
Quality Coordinator



*lines 1-2*



MAY 17 2006



Major

Tool & Machine, Inc.

1458 E. 19th Street, Indianapolis, In 46218  
TEL:(317)636-6433 FAX:(317)634-9420

# Nondestructive Test Certification for Liquid Penetrant Examination

Quality Assurance Documentation for Part ID: SE141-114 - Item: 23

Date of Inspection: 05/26/2006

Type of Material: CAST STAINLESS

NDT#: 16858

<b>Stage of Inspection:</b> <input type="checkbox"/> Incoming Inspection <input type="checkbox"/> In-Process Inspection <input checked="" type="checkbox"/> After Repair <input type="checkbox"/> Final Inspection	<b>Manufacturing Process:</b> <input type="checkbox"/> Weldment <input type="checkbox"/> Bar Stock <input type="checkbox"/> Forging <input checked="" type="checkbox"/> Casting <input type="checkbox"/> Plate <input type="checkbox"/> Other	<b>Surface Condition:</b> <input checked="" type="checkbox"/> Machined <input type="checkbox"/> Rough <input type="checkbox"/> Other FINAL MACHINED	<b>Test Being Run to:</b> <input checked="" type="checkbox"/> Router Instructions <input checked="" type="checkbox"/> Drawing <input type="checkbox"/> Test Plan <input type="checkbox"/> Technique Card SEE NOTES	<b>Heat Treated:</b> <input type="checkbox"/> Yes <input checked="" type="checkbox"/> No
--	---	---	---	--

<b>Part Information:</b> MTM Job Number: 65709/1.0 -Sub:17 -Op:40 Resource ID: 810-LIQUID PENETRANT INSPE Part ID: SE141-114 Part Name: MODULAR COIL WINDING FOR Serial Number: Customer P.O.: S005242-F Customer Unit/Plant:	<b>Test Results:</b> Quantity Inspected: 1 Quantity Accepted: 1 Quantity Rejected: 0  Run Hours: 0.0
--	---

<b>Customer Inspection Plan:</b> SEE NOTES <b>Test Step:</b> <b>Revision:</b> <b>Material Test Number:</b>	<b>Inspection Criteria:</b> <b>Customer Specification:</b> ASTM A903/A903M <b>MTM Spec Number:</b> PS582 (REF NDT-WI-009) <b>Acceptance Standard:</b> ASTM A903 (SEE NOTES)
---	--

<b>Inspection Materials Used:</b> <b>Manufacturer:</b> SHERWIN <b>Type of Penetrant:</b> DP-51 <b>Batch Number:</b> 41-E47 <b>Developer:</b> D-100 <b>Batch Number:</b> 65-C6	<b>Penetrant Examination Processes:</b> <b>Type:</b> II (Visible) / Dwell Time: 20 Minutes <b>Method:</b> C (Solvent Wipe) <b>Method of Drying:</b> Normal Evaporation <b>Form:</b> e (nonaqueous for Type II visible dye) / Dwell Time: 20 Min
--	---

**Inspection Requirements:**

100 % of all accessible surfaces     Joint Preps     Root Pass     Back Gouge     Cover Pass     Other  
OF REPAIR AREA

**Notes:**  
INSPECT 100% OF REPAIR AREA SURFACES AS REPORTED ON NCR-19709.

SPECIFICATION: ASTM A903/A903M  
METHOD: ASTM E165

ACCEPTANCE CRITERIA: ASTM A903/A903M LEVEL I FOR MACHINED SURFACES INCLUDING THE ENTIRE "T" SECTION (HIGH STRESS AREAS)

This is to certify that the pieces specified have been inspected in accordance with the specifications shown.

Inspector: 581-D.EDWARDS

Date: 05/26/2006

*Douglas D. Edwards* Level II





Quality Assurance Documentation for Part ID: SE141-114 - Item: 24

Workorder: 65709/1-0 Sub:17 Op:50

Part: SE141-114 - REWORK / REPAIR PER N/C - N/C #

Drawing ID: SE141-116 Rev: 8			INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY		
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT
*		N C 19709	MASTER GAGE	QA		J-1165	NO PERMEABILITY RE PONSE EQUAL TO OR REATER THAN 1.02μ ( ORSTEADS)	840-G.M		
(10)		RECORD PERMEABILITY READINGS OF THE REPAIRED AREA. MAG PERMEABILITY TO BE NO GREATER THAN 1.02μ.						06-01-06		A

Quality Assurance Documentation for Part ID: SE141-141 - Item: 25

Workorder: 65709/1-0 Sub:18 Op:30

Part: SE141-141 - BEARING PLATE DETAIL TYPE "A" SHORT -

Drawing ID: SE141-141 Rev: 1		INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY			
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT
1*	G2	RECORD MAGNETIC PERMEABILITY. RESULTS TO BE NO GREATER THAN 1.02μ.	MASTER GAGE	QA		J-1271	LESS THAN 1.02	261-T.D		
(10)										05-16-06

A



**INSPECTION DATA CHECKLIST**

Quality Assurance Documentation for Part ID: SE141-142 - Item: 26

Workorder: 65709/1-0 Sub:19 Op:30

Part: SE141-142 - BEARING PLATE DETAIL TYPE "A" LONG -

Drawing ID: SE141-142 Rev: 1			INSPECTION INSTRUCTIONS			RESULTS		INSPECTED BY		
SHEET	ZONE	CHARACTERISTIC	GAGE/EQUIP	BY	SAMPLE	SER#	DATA/REMARKS	INSP	VERFD	AUDIT
1*	G2	RECORD MAGNETIC PERMEABILITY. RESULTS TO BE NO GREATER THAN 1.02μ.	MASTER GAGE	QA		J-1165	LESS THAN 1.02	503-B.H		
(10)								05-18-06		

Employees: 242-M.Griffith / 261-T.Dunn / 339-E.Root / 503-B.Houk / 533-B.Clevenger / 840-G.Masood / 854-R.Upchurch