

Page: 1 Date: 12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev Engineer SE121-003P / --64880/1.0 BLUE/DOUG MCCORKLE

NSCX PROTOTYPE VACUUM VESSEL SEGMENT SCOPE OF WORK: NCSX-SOW-121-01-02

SPECIFICATION: NCSX-CSPEC-121-01-01

Sub ID Part ID Qty Drawing ID / Rev

NSCX PROTOTYPE VACUUM VESSEL SEGMENT SCOPE OF WORK: N SE121-003P / --

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource

Sub: 0 / Seq: 10 700-BLUE TEAM, ENGINEERING 1.00 1.00 1.00 SE121 / A

(F) SOW 3.2.1 TASK 2

MIT/QA PLANS FOR PVVS FOR VVSA

OAP Count: 0 IDC Count: 0 Dwg Count: 5 Pgm Count: 0 NDT Count: 0 WPS Count: 0 **Dimensions**

Piece # Part ID Qty Drawing ID / Rev Vendor 10 4434

INCONEL625_062_GTAW-WELD WIRE/GTAW, .062 DIA 26.0

Vendor Part ID: INCONEL625_062_GTAW Mfg Part ID: INCONEL 625

(F) ASME/AWS SFA 5.14, ERNiCrMo-3

INCONEL 625 WELD WIRE, CUT LENGTH

0.062" DIA. X 36" LONG. SUPPLIED IN 10 LB TUBES.

EACH PIECE OF CUT LENGTH WIRE MUST BE IDENTIFIED AT MINIMUM WITH THE AWS WELD WIRE CLASS.

MATERIAL CERTIFICATION REQ'D WITH SHIPMENT

Material Certification: TRACE ID: 38561

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

QAP Count: 3

Piece # Part ID Qty Drawing ID / Rev Vendor **Dimensions**


4434 30 INCONEL625_093_GTAW-WELD WIRE/GTAW, .093 DIA 36.0

Vendor Part ID: INCONEL625_093_GTAW Mfg Part ID: INCONEL 625

(F) ASME/AWS SFA 5.14, ERNiCrMo-3

INCONEL 625 WELD WIRE, CUT LENGTH

0.093" DIA. X 36" LONG. SUPPLIED IN 10 LB TUBES.



Major
Tool & Machine, Inc.

 Workorder
 Part ID
 Qty
 Drawing ID / Rev
 Engineer

 64880/1.0
 1
 SE121-003P / - BLUE/DOI

BLUE/DOUG MCCORKLE

EACH PIECE OF CUT LENGTH WIRE MUST BE IDENTIFIED AT MINIMUM WITH THE AWS WELD WIRE CLASS.

MATERIAL CERTIFICATION REQ'D WITH SHIPMENT

Material Certification: TRACE ID: 41171

Material Certification: Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

QAP Count: 4

Piece # Part ID Qty Drawing ID / Rev Vendor Dimensions
40 INCONEL625 035 GMAW-WELD WIRE/GMAW. .035 DIA 6.0

INCONEL625_035_GMAW-WELD WIRE/GMAW, .035 DIA Mfg Part ID: INCONEL 625

(R) ASME/AWS SFA 5.14, ERNiCrMo-3

INCONEL625_035_GMAW WELD WIRE, GMAW .035 DIA.

CERTS AND MILL TEST REPORTS REQUIRED WITH SHIPPMENT

Material Certification: Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

QAP Count: 3

QtyPer StartQty EndQt Drawing ID / Rev Operation Resource Sub: 0 / Seq: 11 700-BLUE TEAM, ENGINEERING 1.00 1.00 1.00 (F) SOW 3.1 TASK 1 3.1.1 METHODS FOR FABRICATING VVSA 3.1.2 DESIGN CHANGES 3.1.3 PRELIMINARY MIT/AQ FOR VVSA 3.1.4 BUDGETARY COST/SCHEDULE FOR VVSA IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Vendor Part ID: E308LT1-1_045_FCAW Mfg Part ID: E308LT1-1 FLUX CORE

OperationResourceQtyPerStartQtyEndQt Drawing ID / RevSub: 0 / Seq: 12700-BLUE TEAM, ENGINEERING1.001.001.00(F)SOW 3.3.1 & SOW 3.3.2 Task 8

3.3.1 FINAL MIT/QA FOR VVSA 3.3.2 FINAL COST/SCHEDULE FOR VVSA



Page: 3 Date: 12/23/03 User ID: MCCORKLE

Workorder 64880/1.0

Part ID Qty Drawing ID / Rev Engineer SE121-003P / --BLUE/DOUG MCCORKLE

> IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0

Operation **QtyPer** StartQty EndQt Drawing ID / Rev Resource Sub: 0 / Seq: 13 700-BLUE TEAM, ENGINEERING 1.00 1.00 1.00

(F) ENGINEERING, PLANNING & PROJECT MGT TASK 9

> FOLLOWING IS A LIST STANDARD OPERATING PROCEDURES AND WORK INSTRUCTIONS THAT APPLY IN PART OR IN WHOLE TO THE EXECUTION OF THIS WORK ORDER.

ENGINEERING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURES: ENGSOP01 - Mfg. Quality Plans; ENGSOP02 -Specification-Standard Control; ENGSOP03 - Internal Drawing Generation; ENGSOP04 - Drawing Control.

CAD / CAM OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURE: CADSOP01 - CNC Program Control;

MANUFACTURING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURES: MFGSOP01 - Project Manufacturing; MFGSOP02 -Material Handling and Storage; MTLSOP01 - Material Storage; PCSOP01 - Production Control; QASOP01 - Nonconformance Control; QASOP03 - Traceability-Identification OUALITY ASSURANCE AND INSPECTION OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURES: OASOP01 -Nonconformance Control; QASOP05 - Calibration

RECEIVING INSPECTION OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURE: QASOP04 - Receiving Inspection IN-PROCESS INSPECTION OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURE: QASOP02 - In Process Inspection SHIPPING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURE: SHSOP01 - Shipping-Packaging MACHINING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURE: TLGSOP01 - Cutting Tool Control WELDING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING STANDARD OPERATING PROCEDURES: WLDSOP02 - Qualification of Welders and WPS;

WLDSOP03 - Welding Process Development; WLDSOP04 - Stores Control of Weld Wire; WLDSOP05 - Weld Mapping; WLDSOP06 - Welding Filler Metal and Flux Procurement ENGINEERING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: ENGWI001 - Material Card; ENGWI002 - Drawing Control; ENGWI003 -

Bill of Manufacturing; ENGWI005 - Engineering Contract Review; ENGWI007 - Work Order Review Release; ENGWI008 - Operation Cards; ENGWI009 - Quality Planning; ENGWI010 - Service Cards; ENGWI013 - Work Order Header Card Maintenance; ENGWI014 - Inspection Fields; ENGWI019 - Nonconformance to Customers.

CAD / CAM OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: CADWI004 - Developing a CADCAM program; CADWI005 - Updating CADCAM Program or File

MANUFACTURING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: MFGWI018 - Workmanship; PCWI001 - Use of MTM Routing; PCWI004 - Scheduling System Procedures


CLEANING / WASHING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTION: MFGWI005 - High Pressure-High Temperature Water Cleaning of

SUBCONTRACT OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTION: PCWI005 - Subcontract Procedure; PURWI002 - Vendor Setup and Assessment

NON-DESTRUCTIVE TESTING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: NDTWI001 - NDT Exam Personnel Qualification; NDTWI011 - Visual Weld Inspection

QUALITY ASSURANCE, IN-PROCESS INSPECTION OPERATIONS AND/OR RECEIVING INSPECTION OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: QAWI001 - MTM Inspection Method Guidelines; QAWI006 - Sampling Inspection Criteria; QAWI008 - Receiving Ordered Material; QAWI010 - Calibration; QAWI015 - Checking Out and Returning Gauges; QAWI017 - Recording Inspection Results; QAWI018 - Quality Sign Off Control; QAWI020 - Organization and Control of Quality Records; QAWI021 - Quality Record Storage and Retention; QAWI023 - Nonconformance System Navigation; QAWI026 - Part Relocation with SMX; QAWI027 - SMX Part Inspection Checklist; QAWI028 - QAP Data Package Generation; QAWI029 - Scanning Certifications; QAWI031 - Material Certification Program.

SHIPPING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: SHWI002 - Guidelines for Shipping Documentation; SHWI003 - General Guidelines for Building Containers; SHWI004 - Guidelines for Loading Parts for Shipment; SHWI005 - General Guidelines for Packaging Parts; SHWI007 - Guidelines for Coordinating





Workorder 64880/1.0

Part ID Drawing ID / Rev SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

Transport.

WELDING OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: WLDWI003 - Welding Personnel Training; WLDWI004 - Welder

Performance Qualification; WLDWI005 - Storage and Maintenance of Welding Documents; WLDWI006 - Welding Engineering Work Order Review Process; WLDWI007 - Weld Wire and Stub Control; WLDWI008 - Assessment of Welder's Ability

BLAST BOOTH OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: SBWI001 - General Sandblast Guidelines:

MATERIAL PROCUREMENT OPERATIONS WILL BE PERFORMED PER THE FOLLOWING WORK INSTRUCTIONS: PURWI001 - Purchasing Data; PURWI002 - Vendor Setup

and Assessment

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

OAP Count: 0

NDT Count: 0

WPS Count: 0

Operation Resource Sub: 0 / Seq: 14 700-BLUE TEAM, ENGINEERING

Resource

Resource

1.00 1.00 1.00

QtyPer

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

OAP Count: 0

NDT Count: 0

WPS Count: 0

Operation Sub: 0 / Seq: 15

(U)

(U)

(F)

Resource 805-INPROCESS INSPECTION - PLA

ENGINEERING TECHNICAL SUPPORT

QtyPer 1.00

StartQty EndQt Drawing ID / Rev 1.00

1.00 PPPL / 0

StartQty EndQt Drawing ID / Rev

QUALITY ENGINEERING REVIEW OF CUSTOMER PRODUCT SPECIFICATION AND STATEMENT OF WORK. REFERANCE SPEC NCSX-CSPEC-121-01-01 OR

NCSX-SOW-121-01-02 IN LIBRARIAN BY SEARCHING UNDER THE REFERANCE DOCUMENT ID FOR SPECIFIC SPEC NUMBER OR PPPL.

IDC Count: 0

Dwg Count: 2

Pgm Count: 0

OAP Count: 0

NDT Count: 0

WPS Count: 0

Operation Sub: 0 / Seq: 20

825-FINAL INSPECTION - PLANTS 1

OtvPer 1.00

StartQty 1.00

1.00 SE121 / A

FINAL VISUAL INSPECTION (ENGINEERING CONCURRENCE REQUIRED).

FINAL CLEANLINESS VERIFICATION PER PP475 AND PREPARE CERTIFICATION / CLEANLINESS REPORT

COMPILE ELECTRONIC DATA BOOK INFORMATION PER MTM QAP.

TAKE SEVERAL PHOTOGRAPHS OF PART

PREPARE C OF C AND REQUEST FOR SHIPPING RELEASE (CONTACT ENGINEERING (DOUG McCORKLE) FOR RELEASE FORM IF NOT AVAILABLE ELECTRONICALLY.

EndQt Drawing ID / Rev

WITNESS AND PHOTOGRAPH THE PACKAGING / PREPARATION FOR SHIPMENT (NEXT SEQUENTIAL OPERATION).

Test Certification: CLEANLINESS CERTIFICATION Rev:

Part Number: SE121-003P

Part Description: NCSX PVVS COMPLETE

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 5

QtyPer

Pgm Count: 0

EndQt Drawing ID / Rev

OAP Count: 4

NDT Count: 0

WPS Count: 0

Operation Sub: 0 / Seq: 30 (F)

425-SHIPPING - PLANTS 1 & 2

SHIP PER CUSTOMER RELEASE FORM

(CONTAINER MANUFACTURED IN SUB I.D. 28)

1.00 1.00 SE121 / A 1.00

StartQty

MTTRAVLR.qrp

W:64880/1-0 /Inc Matl /Inc Legs





 Workorder
 Part ID
 Qty
 Drawing ID / Rev
 Engineer

 64880/1.0
 1
 SE121-003P / - BLUE/DOI

BLUE/DOUG MCCORKLE

AT A MINIMUM ENSURE THE PART IS COMPLETELY WRAPPED WITH PLASTIC FOAM AND SHRINK WRAP.

DO NOT APPLY TAPE TO THE PART. THE PLASTIC FOAM CAN BE TAPED ONLY TO ITSELF TO HOLD POSITION UNTIL SHRINK WRAP IS APPLIED.

SPECIAL CRATE REQUIREMENTS:

CONTAINER MUST BE CLEARLY MARKED WITH THE FOLLOWING INFORMATION:

SUPPLIER:

MAJOR TOOL & MACHINE, INC.

1458 E. 19TH ST.

INDIANAPOLIS, IN 46218

CONTENTS:

SE121 NCSX PVVS

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 5 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0

Operation Sub: 0 / Seq: 9876	Resource 601-AUTOMATED SCHEDULI	QtyPer	StartQty EndQ 1.00 1.00	t Drawing ID / Rev		Service ID TESTNG/MISC	
	Drw N/A ID0	N/A IDC Count: 0	Dwg Count: 0	Pgm Count: 0	QAP Count: 0	NDT Count: 0	WPS Count: 0
Sub ID	Part ID		Otv	Drawing ID / Rev			

Sub ID Part ID Qty Drawing ID / Rev

1 SE121 PROTOTYPE VACUUM VESSEL 1 SE121 / A
Parent Sub:0 Op:20

Operation	Resource	QtyPer	StartQty	EndQt	Drawing ID / Rev
Sub: 1 / Seq: 10	230-FABRICATION - WEIDNER	1.00	1.00	1.00	SE121-001P / A
(F)	EARDICATION ODED ATION # 1				

ACQUIRE THE FOLLOWING DIE FORMED PANELS:

SE121-001P-2 PANEL 1

SE121-001P-2 PANEL 2

SE121-001P-2 PANEL 3

SE121-001P-2 PANEL 4

SE121-001P-2 PANEL 5

PRIOR TO FITTING AND TRIMMING, DETERMINE WHICH PANELS ARE GOING TO BE GROUPED AND WELDED TOGETHER AS "SUB-SETS") TO MINIMIZE AND CONTROL WELDING DISTORTION. ENGINEERING CONCURRENCE REQUIRED.

THE PANEL FITTING / INSTALLATION SEQUENCE PLAN IS TO PRODUCE ONE TWO PANEL SUB-SET, AND ONE THREE PANEL SUB SET (ONE WELD AT A TIME). THIS WILL REDUCE THE FINAL ASSEMBLY WELDING DISTORTION FROM 5 TO 2 WELD JOINTS. IT WILL ALSO PROVIDE FOR EASIER ADJUSTMENTS / COMPENSATION AFTER INDIVIDUAL WELDS ARE COMPLETED. THE TWO PANEL SUB-SET WILL BE MADE BY FITTING AND WELDING TWO ADJACENT PANELS TOGETHER, LEAVING EXCESS TRIM STOCK ON EACH OUTER EDGE FOR FITTING THE NEXT PANEL / SUB-SET TO THEM. THE THREE PANEL SUB-SET WILL BEGIN AS A TWO PANEL SUB-SET WITH THE REMAINING INDIVIDUAL PANEL FIT AND WELDED IN PLACE AFTER THE FIRST WELD IS COMPLETED.

Date: 12/23/03 User ID: MCCORKLE

Workorder 64880/1.0

Part ID

Engineer BLUE/DOUG MCCORKLE

ONCE PANEL SUB-SETS AND WELD SEQUENCES HAVE BEEN ESTABLISHED, ALIGN, FIT, AND TRIM EACH PANEL ACCORDING TO THE BUILD FIXTURE REGISTER SURFACES, TRIM LINES, AND ADJACENT PANEL SURFACES.

Qty Drawing ID / Rev

SE121-003P / --

GRIND WELD PREPS AND CLEAN THE WELD JOINT AND APPROXIMATELY THREE INCHES OF THE SURROUNDING AREA PER THE APPLICABLE SECTION OF PP475. CLEANLINESS IS TO BE MONITORED AND MAINTAINED THROUGHOUT THE MANUFACTURING PROCESS.

START BY SETTING EACH PANEL INDIVIDUALLY ONTO THE MACHINED REGISTER OF THE BUILD FIXTURE BASE-PLATE (THE DATUM -B- SURFACE (10 DEGREE OFFSET) DOWN). TRIM THE MATING VERTICAL WELD JOINT OF EACH PANEL SET TO PLUS 0.03" (MINIMUM) FROM THE TRIM LINE. TRIM THE OUTER SURFACES OF THE EACH TWO PANEL SET AT LEAST 0.06" OUTSIDE THE TRIM LINE (TO ENSURE TRIM STOCK IS AVAILABLE FOR ADJACENT PANEL / PANEL SUB-SET).

EACH SUB-SET IS TO BE RELEASED FROM THE BUILD FIXTURE AFTER WELDING TO ENSURE STABILITY PRIOR TO TRIMMING, FITTING, AND WELDING SUBSEQUENT PANELS / SETS.

TRIM THE TOP AND BOTTOM EDGES OF EACH PANEL TO APPROXIMATELY 0.04" (MINIMUM) ABOVE THE FIXTURE RISER FACE (FOR SHRINKAGE AND FINAL TRIMMING ALLOWANCE).

NOTE THAT THE INTERIOR PROFILE FIXTURE REST STOP SURFACES ARE POSITIONED AT NOMINAL GEOMETRIC POSITION TO AVOID STARTING ANY LOWER THAN MID-TOLERANCE. SHIM IF NECESSARY TO MAINTAIN AN AVERAGE PROFILE STARTING POSITION OF (+.090"). ENSURE NO GAPS BETWEEN THE PRODUCTION PANELS AND FIXTURE REST STOPS ARE GREATER THAN (+.18") PRIOR TO TACK WELDING IN PLACE. (ENGINEERING CONCURRENCE REQUIRED) ENSURE THE MATERIAL THICKNESS IS ADEQUATE TO ALLOW NORMAL REDUCTION THAT WILL OCCUR FROM GRINDING / BLENDING / POLISHING THE WELDS. NOTIFY ENGINEERING (DOUG McCORKLE) IF CONCERNS EXIST.

ENSURE EACH PANEL IS ALIGNED (SMOOTH AND CONTINUOUS) TO ITS ADJACENT MEMBER AND MIS-MATCH IS MINIMIZED. CWI / ENGINEERING CONCURRENCE REOUIRED.

AS EACH PANEL IS POSITIONED, FIT AND TRIMMED, LAYOUT AND PRICK PUNCH THE APPROXIMATE INSPECTION POINTS PER DRAWING SE121-001P-1MTM. NOTE THAT THE SOLE PURPOSE OF THE PUNCH MARKS IS TO MAINTAIN REPEATABLE PROFILE INSPECTIONS THROUGHOUT THE FABRICATION PROCESS. THE DEPTH OF EACH PUNCH MARK NEEDS TO BE ONLY DEEP ENOUGH THAT IT WOULD NOT BE REMOVED BY NORMAL PREPARATION / WELDING / BLENDING / BLASTING, ETC.

PREP, AND WELD PANEL SETS TOGETHER (SEQUENCING WELDS AND JOINTS TO MINIMIZE INDIVIDUAL AND OVERALL WELD DISTORTION)

ENSURE QUALITY ASSURANCE AND CERTIFIED WELDING INSPECTORS ARE CLOSELY INVOLVED, AND INTER-PASS PROFILE AND VISUAL INSPECTIONS ARE PERFORMED ON EACH SUB-ASSEMBLY AFTER TACK WELDING, ROOT PASS, EACH INTER-PASS, AND COVER PASS IS COMPLETED.

GRIND PREPS ON EACH PANEL WELD JOINT (*****FINAL WELD PREP CONFIGURATION UNDER DEVELOPMENT!!!!! WILL BE FINALIZED AFTER THE WELD TESTING PERFORMED UNDER TEST SUB ID ******).

***NOTE: THE WELD JOINT ROOT / FACE MUST BE ORIENTATED TO KEEP THE BEAD WIDTH ON THE INTERIOR SIDE OF THE VESSEL (VACUUM SIDE) AS NARROW AS POSSIBLE. INTERIOR SIDE WELD FACES SHOULD BE KEPT AS NARROW AS POSSIBLE (1 WELD BEAD WIDTH MAX).

PURGE EACH WELD JOINT WITH 100% ARGON. PURGE DAM MATERIAL MUST BE MADE FROM EITHER 625 INCONEL OR 300 SERIES STAINLESS STEEL. NOTE THAT THE PURGE IS TO BE MAINTAINED THROUGHOUT THE WELDING PROCESS ON ALL JOINTS. ASSIST O/A WITH PROFILE VERIFICATION.

Part Number: SE121-001P Part Description: NCSX PVVS Specification: PP475 Rev: 8



Page: 7 Date: 12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev 64880/1.0 SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

Specification: PP477 Rev: 5

IDC Count: 15 Dwg Count: 0 Pgm Count: 0 QAP Count: 4 NDT Count: 0 WPS Count: 1

WPS390-PPPL Rev:0 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

Operation Resource OtvPer StartQty EndQt Drawing ID / Rev Sub: 1 / Seq: 20 817-SMX LASER 1.00 1.00 1.00 SE121-001P-1MTM / 2A

(F) INSPECTION OPERATION # 1

> AFTER EACH SUB-SET IS COMPLETELY TACK WELDED, INSPECT / VERIFY POSITIONING, FITUP, AND PROFILE OF EACH TACK WELDED SUB-SET PER THE FOLLOWING:

INCLUDE AT LEAST THREE DATUM TARGETS IN EACH POINT CLOUD SCAN FOR ALIGMENT / VERIFICATION TO THE 3D MODEL.

ENSURE THE PART PROFILE IS WITHIN THE UPPER HALF OF THE APPLIED BI-LATERAL TOLERANCE AS FOLLOWS: VERIFY THAT NO INSPECTION POINT IS ABOVE THE HIGH LIMIT OF TOLERANCE (OUTWARD) OR BELOW NOMINAL (INWARD).

RECORD ACTUAL (HIGH/LOW RANGE) ON MTM IDC

REPORT ANY OUT OF TOLERANCE READINGS VIA MTM NCR

NOTIFY ENGINEERING (DOUG McCORKLE) FOR EVALUATION OF RESULTS PRIOR TO RELEASING THE PART BACK TO PRODUCTION.

INSPECTION POINT GRID: 6" CENTERS THROUGHOUT WITH 1" CENTERS AT AND NEAR WELD JOINTS.

ENSURE THE FIXTURE DATUM TARGETS ARE ADEQUATELY POSITIONED FOR THE REPOSITIONING AT THE NEXT SEQUENTIAL INSPECTION

INSPECT THE MAGNETIC PERMEABILITY AND MATERIAL THICKNESS AT EACH PROFILE INSPECTION POINT.

RECORD PROFILE, MAGNETIC PERMEABILITY, AND MATERIAL THICKNESS ON SE121-001P-1MTM, RESULTS MUST BE RECORDED, REVIEWED BY ENGINEERING,

SCANNED AND LINKED PRIOR TO COMPLETING THE INSPECTION SEQUENCE.

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP475 Rev: 8

(F)

Map(s): SE121-001P-1MTM Rev: 2A

IDC Count: 2 Dwg Count: 1 Pgm Count: 0 QAP Count: 6 NDT Count: 0 WPS Count: 0

Operation StartQty EndQt Drawing ID / Rev Resource **QtyPer** Sub: 1 / Seq: 30 230-FABRICATION - WEIDNER 1.00 1.00 SE121-001P / A

FABRICATION OPERATION # 2

PRIOR TO BEGINNING, NOTIFY ENGINEERING / CFT THE PART IS READY AND AVAILABLE FOR POSSIBLE CUSTOMER HOLD / WITNESS POINT INSPECTION. HOLD FOR RESPONSE AND/OR FURTHER DIRECTION.

BACK PURGE THE WELD JOINT SURFACES WITH 100% ARGON. PURGE DAM MATERIAL MUST BE MADE FROM EITHER 625 INCONEL OR 300 SERIES STAINLESS STEEL.

WELD ROOT PASSES (INCREMENTALLY, USING BACK-STEPPING METHOD TO MINIMIZE SHRINKAGE) ON ALL FIVE WELD JOINTS.

NOTE THAT THE BACK SIDE OF THE JOINT MUST REMAIN PURGED UNTIL THE ENTIRE JOINT IS COMPLETELY FILLED.





Workorder 64880/1.0

 Part ID
 Qty
 Drawing ID / Rev
 Engineer

 1
 SE121-003P / - BLUE/DOUG MCCORKLE

NOTE BURN-THROUGH, AND BACK-WELD FACES SHOULD BE KEPT AS NARROW AS POSSIBLE.

CWI VISUAL INSPECT ROOT WELDS 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER AWS D1.6, 6.29.1.

Test Certification: CWI CERTIFICATE Rev:

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Method: VT-PP-001 Rev: B Specification: PP475 Rev: 8

IDC Count: 5 Dwg Count: 0 Pgm Count: 0 QAP Count: 5 NDT Count: 0 WPS Count: 1

WPS390-PPPL Rev:0 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

 Operation
 Resource
 QtyPer
 StartQty
 EndQt
 Drawing ID / Rev

 Sub: 1 / Seq: 40
 817-SMX LASER
 1.00
 1.00
 1.00
 SE121-001P-1MTM / 2A

(F) INSPECTION OPERATION # 2

AFTER THE ROOT WELDS ARE COMPLETE (FABRICATION DEPT. WILL COORDINATE); RE-INSPECT / VERIFY PART PROFILE IS WITHIN APPLIED TOLERANCE AND RECORD WELDING SHRINKAGE / DISTORTION REALIZED TO THIS POINT.

INSPECTION POINT GRID: 6" CENTERS THROUGHOUT WITH 1" CENTERS AT AND NEAR WELD JOINTS.

INCLUDE AT LEAST THREE DATUM TARGETS IN EACH POINT CLOUD SCAN FOR ALIGMENT / VERIFICATION TO THE 3D MODEL.

RECORD ACTUAL (INDIVIDUAL) MEASUREMENTS ON INSPECTION FORM (SE121-2MTM). RECORD ACTUAL (HIGH/LOW RANGE) ON MTM I.D.C.

INSPECT AND RECORD MAGNETIC PERMEABILITY.

REPORT ANY OUT OF TOLERANCE READINGS VIA MTM NCR.

NOTIFY ENGINEERING (DOUG McCORKLE) FOR EVALUATION OF RESULTS PRIOR TO RELEASING PART. NOTE THAT PROFILE READINGS SHOULD REMAIN NEAR TO ABOVE NOMINAL. INWARD DISTORTION APPROACHING THE LOW LIMIT OF TOLERANCE MUST BE ADDRESSED (AND CORRECTIVE ACTION IMPLEMENTED) PRIOR TO COMPLETING WELDING PROCESS.

ENSURE THE FIXTURE DATUM TARGETS ARE ADEQUATELY POSITIONED FOR THE NEXT SEQUENTIAL INSPECTION.

RECORD PROFILE, MAGNETIC PERMEABILITY, AND MATERIAL THICKNESS ON SE121-001P-1MTM, RESULTS MUST BE RECORDED, REVIEWED BY ENGINEERING, SCANNED AND LINKED PRIOR TO COMPLETING THE INSPECTION SEQUENCE.

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Specification: PP476 Rev: 4

Specification: ASTM A800 Rev: 2001

Specification: PP475 Rev: 8 Specification: PP477 Rev: 5

Map(s): SE121-001P-1MTM Rev: 2A

IDC Count: 2 Dwg Count: 1 Pgm Count: 0 QAP Count: 7 NDT Count: 0 WPS Count: 0

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 1 / Seq: 70230-FABRICATION - WEIDNER1.001.001.005E121-001P / A(F)FABRICATION OPERATION # 3

Page: 9 Date: 12/23/03 **User ID: MCCORKLE**

Workorder 64880/1.0

Part ID

Qty Drawing ID / Rev SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

AFTER OBTAINING ENGINEERING, Q/A PROFILE ACCEPTANCE, AND AUTHORIZATION TO PROCEED, WELD THE REMAINDER OF THE STRUCTURAL WELD JOINTS. SEQUENCE WELDING AND UTILIZE BACK-STEPPING METHODS TO MINIMIZE DISTORTION AND NUMBER OF INTER-PASSES.

WELDING (INCLUDING TACK-WELDING BRACING) WITHIN THE FINISH PART ENVELOP ON THE INTERIOR SIDE MUST BE ABSOLUTELY MINIMIZED. ANY TACKING AND/OR WELDING ON THIS SURFACE MUST BE APPROVED BY ENGINEERING.

CWI VISUAL INSPECT EACH WELD PASS 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER AWS D1.6, 6.29.1. EACH WELD PREP / WELD INTER-PASS MUST BE CLEANED PER PP475 PRIOR TO WELDING THE NEXT SEQUENTIAL BEAD.

AFTER WELDING IS COMPLETE, REMOVE ANY TEMPORARY STIFFENING / SUPPORT / SHOP AID DEVICES. BLEND / TOUCH UP ATTACHMENT WELDS AS

LAYOUT THE PORT ASSEMBLY LOCATION. (ANGULAR LOCATION, OVERALL LENGTH, AND OUTLINE ARE IDENTIFIED ON THE ASSEMBLY FIXTURE). UTILIZE THE LASER TRACKER TO ENSURE POSITION PRIOR TO TACK WELDING.

WELD THE PORT EXTENSION SUB-ASSEMBLY IN PLACE PER DRAWING.

BACK PURGE THE WELD JOINT SURFACES WITH 100% ARGON. PURGE DAM MATERIAL MUST BE MADE FROM EITHER 625 INCONEL OR 300 SERIES STAINLESS STEEL.

NOTE THAT THE BACK SIDE OF THE JOINT MUST REMAIN PURGED UNTIL THE ENTIRE JOINT IS COMPLETELY FILLED.

CWI VISUAL INSPECT THE PORT EXTENSION WELD 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER AWS D1.6, 6.29.1.

FINISH POLISHING (RESTORE TO A 32 MICRO-INCH SURFACE FINISH) AND CLEANING THE INTERIOR SURFACES OF THE PORT SUB-ASSEMBLY. REFER TO **CLEANING PROCEDURE PP475**

CWI NOTE: THE VISUAL INSPECTION CERTIFICATE SHOULD SPECIFY EACH WELD JOINT / STRINGER PASS. IT SHOULD ALSO CLEARLY DIFFERENTIATE BETWEEN THE STRUCTURAL WELDS AND THE PORT EXTENSION WELDS.

RECORD IDC DATA

NOTE: THE NEXT THREE MANUFACTURING SEQUENCES MUST BE CLOSELY COORDINATED (BAKE-OUT, PREPARATION FOR VACUUM TEST, AND VACUUM TEST). NOTIFY PRODUCTION CONTROL, AND CFT IN ADVANCE. COORDINATION TIMES AND DATES WILL BE PROVIDED.

Test Certification: CWI CERTIFICATE Rev:

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT Specification: ASNT 2055 SNT-TC-1A Rev: 1996

Method: VT-PP-001 Rev: B Specification: PP475 Rev: 8 Specification: PP479 Rev: 1

> IDC Count: 5 Dwg Count: 0 Pgm Count: 0 QAP Count: 7 NDT Count: 0 WPS Count: 1

Vendor Part ID: A500 GR B_72 Mfg Part ID: A500 GR B

WPS390-PPPL Rev:0 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

(F)

Operation QtyPer StartQty Resource EndQt Drawing ID / Rev

Sub: 1 / Seq: 71 265-PAINT BOOTH 1.00 1.00 1.00 SE121 / A

> BAKE OUT AT 150 DEGREES C (302F) FOR 6 HOURS TO REMOVE MOISTURE IN PREPARATION FOR THE NEXT SEQUENTIAL OPERATION (VACUUM / LEAK TESTING). NOTE THAT THIS SEQUENCE MUST BE COORDINATED WITH THE VACUUM TESTING SERVICE OPERATION. CONTACT ENGINEERING (DOUG McCORKLE) AND SUBCONTRACT ADMINISTRATOR (BOB JOACHIM) PRIOR TO BEGINNING FOR TIMING AND COORDINATION. CYCLE START TIME WILL BE



Page: 10 Date:12/23/03 **User ID: MCCORKLE**

Workorder 64880/1.0

Sub: 1 / Seq: 72

(F)

Part ID Qty Drawing ID / Rev Engineer

SE121-003P / --

BLUE/DOUG MCCORKLE

ADVISED.

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Furnace charts: FURNACE CHART

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 5 Pgm Count: 0

1.00

QAP Count: 4

NDT Count: 0

WPS Count: 0

Vendor Part ID: A500 GR B_72

Mfg Part ID: A500 GR B

Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev 1.00

230-FABRICATION - WEIDNER

VACUUM TEST PREPARATION:

PRIOR TO BEGINNING, NOTIFY ENGINEERING / CFT THE PART IS READY AND AVAILABLE FOR POSSIBLE CUSTOMER HOLD / WITNESS POINT INSPECTION. HOLD FOR RESPONSE AND/OR FURTHER DIRECTION.

SETUP AND PREPARE FOR SUBCONTRACT VACUUM TESTING (WHICH WILL BE PERFORMED AT SEQUENCE 73) AND RADIOGRAPHIC INSPECTION (WHICH WILL BE PERFORMED AT SEQUENCE 75) AS FOLLOWS:

INSTALL THE SEAL AND VACUUM TEST CAP TO THE CONFLAT FLANGE

INSTALL AND TORQUE THE FLANGE INSTALLATION BOLTS PER MANUFACTURERS INSTRUCTIONS.

1.00

LAYOUT ALL STRUCTURAL WELDS FOR 100% X-RAY.

ASSIST WITH THE VACUUM TEST AND ENSURE THE FOLLOWING PRECAUTIONS ARE OBSERVED:

Caution: The vacuum test procedure will subject the vessel to an internal vacuum that generates tremendous forces. Failure of any part of the vessel or test equipment could result in implosive/explosive reactions, ejected parts

and dangerous noise levels. Unnecessary personnel should vacate the test area whenever a vacuum is present in the vessel (Except essential personnel).

Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

QAP Count: 1

NDT Count: 0

WPS Count: 0

Operation Sub: 1 / Seq: 73 Resource 450-SUBLET

1.00 1.00

OtvPer

1.00 SE121-003P / --

StartOty EndOt Drawing ID / Rev

Service ID MISC/SUBLET

(F) VACUUM TEST THE PORT EXTENSION SUB-ASSEMBLY (WELDED TO THE VESSEL WALL) PER PP478

> MTM CONTRACT ADMINISTRATOR NOTE: THIS SEQUENCE MUST BE COORDINATED WITH THE PRECEDING (BAKE OUT) OPERATION. PRODUCTION CONTROL WILL INIATE COORDINATION PRIOR TO BEGINNING THE BAKE OUT OPERATION.

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Customer: PPPL

Test Certification: VACUUM TEST CERTIFICATE Rev:

Specification: ASTM E 498 Rev: 95 Specification: PP475 Rev: 8



Page: 11 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 1 SE121-003P / -- BLUE/DOUG MCCORKLE

Specification: PP478 Rev: 1

IDC Count: 0 Dwg Count: 1 Pgm Count: 0 QAP Count: 7 NDT Count: 0 WPS Count: 0

Vendor Part ID: A500 GR B_72 Mfg Part ID: A500 GR B

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 1 / Seq: 75818-MQS CONTRACTOR X-RAY1.001.001.00\$E121-001P /

(F) 100% RADIOGRAPHIC INSPECT THE 5 STRUCTURAL WELDS (LOCATIONS IDENTIFIED ON PART) PER THE FOLLOWING:

ASME SECTION VIII, DIVISION 1, UW-51

MAP THE FILM NUMBERS AND FILM LOCATIONS ON PART DRAWING.

Specification: ASME SECTION VIII

Map(s): RADIOGRAPHIC INSPECTION MAP Rev:

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Material Type: 625 INCONEL

Test Certification: RADIOGRAPHIC CERTIFICATE Rev:

Material Thickness: .375" Specification: 20.A.100 Rev: Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 9 NDT Count: 0 WPS Count: 0

Vendor Part ID: A500 GR B_72

Mfg Part ID: A500 GR B

Operation	Resource	QtyPer	StartQty	EndQt	Drawing ID / Rev
Sub: 1 / Seq: 80	817-SMX LASER	1.00	1.00	1.00	SE121-001P-1MTM / 2A

(F) INSPECTION OPERATION # 3

RE-INSPECT / VERIFY PART PROFILE IS WITHIN APPLIED TOLERANCE AND RECORD PRIMARY STRUCTURAL WELDING SHRINKAGE / DISTORTION.

INSPECTION POINT GRID: 6" CENTERS THROUGHOUT WITH 1" CENTERS AT AND NEAR WELD JOINTS.

INCLUDE AT LEAST THREE DATUM TARGETS IN EACH POINT CLOUD SCAN FOR ALIGMENT / VERIFICATION TO THE 3D MODEL.

RECORD ACTUAL (INDIVIDUAL) MEASUREMENTS ON INSPECTION FORM (SE121-2MTM). RECORD ACTUAL (HIGH/LOW RANGE) ON MTM IDC

INSPECT AND RECORD MAGNETIC PERMEABILITY.

REPORT ANY OUT OF TOLERANCE READINGS VIA MTM NCR.

NOTIFY ENGINEERING (DOUG McCORKLE) FOR EVALUATION OF RESULTS PRIOR TO RELEASING PART.

ENSURE THE FIXTURE DATUM TARGETS ARE ADEQUATELY POSITIONED FOR THE NEXT SEQUENTIAL INSPECTION.

 $RECORD\ PROFILE,\ MAGNETIC\ PERMEABILITY,\ AND\ MATERIAL\ THICKNESS\ ON\ SE121-001P-1MTM,\ RESULTS\ MUST\ BE\ RECORDED,\ REVIEWED\ BY\ ENGINEERING,$

SCANNED AND LINKED PRIOR TO COMPLETING THE INSPECTION SEQUENCE.

Part Number: SE121-001P

Part Description: PVVS PRIMARY WELDMENT

Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5

W:64880/1-0 /Inc Matl /Inc Legs



Page: 12 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 1 SE121-003P / -- BLUE/DOUG MCCORKLE

Map(s): SE121-001P-1MTM Rev: 2A

IDC Count: 2 Dwg Count: 1 Pgm Count: 0 QAP Count: 6 NDT Count: 0 WPS Count: 0

Vendor Part ID: A500 GR B_72 Mfg Part ID: A500 GR B

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 1 / Seq: 90230-FABRICATION - WEIDNER1.001.001.00\$E121-002P / --

(F) LAYOUT AND PLASMA CUT THE PORT EXTENSION TUBE OFF THE VESSEL WALL (NORMAL TO VESSEL SURFACE) PER DRAWING.

PLASMA CUT THE PORT OPENING INTO THE VESSEL WALL PER DRAWING (CUT UNDERSIZE ALLOWING FOR GRINDING / SIZING TO PORT EXTENSION I.D.) USE A

CIRCLE CUTTING DEVICE TO ENSURE PROPER SIZE AND ROUNDNESS.

REMOVE RECAST / HEAT AFFECTED ZONE FROM EACH CUT SURFACE BY GRINDING. GRIND / BLEND THE PORT EXTENSION EDGE AND VESSEL WALL OPENING

SMOOTH (MAINTAINING PROPER SIZE AND RELATIONSHIP TO THE I.D. OF THE PORT EXTENSION TUBE).

PREP THE EDGES OF THE PORT STUB AND PORT EXTENSION TUBE FOR RE-INSTALLATION.

 $POSITION\ AND\ SKIP\ WELD\ THE\ BACKING\ RING\ (SE121-003P-4)\ IN\ PLACE\ (TO\ THE\ END\ OF\ THE\ DETACHED\ PORT\ EXTENSION\ TUBE)\ PER\ DRAWING\ SE121-003P-4)$

RE-INSTALL THE PORT EXTENSION ASSEMBLY TO THE PORT STUB AND WELD IN PLACE PER DRAWING SE121-003P.

GRIND AND BLEND THE PORT EXTENSION INTERIOR WELD SMOOTH.

CWI VISUAL INSPECT EACH WELD PASS 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER AWS D1.6, 6.29.1.

ENSURE ALL COSMETIC WELDING AND BLENDING IS COMPETE, ENSURE ALL INTERIOR SURFACES ARE POLISHED AND CLEANED, AND PREPARE PART FOR

FINAL (EXTERIOR) BLAST AND FINAL INSPECTION.

Test Certification: VISUAL INSPECTION CERT Rev:

Part Number: SE121-003P

Part Description: NCSX PVVS COMPLETE Specification: ASNT 2055 SNT-TC-1A Rev: 1996

Method: VT-PP-001 Rev: B Specification: PP475 Rev: 8

IDC Count: 5 Dwg Count: 1 Pgm Count: 0 QAP Count: 6 NDT Count: 0 WPS Count: 1

Vendor Part ID: A500 GR B_72 Mfg Part ID: A500 GR B

WPS390-PPPL Rev:0 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

 Operation
 Resource
 QtyPer
 StartQty
 EndQt
 Drawing ID / Rev

 Sub: 1 / Seq: 100
 817-SMX LASER
 1.00
 1.00
 1.00
 SE121-001P-1MTM / 2A

(F) INSPECT PROFILE IN THE AREA OF THE PORT STUB / PORT EXTENSION.

INCLUDE AT LEAST THREE DATUM TARGETS IN EACH POINT CLOUD SCAN FOR ALIGMENT / VERIFICATION TO THE 3D MODEL.

INSPECT MAGNETIC PERMEABILITY IN THE AREA OF THE PORT STUB / PORT EXTENSION WELDING.

INSPECT THE INTERIOR SURFACE FINISH OF THE PORT EXTENSION.

RECORD IDC DATA Part Number: SE121-003P

Part Description: NCSX PVVS COMPLETE



Page: 13 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

> Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5

Map(s): SE121-001P-1MTM Rev: 2A

IDC Count: 3 Dwg Count: 1 Pgm Count: 0 OAP Count: 6 NDT Count: 0 WPS Count: 0

WPS Count: 0

Vendor Part ID: 304_11 Mfg Part ID: 304 MATERIAL

Operation EndQt Drawing ID / Rev Resource **QtyPer** StartQty

Sub: 1 / Seq: 105 230-FABRICATION - WEIDNER 1.00 1.00 1.00 SE121-003P / --

INSTALL SUPPORT DEVICES TO LOCATE THE PART BACK ONTO THE FIXTURE SURFACE (UNRESTRAINED) FOR FINAL INSPECTION. (U)

Dwg Count: 1 Drw N/A IDC N/A IDC Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0

Vendor Part ID: 304_14 Mfg Part ID: 304 MATERIAL

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource

Sub: 1 / Seq: 110 260-SANDBLAST 1.00 1.00 1.00 SE121 / A

(F) MASK THE INTERIOR SURFACES AND CONFLAT FLANGE FACE. BLAST THE OUTSIDE SURFACE 100% USING 220 GRIT VIRGIN ALUMINUM OXIDE.

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 5 NDT Count: 0 WPS Count: 0 Pgm Count: 0 QAP Count: 1

Vendor Part ID: 304L_5

Mfg Part ID: 304L STAINLESS

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource

Sub: 1 / Seq: 115 1.00 1.00 1.00 SE121-003P / --230-FABRICATION - WEIDNER

(F) SET THE PVVS ONTO THE TEMPORARY SUPPORT DEVICES AND TACK WELD IN PLACE

INSTALL TOOLING BALLS TO THE PERIPHERY, TACK WELD IN PLACE. FINAL LOCATION / POSITION TO BE DETERMINED BY Q/A AND APPROVED BY

ENGINEERING PRIOR TO WELDING.

ENSURE ADEQUATE INERT GAS COVERAGE IS MAINTAINED (on both surfaces) THROUGHOUT THE WELDING AND COOLING PROCESS TO AVOID OXIDATION /

DISCOLORATION)

REMOVE MASKING AND PROTECTIVE PLASTIC

CLEAN PART PER PP475

INSTALL NAMEPLATE PER ENGINEERING DIRECTION

Part Number: SE121-003P Part Description: NCSX PVVS Specification: PP475 Rev: 8

> IDC Count: 5 Dwg Count: 1 Pgm Count: 0 OAP Count: 3 NDT Count: 0 WPS Count: 1

Vendor Part ID: 304_13 Mfg Part ID: 304 MATERIAL WPS390-PPPL Rev:0 GTAW MAN



Page: 14 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 1 / Seq: 120 1.00 SE121-003P / --817-SMX LASER 1.00 1.00

(F) FINAL DIMENSIONAL INSPECTION / POTENTIAL CUSTOMER SOURCE INSPECTION.

> PRIOR TO BEGINNING, NOTIFY ENGINEERING / CFT THE PART IS READY AND AVAILABLE FOR POSSIBLE CUSTOMER HOLD / WITNESS POINT INSPECTION. HOLD FOR RESPONSE AND/OR FURTHER DIRECTION.

FINAL PROFILE INSPECTION. INSPECT AND RECORD THE VESSEL PROFILE, TRIM LINES (20 DEGREE SURFACES), AND PORT EXTENSION POSITION.

INCLUDE AT LEAST THREE DATUM TARGETS IN EACH POINT CLOUD SCAN FOR ALIGMENT / VERIFICATION TO THE 3D MODEL.

FINAL MAGNETIC PERMEABLITY VERIFICATION.

VERIFY MAGNETIC PERMEABILITY OF ALL STRUCTURAL WELDS (1" increments), VESSEL WALL (6" grid), PORT EXTENSION TUBE (6" grid), CONFLAT FLANGE,

FLANGE TO TUBE WELD.

RECORD THE COORDINANTS OF EACH ATTACHED MONUMENT (ENGINEERING INPUT REQUIRED). THESE COODINANTS WILL BE USED TO SETUP FOR PROFILE

VERIFICATION AT PRINCETON.

FINAL INTERIOR SURFACE FINISH VERIFICATION. VISUAL INSPECT THE ENTIRE INTERIOR. VERIFY THE ENTIRE SURFACE IS SMOOTH AND FREE OF PITS, DENTS, IRREGULARITIES, GRINDING / SANDING MARKS, ETC... ENSURE THE ENTIRE SURFACE CAN BE WIPED CLEAN WITH A LINT FREE WIPE WITHOUT SNAGGING. INSPECT (APROXIMATE 6" GRID) WITH PROFILOMETER. REFERENCE PP479 RECORD FINAL SURFACE FINISH INFORMATION ON THE INSPECTION DRAWING

RECORD IDC DATA

Part Number: SE121-003P

Part Description: NCSX PVVS COMPLETE

Specification: ASME B46.1 Rev: 95

Certification: MAG. PERM. CERTIFICATION Certification: PROFILE CERTIFICATION Certification: INT. SURF. FINISH CERT.

Specification: PP475 Rev: 8

Specification: PP477 Rev: 5 Specification: PP476 Rev: 4

Specification: PP479 Rev: 1

Map(s): SE121-001P-1MTM Rev: 2A

WPS Count: 0 IDC Count: 5 Dwg Count: 1 Pgm Count: 0 QAP Count: 11 NDT Count: 0

Sub ID Qty Drawing ID / Rev Part ID 14 SE121-001P-2 PANEL # 1 SE121-001P / A

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev

1.00 (C) INSPECT BLANK SIZE PER DEVELOPMENT DRAWING (AUDIT DIMENSIONS WILL BE PROVIDED BY DOUG McCORKLE)

MTTRAVLR.qrp W:64880/1-0 /Inc Matl /Inc Legs

Vendor Part ID: 316L_100

1.00

Sub: 14 / Seq: 10

820-RECEIVING INSPECTION

Parent Sub:1 Op:10

1.00 SE121-001P / A

Part ID

Workorder

64880/1.0

Page: 15 Date: 12/23/03 **User ID: MCCORKLE**

INSPECT MATERIAL THICKNESS PER PP477

VISUAL INSPECT SURFACE FINISH (PANEL SURFACE SHOULD BE A SMOOTH MILL PRODUCED SURFACE, WITHOUT SCRAPES, GOUGES, HEAVY PITS, ETC... IT SHOULD BE IN A CONDITION THAT CAN BE READILY POLISHED WITHOUT EXCESSIVE MATERIAL REMOVAL (CONTACT ENGINEERING (DOUG McCORKLE IF FURTHER CLARIFICATION IS NEEDED)

SAMPLE INSPECT MAGNETIC PERMEABILITY PER PP476, AND ASTM A800, SUPPLIMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT). SAMPLE LOT SIZE: AT LEAST 10 EVENLY SPACED LOCATIONS.

Qty Drawing ID / Rev

SE121-003P / --

RECORD IDC DATA

Specification: ASTM A800 Rev: 2001 Part Number: SE121-001P-2 PANEL 1 Part Description: DIE FORMED PANEL

Customer: PPPL

Specification: ASTM B443 Rev: 00 Specification: ASME B46.1 Rev: 95 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP475 Rev: 8 Specification: ASTM A380 Rev: 99

IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 10 NDT Count: 0 WPS Count: 0

Piece # Drawing ID / Rev Vendor **Dimensions** 10 SE121-001P-2 PANEL # 1-PANEL BLANK .375" THK INCONEL 625 SE121 / --1810

Vendor Part ID: SE121-001P-2 PANEL # 1

(C) PANEL BLANK AWJ CUT FROM .375" INCONEL 625 TO PROVIDED GEOMETRICAL SHAPE

(SE121-001P-2 PANEL # 1.DXF, REV. --)

MATERIAL REQUIREMENTS: INCONEL 625 (UNS N06625) PER ASTM B 443-00 ANNEALED

MAGNETIC PERMEABILITY SHALL NOT EXCEED 1.00 (REF. ASTM A800).

SURFACE MUST BE PROTECTED FROM CONTACT WITH IRON AND IRON ALLOY MATERIALS

CERTS & MILL TEST REPORTS REQ'D WITH SHIPMENT.

APPROXIMATE OVERALL SIZE: 54.97*76.37

Material Certification:

Part Number: SE121-001P-2 PANEL 1 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 2001 Specification: ASTM B443 Rev: 00 Specification: ASTM B46.1 Rev: 95

QAP Count: 6

Engineer

BLUE/DOUG MCCORKLE

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 14 / Seq: 18 1.00 1.00 105-DEBURR PLT 1 LOW BAY SE121-001P / A (C) RADIUS ALL CUT EDGES PRIOR TO FORMING Specification: PP475 Rev: 8 WPS Count: 0 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0



Page: 16 Date:12/23/03 **User ID: MCCORKLE**

WPS Count: 0

Workorder 64880/1.0

Sub: 14 / Seq: 30

Part ID Qty Drawing ID / Rev Engineer SE121-003P / --BLUE/DOUG MCCORKLE

Vendor Part ID: 304_802 Mfg Part ID: 304 MATERIAL

Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 14 / Seq: 20 1.00 SE121-001P / A 341-PACIFIC 750 1.00 1.00

(F) 1ST FORM OPERATION:

LOAD, ALIGN, AND BOLT DIE SET # MTMFX-2883 - MTMFX-2884 INTO THE 750 TON HYDRAULIC PRESS.

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

ENSURE THE PANEL BLANK IS CLEAN AND FREE OF FOREIGN MATTER.

LOAD THE PANEL BLANK INTO THE DIE SET.

HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2903.

NOTE THAT THE FINAL PANEL TO GAGE GAP TOLERANCE IS .094" MAX. IT IS DESIRED TO GET AS CLOSE TO THIS AS POSSIBLE PRIOR TO ANNEALING. CLOSELY WATCH THE FORMING, WRINKLING, AND SPRING-BACK CHARACTERISTICS OF THE MATERIAL DURING THE FORMING PROCESS. WHEN IT'S APPARENT THE MATERIAL IS WORK HARDENING TO A DEGREE THAT FORMING BECOMES DIFFICULT, OR THE PHYSICAL INTEGRITY OF THE MATERIAL IS AT RISK, PROCEED TO THE NEXT SEQUENTIAL OPERATION (BLAST AND ANNEAL). A FINAL FORMING SEQUENCE IS PROVIDED FOR "FINAL SIZING" AFTER THE MATERIAL HAS BEEN ANNEALED.

ENSURE THE PANEL MATERIAL EXTENDS BEYOND THE PERIMETER OF THE GAGE (ENOUGH TO PROVIDE ADEQUATE STOCK ALLOWANCE FOR RE-POSITIONING, RE-STRIKING, AND ACCURATE TRIMMING AFTER ANNEALING).

Part Number: SE121-001P-2 PANEL 1 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

WPS Count: 0 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0

QAP Count: 1

NDT Count: 0

Pgm Count: 0

Vendor Part ID: 316-L 340 Mfg Part ID: 316-L MATERIAL

Operation Resource StartQty EndQt Drawing ID / Rev **QtyPer** Sub: 14 / Seq: 25 260-SANDBLAST 1.00 1.00 1.00 SE121-001P / A

(C) SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE INITIAL

FORMING PROCESS.

MAINTAIN AN APPROXIMATE BLAST ANGLE OF 20 TO 40 DEGREES

BLOW OFF ALL RESIDUAL BLAST MEDIA PRIOR TO HANDLING.

Specification: PP475 Rev: 8

Vendor Part ID: 316L_15

Operation StartQty EndQt Drawing ID / Rev Service ID Resource QtyPer 1.00 SE121-001P / A THRML TR/NA SA

Dwg Count: 0

(C) SOLUTION ANNEAL FORMED PANEL PER THE FOLLOWING:

520-SUBLET, EXOTIC HEAT TREAT

ATTACH A MINIMUM OF THREE EQUALLY SPACED THERMOCOUPLES TO THE FORMED PANEL CHARGE FURNACE AND HEAT PART UNTIL THERMOCOUPE READINGS ARE WITHIN 1900 +/-15F.

1.00

IDC Count: 0



Page: 17 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

HOLD PART TEMPERATURE AT 1900 DEGREES F. (+/- 15 DEGREES) HOLD FOR 45 MINUTES (+/ 5 MINUTES)

RAPID COOL (VIA. WATER QUENCHING OR FORCED AIR CIRCULATION) TO 1000 DEGREES F. OPEN AIR COOL TO AMBIENT TEMP.

Specification: AMS2774 Rev: JUL95 Certification: H/T CERTIFICATE Part Number: SE121-001P-2 PANEL 1 Part Description: DIE FORMED PANEL

Customer: PPPL

Furnace charts: FURNACE CHART

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 6 NDT Count: 0 WPS Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 14 / Seq: 31 820-RECEIVING INSPECTION 1.00 1.00 1.00 SE121-001P / A (U) REVIEW HEAT TREAT CERTIFICATE AND FURNACE CHART IDC Count: 1 Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 0

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 14 / Seq: 35 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121-001P / A

(C) VISUAL INSPECT SURFACE FOR DAMAGE, PITTING, GOUGES, SCRAPES ETC.....

> ON THE INSIDE (CONCAVE SURFACE), LOOK FOR ANY SURFACE DEFECTS OR IRREGULARITIES THAT MAY INHIBIT ACHIEVING THE REQURIED 32 MICRO-INCH FINISH REQURIEMENT. ON THE OUTSIDE (CONVEX SURFACE), VERIFY THE SURFACE FINISH STILL MEETS THE REQUIREMENTS OF ASTM B 443-00.

NOTIFY ENGINEERING (DOUG McCORKLE) FOR CONCURRENCE

VERIFY MAGNETIC PERMEABILITY AND RECORD I.D.C. DATA

Part Number: SE121-001P-2 PANEL 1 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8 Specification: ASTM B443 Rev: 00 Specification: PP476 Rev: 4

> IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 5 NDT Count: 0 WPS Count: 0

Operation Resource OtvPer StartQty EndQt Drawing ID / Rev Sub: 14 / Seq: 40 SE121-001P / A 341-PACIFIC 750 1.00 1.00 1.00

(C) 2ND FORMING OPERATION

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

LOAD THE PREFORMED / ANNEALED PANEL INTO THE DIE SET.

"RE-STRIKE" HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2903. PANEL TO GAGE GAP

TOLERANCE: .094" MAX.

NOTIFY INSPECTOR FOR Q/A IDC VERIFICATION

Part Number: SE121-001P-2 PANEL 1 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8



Page: 18 Date:12/23/03 **User ID: MCCORKLE**

Workorder 64880/1.0

Part ID

Drawing ID / Rev SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

IDC Count: 1

Dwg Count: 0

Pgm Count: 0

QAP Count: 3 NDT Count: 0 WPS Count: 0

Operation Sub: 14 / Seq: 50

260-SANDBLAST

StartQty EndQt Drawing ID / Rev **QtyPer** 1.00 1.00 1.00 SE121-001P / A

(C)

SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE FINAL FORMING

PROCESS.

Resource

MAINTAIN AN APPROXIMATE 20 - 40 DEGREE BLAST ANGLE

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0

Vendor Part ID: 316-L_340 Mfg Part ID: 316-L MATERIAL

Operation

(F)

Resource

QtyPer StartQty EndQt Drawing ID / Rev

Sub: 14 / Seq: 60 230-FABRICATION - WEIDNER 1.00 1.00 1.00 SE121-001P / A

TRIM PERIMETER TO PROVIDED TRIM-LINES (LEAVING STOCK FOR POSITIONING AND FITTING ON THE FAB FIXTURE). NOTE THAT INSTALLING THE WELD

PREP IS NOT REQUIRED AT THIS STAGE (ADDITIONAL FITTING / TRIMMING WILL BE REQUIRED AT INSTALLATION)

HIGH PRESSURE WASH PER PP475

NOTIFY Q/A FOR FINAL PANEL PROFILE CONFIRMATION PRIOR TO COMPLETING THE POLISHING AND INSTALLATION OF PROTECTIVE PLASTIC

SAND AND POLISH THE INSIDE SURFACE 100% TO ACHIEVE A 32 MICRO SURFACE FINISH (WITH THE EXCEPTION OF THE WELDING / TRIMMING ZONES).

CLEAN PANEL PER PP475

APPLY PROTECTIVE PLASTIC FILM (CONTACT DOUG McCORKLE FOR MATERIAL)

STAGE PANEL FOR INSTALLATION

Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

OAP Count: 1

NDT Count: 0

WPS Count: 0

Vendor Part ID: 304L_12 Mfg Part ID: 304L MATERIAL

Operation Sub: 14 / Seq: 70 Resource

805-INPROCESS INSPECTION - PLA

OtvPer 1.00

1.00

StartOtv

EndQt Drawing ID / Rev 1.00 SE121-001P / A

(F)

VERIFY PROFILE TO INSPECTION GAGE # MTMFX-2903. GAP TOLERANCE: .094" MAX. RECORD ACTUAL GAP READINGS ON INSPECTION DRAWING VERIFY PART PERIMETER EXCEEDS GAGE PERIMETER FOR TRIMMING AND FITTING AT ASSEMBLY

INSPECT AND RECORD INTERIOR SIDE SURFACE FINISH (LESS PERIMETER / WELD ZONES) AND RECORD ACTUAL READINGS ON INSPECTION DRAWING INSPECT MAGNETIC PERMEABILITY PER PP476 AND ASTM A800, SUPPLEMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT. THE SURFACES OF THE PVVS SHELL AND PORT EXTENSION SHALL BE CHECKED AND DOCUMENTED ON A 6" GRID. THE SURFACES AT AND NEAR WELDS WILL BE CHECKED ON A 1" GRID.

RECORD ACTUAL PERMEABILITY READINGS ON INSPECTION DRAWING

INSPECT MATERIAL THICKNESS PER PP477 (6" GRID)

RECORD ACTUAL MATERIAL THICKNESS ON INSPECTION DRAWING

Test Certification: SE121-001P-10MTM Rev: 2A

Part Number: SE121-001P-2 PANEL 1





Page: 19 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 1 SE121-003P / -- BLUE/DOUG MCCORKLE

Part Description: DIE FORMED PANEL Specification: ASME B46.1 Rev: 95 Specification: ASTM A800 Rev: 2001

Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP479 Rev: 1

IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 9 NDT Count: 0 WPS Count: 0

Vendor Part ID: INCONEL 625_2 Mfg Part ID: INCONEL 625

Sub ID Part ID Qty Drawing ID / Rev

15 SE121-001P-2 PANEL # 2 1 /
Parent Sub:1 Op:10

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 15 / Seq: 10820-RECEIVING INSPECTION1.001.001.00\$E121-001P / A

(C) INSPECT BLANK SIZE PER DEVELOPMENT DRAWING (AUDIT DIMENSIONS WILL BE PROVIDED BY DOUG McCORKLE)

INSPECT MATERIAL THICKNESS PER PP477

VISUAL INSPECT SURFACE FINISH (PANEL SURFACE SHOULD BE A SMOOTH MILL PRODUCED SURFACE, WITHOUT SCRAPES, GOUGES, HEAVY PITS, ETC... IT SHOULD BE IN A CONDITION THAT CAN BE READILY POLISHED WITHOUT EXCESSIVE MATERIAL REMOVAL (CONTACT ENGINEERING (DOUG McCORKLE IF FURTHER CLARIFICATION IS NEEDED)

SAMPLE INSPECT MAGNETIC PERMEABILITY PER PP476, AND ASTM A800, SUPPLIMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT). SAMPLE LOT SIZE: AT LEAST 10 EVENLY SPACED LOCATIONS.

RECORD IDC DATA

Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 2001

Customer: PPPL

Specification: ASTM B443 Rev: 00 Specification: ASME B46.1 Rev: 95 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: ASTM A380 Rev: 99

IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 10 NDT Count: 0 WPS Count: 0

Piece #Part IDQtyDrawing ID / RevVendorDimensions10SE121-001P-2 PANEL # 2-PANEL BLANK .375" THK INCONEL 6251.0SE121 / --1810

Vendor Part ID: SE121-001P-2 PANEL # 2

(C) PANEL BLANK AWJ CUT FROM .375" INCONEL 625 TO PROVIDED GEOMETRICAL SHAPE

(SE121-001P-2 PANEL # 2.DXF, REV. --)

MATERIAL REQUIREMENTS: INCONEL 625 (UNS N06625) PER ASTM B 443-00 ANNEALED



Page: 20 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

MAGNETIC PERMEABILITY SHALL NOT EXCEED 1.00 (REF. ASTM A800).

SURFACE MUST BE PROTECTED FROM CONTACT WITH IRON AND IRON ALLOY MATERIALS

CERTS & MILL TEST REPORTS REQ'D WITH SHIPMENT.

APPROXIMATE OVERALL SIZE: 35.07*44.03

Material Certification:

Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 01 Specification: ASTM B443 Rev: 00 Specification: ASTM B46.1 Rev: 95

QAP Count: 6

Operation	Resource	QtyPer	StartQty	EndQt	Drawing ID / Rev			
Sub: 15 / Seq: 18	105-DEBURR PLT 1 LOW BAY	1.00	1.00	1.00	SE121-001P / A			
(C)	RADIUS ALL CUT EDGES PRIOR TO FORMING							
	Specification: PP475 Rev: 8							
	IDC Coun	t:0	Dwg Cou	nt: 0	Pgm Count: 0	QAP Count: 1	NDT Count: 0	WPS Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 15 / Seq: 20 341-PACIFIC 750 1.00 1.00 SE121-001P / A

(C) 1ST FORM OPERATION:

LOAD, ALIGN, AND BOLT DIE SET # MTMFX-2885 - MTMFX-2886 INTO THE 750 TON HYDRAULIC PRESS.

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

ENSURE THE PANEL BLANK IS CLEAN AND FREE OF FOREIGN MATTER.

LOAD THE PANEL BLANK INTO THE DIE SET.

HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2904.

NOTE THAT THE FINAL PANEL TO GAGE GAP TOLERANCE IS .094" MAX. IT IS DESIRED TO GET AS CLOSE TO THIS AS POSSIBLE PRIOR TO ANNEALING. CLOSELY WATCH THE FORMING, WRINKLING, AND SPRING-BACK CHARACTERISTICS OF THE MATERIAL DURING THE FORMING PROCESS. WHEN IT'S APPARENT THE MATERIAL IS WORK HARDENING TO A DEGREE THAT FORMING BECOMES DIFFICULT, OR THE PHYSICAL INTEGRITY OF THE MATERIAL IS AT RISK, PROCEED TO THE NEXT SEQUENTIAL OPERATION (BLAST AND ANNEAL). A FINAL FORMING SEQUENCE IS PROVIDED FOR "FINAL SIZING" AFTER THE MATERIAL HAS BEEN ANNEALED.


ENSURE THE PANEL MATERIAL EXTENDS BEYOND THE PERIMETER OF THE GAGE (ENOUGH TO PROVIDE ADEQUATE STOCK ALLOWANCE FOR RE-POSITIONING, RE-STRIKING, AND ACCURATE TRIMMING AFTER ANNEALING).

Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 3 NDT Count: 0 WPS Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev



Major
Tool & Machine, Inc.

Operation

Sub: 15 / Seq: 31

Resource

820-RECEIVING INSPECTION

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE Sub: 15 / Seq: 22 1.00 1.00 1.00 230-FABRICATION - WEIDNER (C) CUT OUT A LIFTING EYE FROM THE EXCESS TRIM STOCK THAT WAS REMOVED DURING THE FORMING CYCLE. INSTALL AND WELD IT TO THE PERIPHERAL EDGE OF THE FORMED PANEL (WHICH STILL HAS EXCESS TRIM STOCK REMAINING). POSITIONING CONSIDERATIONS: 1. POSITION TO SUIT NORMAL HANDLING AND LIFTING. 2. POSITION TO SUIT SETTING IN A VERTICAL STANCE IN THE HEAT TREAT OVEN (WIDE SIDE DOWN). 3. SHAPE AND POSITION THE LIFTING HOOK FOR A "QUICK AND EASY GAFF HOOK STYLE GRAB" WHEN REMOVING THE PARTS FROM THE HOT OVEN FOR A RAPID COOLING CYCLE. Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 1 WPS115 Rev:1 GTAW MAN GTAW - Manual Fillers: INCONEL625_035_GMAW / INCONEL625_062_GTAW / INCONEL625_093_GTAW Notes: LIFTING HOOK TO PANEL EDGE Operation StartQty Resource **QtyPer** EndQt Drawing ID / Rev Sub: 15 / Seq: 25 260-SANDBLAST 1.00 1.00 1.00 SE121-001P / A SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE INITIAL (C) FORMING PROCESS. MAINTAIN AN APPROXIMATE BLAST ANGLE OF 20 TO 40 DEGREES BLOW OFF ALL RESIDUAL BLAST MEDIA PRIOR TO HANDLING. Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 NDT Count: 0 WPS Count: 0 Operation EndQt Drawing ID / Rev Service ID Resource OtvPer StartQty Sub: 15 / Seq: 30 1.00 1.00 SE121-001P / A THRML TR/NA SA 520-SUBLET, EXOTIC HEAT TREAT 1.00 SOLUTION ANNEAL FORMED PANEL PER THE FOLLOWING: (C) ATTACH A MINIMUM OF THREE EQUALLY SPACED THERMOCOUPLES TO THE FORMED PANEL CHARGE FURNACE AND HEAT PART UNTIL THERMOCOUPE READINGS ARE WITHIN 1900 +/-15F. HOLD PART TEMPERATURE AT 1900 DEGREES F. (+/- 15 DEGREES) HOLD FOR 45 MINUTES (+/ 5 MINUTES) RAPID COOL (VIA. WATER QUENCHING OR FORCED AIR CIRCULATION) TO 1000 DEGREES F. OPEN AIR COOL TO AMBIENT TEMP. Specification: AMS2774 Rev: JUL95 Certification: H/T CERTIFICATE Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL Customer: PPPL Furnace charts: FURNACE CHART Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 7 NDT Count: 0 WPS Count: 0

MTTRAVLR.qrp
W:64880/1-0 /Inc Matl /Inc Legs

EndQt Drawing ID / Rev

SE121-001P / A

OtvPer

1.00

StartQty

1.00



Page: 22 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE (R) REVIEW HEAT TREAT CERTIFICATE AND FURNACE CHART IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 15 / Seq: 35 1.00 SE121-001P / A 805-INPROCESS INSPECTION - PLA 1.00 1.00 VISUAL INSPECT SURFACE FOR DAMAGE, PITTING, GOUGES, SCRAPES ETC..... (R) ON THE INSIDE (CONCAVE SURFACE), LOOK FOR ANY SURFACE DEFECTS OR IRREGULARITIES THAT MAY INHIBIT ACHIEVING THE REQURIED 32 MICRO-INCH FINISH REQURIEMENT. ON THE OUTSIDE (CONVEX SURFACE), VERIFY THE SURFACE FINISH STILL MEETS THE REQUIREMENTS OF ASTM B 443-00. NOTIFY ENGINEERING (DOUG McCORKLE) FOR CONCURRENCE VERIFY MAGNETIC PERMEABILITY AND RECORD I.D.C. DATA Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL Specification: PP475 Rev: 8 Specification: ASTM B443 Rev: 00 Specification: PP476 Rev: 4 IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 5 NDT Count: 0 WPS Count: 0 Operation OtvPer StartQty EndQt Drawing ID / Rev Resource Sub: 15 / Seq: 40 341-PACIFIC 750 1.00 1.00 1.00 SE121-001P / A 2ND FORMING OPERATION (R) ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC.... LOAD THE PREFORMED / ANNEALED PANEL INTO THE DIE SET. "RE-STRIKE" HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2904. PANEL TO GAGE GAP TOLERANCE: .094" MAX. NOTIFY INSPECTOR FOR Q/A IDC VERIFICATION Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL Specification: PP475 Rev: 8 IDC Count: 1 Dwg Count: 0 Pgm Count: 0 OAP Count: 3 NDT Count: 0 WPS Count: 0 Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 15 / Seq: 50 260-SANDBLAST 1.00 1.00 1.00 SE121-001P / A (F) SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE FINAL FORMING PROCESS. Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0 Vendor Part ID: SE120-002-2 PANEL 3 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev



Page: 23 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE Sub: 15 / Seq: 60 1.00 1.00 1.00 SE121-001P / A 230-FABRICATION - WEIDNER (F) TRIM PERIMETER TO PROVIDED TRIM-LINES (LEAVING STOCK FOR POSITIONING AND FITTING ON THE FAB FIXTURE). NOTE THAT INSTALLING THE WELD PREP IS NOT REQUIRED AT THIS STAGE (ADDITIONAL FITTING / TRIMMING WILL BE REQUIRED AT INSTALLATION) HIGH PRESSURE WASH PER PP475 NOTIFY Q/A FOR FINAL PANEL PROFILE CONFIRMATION PRIOR TO COMPLETING THE POLISHING AND INSTALLATION OF PROTECTIVE PLASTIC SAND AND POLISH THE INSIDE SURFACE 100% TO ACHIEVE A 32 MICRO SURFACE FINISH (WITH THE EXCEPTION OF THE WELDING / TRIMMING ZONES). **CLEAN PANEL PER PP475** APPLY PROTECTIVE PLASTIC FILM (CONTACT DOUG McCORKLE FOR MATERIAL) STAGE PANEL FOR INSTALLATION Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 NDT Count: 0 WPS Count: 0 Operation EndQt Drawing ID / Rev Resource OtvPer StartOtv Sub: 15 / Seq: 70 805-INPROCESS INSPECTION - PLA 1.00 SE121-001P / A 1.00 1.00 (F) VERIFY PROFILE TO INSPECTION GAGE # MTMFX-2904. GAP TOLERANCE: .094" MAX. RECORD ACTUAL GAP READINGS ON INSPECTION DRAWING VERIFY PART PERIMETER EXCEEDS GAGE PERIMETER FOR TRIMMING AND FITTING AT ASSEMBLY INSPECT AND RECORD INTERIOR SIDE SURFACE FINISH (LESS PERIMETER / WELD ZONES) AND RECORD ACTUAL READINGS ON INSPECTION DRAWING INSPECT MAGNETIC PERMEABILITY PER PP476 AND ASTM A800, SUPPLEMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT. THE SURFACES OF THE PVVS SHELL AND PORT EXTENSION SHALL BE CHECKED AND DOCUMENTED ON A 6" GRID. THE SURFACES AT AND NEAR WELDS WILL BE CHECKED ON A 1" GRID. RECORD ACTUAL PERMEABILITY READINGS ON INSPECTION DRAWING INSPECT MATERIAL THICKNESS PER PP477 (6" GRID) RECORD ACTUAL MATERIAL THICKNESS ON INSPECTION DRAWING Test Certification: SE121-001P-10MTM Rev: 2A Part Number: SE121-001P-2 PANEL 2 Part Description: DIE FORMED PANEL Specification: ASME B46.1 Rev: 95 Specification: ASTM A800 Rev: 2001 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP479 Rev: 1 IDC Count: 3 Dwg Count: 0 Pgm Count: 0 OAP Count: 9 NDT Count: 0 WPS Count: 0 Sub ID Drawing ID / Rev Part ID Qty 16 SE121-001P-2 PANEL # 3 Parent Sub:1 Op:10

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 16 / Seq: 10 820-RECEIVING INSPECTION 1.00 1.00 1.00 SE121-001P / A (C)

INSPECT BLANK SIZE PER DEVELOPMENT DRAWING (AUDIT DIMENSIONS WILL BE PROVIDED BY DOUG McCORKLE)



Part ID

Workorder

64880/1.0

Page: 24 Date:12/23/03 **User ID: MCCORKLE**

INSPECT MATERIAL THICKNESS PER PP477

VISUAL INSPECT SURFACE FINISH (PANEL SURFACE SHOULD BE A SMOOTH MILL PRODUCED SURFACE, WITHOUT SCRAPES, GOUGES, HEAVY PITS, ETC... IT SHOULD BE IN A CONDITION THAT CAN BE READILY POLISHED WITHOUT EXCESSIVE MATERIAL REMOVAL (CONTACT ENGINEERING (DOUG McCORKLE IF FURTHER CLARIFICATION IS NEEDED)

SAMPLE INSPECT MAGNETIC PERMEABILITY PER PP476, AND ASTM A800, SUPPLIMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT). SAMPLE LOT SIZE: AT LEAST 10 EVENLY SPACED LOCATIONS.

Qty Drawing ID / Rev

SE121-003P / --

RECORD IDC DATA

Part Number: SE121-001P-2 PANEL 3 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 2001

Customer: PPPL

Specification: ASTM B443 Rev: 00 Specification: ASME B46.1 Rev: 95 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5

Specification: ASTM A380 Rev: --

IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 10 NDT Count: 0 Vendor

Piece # Drawing ID / Rev **Dimensions** 10 SE121-001P-2 PANEL # 3-PANEL BLANK .375" THK INCONEL 625 SE121 / --1810

Vendor Part ID: SE121-001P-2 PANEL # 3

(C) PANEL BLANK AWJ CUT FROM .375" INCONEL 625 TO PROVIDED GEOMETRICAL SHAPE

(SE121-001P-2 PANEL # 1.DXF, REV. --)

MATERIAL REQUIREMENTS: INCONEL 625 (UNS N06625) PER ASTM B 443-00 ANNEALED

MAGNETIC PERMEABILITY SHALL NOT EXCEED 1.00 (REF. ASTM A800).

SURFACE MUST BE PROTECTED FROM CONTACT WITH IRON AND IRON ALLOY MATERIALS

CERTS & MILL TEST REPORTS REQ'D WITH SHIPMENT.

APPROXIMATE OVERALL SIZE: 54.97*76.37

Material Certification:

Part Number: SE121-001P-2 PANEL # 1 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 01 Specification: ASTM B443 Rev: 00 Specification: ASTM B46.1 Rev: 95

QAP Count: 6

Engineer

BLUE/DOUG MCCORKLE

WPS Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 16 / Seq: 18 1.00 1.00 105-DEBURR PLT 1 LOW BAY SE121-001P / A (C) RADIUS ALL CUT EDGES PRIOR TO FORMING Specification: PP475 Rev: 8 WPS Count: 0 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0



Date:12/23/03 **User ID: MCCORKLE**

Workorder 64880/1.0

(C)

Part ID Drawing ID / Rev Engineer

SE121-003P / --BLUE/DOUG MCCORKLE

StartQty EndQt Drawing ID / Rev Operation Resource QtyPer Sub: 16 / Seq: 20 1.00 1.00 1.00 SE121-001P / A 341-PACIFIC 750

(C) 1ST FORM OPERATION:

LOAD, ALIGN, AND BOLT DIE SET # MTMFX-2887 - MTMFX-2892 INTO THE 750 TON HYDRAULIC PRESS.

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

ENSURE THE PANEL BLANK IS CLEAN AND FREE OF FOREIGN MATTER.

LOAD THE PANEL BLANK INTO THE DIE SET.

HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2905.

NOTE THAT THE FINAL PANEL TO GAGE GAP TOLERANCE IS .094" MAX. IT IS DESIRED TO GET AS CLOSE TO THIS AS POSSIBLE PRIOR TO ANNEALING. CLOSELY WATCH THE FORMING, WRINKLING, AND SPRING-BACK CHARACTERISTICS OF THE MATERIAL DURING THE FORMING PROCESS. WHEN IT'S APPARENT THE MATERIAL IS WORK HARDENING TO A DEGREE THAT FORMING BECOMES DIFFICULT, OR THE PHYSICAL INTEGRITY OF THE MATERIAL IS AT RISK, PROCEED TO THE NEXT SEQUENTIAL OPERATION (BLAST AND ANNEAL). A FINAL FORMING SEQUENCE IS PROVIDED FOR "FINAL SIZING" AFTER THE MATERIAL HAS BEEN ANNEALED.

ENSURE THE PANEL MATERIAL EXTENDS BEYOND THE PERIMETER OF THE GAGE (ENOUGH TO PROVIDE ADEQUATE STOCK ALLOWANCE FOR RE-POSITIONING, RE-STRIKING, AND ACCURATE TRIMMING AFTER ANNEALING).

Part Number: SE121-001P-2 PANEL 3 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

IDC Count: 0 WPS Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0

Operation Resource OtvPer StartQty EndQt Drawing ID / Rev

Sub: 16 / Seq: 22 230-FABRICATION - WEIDNER 1.00 1.00

CUT OUT A LIFTING EYE FROM THE EXCESS TRIM STOCK THAT WAS REMOVED DURING THE FORMING CYCLE. INSTALL AND WELD IT TO THE PERIPHERAL

EDGE OF THE FORMED PANEL (WHICH STILL HAS EXCESS TRIM STOCK REMAINING).

POSITIONING CONSIDERATIONS:

1. POSITION TO SUIT NORMAL HANDLING AND LIFTING.

- 2. POSITION TO SUIT SETTING IN A VERTICAL STANCE IN THE HEAT TREAT OVEN (WIDE SIDE DOWN).
- 3. SHAPE AND POSITION THE LIFTING HOOK FOR A "QUICK AND EASY GAFF HOOK STYLE GRAB" WHEN REMOVING THE PARTS FROM THE HOT OVEN FOR A RAPID COOLING CYCLE.

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 NDT Count: 0 WPS Count: 1

Operation EndQt Drawing ID / Rev Resource **QtyPer** StartQty Sub: 16 / Seq: 25 1.00 SE121-001P / A 260-SANDBLAST 1.00 1.00


(C) SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE INITIAL

FORMING PROCESS.

MAINTAIN AN APPROXIMATE BLAST ANGLE OF 20 TO 40 DEGREES

BLOW OFF ALL RESIDUAL BLAST MEDIA PRIOR TO HANDLING.

Specification: PP475 Rev: 8



Part ID Workorder Drawing ID / Rev SE121-003P / --64880/1.0

Engineer BLUE/DOUG MCCORKLE

IDC Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0 Dwg Count: 0 Pgm Count: 0

Operation StartQty EndQt Drawing ID / Rev Service ID Resource **QtyPer** 520-SUBLET, EXOTIC HEAT TREAT Sub: 16 / Seq: 30 1.00 1.00 1.00 SE121-001P / A THRML TR/NA SA

SOLUTION ANNEAL FORMED PANEL PER THE FOLLOWING: (C)

> ATTACH A MINIMUM OF THREE EQUALLY SPACED THERMOCOUPLES TO THE FORMED PANEL CHARGE FURNACE AND HEAT PART UNTIL THERMOCOUPE READINGS ARE WITHIN 1900 +/-15F.

HOLD PART TEMPERATURE AT 1900 DEGREES F. (+/- 15 DEGREES) HOLD FOR 45 MINUTES (+/ 5 MINUTES)

RAPID COOL (VIA. WATER QUENCHING OR FORCED AIR CIRCULATION) TO 1000 DEGREES F. OPEN AIR COOL TO AMBIENT TEMP.

Specification: AMS2774 Rev: JUL95 Certification: H/T CERTIFICATE Part Number: SE121-001P-2 PANEL 3 Part Description: DIE FORMED PANEL

Customer: PPPL

Furnace charts: FURNACE CHART Specification: PP475 Rev: 8

> NDT Count: 0 WPS Count: 0 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 7

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 16 / Seq: 31 820-RECEIVING INSPECTION 1.00 1.00 1.00 SE121-001P / A

(U) REVIEW HEAT TREAT CERTIFICATE AND FURNACE CHART

Dwg Count: 0 WPS Count: 0 IDC Count: 1 Pgm Count: 0 QAP Count: 0 NDT Count: 0

Operation StartOty EndOt Drawing ID / Rev Resource OtvPer Sub: 16 / Seq: 35 805-INPROCESS INSPECTION - PLA 1.00 1.00 SE121-001P / A 1.00

(R) VISUAL INSPECT SURFACE FOR DAMAGE, PITTING, GOUGES, SCRAPES ETC.....

ON THE INSIDE (CONCAVE SURFACE), LOOK FOR ANY SURFACE DEFECTS OR IRREGULARITIES THAT MAY INHIBIT ACHIEVING THE REQURIED 32 MICRO-INCH

FINISH REQURIEMENT. ON THE OUTSIDE (CONVEX SURFACE), VERIFY THE SURFACE FINISH STILL MEETS THE REQUIREMENTS OF ASTM B 443-00.

NOTIFY ENGINEERING (DOUG McCORKLE) FOR CONCURRENCE

VERIFY MAGNETIC PERMEABILITY AND RECORD I.D.C. DATA

Part Number: SE121-001P-2 PANEL 3 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8 Specification: ASTM B443 Rev: 00 Specification: PP476 Rev: 4

> IDC Count: 1 Dwg Count: 0 QAP Count: 5 NDT Count: 0 WPS Count: 0 Pgm Count: 0

Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 16 / Seq: 40 1.00 1.00 SE121-001P / A 341-PACIFIC 750 1.00

(R) 2ND FORMING OPERATION



Date:12/23/03 **User ID: MCCORKLE**

Part ID Workorder Drawing ID / Rev 64880/1.0 SE121-003P / --

Engineer

BLUE/DOUG MCCORKLE

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

LOAD THE PREFORMED / ANNEALED PANEL INTO THE DIE SET.

"RE-STRIKE" HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2905. PANEL TO GAGE GAP

TOLERANCE: .094" MAX.

NOTIFY INSPECTOR FOR Q/A IDC VERIFICATION

Part Number: SE121-001P-2 PANEL 3 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0

Operation Resource OtvPer StartOtv EndQt Drawing ID / Rev Sub: 16 / Seq: 50 1.00 1.00 SE121-001P / A 260-SANDBLAST 1.00

SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE FINAL FORMING

PROCESS.

(R)

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 WPS Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 16 / Seq: 60 1.00 1.00 1.00 SE121-001P / A 230-FABRICATION - WEIDNER

(R) TRIM PERIMETER TO PROVIDED TRIM-LINES (LEAVING STOCK FOR POSITIONING AND FITTING ON THE FAB FIXTURE). NOTE THAT INSTALLING THE WELD

PREP IS NOT REQUIRED AT THIS STAGE (ADDITIONAL FITTING / TRIMMING WILL BE REQUIRED AT INSTALLATION)

HIGH PRESSURE WASH PER PP475

NOTIFY Q/A FOR FINAL PANEL PROFILE CONFIRMATION PRIOR TO COMPLETING THE POLISHING AND INSTALLATION OF PROTECTIVE PLASTIC

SAND AND POLISH THE INSIDE SURFACE 100% TO ACHIEVE A 32 MICRO SURFACE FINISH (WITH THE EXCEPTION OF THE WELDING / TRIMMING ZONES).

CLEAN PANEL PER PP475

APPLY PROTECTIVE PLASTIC FILM (CONTACT DOUG McCORKLE FOR MATERIAL)

STAGE PANEL FOR INSTALLATION

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 NDT Count: 0 WPS Count: 0

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 16 / Seq: 70 1.00 SE121-001P / A 805-INPROCESS INSPECTION - PLA 1.00 1.00

VERIFY PROFILE TO INSPECTION GAGE # MTMFX-2905. GAP TOLERANCE: .094" MAX. RECORD ACTUAL GAP READINGS ON INSPECTION DRAWING (R)

VERIFY PART PERIMETER EXCEEDS GAGE PERIMETER FOR TRIMMING AND FITTING AT ASSEMBLY INSPECT AND RECORD INTERIOR SIDE SURFACE FINISH (LESS PERIMETER / WELD ZONES) AND RECORD ACTUAL READINGS ON INSPECTION DRAWING

INSPECT MAGNETIC PERMEABILITY PER PP476 AND ASTM A800, SUPPLEMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE

PERMEABILITY RATHER THAN FERRITE CONTENT. THE SURFACES OF THE PVVS SHELL AND PORT EXTENSION SHALL BE CHECKED AND DOCUMENTED ON A 6"

GRID. THE SURFACES AT AND NEAR WELDS WILL BE CHECKED ON A 1" GRID.

RECORD ACTUAL PERMEABILITY READINGS ON INSPECTION DRAWING

INSPECT MATERIAL THICKNESS PER PP477 (6" GRID)



Page: 28 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

RECORD ACTUAL MATERIAL THICKNESS ON INSPECTION DRAWING

Test Certification: SE121-001P-10MTM Rev: 2A

Part Number: SE121-001P-2 PANEL 3 Part Description: DIE FORMED PANEL Specification: ASME B46.1 Rev: 95 Specification: ASTM A800 Rev: 2001

Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP479 Rev: 1

> IDC Count: 3 NDT Count: 0 WPS Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 9

Sub ID Part ID Drawing ID / Rev Qty 17 SE121-001P-2 PANEL # 4 1

Parent Sub:1 Op:10

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 17 / Seq: 10 820-RECEIVING INSPECTION 1.00 1.00 1.00 SE121-001P / A

(C) INSPECT BLANK SIZE PER DEVELOPMENT DRAWING (AUDIT DIMENSIONS WILL BE PROVIDED BY DOUG McCORKLE)

INSPECT MATERIAL THICKNESS PER PP477

VISUAL INSPECT SURFACE FINISH (PANEL SURFACE SHOULD BE A SMOOTH MILL PRODUCED SURFACE, WITHOUT SCRAPES, GOUGES, HEAVY PITS, ETC... IT SHOULD BE IN A CONDITION THAT CAN BE READILY POLISHED WITHOUT EXCESSIVE MATERIAL REMOVAL (CONTACT ENGINEERING (DOUG McCORKLE IF FURTHER CLARIFICATION IS NEEDED)

SAMPLE INSPECT MAGNETIC PERMEABILITY PER PP476, AND ASTM A800, SUPPLIMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT). SAMPLE LOT SIZE: AT LEAST 10 EVENLY SPACED LOCATIONS.

RECORD IDC DATA

Part Number: SE121-001P-2 PANEL 4 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 2001

Customer: PPPL

Specification: ASTM B443 Rev: 00 Specification: ASME B46.1 Rev: 95 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: ASTM A380 Rev: 99

> IDC Count: 3 Dwg Count: 0 Pgm Count: 0 OAP Count: 10 NDT Count: 0 WPS Count: 0

Piece # Part ID Drawing ID / Rev Vendor **Dimensions** SE121-001P-2 PANEL # 4-PANEL BLANK .375" THK INCONEL 625 SE121 / --1810 10

Vendor Part ID: SE121-001P-2 PANEL # 4

(C) PANEL BLANK AWJ CUT FROM .375" INCONEL 625 TO PROVIDED GEOMETRICAL SHAPE



Page: 29 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev **Engineer** 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

(SE121-001P-2 PANEL # 1.DXF, REV. --)

MATERIAL REQUIREMENTS: INCONEL 625 (UNS N06625) PER ASTM B 443-00 ANNEALED

MAGNETIC PERMEABILITY SHALL NOT EXCEED 1.00 (REF. ASTM A800).

SURFACE MUST BE PROTECTED FROM CONTACT WITH IRON AND IRON ALLOY MATERIALS

CERTS & MILL TEST REPORTS REQ'D WITH SHIPMENT.

APPROXIMATE OVERALL SIZE: 54.97*76.37

Material Certification:

Part Number: SE121-001P-2 PANEL # 1 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 01 Specification: ASTM B443 Rev: 00 Specification: ASTM B46.1 Rev: 95

QAP Count: 6

Operation	Resource	QtyPer	StartQty	EndQt	Drawing ID / Rev			
Sub: 17 / Seq: 18	105-DEBURR PLT 1 LOW BAY	1.00	1.00	1.00	SE121-001P / A			
(C)	RADIUS ALL CUT EDGES PRIOR TO FORMING							
	Specification: PP475 Rev: 8							
	IDC Cour	t:0	Dwg Cou	nt: 0	Pgm Count: 0	QAP Count: 1	NDT Count: 0	WPS Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 17 / Seq: 20 341-PACIFIC 750 1.00 1.00 1.00 SE121-001P / A

(C) 1ST FORM OPERATION:

LOAD, ALIGN, AND BOLT DIE SET # MTMFX-2888 - MTMFX-2889 INTO THE 750 TON HYDRAULIC PRESS.

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

ENSURE THE PANEL BLANK IS CLEAN AND FREE OF FOREIGN MATTER.

LOAD THE PANEL BLANK INTO THE DIE SET.

HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2906.

NOTE THAT THE FINAL PANEL TO GAGE GAP TOLERANCE IS .094" MAX. IT IS DESIRED TO GET AS CLOSE TO THIS AS POSSIBLE PRIOR TO ANNEALING. CLOSELY WATCH THE FORMING, WRINKLING, AND SPRING-BACK CHARACTERISTICS OF THE MATERIAL DURING THE FORMING PROCESS. WHEN IT'S APPARENT THE MATERIAL IS WORK HARDENING TO A DEGREE THAT FORMING BECOMES DIFFICULT, OR THE PHYSICAL INTEGRITY OF THE MATERIAL IS AT RISK, PROCEED TO THE NEXT SEQUENTIAL OPERATION (BLAST AND ANNEAL). A FINAL FORMING SEQUENCE IS PROVIDED FOR "FINAL SIZING" AFTER THE MATERIAL HAS BEEN ANNEALED.

ENSURE THE PANEL MATERIAL EXTENDS BEYOND THE PERIMETER OF THE GAGE (ENOUGH TO PROVIDE ADEQUATE STOCK ALLOWANCE FOR RE-POSITIONING, RE-STRIKING, AND ACCURATE TRIMMING AFTER ANNEALING).

Part Number: SE121-001P-2 PANEL 4 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0

W:64880/1-0/Inc Matl/Inc Legs MTTRAVLR.qrp



Page: 30 Date:12/23/03 **User ID: MCCORKLE**

Workorder 64880/1.0

(C)

Part ID

Drawing ID / Rev SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

Operation Resource OtvPer StartQty EndQt Drawing ID / Rev

Sub: 17 / Seq: 22 230-FABRICATION - WEIDNER 1.00 1.00 1.00

> CUT OUT A LIFTING EYE FROM THE EXCESS TRIM STOCK THAT WAS REMOVED DURING THE FORMING CYCLE. INSTALL AND WELD IT TO THE PERIPHERAL EDGE OF THE FORMED PANEL (WHICH STILL HAS EXCESS TRIM STOCK REMAINING).

POSITIONING CONSIDERATIONS:

1. POSITION TO SUIT NORMAL HANDLING AND LIFTING.

2. POSITION TO SUIT SETTING IN A VERTICAL STANCE IN THE HEAT TREAT OVEN (WIDE SIDE DOWN).

3. SHAPE AND POSITION THE LIFTING HOOK FOR A "QUICK AND EASY GAFF HOOK STYLE GRAB" WHEN REMOVING THE PARTS FROM THE HOT OVEN FOR A

RAPID COOLING CYCLE. Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

QAP Count: 1

NDT Count: 0

WPS Count: 1

Operation StartQty EndQt Drawing ID / Rev Resource QtyPer Sub: 17 / Seq: 25

1.00 1.00 1.00 SE121-001P / A 260-SANDBLAST (C)

SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE INITIAL

FORMING PROCESS.

MAINTAIN AN APPROXIMATE BLAST ANGLE OF 20 TO 40 DEGREES BLOW OFF ALL RESIDUAL BLAST MEDIA PRIOR TO HANDLING.

Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

SE121-001P / A

QAP Count: 1

NDT Count: 0

WPS Count: 0

THRML TR/NA SA

Operation Resource OtvPer StartQty EndQt Drawing ID / Rev Service ID Sub: 17 / Seq: 30 1.00

(C) SOLUTION ANNEAL FORMED PANEL PER THE FOLLOWING:

520-SUBLET, EXOTIC HEAT TREAT

ATTACH A MINIMUM OF THREE EQUALLY SPACED THERMOCOUPLES TO THE FORMED PANEL

CHARGE FURNACE AND HEAT PART UNTIL THERMOCOUPE READINGS ARE WITHIN 1900 +/-15F.

HOLD PART TEMPERATURE AT 1900 DEGREES F. (+/- 15 DEGREES) HOLD FOR 45 MINUTES (+/ 5 MINUTES)

1.00

RAPID COOL (VIA. WATER QUENCHING OR FORCED AIR CIRCULATION) TO 1000 DEGREES F. OPEN AIR COOL TO AMBIENT TEMP.

Specification: AMS2774 Rev: JUL95 Certification: H/T CERTIFICATE Part Number: SE121-001P-2 PANEL 4 Part Description: DIE FORMED PANEL

Customer: PPPL

Furnace charts: FURNACE CHART Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0


QAP Count: 7

NDT Count: 0

WPS Count: 0

Vendor Part ID: SE120-002-2 PANEL 4

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 17 / Seq: 31 SE121-001P / A 820-RECEIVING INSPECTION 1.00 1.00





Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE (U) REVIEW HEAT TREAT CERTIFICATE AND FURNACE CHART IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 17 / Seq: 35 1.00 SE121-001P / A 805-INPROCESS INSPECTION - PLA 1.00 1.00 (R) VISUAL INSPECT SURFACE FOR DAMAGE, PITTING, GOUGES, SCRAPES ETC..... ON THE INSIDE (CONCAVE SURFACE), LOOK FOR ANY SURFACE DEFECTS OR IRREGULARITIES THAT MAY INHIBIT ACHIEVING THE REQURIED 32 MICRO-INCH FINISH REQURIEMENT. ON THE OUTSIDE (CONVEX SURFACE), VERIFY THE SURFACE FINISH STILL MEETS THE REQUIREMENTS OF ASTM B 443-00. NOTIFY ENGINEERING (DOUG McCORKLE) FOR CONCURRENCE VERIFY MAGNETIC PERMEABILITY AND RECORD I.D.C. DATA Part Number: SE121-001P-2 PANEL 4 Part Description: DIE FORMED PANEL Specification: PP475 Rev: 8 Specification: ASTM B443 Rev: 00 Specification: PP476 Rev: 4 IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 5 NDT Count: 0 WPS Count: 0 Operation OtvPer StartQty EndQt Drawing ID / Rev Resource Sub: 17 / Seq: 40 341-PACIFIC 750 1.00 1.00 1.00 SE121-001P / A (R) 2ND FORMING OPERATION ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC.... LOAD THE PREFORMED / ANNEALED PANEL INTO THE DIE SET. "RE-STRIKE" HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2906. PANEL TO GAGE GAP TOLERANCE: .094" MAX. NOTIFY INSPECTOR FOR Q/A IDC VERIFICATION Part Number: SE121-001P-2 PANEL 4 Part Description: DIE FORMED PANEL Specification: PP475 Rev: 8 IDC Count: 1 Dwg Count: 0 Pgm Count: 0 OAP Count: 3 NDT Count: 0 WPS Count: 0 Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 17 / Seq: 50 260-SANDBLAST 1.00 1.00 1.00 SE121-001P / A (F) SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE FINAL FORMING PROCESS. Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0 Operation Resource OtvPer StartQty EndQt Drawing ID / Rev Sub: 17 / Seq: 60 1.00 SE121-001P / A 230-FABRICATION - WEIDNER 1.00



(C)

INSPECT MATERIAL THICKNESS PER PP477

Page: 32 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE (F) TRIM PERIMETER TO PROVIDED TRIM-LINES (LEAVING STOCK FOR POSITIONING AND FITTING ON THE FAB FIXTURE). NOTE THAT INSTALLING THE WELD PREP IS NOT REQUIRED AT THIS STAGE (ADDITIONAL FITTING / TRIMMING WILL BE REQUIRED AT INSTALLATION) HIGH PRESSURE WASH PER PP475 NOTIFY Q/A FOR FINAL PANEL PROFILE CONFIRMATION PRIOR TO COMPLETING THE POLISHING AND INSTALLATION OF PROTECTIVE PLASTIC SAND AND POLISH THE INSIDE SURFACE 100% TO ACHIEVE A 32 MICRO SURFACE FINISH (WITH THE EXCEPTION OF THE WELDING / TRIMMING ZONES). **CLEAN PANEL PER PP475** APPLY PROTECTIVE PLASTIC FILM (CONTACT DOUG McCORKLE FOR MATERIAL) STAGE PANEL FOR INSTALLATION Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0 Operation Resource OtvPer StartOtv EndQt Drawing ID / Rev Sub: 17 / Seq: 70 1.00 1.00 SE121-001P / A 805-INPROCESS INSPECTION - PLA 1.00 (F) VERIFY PROFILE TO INSPECTION GAGE # MTMFX-2906. GAP TOLERANCE: .094" MAX. RECORD ACTUAL GAP READINGS ON INSPECTION DRAWING VERIFY PART PERIMETER EXCEEDS GAGE PERIMETER FOR TRIMMING AND FITTING AT ASSEMBLY INSPECT AND RECORD INTERIOR SIDE SURFACE FINISH (LESS PERIMETER / WELD ZONES) AND RECORD ACTUAL READINGS ON INSPECTION DRAWING INSPECT MAGNETIC PERMEABILITY PER PP476 AND ASTM A800, SUPPLEMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT. THE SURFACES OF THE PVVS SHELL AND PORT EXTENSION SHALL BE CHECKED AND DOCUMENTED ON A 6" GRID. THE SURFACES AT AND NEAR WELDS WILL BE CHECKED ON A 1" GRID. RECORD ACTUAL PERMEABILITY READINGS ON INSPECTION DRAWING INSPECT MATERIAL THICKNESS PER PP477 (6" GRID) RECORD ACTUAL MATERIAL THICKNESS ON INSPECTION DRAWING Test Certification: SE121-001P-10MTM Rev: 2A Part Number: SE121-001P-2 PANEL 4 Part Description: DIE FORMED PANEL Specification: ASME B46.1 Rev: 95 Specification: ASTM A800 Rev: 2001 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP479 Rev: 1 IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 9 NDT Count: 0 WPS Count: 0 Sub ID Part ID Drawing ID / Rev Qty 18 SE121-001P-2 PANEL # 5 Parent Sub:1 Op:10 StartQty EndQt Drawing ID / Rev Operation **QtyPer** Resource SE121-001P / A Sub: 18 / Seq: 10 820-RECEIVING INSPECTION 1.00 1.00 1.00

MTTRAVLR.qrp W:64880/1-0 /Inc Matl /Inc Legs

INSPECT BLANK SIZE PER DEVELOPMENT DRAWING (AUDIT DIMENSIONS WILL BE PROVIDED BY DOUG McCORKLE)



Page: 33 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Qty Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

> VISUAL INSPECT SURFACE FINISH (PANEL SURFACE SHOULD BE A SMOOTH MILL PRODUCED SURFACE, WITHOUT SCRAPES, GOUGES, HEAVY PITS, ETC... IT SHOULD BE IN A CONDITION THAT CAN BE READILY POLISHED WITHOUT EXCESSIVE MATERIAL REMOVAL (CONTACT ENGINEERING (DOUG McCORKLE IF FURTHER CLARIFICATION IS NEEDED)

SAMPLE INSPECT MAGNETIC PERMEABILITY PER PP476, AND ASTM A800, SUPPLIMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT). SAMPLE LOT SIZE: AT LEAST 10 EVENLY SPACED LOCATIONS.

RECORD IDC DATA

Part Number: SE121-001P-2 PANEL 5 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 2001

Customer: PPPL

Specification: ASTM B443 Rev: 00 Specification: ASME B46.1 Rev: 95 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5

Specification: ASTM A380 Rev: 99

OAP Count: 10 NDT Count: 0 WPS Count: 0 IDC Count: 3 Dwg Count: 0 Pgm Count: 0 Piece # Part ID Drawing ID / Rev Vendor **Dimensions** Qty

SE121 / --1810 10 SE121-001P-2 PANEL # 5-PANEL BLANK .375" THK INCONEL 625 1.0

Vendor Part ID: SE121-001P-2 PANEL # 5

(C) PANEL BLANK AWJ CUT FROM .375" INCONEL 625 TO PROVIDED GEOMETRICAL SHAPE

(SE121-001P-2 PANEL # 1.DXF, REV. --)

MATERIAL REQUIREMENTS: INCONEL 625 (UNS N06625) PER ASTM B 443-00 ANNEALED

MAGNETIC PERMEABILITY SHALL NOT EXCEED 1.00 (REF. ASTM A800).

SURFACE MUST BE PROTECTED FROM CONTACT WITH IRON AND IRON ALLOY MATERIALS

CERTS & MILL TEST REPORTS REQ'D WITH SHIPMENT.

APPROXIMATE OVERALL SIZE: 54.97*76.37

Material Certification:

Part Number: SE121-001P-2 PANEL # 1 Part Description: DIE FORMED PANEL Specification: ASTM A800 Rev: 01 Specification: ASTM B443 Rev: 00 Specification: ASTM B46.1 Rev: 95

QAP Count: 6

Operation **QtyPer** StartQty EndQt Drawing ID / Rev Resource Sub: 18 / Seq: 18 1.00 1.00 1.00 SE121-001P / A 105-DEBURR PLT 1 LOW BAY (C) RADIUS ALL CUT EDGES PRIOR TO FORMING Specification: PP475 Rev: 8 IDC Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0 Dwg Count: 0 Pgm Count: 0



Page: 34 Date:12/23/03 User ID: MCCORKLE

Workorder 64880/1.0

(F)

(R)

Part ID

Qty Drawing ID / Rev 1 SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

 Operation
 Resource
 QtyPer
 StartQty
 EndQt
 Drawing ID / Rev

 Sub: 18 / Seq: 20
 341-PACIFIC 750
 1.00
 1.00
 1.00
 SE121-001P / A

(R) 1ST FORM OPERATION:

LOAD. ALIGN. AND BOLT DIE SET # MTMFX-2890 - MTMFX-2891 INTO THE 750 TON HYDRAULIC PRESS.

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

ENSURE THE PANEL BLANK IS CLEAN AND FREE OF FOREIGN MATTER.

LOAD THE PANEL BLANK INTO THE DIE SET.

HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2907.

NOTE THAT THE FINAL PANEL TO GAGE GAP TOLERANCE IS .094" MAX. IT IS DESIRED TO GET AS CLOSE TO THIS AS POSSIBLE PRIOR TO ANNEALING. CLOSELY WATCH THE FORMING, WRINKLING, AND SPRING-BACK CHARACTERISTICS OF THE MATERIAL DURING THE FORMING PROCESS. WHEN IT'S APPARENT THE MATERIAL IS WORK HARDENING TO A DEGREE THAT FORMING BECOMES DIFFICULT, OR THE PHYSICAL INTEGRITY OF THE MATERIAL IS AT RISK, PROCEED TO THE NEXT SEQUENTIAL OPERATION (BLAST AND ANNEAL). A FINAL FORMING SEQUENCE IS PROVIDED FOR "FINAL SIZING" AFTER THE MATERIAL HAS BEEN ANNEALED.

ENSURE THE PANEL MATERIAL EXTENDS BEYOND THE PERIMETER OF THE GAGE (ENOUGH TO PROVIDE ADEQUATE STOCK ALLOWANCE FOR RE-POSITIONING, RE-STRIKING, AND ACCURATE TRIMMING AFTER ANNEALING).

Part Number: SE121-001P-2 PANEL 5
Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0

Operation Resource OtyPer StartQty EndQt Drawing ID / Rev

Sub: 18 / Seq: 22 230-FABRICATION - WEIDNER 1.00 1.00 1.00

CUT OUT A LIFTING EYE FROM THE EXCESS TRIM STOCK THAT WAS REMOVED DURING THE FORMING CYCLE. INSTALL AND WELD IT TO THE PERIPHERAL EDGE OF THE FORMED PANEL (WHICH STILL HAS EXCESS TRIM STOCK REMAINING).

POSITIONING CONSIDERATIONS:

- 1. POSITION TO SUIT NORMAL HANDLING AND LIFTING.
- 2. POSITION TO SUIT SETTING IN A VERTICAL STANCE IN THE HEAT TREAT OVEN (WIDE SIDE DOWN).
- 3. SHAPE AND POSITION THE LIFTING HOOK FOR A "QUICK AND EASY GAFF HOOK STYLE GRAB" WHEN REMOVING THE PARTS FROM THE HOT OVEN FOR A

RAPID COOLING CYCLE. Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 1

WPS115 Rev:1 GTAW MAN

GTAW - Manual Fillers: INCONEL625_035_GMAW / INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes: LIFTING HOOK TO PANEL EDGE

 Operation
 Resource
 QtyPer
 StartQty
 EndQt
 Drawing ID / Rev

 Sub: 18 / Seq: 25
 260-SANDBLAST
 1.00
 1.00
 1.00
 SE121-001P / A

SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE INITIAL

FORMING PROCESS.

MAINTAIN AN APPROXIMATE BLAST ANGLE OF 20 TO 40 DEGREES



Page: 35 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Drawing ID / Rev Engineer

64880/1.0 SE121-003P / -- BLUE/DOUG MCCORKLE

BLOW OFF ALL RESIDUAL BLAST MEDIA PRIOR TO HANDLING.

Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

QAP Count: 1

NDT Count: 0

WPS Count: 0

Operation QtyPer StartQty EndQt Drawing ID / Rev Service ID Resource 1.00

Sub: 18 / Seq: 30 520-SUBLET, EXOTIC HEAT TREAT 1.00

1.00 SE121-001P / A

THRML TR/NA SA

(R) SOLUTION ANNEAL FORMED PANEL PER THE FOLLOWING:

> ATTACH A MINIMUM OF THREE EQUALLY SPACED THERMOCOUPLES TO THE FORMED PANEL CHARGE FURNACE AND HEAT PART UNTIL THERMOCOUPE READINGS ARE WITHIN 1900 +/-15F.

HOLD PART TEMPERATURE AT 1900 DEGREES F. (+/- 15 DEGREES) HOLD FOR 45 MINUTES (+/ 5 MINUTES)

RAPID COOL (VIA. WATER QUENCHING OR FORCED AIR CIRCULATION) TO 1000 DEGREES F. OPEN AIR COOL TO AMBIENT TEMP.

Specification: AMS2774 Rev: JUL95 Certification: H/T CERTIFICATE Part Number: SE121-001P-2 PANEL 5 Part Description: DIE FORMED PANEL

Customer: PPPL

Furnace charts: FURNACE CHART Specification: PP475 Rev: 8

IDC Count: 0

Dwg Count: 0

Pgm Count: 0

OAP Count: 7

NDT Count: 0

WPS Count: 0

Operation Resource OtvPer StartQty EndQt Drawing ID / Rev 1.00

Sub: 18 / Seq: 31 820-RECEIVING INSPECTION 1.00

SE121-001P / A 1.00

REVIEW HEAT TREAT CERTIFICATE AND FURNACE CHART (U)

IDC Count: 1

Dwg Count: 0

Pgm Count: 0

OAP Count: 0

NDT Count: 0

WPS Count: 0

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 18 / Seq: 35 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121-001P / A

VISUAL INSPECT SURFACE FOR DAMAGE, PITTING, GOUGES, SCRAPES ETC.....

ON THE INSIDE (CONCAVE SURFACE), LOOK FOR ANY SURFACE DEFECTS OR IRREGULARITIES THAT MAY INHIBIT ACHIEVING THE REQURIED 32 MICRO-INCH FINISH REQURIEMENT. ON THE OUTSIDE (CONVEX SURFACE), VERIFY THE SURFACE FINISH STILL MEETS THE REQUIREMENTS OF ASTM B 443-00.

NOTIFY ENGINEERING (DOUG McCORKLE) FOR CONCURRENCE VERIFY MAGNETIC PERMEABILITY AND RECORD I.D.C. DATA

Part Number: SE121-001P-2 PANEL 5 Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8 Specification: ASTM B443 Rev: 00 Specification: PP476 Rev: 4

> IDC Count: 1 Dwg Count: 0

Pgm Count: 0

OAP Count: 5

NDT Count: 0

WPS Count: 0

Operation Resource

(F)

QtyPer StartQty EndQt Drawing ID / Rev



Page: 36 Date:12/23/03 User ID: MCCORKLE

WorkorderPart IDQtyDrawing ID / RevEngineer64880/1.01SE121-003P / --BLUE/DOUG MCCORKLE

Sub: 18 / Seq: 40 341-PACIFIC 750 1.00 1.00 1.00 SE121-001P / A

(F) 2ND FORMING OPERATION

ENSURE THE DIE SET FACES ARE CLEAN AND FREE OF DIRT, OIL, GRIME, FOREIGN MATTER, RAISED OR EMBEDDED MATERIAL, ETC....

LOAD THE PREFORMED / ANNEALED PANEL INTO THE DIE SET.

"RE-STRIKE" HYDRAULIC FORM THE PANEL TO ACHIEVE THE GEOMETRICAL SHAPE CONFORMING TO INSPECTION GAGE # MTMFX-2907. PANEL TO GAGE GAP

TOLERANCE: .094" MAX.

NOTIFY INSPECTOR FOR Q/A IDC VERIFICATION

Part Number: SE121-001P-2 PANEL 5
Part Description: DIE FORMED PANEL

Specification: PP475 Rev: 8

IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev
Sub: 18 / Seq: 50 260-SANDBLAST 1.00 1.00 1.00 1.00 SE121-001P / A

(F) SHOT BLAST THE ENTIRE PANEL 100% USING 180-220 GRIT VIRGIN ALUMINUM OXIDE MEDIA TO REMOVE ANY RESIDUE / MARKINGS FROM THE FINAL FORMING PROCESS.

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 18 / Seq: 60230-FABRICATION - WEIDNER1.001.001.00SE121-001P / A

(F) TRIM PERIMETER TO PROVIDED TRIM-LINES (LEAVING STOCK FOR POSITIONING AND FITTING ON THE FAB FIXTURE). NOTE THAT INSTALLING THE WELD

PREP IS NOT REQUIRED AT THIS STAGE (ADDITIONAL FITTING / TRIMMING WILL BE REQUIRED AT INSTALLATION)

HIGH PRESSURE WASH PER PP475

NOTIFY Q/A FOR FINAL PANEL PROFILE CONFIRMATION PRIOR TO COMPLETING THE POLISHING AND INSTALLATION OF PROTECTIVE PLASTIC SAND AND POLISH THE INSIDE SURFACE 100% TO ACHIEVE A 32 MICRO SURFACE FINISH (WITH THE EXCEPTION OF THE WELDING / TRIMMING ZONES).

CLEAN PANEL PER PP475

APPLY PROTECTIVE PLASTIC FILM (CONTACT DOUG McCORKLE FOR MATERIAL)

STAGE PANEL FOR INSTALLATION

Specification: PP475 Rev: 8

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 1 NDT Count: 0 WPS Count: 0

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 18 / Seq: 70805-INPROCESS INSPECTION - PLA1.001.001.00SE121-001P / A

(F) VERIFY PROFILE TO INSPECTION GAGE # MTMFX-2907. GAP TOLERANCE: .094" MAX. RECORD ACTUAL GAP READINGS ON INSPECTION DRAWING

VERIFY PART PERIMETER EXCEEDS GAGE PERIMETER FOR TRIMMING AND FITTING AT ASSEMBLY

INSPECT AND RECORD INTERIOR SIDE SURFACE FINISH (LESS PERIMETER / WELD ZONES) AND RECORD ACTUAL READINGS ON INSPECTION DRAWING INSPECT MAGNETIC PERMEABILITY PER PP476 AND ASTM A800, SUPPLEMENTARY REQUIREMENT S1 (BUT THE MEASUREMENT SHALL BE TAKEN IN RELATIVE PERMEABILITY RATHER THAN FERRITE CONTENT. THE SURFACES OF THE PVVS SHELL AND PORT EXTENSION SHALL BE CHECKED AND DOCUMENTED ON A 6" GRID. THE SURFACES AT AND NEAR WELDS WILL BE CHECKED ON A 1" GRID.






Workorder Part ID Drawing ID / Rev **Engineer** 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE RECORD ACTUAL PERMEABILITY READINGS ON INSPECTION DRAWING INSPECT MATERIAL THICKNESS PER PP477 (6" GRID) RECORD ACTUAL MATERIAL THICKNESS ON INSPECTION DRAWING Test Certification: SE121-001P-10MTM Rev: 2A Part Number: SE121-001P-2 PANEL 5 Part Description: DIE FORMED PANEL Specification: ASME B46.1 Rev: 95 Specification: ASTM A800 Rev: 2001 Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP479 Rev: 1 Dwg Count: 0 IDC Count: 3 Pgm Count: 0 QAP Count: 9 NDT Count: 0 WPS Count: 0 Sub ID Part ID Drawing ID / Rev Qty 24 SURFACE FINISH TESTING TEST P 1 Parent Sub:1 Op:10 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 24 / Seq: 10 410-BURNOUT TABLE 1.00 1.00 1.00 SE121-001P / A (C) BURNOUT TEST PLATES PER MATERIAL CARD. DEBURR AND SAND EDGES SMOOTH (WITH UNCONTAMINATED GRINDING WHEEL ONLY). FORWARD ONE PLATE TO ENGINEERING (DOUG McCORKLE) AND PROCESS THE OTHER PER THE FOLLOWING ROUTING STEPS. Dwg Count: 0 QAP Count: 0 NDT Count: 0 IDC Count: 0 Pgm Count: 0 WPS Count: 0 Piece # Part ID Qty Drawing ID / Rev Vendor **Dimensions** 10 INCONEL 625_670-SHEET, NICKEL ALLOY .25" THK 480.0 480 (C) INCONEL 625 SHEET, .25" THICK PER CERT AND MILL TEST REPORT REQ'D WITH SHIPMENT. Material Certification: NONE REQ'D TEST SAMPLE QAP Count: 1 Operation StartQty EndQt Drawing ID / Rev Resource QtyPer Sub: 24 / Seq: 20 230-FABRICATION - WEIDNER 1.00 1.00 1.00 SE121-001P / A (C) SAND AND POLISH THE TEST PIECE (ONE SIDE) TO A 32 RA MICRO SURFACE FINISH Dwg Count: 0 WPS Count: 0 IDC Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 Vendor Part ID: SE120-002-2 PANEL 5 Operation QtyPer StartQty EndQt Drawing ID / Rev Resource




Page: 38 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE Sub: 24 / Seq: 25 1.00 1.00 1.00 SE121-001P / A 260-SANDBLAST MASK THE POLISHED SIDE AND BLAST THE OTHER SIDE WITH 180-220 GRIT VIRGIN ALUMINUM OXIDE. (C) IDC Count: 0 Dwg Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 0 Drw N/A Pgm Count: 0 Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 24 / Seq: 28 230-FABRICATION - WEIDNER 1.00 1.00 1.00 PP475 / 6 CLEAN SAMPLE MATERIAL SURFACES PER PP475, 5.7 & 5.8. WRAP THE PART IN PLASTIC FOAM. (C) IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 24 / Seq: 30 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121-001P / A (C) VERIFY THE FOLLOWING TEST SAMPLE ATTIBUTES: SURFACE FINISH (PER ASME B46.1-1995) POLISHED 32 MICRO ON ONE SIDE, SMOOTH BLASTED SURFACE SIDE OPPOSITE (NO PITS, SCRAPES, GOUGES, ETC...). CLEANLINESS PER PP475. MAGNETIC PERMEABILITY (1.01 MAX) REPORT RESULTS TO ENGINEERING (DOUG McCORKLE). IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Sub ID Part ID Qty Drawing ID / Rev 26 SE121-001P-2 TEST PANEL NOTE: Parent Sub:1 Op:10 Operation Resource OtvPer StartQty EndQt Drawing ID / Rev Sub: 26 / Seq: 60 1.00 1.00 1.00 SE121-001P / A 230-FABRICATION - WEIDNER OBTAIN THE DIE SET NUMBER ONE DEVELPMENT PANEL (PRODUCED UNDER 64880/2, SUB ID 1) (R) SPLIT THE PANEL TO SIMULATE PRODUCTION WELD JOINT(S). PREP, FIT AND WELD JOINTS TO DEVELOP WELDING SEQUENCES AND MINIMIZE WELDING DISTORTION. ENSURE THE PART IS RESTRAINED IN A MANNER SIMULATING PRODUCTION THROUGHOUT THE WELDING PROCESS. MAXIMUM INTERIOR (CONCAVE) SURFACE WELD FACE: 1 BEAD WIDTH CWI VISUAL INSPECT WELDS (CERTIFY EACH PASS) 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER AWS D1.6, 6.29.1. NO CERTIFICATE REQUIRED. THIS IS A TEST PIECE. REVIEW RESULTS WITH ENGINEERING (DOUG McCORKLE) SAND AND POLISH THE INSIDE (CONCAVE SIDE) SURFACE 100% TO ACHIEVE A 32 MICRO SURFACE FINISH. CLEAN TEST PANEL PER CLEANING PROCDURE PP475. ENGINEERING / PRODUCTION REVIEW REQUIRED UPON COMPLETION. Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 NDT Count: 0 WPS Count: 1 WPS390-PPPL Rev:0 GTAW MAN GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW Notes:



Major
Tool & Machine, Inc.

Workorder Part ID Drawing ID / Rev Engineer SE121-003P / --64880/1.0 BLUE/DOUG MCCORKLE Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 26 / Seq: 70 805-INPROCESS INSPECTION - PLA 1.00 1.00 SE121-001P / A VERIFY PROFILE TO INSPECTION GAGE # MTMFX-2903. GAP TOLERANCE: .188" MAX. (R) INSPECT AND RECORD INTERIOR SIDE SURFACE FINISH. INSPECT AND RECORD MAGNETIC PERMEABILY. Part Number: SE121-001P-2 TEST PANEL Part Description: DIE FORMED PANEL Specification: PP475 Rev: 8 IDC Count: 3 Dwg Count: 0 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0 Sub ID Part ID Drawing ID / Rev Qty 30 PQR PROCESS Parent Sub:26 Op:60 Operation **QtyPer** StartQty EndQt Drawing ID / Rev Resource Sub: 30 / Seq: 10 1.00 410-BURNOUT TABLE 1.00 (C) BURN OUT TWO TEST PLATES 6 X 15 AND CLEANUP. NOTIFY WELDING ENGINEERING WHEN PARTS ARE AVALIABLE IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Piece # Part ID Drawing ID / Rev Vendor **Dimensions** Qty INCONEL 625_5-PLATE, NICKEL ALLOY .375" THK 1810 15.375*22 10 338.3 Vendor Part ID: INCONEL 625_5 INCONEL 625 (UNS N06625) PER ASTM B 443-00 (C) ANNEALED MAGNETIC PERMEABILITY SHALL NOT EXCEED 1.00 (REF. ASTM A800). SURFACE MUST BE PROTECTED FROM CONTACT WITH IRON AND IRON ALLOY MATERIALS CERTS & MILL TEST REPORTS REQ'D WITH SHIPMENT. OAP Count: 2 Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 30 / Seq: 20 1.00 1.00 1.00 230-FABRICATION - WEIDNER (C) WELD PQR PLATE PER WELDING ENGINEERING DIRECTION. Dwg Count: 0 Pgm Count: 0 IDC Count: 0 OAP Count: 0 NDT Count: 1 WPS Count: 0 Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 30 / Seq: 30 705-WELD ENGINEERING/CWI 1.00 1.00 1.00 (C) CWI to visually inspect PQR test plate per the requirements of ASME Sect. IX, AWS D1.1, and AWS B2.1. MTM NDT certification form required IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 0



Major
Tool & Machine, Inc.

Workorder Part ID Drawing ID / Rev Engineer SE121-003P / --64880/1.0 BLUE/DOUG MCCORKLE Resource StartQty EndQt Drawing ID / Rev Operation QtyPer Sub: 30 / Seq: 40 818-MQS CONTRACTOR X-RAY 1.00 1.00 (C) Radiographically inspect PQR test plate per the requirements of ASME Sect. IX, AWS D1.1, and AWS B2.1. Reference acceptance to all three specifications on the reader sheet. IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Operation **QtyPer** StartQty EndQt Drawing ID / Rev Service ID Resource Sub: 30 / Seq: 50 450-SUBLET TESTNG/MISC 1.00 1.00 1.00 * Perform destructive testing (ref: 2 tensile tests, 2 face bend tests, and 2 root bend tests) to the requirements of the following three specifications; (C) ASME Sect. IX, AWS D1.1, and AWS B2. * All test samples and remaining plate to be returned to Major Tool and Machine when complete. * Separate test reports are required for each specification. Test reports are to reference the PQR number and must provide the tensile failure locations/characterss. * All NDT has been performed by Major Tool and Machine. A copy of the radiographic report is included with the test plate for reference. * A reference sheet with pertinent welding data is included with the test plate. * Test plate info: - One plate - 3/8" thick 304L stainless steel - One plate - 3/8" thick Inconel 625 - Both plates butt welded using filler material ERNiCrMo-3 (Inconel 625) - No post-weld heat treatment is required. - Test plate is supplied in the as-welded condition. IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Sub ID Part ID Drawing ID / Rev Qty 37 PQR PROCESS Parent Sub:26 Op:60 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 37 / Seq: 20 230-FABRICATION - WEIDNER 1.00 1.00 1.00 PLASMA CUT TWO TEST PIECES 7"*18* (C) CLEANUP, REMOVE HEAT AFFECTED ZONE. INSPECT MAGNETIC PERMEABILITY AND RECORD IDC PREP, WELD PQR PLATE PER WELDING ENGINEERING DIRECTION. Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 0 IDC Count: 0 Operation QtyPer StartQty EndQt Drawing ID / Rev Resource Sub: 37 / Seq: 30 1.00 1.00 1.00 705-WELD ENGINEERING/ CWI (C) CWI to visually inspect PQR test plate per the requirements of ASME Sect. IX, AWS D1.1, and AWS B2.1. MTM NDT certification form required IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 1 WPS Count: 0



Page: 41 Date: 12/23/03 **User ID: MCCORKLE**

Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE Resource StartQty EndQt Drawing ID / Rev Operation QtyPer Sub: 37 / Seq: 40 818-MQS CONTRACTOR X-RAY 1.00 1.00 (C) Radiographically inspect PQR test plate per the requirements of ASME Sect. IX, AWS D1.1, and AWS B2.1. Reader sheet to state acceptance to all three specifications. * PQR390 * Test plate material: .375" thick Inconel 625. * Butt weld using Inconel 625 filler / GTAW process. IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 0 Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Service ID Sub: 37 / Seq: 50 450-SUBLET 1.00 1.00 TESTNG/MISC 1.00 * Perform destructive testing (ref: 2 tensile tests, 2 face bend tests, and 2 root bend tests) per the requirements of the following three specifications; (C) ASME Sect. IX, AWS D1.1, and AWS B2.1 * All test samples and remaining plate to be returned to Major Tool and Machine when complete. * Separate test reports are required for each specification. Test reports are to reference the PQR number and must provide the tensile failure locations/characteristics. * All NDT has been performed by Major Tool and Machine. A copy of the radiographic report is included with the test plate for reference. * A reference sheet with pertinent welding data is included with the test plate. * Test plate info: - Test plate number: PQR390 - One plate - 3/8" thick Inconel 625 - One plate - 3/8" thick Inconel 625 - Both plates butt welded using filler material ERNiCrMo-3 (Inconel 625) - No post-weld heat treatment is required. - Test plate is supplied in the as-welded condition. Test Certification: VENDOR FORM IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 NDT Count: 0 WPS Count: 0 Sub ID Part ID Qty Drawing ID / Rev 34 SOURCE NOTIFICATION 1 Parent Sub:1 Op:30 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 34 / Seq: 10 1.00 1.00 1.00 830-SOURCE WITNESS POINT -IN P AFTER TACK WELDING, AND PRIOR TO WELDING SOURCE NOTIFICATION IS REQUIRED. CUSTOMER DECISION WILL FOLLOW. NOTIFICATION VIA CFT. (U) IDC Count: 0 Dwg Count: 0 Pgm Count: 0 NDT Count: 0 WPS Count: 0 QAP Count: 0 Sub ID Part ID Qty Drawing ID / Rev 19 SE212-003P-3-PORT EXTENSION Parent Sub:1 Op:70

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev



Page: 42 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 1 SE121-003P / -- BLUE/DOUG MCCORKLE

Sub: 19 / Seq: 10 230-FABRICATION - WEIDNER 1.00 1.00 5E121-002P / --

(F) POSITION, INSTALL AND WELD CONFLAT FLANGE TO TUBE PER DRAWING.
FIT AND TRIM THE LENGTH FOR INSTALLATION. PREP FOR WELDING IN PLACE.

GRIND / BLEND THE INTERIOR WELD SMOOTH.

POLISH THE ENTIRE INSIDE SURFACE SMOOTH TO ACHIEVE A 32 MICRO SURFACE FINISH. CLEAN PER PP475

CWI VISUAL INSPECT THE PORT EXTENSION TUBE TO CONFLAT FLANGE WELD 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V.

ACCEPTANCE PER AWS D1.6, 6.29.1.

Part Number: SE212-003P-3 Specification: PP475 Rev: 8

Part Description: PORT EXTENSION Certification: CWI CERTIFICATION

IDC Count: 5 Dwg Count: 1 Pgm Count: 0 QAP Count: 4 NDT Count: 0 WPS Count: 1

WPS328.5-PPPL Rev:2 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev

Sub: 19 / Seq: 20 805-INPROCESS INSPECTION - PLA 1.00 1.00 SE121-002P / --

(F) VERIFY CLEANLINESS

INSPECT THE INTERIOR SURFACE FINISH OF THE PORT SUB-ASSY.

INSPECT THE MAGNETIC PERMEABILITY OF THE PORT EXTENSION TO FLANGE WELD AND SURROUNDING AREA.

RECORD IDC DATA

Part Number: SE212-003P-3

Part Description: PORT EXTENSION

Customer: PPPL

Specification: ASME B46.1 Rev: 95 Specification: A800 Rev: 2001 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: PP475 Rev: 8

IDC Count: 2 Dwg Count: 1 Pgm Count: 0 QAP Count: 8 NDT Count: 0 WPS Count: 0

Sub IDPart IDQtyDrawing ID / Rev20CONFLAT FLANGE1/

Parent Sub:19 Op:10


OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 20 / Seq: 10820-RECEIVING INSPECTION1.001.001.00\$E121-002P / --

(C) RECEIVING INSPECTION

RECEIVE AND INSPECT THE FOLLOWING PARTS:

(THEY SHOULD ALL ARRIVE TOGETHER)

F10000000NC4





Workorder 64880/1.0	Part ID	Qty 1	Drawing ID / Rev SE121-003P /			ngineer LUE/DOUG MCCORKLE
Piece # 10 (C)	FG1000CI FG1000VU FB1000C12S GC0275S CONTACT ENGINEERING (DOUG McCORKLE) WHEN PARTS ARRIVE. IDC N/A IDC Count: 0 Dwg Count Part ID F10000000NC4-FLANGE, CONFLAT, NON-ROTATE, 10.00" FLANGE, CONFLAT, NON-ROTATABLE 10.00 X BLANK X 0.97", CLEAR BOLT HOLES, 304L Material Certification:	t: 1 Qty 1.0	Pgm Count: 0 Drawing ID / Rev	QAP Count: 0 Vendor	NDT Count: 0 Dimensions	WPS Count: 0
	Part Number: F10000000NC4			QAP Count: 2		
Piece # 20 (C)	Part ID FG1000CI-GASKET KIT (10/PK), COPPER, FOR 10" CFF GASKET KIT (10/PACK), COPPER, INDIVIDUAL SEAL, FOR 10" CONFLAVARIAN VACUUM TECHNOLOGIES	Qty 1.0 T FLA	Drawing ID / Rev NGE	Vendor	Dimensions	
	Material Certification: Part Number: FG1000CI			QAP Count: 2		
Piece # 30 (C)	Part ID FG1000VU-GASKET, VITON, FOR 10" CFF GASKET, VITON, FOR 10" CONFLAT FLANGE VARIAN VACUUM TECHNOLOGIES	Qty 1.0	Drawing ID / Rev	Vendor	Dimensions	
	Material Certification: Part Number: FG1000VU			QAP Count: 2		
Piece # 40 (C)	Part ID FB1000C12S-BOLT AND NUT KIT, 12 PT, SILVER PLATED BOLT AND NUT KIT (25/PACK), 12 POINT, ASTM A193 GR. B8 SILVER F VARIAN VACUUM TECHNOLOGIES	Qty 1.0 PLATE	Drawing ID / Rev D, FOR 10" CONFLAT FL	Vendor LANGE	Dimensions	
	Material Certification: Part Number: FB1000C12S			QAP Count: 2		
Piece # 50 (C)	Part ID GC0275S-GASKET CLIP KIT (10/PK), FOR 10" CFF GASKET CLIP KIT (10/PACK)	Qty 1.0	Drawing ID / Rev	Vendor	Dimensions	



Page: 44 Date:12/23/03 **User ID: MCCORKLE**


Workorder Part ID Qty Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

FOR 10" CONFLAT FLANGE VARIAN VACUUM TECHNOLOGIES

> Material Certification: Part Number: GC0275S

> > QAP Count: 2

Operation StartQty EndQt Drawing ID / Rev Resource QtyPer Sub: 20 / Seq: 20 108-TOOL ROOM - PLANT 1 1.00 1.00 1.00 SE121-002P / --**HOLD FOR ENGINEERING PROCESS DRAWING. (F) MACHINE SPECIAL PORT FEATURE FOR VACUUM TESTING. SPOTFACE, DRILL A CENTER DRILL SPOT IN THE CENTER OF THE FLANGE (FOR INSTALLATION / POSITIONING AID). IDC Count: 0 Dwg Count: 1 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Sub ID Part ID Drawing ID / Rev Qty PORT EXTENSION TUBE 21 1 Parent Sub:19 Op:10 Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 21 / Seq: 10 1.00 1.00 1.00 SE121-002P / --230-FABRICATION - WEIDNER (C) INSPECT DIAMETERS AND LENGTH RECORD IDC INFORMATION NOTIFY ENGINEERING (DOUG McCORKLE) OF RESULTS WELD / BLEND MIS-ALIGNMENT OF MANUFACTURERS WELDS POLISH THE ENTIRE INSIDE SURFACE TO A 32 MICRO-INCH SURFACE FINISH. LAYOUT ONE AND CUT ONE END SQUARE FOR FLANGE INSTALLATION (REMOVE MINIMAL MATERIAL FOR LATER INSTALLATION 16" MINIMUM LENGTH) IDC Count: 0 Dwg Count: 1 Pgm Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 1 Piece # Part ID Qty Drawing ID / Rev Vendor Dimensions 10 SE121-001P-5-INCO 625 TUBE 8.0" OD X .12" WA. X 18.0" 1.0 5647 Vendor Part ID: SE121-001P-5 (C) TUBE, ROUND, INCONEL 625, SEAMLESS OR WELDED. ASTM B444 OR ASTM B705 MTM AUTHORIZATION OF WELDING PROCEDURE REQUIRED PRIOR TO STARTING WORK. NOTE THAT THE FOLLOWING REQUIREMENTS WILL BE PERFORMED / TESTED BY MAJOR TOOL & MACHINE AFTER DELIVERY. ALL EFFORTS TO ACCOMDDATE / ENSURE SUCESS MUST BE MAINTAINED: MAGNETIC PERMEABILITY REQUIREMENT: 1.01 MAX. VACUUM INTEGRITY REQUIREMENT: TOTAL HELIUM LEAK RATE FOR THE TUBE SHALL BE LESS THAN OR EQUAL TO 1.7 X 10(-9) TORR-L/S INTERIOR SURFACE FINISH REQUIREMENT: INTERIOR WELD BEADS WILL BE GROUND FLUSH. THE ENTIRE INTERIOR SURFACE WILL BE POLISHED TO A 32 MICRO SURFACE FINISH AND VERIFIED PER ASME B46.1. EXTERIOR SURFACE FINISH: MILL SURFACE ACCEPTABLE. NO PITS, SCRAPES OR GOUGES. MATERIAL CERTIFICATION AND TEST REPORTS REQ'D WITH SHIPMENT. WPS390-PPPL Rev:0 GTAW MAN GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW



WPS Count: 0

Tool & Machine, Inc.

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 1 SE121-003P / -- BLUE/DOUG MCCORKLE

Notes:

QAP Count: 3

Sub ID Part ID

29 PORT EXTENSION TUBE (TAKE 2)

1 SE121-002P / -Parent Sub:19 Op:10

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev

Sub: 29 / Seq: 10 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121-002P / --

(C) PRIOR TO CUTTING / FORMING, INSPECT AND RECORD THE MAGNETIC PERMEABILITY OF THE SHEET (COORDINATE WITH MATERIALS DEPT. AND INSPECT

THE APPROXIMATE PART ENVELOPE WITHIN THE STOCK SHEET)

Part Number: SE121-001P-3

Part Description: PVVS PORT EXTENSION TUBE

Specification: PP476 Rev: 4

IDC Count: 1 Dwg Count: 1 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0

OperationResourceQtyPerStartQtyEndQtDrawing ID / RevSub: 29 / Seq: 20415-ROLLING/SHEAR/BRAKE PRESS1.001.001.00SE121-002P / --

(C) 1. SHEAR RECTANGLE PER MATERIAL CARD DIMENSIONS

2. ROLL TO 8" O.D. =/-0.03" X 20" LONG. LEAVE TRIM STOCK OVERLAPPED (FABRICATOR WILL TRIM). ENSURE OVERLAP IS ADEQUATE TO TRIM AND FIT THE DIAMETER REMOVING ANY ROLL FLATS RESULTANT FROM STARTING AND FINISHING THE ROLLING SEQUENCE.

3. NOTIFY Q/A FOR DIMENSIONAL / MAGNETIC PERMEABILITY VERIFICATION.

IDC Count : 0 Dwg Count: 1 Pgm Count: 0 QAP Count: 0 NDT Count: 0
Piece # Part ID Qty Drawing ID / Rev Vendor Dimensions

Piece # Part ID Qty Drawing ID / Rev Vendor Dimension
10 INCONEL 625_660-SHEET,NICKEL ALLOY .125" THK 760.0 20*38

(C) INCONEL 625 SHEET, .125" THICK PER AMS 5599 / ASTM B443 (UNS N06625).

CERT AND MILL TEST REPORT REQ'D WITH SHIPMENT.

Material Certification: Part Number: SE121-001P-3

Part Description: PORT EXTENSION TUBE

QAP Count: 3

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev

INSPECT AND RECORD MAGNETIC PERMEABILITY (AFTER ROLLING)

Sub: 29 / Seq: 30 805-INPROCESS INSPECTION - PLA 1.00 1.00 SE121-002P / --


Part Number: SE121-001P-3

(C)

Part Description: PVVS PORT EXTENSION TUBE

Specification: PP476 Rev: 4

IDC Count: 1 Dwg Count: 1 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0



Workorder 64880/1.0

Part ID

Drawing ID / Rev SE121-003P / --

BLUE/DOUG MCCORKLE

Engineer

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource

Sub: 29 / Seq: 40

(F)

(F)

1.00 1.00 SE121-002P / --230-FABRICATION - WEIDNER 1.00

IDC Count: 0

(C)

TRIM, FIT, (PURGE WELD JOINT WITH 100% ARGON. PURGE DAM MATERIAL MUST BE MADE FROM EITHER 625 INCONEL OR 300 SERIES STAINLESS STEEL) AND

Pgm Count: 0

TACK WELD INTO 8" O.D. TUBE.

CLEAN AND PREPARE FOR PLASMA ARC WELDING

Specification: PP475 Rev: 8

Dwg Count: 1

QAP Count: 1

NDT Count: 0

WPS Count: 1

WPS390-PPPL Rev:0 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource 1.00 1.00 1.00 SE121-002P / --

Sub: 29 / Seq: 50 205-PLASMA WORKCENTER

SETUP, PURGE WELD JOINT WITH 100% ARGON. PURGE DAM MATERIAL MUST BE MADE FROM EITHER 625 INCONEL OR 300 SERIES STAINLESS STEEL.

PLASMA ARC WELD THE AXIAL JOINT PER DRAWING.

CWI VISUAL INSPECT THE PORT EXTENSION TUBE AXIAL WELD 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER

AWS D1.6, 6.29.1.

Test Certification: CWI CERTIFICATE Rev:

Part Number: SE121-001P-3

Part Description: PORT EXTENSION TUBE

IDC Count: 5 Dwg Count: 1 Pgm Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 1

WPS380-PPPL Rev:2 PAW MAC

PAW - Machine Fillers: INCONEL625_035_GMAW

Notes: PLASMA WELDING

Operation QtyPer StartQty EndQt Drawing ID / Rev Resource

Sub: 29 / Seq: 60 230-FABRICATION - WEIDNER 1.00 1.00 1.00 SE121-002P / --

BLEND THE INTERIOR WELD SURFACE FLUSH TO THE BASE MATERIAL.

POLISH THE ENTIRE INTERIOR OF THE TUBE TO ACHIEVE A 32 MICRO-INCH RA SURFACE FINISH.

CLEAN PER PP475

Specification: PP475 Rev: 8

WPS Count: 1 IDC Count: 0 Dwg Count: 1 Pgm Count: 0 QAP Count: 1 NDT Count: 0

WPS390-PPPL Rev:0 GTAW MAN

GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW

Notes:

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev Sub: 29 / Seq: 70 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121-002P / --

(F) INSPECT DIAMETER, ROUNDNESS, WELDING DISTORTION, MAGNETIC PERMEABILITY, AND INTERIOR SURFACE FINISH.

WPS Count: 0



Workorder Part ID Drawing ID / Rev Engineer 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

RECORD IDC DATA Part Number: SE121-001P-3

Part Description: PVVS PORT EXTENSION TUBE

Specification: PP475 Rev: 8 Specification: PP476 Rev: 4 Specification: PP477 Rev: 5 Specification: ASME B46.1 Rev: 95 Specification: A800 Rev: 2001

> IDC Count: 2 Dwg Count: 1 Pgm Count: 0 QAP Count: 7 NDT Count: 0 WPS Count: 0

Sub ID Part ID Drawing ID / Rev 32 PLASMA PQR 1

Parent Sub:29 Op:50

StartQty EndQt Drawing ID / Rev Operation Resource QtyPer Sub: 32 / Seq: 10 705-WELD ENGINEERING/CWI 1.00 1.00 1.00 (C) CWI to visually inspect PQR test plate per the requirements of ASME Sect. IX, AWS D1.1, and AWS B2.1. MTM NDT certification form required WPS Count: 0

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 1

Pgm Count: 0

Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev

Sub: 32 / Seq: 20 818-MQS CONTRACTOR X-RAY 1.00 1.00 1.00

Radiographically inspect PQR test plate per the requirements of ASME Sect. IX, AWS D1.1, and AWS B2.1. Reference acceptance to all three specifications on the reader sheet. (C)

OAP Count: 0

NDT Count: 0

Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Service ID Sub: 32 / Seq: 30 450-SUBLET 1.00 1.00 1.00 TESTNG/MISC

Dwg Count: 0

(C) * Perform destructive testing (ref: 2 tensile tests, 2 face bend tests, and 2 root bend tests) to the requirements of the following three specifications;

ASME Sect. IX, AWS D1.1, and AWS B2.

* All test samples and remaining plate to be returned to Major Tool and Machine when complete.

IDC Count: 0

- * Separate test reports are required for each specification. Test reports are to reference the PQR number and must provide the tensile failure locations/characterss.
- * All NDT has been performed by Major Tool and Machine. A copy of the radiographic report is included with the test plate for reference.
- * A reference sheet with pertinent welding data is included with the test plate.
- * Test plate info:
- One plate 3/8" thick Inconel 625
- One plate 3/8" thick Inconel 625
- Both plates butt welded using filler material ERNiCrMo-3 (Inconel 625)
- No post-weld heat treatment is required.
- Test plate is supplied in the as-welded condition.

WPS Count: 0 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 0



Page: 48 Date:12/23/03 User ID: MCCORKLE

WPS Count: 0

WPS Count: 1

WorkorderPart IDQtyDrawing ID / RevEngineer64880/1.01SE121-003P / --BLUE/DOUG MCCORKLE

Sub ID Part ID Qty Drawing ID / Rev

ASTM B 705 MECHANICAL TEST PIE 1 /
Parent Sub:19 Op:10

Operation Resource OtyPer StartQty EndQt Drawing ID / Rev

Sub: 33 / Seq: 10 415-ROLLING/SHEAR/BRAKE PRESS 1.00 1.00 1.00

(F) 1. SHEAR RECTANGLE PER MATERIAL CARD DIMENSIONS

2. ROLL TO 8" O.D. =/-0.03" X 6" LONG. LEAVE TRIM STOCK OVERLAPPED (FABRICATOR WILL TRIM). ENSURE OVERLAP IS ADEQUATE TO TRIM AND FIT THE

DIAMETER REMOVING ANY ROLL FLATS RESULTANT FROM STARTING AND FINISHING THE ROLLING SEQUENCE.

IDC Count : 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0
Piece # Part ID Oty Drawing ID / Rev Vendor Dimensions

Dwg Count: 0

10 INCONEL 625 660-SHEET.NICKEL ALLOY .125" THK 180.0 6*30

10 INCONEL 625_660-SHEET,NICKEL ALLOY .125" THK
(F) INCONEL 625 SHEET, .125" THICK PER

AMS 5599 / ASTM B443 (UNS N06625).

CERT AND MILL TEST REPORT REQ'D WITH SHIPMENT.

Material Certification:
Part Number: SE121-001P-3

Part Description: PORT EXTENSION TUBE

QAP Count: 0

QAP Count: 0

NDT Count: 0

Operation Resource OtyPer StartQty EndQt Drawing ID / Rev

IDC Count: 0

Sub: 33 / Seq: 20 205-PLASMA WORKCENTER 1.00 1.00 1.00 SE121 / --

(F) TRIM FIT AND TACK WELD CYLINDER.

SETUP, PURGE WELD JOINT WITH 100% ARGON. PURGE DAM MATERIAL MUST BE MADE FROM EITHER 625 INCONEL OR 300 SERIES STAINLESS STEEL, AND

PLASMA ARC WELD THE JOINT

PLASMA ARC WELD THE JOINT

Pgm Count: 0

WPS380-PPPL Rev:2 PAW MAC

PAW - Machine Fillers: INCONEL625_035_GMAW

Notes: PLASMA WELDING

Operation Resource QtyPer StartQty EndQt Drawing ID / Rev

Sub: 33 / Seq: 30 230-FABRICATION - WEIDNER 1.00 1.00 1.00


(F) TRIM BOTH ENDS TO PRODUCE A TEST PIECE 4" MINIMUM LENGTH

PERFORM A FLATTENING TEST PER ASTM B 705, 7.2

(ENGINEERING WITNESS REQUIRED) FILL OUT VISUAL TEST CERTIFICATE

Specification: ASTM B705 Rev: 94


Test Certification: VISUAL INSPECTION CERT Part Number: ASTM B 705 MECH. TEST PIECE





Specification: PP475 Rev: 8 Specification: PP476 Rev: 4

Part ID Drawing ID / Rev Workorder Engineer SE121-003P / --64880/1.0 BLUE/DOUG MCCORKLE IDC Count: 0 Dwg Count: 0 QAP Count: 3 NDT Count: 0 WPS Count: 0 Pgm Count: 0 Sub ID Part ID Drawing ID / Rev Qty 35 SOURCE NOTIFICATION Parent Sub:1 Op:72 Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 35 / Seq: 10 830-SOURCE WITNESS POINT -IN P 1.00 1.00 (U) SOURCE NOTIFICATION REQURIED ONE TO TWO WEEKS PRIOR TO VACUUM TESTING PORT SUB-ASSEMBLY. CUSTOMER DECISION WILL FOLLOW. NOTIFICATION VIA CFT Dwg Count: 0 WPS Count: 0 Drw N/A IDC N/A IDC Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 Sub ID Part ID Drawing ID / Rev Qty 25 SE121-003P-4-PORT EXTENSION WELD BACKING RING 1 Parent Sub:1 Op:90 StartQty EndQt Drawing ID / Rev Operation Resource OtvPer Sub: 25 / Seq: 10 415-ROLLING/SHEAR/BRAKE PRESS 1.00 1.00 1.00 SE121-003P / 0 (C) 1. SHEAR STRIP PER MATERIAL CARD AND DEBURR. 2. ROLL THE EASY WAY TO A 8.093" I.D. OBJ (0.031" WELD SHRINKAGE ALLOWANCE). 3. NOTIFY Q/A FOR DIMENSIONAL / MAGNETIC PERMEABILITY VERIFICATION. Specification: PP475 Rev: 8 NDT Count: 0 WPS Count: 0 IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 1 Piece # Part ID Drawing ID / Rev Vendor **Dimensions** Qty 10 INCONEL 625_660-SHEET, NICKEL ALLOY .125" THK 162.0 4.5*36 (C) INCONEL 625 SHEET, .125" THICK PER AMS 5599 / ASTM B443 (UNS N06625). CERT AND MILL TEST REPORT REQ'D WITH SHIPMENT. Material Certification: Part Number: SE121-003P-4 Part Description: WELD BACKING RING QAP Count: 3 Operation Resource **QtyPer** StartQty EndQt Drawing ID / Rev Sub: 25 / Seq: 15 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121 / --INSPECT AND RECORD MAGNETIC PERMEABILITY (AFTER ROLLING) (C) Part Number: SE121-001P-4 Part Description: PVVS PORT EXTENSION WELD RING





Part ID Drawing ID / Rev Workorder Engineer SE121-003P / --64880/1.0 BLUE/DOUG MCCORKLE IDC Count: 1 QAP Count: 4 NDT Count: 0 WPS Count: 0 Dwg Count: 0 Pgm Count: 0 Operation StartQty EndQt Drawing ID / Rev Resource **QtyPer** Sub: 25 / Seq: 20 SE121-003P / 0 230-FABRICATION - WEIDNER 1.00 1.00 1.00 1. TRIM AND FIT TO VESSEL CONTOUR, CUT WIDTH, PREP (F) 2. WELD PER DRAWING (SIZE TO EXISTING PORT TUBE) 3. BLEND WELD FLUSH TO BASE METAL 4. CWI VISUAL INSPECT WELD 100% UNDER 8X MAGNIFICATION PER ASME CODE ARTICLE 6, SECTION V. ACCEPTANCE PER AWS D1.6, 6.29.1. Specification: PP475 Rev: 8 Part Number: SE121-003P-4 Part Description: WELD BACKING RING Certification: CWI CERTIFICATE IDC Count: 5 Dwg Count: 0 Pgm Count: 0 QAP Count: 4 NDT Count: 0 WPS Count: 1 WPS390-PPPL Rev:0 GTAW MAN GTAW - Manual Fillers: INCONEL625_062_GTAW / INCONEL625_093_GTAW Notes: Operation **QtyPer** StartQty EndQt Drawing ID / Rev Resource Sub: 25 / Seq: 30 415-ROLLING/SHEAR/BRAKE PRESS 1.00 1.00 1.00 SE121 / A (F) RE-ROLL / ROUND UP BAND (IF NECESSARY) Specification: PP475 Rev: 8 IDC Count: 0 Dwg Count: 5 NDT Count: 0 WPS Count: 0 Pgm Count: 0 QAP Count: 1 Operation Resource OtvPer StartOtv EndQt Drawing ID / Rev Sub: 25 / Seq: 40 805-INPROCESS INSPECTION - PLA 1.00 1.00 1.00 SE121-003P / --(F) VERIFY DIMENSIONAL CONDITION VERIFY MAGNETIC PERMEABILITY VERIFY CLEANLINESS RECORD I.D.C. DATA Part Number: SE121-003P-4 Specification: ASTM A800 Rev: 2001 Specification: PP476 Rev: 4 Specification: PP475 Rev: 8 Part Description: WELD BACKING RING Dwg Count: 1 Pgm Count: 0 WPS Count: 0 IDC Count: 2 QAP Count: 5 NDT Count: 0 Sub ID Part ID Drawing ID / Rev Qty STORAGE / SHIPPING CRATE 28 Parent Sub:1 Op:115



Page: 51 Date:12/23/03 User ID: MCCORKLE

Workorder Part ID Drawing ID / Rev Engineer SE121-003P / --64880/1.0 BLUE/DOUG MCCORKLE QtyPer StartQty EndQt Drawing ID / Rev Operation Resource Sub: 28 / Seq: 10 425-SHIPPING - PLANTS 1 & 2 1.00 1.00 1.00 SE121 / A BUILD A CUSTOM STORAGE / SHIPPING CRATE PER ENGINEERING DIRECTION TO SUIT THE FOLLOWING REQUIREMENTS: (F) 1. THE CONTAINER MUST PROTECT THE PART FROM DAMAGE AND CONTAMINATION DURING STORAGE / HANDLING DURING THE MANUFACTURING PROCESS AT MTM. 2. THE PART RESTS / SUPPORTS MUST BE HARDWOOD AND CONFIGURED SO NO NAILS OR SCREWS COME INTO CONTACT WITH THE PART. 3. THE CONTAINER MUST HAVE PROVISIONS TO BE LIFTED AND HANDLED BY EITHER A FORKLIFT, OR CRANE / LIFTING STRAPS. IDC Count: 0 Dwg Count: 5 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Sub ID Part ID Qty Drawing ID / Rev 31 NAMEPLATE Parent Sub:1 Op:115 Operation Resource OtvPer StartQty EndQt Drawing ID / Rev Sub: 31 / Seq: 10 1.00 1.00 1.00 415-ROLLING/SHEAR/BRAKE PRESS (C) SHEAR RECTANGLE PER MATERIAL CARD DEBURR EDGES AND CLEANUP NOTIFY Q/A AND HAVE THE MAGNETIC PERMEABILITY CHECKED (AND RECORDED) PRIOR TO SUBCONTRACTING. IDC Count: 1 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0 Piece # Part ID Drawing ID / Rev Vendor **Dimensions** 24.0 4*6 INCONEL 625_660-SHEET, NICKEL ALLOY .125" THK (C) INCONEL 625 SHEET, .125" THICK PER AMS 5599 / ASTM B443 (UNS N06625). CERT AND MILL TEST REPORT REQ'D WITH SHIPMENT. Material Certification: TRACE ID: 92220 Part Number: NAMEPLATE QAP Count: 2 QtyPer StartQty EndQt Drawing ID / Rev Operation Resource Sub: 31 / Seq: 11 1.00 260-SANDBLAST 1.00 1.00 (C) BLAST 100% WITH 180-220 VIRGIN ALUMINUM OXIDE MEDIA CLEANUP AND WIPE DOWN WITH ISOPROPANOL USING LINT FREE WIPES (AVAILABLE IN Q/A) CONTACT ENGINEERING (DOUG McCORKLE) FOR VISUAL INSPECTION. AFTER ACCEPTED, WRAP AND TAPE WITH FOAM PROTECTION. IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 0 NDT Count: 0 WPS Count: 0 Operation StartQty EndQt Drawing ID / Rev Service ID Resource QtyPer Sub: 31 / Seq: 15 450-SUBLET 1.00 ENGRVNG/ETCHNG 1.00 1.00 (F) ETCH THE FOLLOWING INFORMATION PER PROVIDED DRAWING: MAJOR TOOL & MACHINE, INC. LOGO (USE FURNISHED ARTWORK)



Page: 52 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev **Engineer** 64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

PPPL LOGO (USE FURNISHED ARTWORK)

SE121-01

NATIONAL COMPACT STELLARATOR EXPERIMENT

PROTOTYPE VACUUM VESSEL SEGMENT PRIME-CONTRACT: DE-AC02-76-CH03073

SUB-CONTRACT: S-04344-F SCOPE: NCSX-SOW-121-01-02

SPECIFICATION: NCSX-CSPEC-121-01-01

MANUFACTURER: MAJOR TOOL AND MACHINE, INC.

MTM #: 64880

NOTES:

Sub: 38 / Seq: 10

(U)

THE SUPPLIED DRAWING IS ONLY A CONCEPT AND IS PROVIDED TO DEFINE THE NECESSARY IDENTIFICATION INFORMATION. THE FINAL COMPOSITION IS TO BE DETERMINED BY THE MANUFACTURER.

VENDOR IS TO PROVIDE PROTOTYPE SAMPLES (EITHER A PHYSICAL SAMPLE OR RENDERING) OF I.D. TAG DESIGN / COMPOSITION FOR MTM APPROVAL PRIOR TO PRODUCING THE FINAL ARTICLE.

THE MATERIAL OF THE TAG (625 INCONEL, OR 316L STAINLESS) HAS BEEN SELECTED BASED ON IT'S LOW MAGNETIC PERMEABILITY PROPERTIES. EXTREME CARE MUST BE MAINTAINED DURING THE PROCESSING AND HANDLING OF THE TAG. ALL EFFORTS MUST BE MADE TO AVOID THE INDUCTION OF MAGNETIC PROPERTIES BY MEANS OF CONTAMINATION FROM CONTACT WITH IRON BASED MATERIALS (EG PLATTENS, WORK TABLES, HAND TOOLS, ETC....) THE METHOD OF PART MARKING ALSO MUST NOT AFFECT MAGNETIC PERMEABILITY. REFERENCE MTM CLEANLINESS CONTROL PROCEDURE PP475

Specification: PP475 Rev: 8 Part Number: PVVS NAMEPLATE

820-RECEIVING INSPECTION

RECEIVE AND INSPECT

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 OAP Count: 2 NDT Count: 0 WPS Count: 0

Operation	Resource	QtyPer	StartQty End(t Drawing ID / Rev				
Sub: 31 / Seq: 20	820-RECEIVING INSPECTION	1.00	1.00 1.00					
(F)	RECEIVE AND INSPECT NAMEPLATE PER M	ITM PURCHAS	SE ORDER					
	INSPECT MAGNETIC PERMEABLITY AND RECORD IDC DATA							
	Specification: PP476 Rev: 4							
	IDC (Count: 1	Dwg Count: 0	Pgm Count: 0	QAP Count: 1	NDT Count: 0	WPS Count: 0	
	D. (ID.		04	D				
Cuk ID								
Sub ID	Part ID		Qty	Drawing ID / Rev				
Sub ID 38	FIXED DATUM TARGETS FOR PROFIL		Qty 1	/ Parent Sub:1 Op:115				

MTTRAVLR.qrp W:64880/1-0 /Inc Matl /Inc Legs

1.00

Pgm Count: 0

QAP Count: 0

NDT Count: 0

WPS Count: 0

1.00

IDC Count: 0

1.00

Dwg Count: 0



Page: 53 Date:12/23/03 **User ID: MCCORKLE**

Workorder Part ID Qty Drawing ID / Rev Engineer

64880/1.0 SE121-003P / --BLUE/DOUG MCCORKLE

Qty Drawing ID / Rev Sub ID Part ID

36 SOURCE NOTIFICATION Parent Sub:1 Op:120

QtyPer StartQty EndQt Drawing ID / Rev Operation Resource

Sub: 36 / Seq: 10 831-SOURCE INSPECTION - FINAL 1.00 1.00 1.00 (U) FINAL SOURCE INSPECTION NOTIFICATION REQUIRED ONE TO TWO WEEKS PRIOR TO FINAL INSPECTION. CUSTOMER DECISION WILL FOLLOW.

NOTIFICATION VIA CFT.

IDC Count: 0 Dwg Count: 0 Pgm Count: 0 QAP Count: 0 NDT Count: 0 WPS Count: 0

W:64880/1-0/Inc Matl/Inc Legs MTTRAVLR.qrp